



Industrial Wood Coatings

SHER-WOOD® Precat Primer Surfacer

White.....E63W30

Catalyst.....DV507WC00

DESCRIPTION

SHER-WOOD® Precat Primer Surfacer is a fast drying, high performance conversion primer surfacer for the general wood finishing market. After catalyzation, it provides a 3 month pot life as a white pre-cat primer surfacer.

Advantages:

- Meets KCMA performance properties when topcoated with Sher-Wood White Hi-Bild Precat Lacquer.
- HAPS compliant as packaged*
- White Precat primer surfacer with 3 months working pot life
- Very fast dry to sand and pack
- Ready to spray. No reduction needed
- Excellent filling properties suitable for filling MDF
- Good flexibility - passes 20 cold check cycles
- Versatile application - may be applied by conventional, airless, air-assisted airless and HVLP spray methods
- Ideal for kitchen cabinets, vanities, chairs, office furniture, household furniture, novelties, and a wide range of interior wood products

*National Standards for Hazardous Air Pollutants (HAPS) Emissions for Wood Furniture Manufacturing Operations CFR40, Part 63, Subpart JJ

An Environmental Data Sheet is available from your local Sherwin-Williams facility, or at www.paintdocs.com.


CHARACTERISTICS

Volume Solids: 26 ± 1%

Weight Solids: 44.5 ± 1%

Viscosity:

23-27 sec #4 Ford cup



The above chart is for information only and should not be used as product specifications

Recommended film thickness:

Mils Wet 3.0 - 5.0
Mils Dry 0.8 - 1.3

Spreading Rate (no application loss)
305-535 sq ft/gal @ 0.8-1.3 mils DFT

Drying (77°F, 50% RH):

To Touch: 10 minutes
To Handle: 20 minutes
To Sand: 20-30 minutes
To Recoat: no critical recoat
To Pack: Overnight
Force Dry: 5 minutes at 110- 140°F

Flash Point: 4°F Pensky-Martens
Closed Cup

Mixing Ratio:

1 gallon Primer Surfacer
4.0 oz Catalyst DV507WC00

Pot Life: 3 months

Package Life: 2 years, unopened

Air Quality Data:

- Non-photochemically reactive
- Volatile Organic Compounds (VOC) theoretical as packaged, maximum less exempt solvents:
5.17 lb/gal, 620 g/L
- Hazardous Air Pollutants (HAPS) as packaged maximum:
0.0 lb/lb of solids

SPECIFICATIONS

Wood (interior only): Must be clean, dry, and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties. Moisture content of wood should be 6 to 8%.

Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

APPLICATION Typical Setups	ADDITIONAL INFORMATION	CAUTIONS
May be applied by: Conventional Spray Airless Spray Air Assisted Airless HVLP Reduce as needed for application up to 20% with TT5906000 Thinner 0988 HAPS Free Typical Setups Conventional Spray: Air Pressure40 – 50 psi Fluid Pressure 8 – 12 psi Airless Spray: Pressure 1500 - 1800 psi Tip..... .011" - .013" Air Assisted Airless: Air Assist Pressure..... 15 - 25 psi Fluid Pressure..... 500 - 900 psi Tip..... .011" - .013" HVLP Gun.....Binks Mach 1 Air Pressure at the cap..... 9 psi Fluid Pressure..... 12 psi Cap/Tip97AP Blue Max/94 Cleanup: Clean tools/equipment immediately after use with R7K320 HAPS Compliant Lacquer Thinner Follow manufacturer's safety recommendations when using any solvent.	• This product must be catalyzed with Catalyst DV507WC00 before use at a level of 3% (4.0 ounces per gallon). Product will typically be catalyzed before delivery to the customer. Complete cross-linking and film properties will not be attained without catalyzation. Catalyst must be added by the user or by the Sherwin-Williams outlet. • This product should be used within 3 months after being catalyzed to obtain optimum properties. The catalyst causes a chemical reaction in the package and dissipates after 3 months and performance properties are downgraded. Adding additional catalyst does not restore film properties. • Store at room temperature (under 80F) after catalyzation. Higher temperatures will reduce the pot life. • To achieve maximum performance properties a minimum of 2 mils DFT is required. • Total film thickness of systems must not exceed 4.0 mils dry film because heavier films may show cracking and checking tendencies. • For interior use only. • Catalyst DV5701000 is an acid. To prevent acid corrosion and pitting, all equipment should be made of stainless steel. Containers should be stainless steel or plastic. • Do not catalyze with other acid catalysts because of fast reactivity and pot life problems. • Maximum cure and chemical resistance is attained after 10 days air-drying. • To maintain HAPS compliance, only reduce with HAPS compliant reducers. • Can be tinted with OptiColor® XP or GIS colorants up to 6 ounces per gallon. All trademarks are the property of their respective owners.	FOR INDUSTRIAL SHOP APPLICATION ONLY Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product. To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com. Please direct any questions or comments to your local Sherwin-Williams facility. Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found by following this link (click here) Please review these terms and conditions prior to the purchase of the products. Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.