




Industrial Wood Coatings

SHER-WOOD® Hi-Bild™ Precat Lacquer

GlossT77C55
Dull Rubbed Effect... T77F58

Bright Rubbed Effect.....T77F56
Flat.....T77F59

Medium Rubbed Effect.....T77F57
Catalyst.....DV507WC0

DESCRIPTION	CHARACTERISTICS	SPECIFICATIONS										
SHER-WOOD® Hi-Bild™ Precat Lacquer is a fast drying, high performance, clear, conversion lacquer for the general wood finishing market. After catalyzation, it provides a 4 month pot life. Advantages: • 20% higher volume solids than traditional precat lacquers. • Meets KCMA specifications as a self sealing system • Fast dry to sanding and packing. • Contains UV absorber to significantly reduce the discoloration of natural wood from exposure to sunlight. • Good resistance to household chemicals. • Good flexibility - passes 20 KCMA cold check cycles. • Versatile application – may be applied by conventional, airless, air-assisted airless spray. • Pale water white color. • Ideal for kitchen cabinets, vanities, chairs, office furniture, household furniture Air Quality Data: • Non-photochemically reactive • Volatile Organic Compounds (VOC) theoretical as packaged, maximum less exempt solvents: 5.18 lb/gal, 620 g/L. Catalyzed and reduced (R7K305 at 10%) 5.31 lb/gal 630 g/L • Volatile Hazardous Air Pollutants (VHAPS) as packaged maximum: No reportable VHAPS VOC compliance limits vary from state to state; please consult local Air Quality rules and regulations An Environmental Data Sheet is available from your local Sherwin-Williams facility, or at www.paintdocs.com.	Gloss: <table><tr><td>Gloss</td><td>85+ units</td></tr><tr><td>BRE</td><td>55-59 units</td></tr><tr><td>MRE</td><td>34-38 units</td></tr><tr><td>DRE</td><td>17-21 units</td></tr><tr><td>Flat</td><td>4-8 units</td></tr></table> Volume Solids: 25 ± 2% Weight Solids: 33 ± 2% Viscosity: T77F59: 20-25 seconds #2 Zahn Cup All others 25-30 seconds #2 Zahn cup  The above chart is for information only and should not be used as product specifications Recommended film thickness: Mils Wet 3.0 - 5.0 Mils Dry 0.75 – 1.25 Maximum dry film thickness of the entire system should not exceed 4.0 mils Spreading Rate (no application loss) 395-580 sq ft/gal @ 0.75-1.25 mils DFT Drying (77°F, 50% RH): To Touch: 10-15 minutes To Handle: 15-20 minutes To Sand: 30-45 minutes To Recoat: 30-45 minutes To Pack: 8 hour minimum Force Dry: 5-10 minutes at 110- 140°F, then air dry 1 hour minimum to pack Flash Point: 4°F Pensky-Martens Closed Cup Mixing Ratio: 1 gallon Lacquer 3.0 ounces Catalyst, DV507WC00 Pot Life: 4 months Package Life: 2 years, unopened	Gloss	85+ units	BRE	55-59 units	MRE	34-38 units	DRE	17-21 units	Flat	4-8 units	Wood (interior only): Must be clean, dry, and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties. Moisture content of wood should be 6 to 8%. Wood Finishing System: THIS PRODUCT MUST BE CATALYZED. Do not exceed 4.0 mils DFT for the total system. Testing: The information, data, and recommendations set forth in this Prod- uct Data Sheet are based upon test re- sults believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, applica- tion methods, and environments, the customer should test the complete sys- tem for adhesion, compatibility and per- formance prior to full scale application.
Gloss	85+ units											
BRE	55-59 units											
MRE	34-38 units											
DRE	17-21 units											
Flat	4-8 units											

APPLICATION

Typical Setups

THIS PRODUCT MUST BE CATALYZED
DETERMINE IF IT HAS BEEN CATALYZED. If not catalyzed, add 2.3% (3.0 oz/gal) Sher Wood Hi-Bild Precat Catalyst, V66V3. Potlife after catalyzation is 4 months. Record the catalyzation date on the container.

Reduction: Product is normally applied without reduction.

Conventional Spray:

Air Pressure 35 - 60 psi
Fluid Pressure 6 - 10 psi
Cap/Tip 797

Airless Spray:

Pressure 1500 - 1800 psi
Tip011 - .013"

Air Assisted Airless:

Air Pressure 20 - 30 psi
Fluid Pressure 500 - 900 psi
Cap/Tip011 - .013

HVLP:

Gun Binks Mach 1
Atomizing Air Pressure at the cap 9 psi
Fluid Pressure 12 psi
Cap/Tip 97AP Blue Max/94

Cleanup:

Clean tools/equipment immediately after use with TT5906000 Thinner 098 HAPS Free

Follow manufacturer's safety recommendations when using any solvent.

Performance Tests:

Household Chemicals Test

Using ANSI-KCMA A161.1-2012 test procedures, panels were cured by air drying and allowed to age 10 days at ambient conditions before testing. Tests were conducted on self-sealed (2 coat) finished panels at 2.0 mils total DFT. Materials were washed off with clear water after 24 hours and allowed to recover for 10 days then the finish was examined and the following results noted:

Vinegar no effect
Lemon Juice no effect
Orange Juice no effect
Grape Juice no effect
Tomato Catsup no effect
Coffee @ 115° F no effect
Olive Oil no effect
100 Proof Alcohol no effect
Water & Detergent no effect
Mustard (1 hour) no effect
Cold Checks 20 cycles Pass
Edge Soak Pass

ADDITIONAL INFORMATION

- This product **must** be catalyzed with Catalyst DV507WC00, before use at a level of 2.3% (3.0 oz/gal). Complete crosslinking and film properties will not be attained without catalyzation. Product will typically be catalyzed before delivery to the customer.
- This product should be used within 4 months after being catalyzed to obtain optimum properties. The catalyst causes a chemical reaction in the package and dissipates after 4 months and performance properties are downgraded. **Adding additional catalyst does not restore film properties.**
- Store at room temperature (under 80° F) after catalyzation. Higher temperatures will reduce the storage life.
- Self-seal to meet KCMA requirements.
- To achieve optimal results, a minimum of 2 mils DFT is required.
- Total film thickness of systems must not exceed 4 mils DFT because heavier films may show cracking and checking tendencies.
- For interior use only.
- Catalyst DV507WC00 is an acid. To prevent acid corrosion and pitting, all equipment should be made of stainless steel. Containers should be stainless steel or plastic.
- Do not catalyze with other acid catalysts because of fast reactivity and pot life issues.
- Maximum cure and chemical resistance is attained after 10 days air drying.
- Natural wood will change color by itself and clear wood finishes will not keep this from occurring.
- To maintain HAPS compliance, only reduce with HAPS compliant reducers.

All trademarks are the property of their respective owners.

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com.

Please direct any questions or comments to your local Sherwin-Williams facility.

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found [by following this link \(click here\)](#). Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.**

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.