




Industrial Wood Coatings

SHER-WOOD® White Hi-Bild™ Precat Lacquer

Gloss WhiteT77W10

Catalyst.....DV507WC00

DESCRIPTION	CHARACTERISTICS	SPECIFICATIONS
SHER-WOOD® White Hi-Bild™ Precat Lacquers is a fast drying, high performance, pigmented, conversion lacquer for the general wood finishing market. After catalyzation, it provides 3 months pot life as a white precat lacquer. Advantages: • Meets KCMA specifications as a self-sealed system • White Precat lacquer with 3 months working pot life. • Contains UV absorber for improved resistance to yellowing. • Very fast dry to sanding and packing like nitrocellulose lacquer. • Ready to spray - No reduction needed • Good resistance to household stains. • Good flexibility - Passes 20 cold check cycles • Versatile application - May be applied by conventional, airless, air-assisted airless and HVLP spray methods • Ideal for kitchen cabinets, vanities, chairs, office furniture, household furniture, novelties, and a wide range of interior wood products • HAPS compliant* as packaged • Available in a broad range of colors and gloss levels *National Standards for Hazardous Air Pollutants (HAPS) Emissions for Wood Furniture Manufacturing Operations CFR40, Part 63, Subpart JJ Air Quality Data: • Non-photochemically reactive • Volatile Organic Compounds (VOC) theoretical as packaged, maximum less exempt solvents: 5.21 lb/gal, 624 g/L • Hazardous Air Pollutants (HAPS) as packaged maximum: 0.08 lb/lb of solids VOC compliance limits vary from state to state; please consult local Air Quality rules and regulations	Gloss: Gloss Full Volume Solids: 26 ± 1% Weight Solids: 40 ± 1% Viscosity: 20-24 seconds #2 Zahn cup  <i>The above chart is for information only and should not be used as product specifications</i> Recommended film thickness: Mils Wet 3.0 - 5.0 Mils Dry 0.8 – 1.3 Spreading Rate (no application loss) 309-541 sq ft/gal @ 0.8-1.3 mils DFT Drying (77°F, 50% RH): To Touch: 15-20 minutes To Handle: 20-30 minutes To Sand: 40-50 minutes To Recoat: no critical recoat To Pack: Overnight Force Dry: 5 minutes at 110- 140°F Flash Point: 22°F Pensky-Martens Closed Cup Mixing Ratio: 1 gallon Lacquer 3.0 ounces Catalyst, DV507WC00 Pot Life: 3 months Package Life: 2 years, unopened An Environmental Data Sheet is available from your local Sherwin-Williams facility, or at www.paintdocs.com.	Wood (interior only): Must be clean, dry, and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties. Moisture content of wood should be 6 to 8%. Do not exceed 4.0 mils DFT for the total system. Testing: The information, data, and recommendations set forth in this Product Data Sheet are based upon test results believed to be reliable. However, due to the wide variety of substrates, substrate properties, surface preparation methods, equipment and tools, application methods, and environments, the customer should test the complete system for adhesion, compatibility and performance prior to full scale application.

APPLICATION

Typical Setups

May be applied by:

Conventional Spray
Airless Spray
Air Assisted Airless
HVLV

Reduce as needed for application up to 20% with TT590600 Thinner 0988 HAPS Free

Typical Setups

Conventional Spray:

Air Pressure40 – 50 psi
Fluid Pressure 8 – 12 psi

Airless Spray:

Pressure 1500 - 1800 psi
Tip..... .011" - .013"

Air Assisted Airless:

Air Assist Pressure..... 15 - 25 psi
Fluid Pressure..... 500 - 900 psi
Tip..... .011" - .013"

HVLV

Gun.....Binks Mach 1
Air Pressure at the cap..... 9 psi
Fluid Pressure..... 12 psi
Cap/Tip97AP Blue Max/94

Cleanup:

Clean tools/equipment immediately after use with R7K320 HAPS Compliant Lacquer Thinner

Follow manufacturer's safety recommendations when using any solvent.

Household Chemicals Test

Panels were aged 10 days at room conditions and tested per KCMA A161.1-2012-9.3. After removal, the finish was examined and the following results noted:

Vinegar no visual effect
Lemon Juice..... no visual effect
100 proof alcohol..... no visual effect
Mustard.....Initial stain fades in 14 days
Olive oil..... no visual effect
Coffee no visual effect
Orange juice..... no visual effect
Grape juice..... no visual effect
Catsup no visual effect
Detergent solution..... no visual effect

Performance Tests

Cold Check Resistance 20 cycles
Print Resistance..... No print
2.0 mils DFT, 16 hours air dry, at 2 psi at 77°F in direct contact with 8 oz. duck cloth.

ADDITIONAL INFORMATION

- This product must be catalyzed with Catalyst DV507WC00 before use at a level of 2.3% (3.0 ounces per gallon). Product will typically be catalyzed before delivery to the customer. Complete cross-linking and film properties will not be attained without catalyzation. Catalyst must be added by the user or by the Sherwin-Williams outlet.
- This product should be used within 3 months after being catalyzed to obtain optimum properties. The catalyst causes a chemical reaction in the package which dissipates after 3 months and performance properties are downgraded. Adding additional catalyst does not restore film properties.
- Can be tinted with Chroma-Chem® 844, Maxitoner or OptiColor® XP colorants up to 4 ounces per gallon under agitation. Store at temperatures ranging from 40°F-80°F. Higher temperatures will reduce the pot life and may cause settling.
- To achieve maximum performance properties a minimum of 2 mils DFT is required.
- Total film thickness of systems must not exceed 4.0 mils dry film because heavier films may show cracking and checking tendencies.
- For interior use only.
- Catalyst DV507WC00 is an acid. To prevent acid corrosion and pitting, all equipment should be made of stainless steel. Containers should be stainless steel or plastic.
- Do not catalyze with other acid catalysts because of fast reactivity and pot life problems.

All trademarks are the property of their respective owners.

CAUTIONS

FOR INDUSTRIAL SHOP APPLICATION ONLY

Thoroughly review product label and Safety Data Sheet (SDS) for safety information and cautions prior to using this product.

To obtain the most current version of the Environmental Data Sheet (EDS), Product Data Sheet (PDS), or Safety Data Sheet (SDS) please visit your local Sherwin-Williams facility or www.paintdocs.com.

Please direct any questions or comments to your local Sherwin-Williams facility.

Note: All purchases of products from Sherwin-Williams are exclusively subject to Sherwin-Williams' terms and conditions of sale which can be found [by following this link \(click here\)](#). Please review these terms and conditions prior to the purchase of the products.

Sherwin-Williams warrants the product to be free of manufacturing defect in accordance with Sherwin-Williams' quality control procedures. Except for the preceding sentence, due to factors that are outside of Sherwin-Williams' control, including substrate selection, and customer handling, preparation, and application, Sherwin-Williams cannot make any other warranties related to the product or the performance of the product. **SHERWIN-WILLIAMS DISCLAIMS ALL WARRANTIES OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTY OF MERCHANTABILITY, THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE.**

Liability for products proven to be defectively manufactured will be limited solely to replacement of the defective product or the refund of the purchase price paid for the defective product, as determined by Sherwin-Williams. Under no circumstances shall Sherwin-Williams be liable for indirect, special, incidental or consequential damages, lost profits or punitive damages arising from any cause whatsoever.