Paper 1 — Research Approach

Drop Impact of Dense TPM vs. Cornstarch Suspensions:
Jamming, Unjamming, and the Role of Particle Identity

Driscoll Lab · Northwestern University · May 2026

Target journal: *Physical Review Fluids* (primary) | *Soft Matter* (secondary)
Submission target: August 2026

---

1. Scientific Narrative — The Central Claim

Primary claim: The jamming and unjamming dynamics during drop impact are controlled by *particle identity* — specifically particle size, porosity, and surface chemistry — and cannot be predicted from bulk shear-thickening rheology alone, even when bulk flow curves are matched between materials.

Sub-claim 1 (kinetic asymmetry): TPM sphere drops (≈830 nm, $\phi_{\text{eff}} = 0.42$–0.50) jam an order of magnitude *sooner* after impact than cornstarch drops at matched effective volume fraction, despite comparable bulk rheology.

Sub-claim 2 (relaxation paradox): Despite having near-Brownian diffusion timescales during unjamming ($\text{Pe}_{\text{unjam}} \sim \mathcal{O}(1)$ for TPM vs. $\gg 1$ for cornstarch), TPM relaxes orders of magnitude *more slowly*. Brownian motion does not accelerate unjamming; contact-network geometry and pore-fluid mechanics dominate.

Sub-claim 3 (mechanism): Cornstarch unjams rapidly via Reynolds–Darcy pore-fluid dilatancy [8], a pathway unavailable to non-porous TPM. Without it, the TPM contact network relaxes via a slowly-evolving frictional state described by KWW kinetics. At high ϕ_{eff}, β_{KWW} may approach or exceed unity (compressed-exponential form), consistent phenomenologically with compressed-exponential relaxation observed in dense colloidal systems near the glass/jamming transition [10]. Note that the microscopic origin of compressed-exponential relaxation in Ballesta et al. — internal stress from arrested phase separation — differs from the contact-network stress driving post-impact relaxation; the connection here is functional (same KWW form with $\beta_{\text{KWW}} > 1$) rather than mechanistic identity.

2. Scientific Gap Analysis

The following five gaps in the existing literature make this paper publishable at the PRF/Soft Matter level.

Gap 1: No systematic Brownian/non-Brownian comparison in drop impact. Nearly all drop impact studies use a single material (cornstarch *or* silica, never both

matched). Waitukaitis & Jaeger (2012) [2] established impact-activated solidification and jamming-front propagation in cornstarch, and Han et al. (2016) [4] confirmed the mechanism via high-speed ultrasound imaging. Peters et al. (2016) [3] demonstrated dynamic shear jamming in dense suspension extension flows. None of these studies compare Brownian-regime particles ($\mathrm{Pe}_{\mathrm{unjam}} \sim 1$) to non-Brownian particles ($\mathrm{Pe}_{\mathrm{unjam}} \gg 1$) under controlled, matched conditions. *Closest prior work:* Shah et al. (2022) [6] used colloidal silica drops and identified coexisting solid/liquid phases, but did not compare to cornstarch or frame the result in $\mathrm{Pe}_{\mathrm{unjam}}$ terms.

Gap 2: Effective viscosity approach never tested across particle identity. Shah et al. (2025) [7] validated the $\eta_{\mathrm{eff}}(\dot{\gamma}_c) \rightarrow$ Laan–Padé mapping across concentration and velocity for one material at a time. Whether it holds when particle identity changes — and whether the prefactor A is universal or material-dependent — is untested. The $A = 0.09$ anomaly in Shah et al. (2022) [6] remains unexplained and is directly addressed here.

Gap 3: KWW exponent β_{KWW} never measured as a function of particle type. Post-impact relaxation has been fit with KWW forms exclusively for cornstarch. Whether colloidal silica drops show compressed exponential relaxation ($\beta_{\mathrm{KWW}} > 1$), as predicted for dense colloidal systems near jamming [10], is completely open.

Gap 4: Reynolds–Darcy dilatancy mechanism untested for non-porous particles. Mobaseri et al. (2026) [8] established that cornstarch retraction is governed by inertia–dilatancy interplay with pore-fluid pressure driving rapid unjamming. This is an explicitly material-specific mechanism. No paper has tested whether removing particle porosity (TPM) eliminates this relaxation pathway and produces qualitatively different dynamics.

Gap 5: $\mathrm{Pe}_{\mathrm{unjam}}$ has never been defined or measured in drop impact. Existing literature defines Pe only at impact timescales, where both materials are non-Brownian. The unjamming-timescale Pe ($\mathrm{Pe}_{\mathrm{unjam}} = \tau_B/\tau_{\mathrm{KWW}}$) has not been introduced, computed, or used to frame unjamming physics.

3. The Péclet Number Framework

We define and separate two distinct Péclet numbers for this work.

3.1. Impact-time Péclet number (both materials non-Brownian)

$$\mathrm{Pe}_{\mathrm{impact}} = \frac{\dot{\gamma}_c \cdot a^2}{D_B} = \frac{U_0/(D_0/2) \cdot a^2}{k_B T/(6\pi\eta_0 a)} \tag{1}$$

For representative conditions ($U_0 = 1\,\mathrm{m/s}$, $D_0 = 3\,\mathrm{mm}$, $\eta_0 = 1\,\mathrm{mPa{\cdot}s}$, $T = 298\,\mathrm{K}$):

	TPM ($a = 415\,\mathrm{nm}$)	Cornstarch ($a \approx 5\,\mu\mathrm{m}$)
D_B (m^2/s)	5.3×10^{-13}	4.4×10^{-14}
$\dot{\gamma}_c$ (s^{-1})	667	667
$\mathrm{Pe}_{\mathrm{impact}}$	≈ 220	$\approx 380{,}000$

Both materials are mechanically driven (non-Brownian) during spreading. Brownian motion does not influence the impact dynamics *per se*.

3.2. Unjamming-time Péclet number (the novel frame)

$$\mathrm{Pe}_{\mathrm{unjam}} = \frac{\tau_B}{\tau_{\mathrm{KWW}}}, \qquad \tau_B = \frac{a^2}{D_B} \tag{2}$$

	TPM	Cornstarch
τ_B	$\approx$325 ms	$\approx$570 s
τ_{KWW} (expected)	400–500 ms	50–200 ms
$\mathrm{Pe}_{\mathrm{unjam}}$	$\approx$**0.6–0.8**	$\approx$**3,000–10,000**

The paradox, stated quantitatively. Brownian diffusion operates on the unjamming timescale for TPM ($\mathrm{Pe}_{\mathrm{unjam}} < 1$) but is completely irrelevant for cornstarch ($\mathrm{Pe}_{\mathrm{unjam}} \gg 1$). Yet TPM relaxes $\sim$4$\times$ or more slowly. If Brownian motion were the controlling mechanism, TPM would unjam *faster* — the opposite is observed. This decoupling of $\mathrm{Pe}_{\mathrm{unjam}}$ from τ_{KWW} is the core finding and is inconsistent with the simplest thermal-fluctuation model of unjamming.

$\mathrm{Pe}_{\mathrm{unjam}}$ is a lower bound: bare D_B overestimates collective diffusion. The calculation above uses the *bare* single-particle Stokes–Einstein diffusivity $D_B = k_B T/(6\pi\eta_0 a)$, valid for an isolated particle in pure solvent. Inside a dense suspension at $\phi_{\mathrm{eff}} \approx 0.46$, the long-time self-diffusivity D_s^l is dramatically suppressed relative to D_B by cage trapping and correlated motion. For hard-sphere-like colloids at $\phi_{\mathrm{eff}} \approx 0.5$, $D_s^l/D_B \sim 10^{-2}$–10^{-3} is commonly reported. The effective Brownian timescale for collective particle rearrangements is therefore $\tau_B^{\mathrm{eff}} = a^2/D_s^l \gg \tau_B$, pushing the effective $\mathrm{Pe}_{\mathrm{unjam}}$ for TPM well above unity. This actually *strengthens* the argument: even with the most favorable (lowest) estimate of the Brownian timescale (τ_B based on D_B), Brownian diffusion still does not predict the observed unjamming hierarchy. When framing this in the manuscript, state explicitly that $\mathrm{Pe}_{\mathrm{unjam}}$ is computed using bare D_B and represents a lower bound on the unjamming Péclet number. Avoid language implying that $\mathrm{Pe}_{\mathrm{unjam}} < 1$ definitively places TPM in a Brownian-dominated regime.

4. Volume Fraction Normalization

Getting ϕ_{eff} right is non-negotiable. All TPM–cornstarch comparisons are invalid unless both materials are reported at matched *effective* volume fraction. Use the Han, Van

Ha & Jaeger (2017) correction [5] for cornstarch and verify TPM ϕ by DLS + gravimetry. Normalize all dimensionless timescales using $\eta_0(\phi_{\text{eff}})$ from the low-shear plateau of the measured flow curve, not the pure-solvent viscosity.

4.1. Cornstarch porosity correction [5]

Cornstarch particles are porous with measured porosity $p \approx 0.31$ (31% of particle volume is liquid-filled pores).

$$\phi_{\text{eff}} = \frac{\phi_{\text{nom}}}{1-p} \approx \frac{\phi_{\text{nom}}}{0.69} \approx 1.45\,\phi_{\text{nom}} \tag{3}$$

A separate moisture-content correction accounts for surface-adsorbed water. Both corrections must be applied before comparing to TPM results. Target cornstarch $\phi_{\text{nom}} \approx 0.29$–$0.34$ to match TPM $\phi_{\text{eff}} = 0.42$–0.50.

Correction factor must be verified and locked before data analysis. Equation (3) gives $\phi_{\text{eff}} \approx 1.45\,\phi_{\text{nom}}$ from the porosity correction alone ($p = 0.31$). A two-step variant of the Han et al. correction — which accounts for surface-adsorbed moisture reducing the apparent dry solid fraction before applying the porosity factor — yields a significantly lower effective multiplier (≈1.14 depending on measured moisture content).

A factor discrepancy of ∼25% in ϕ_{eff} shifts the Boyer jamming distance $\psi = 1 - \phi_{\text{eff}}/\phi_J$ by a comparable amount and invalidates all matched-ϕ_{eff} comparisons between TPM and cornstarch.

Required action:

1. Measure moisture content of your cornstarch stock by oven drying (mass loss at 105 °C for 2 h) as described in Han et al. (2017) [5].
2. Apply both the moisture-content correction *and* the porosity correction in the prescribed order, using the measured values — do not use the single-factor shorthand until you have verified it against the two-step result for your specific preparation.
3. Record the factor used and cite the measured moisture content explicitly in the Methods section.

4.2. Viscosity normalization

For cornstarch, use $\eta_0(\phi_{\text{eff}})$ from the low-shear plateau of the measured flow curve at the corrected ϕ_{eff} — **not** pure-water viscosity. This is mandatory for correctly computing the viscous timescale $\tau_v = \eta_0 D_0/\sigma$ and the effective shear rate $\dot{\gamma}_c$.

4.3. Boyer jamming distance

Near jamming, using Boyer et al. (2011) [11] unified rheology, define the *jamming distance* $\psi = 1 - \phi_{\text{eff}}/\phi_J$. For cornstarch: $\phi_J \approx 0.57$ (irregular particles); for TPM: $\phi_J \approx 0.64$ (monodisperse spheres). At matched $\phi_{\text{eff}} = 0.46$: $\psi_{\text{cornstarch}} \approx 0.19$, $\psi_{\text{TPM}} \approx 0.28$. Cornstarch is geometrically *closer* to jamming at the same ϕ_{eff}, making TPM's earlier t_{jam} genuinely surprising and mechanistically interesting.

5. Experimental Design

5.1. Materials

TPM spheres [3-(trimethoxysilyl)propyl methacrylate]:

- Diameter $2a \approx 830\,\text{nm}$; PDI $< 5\%$ (verify by DLS post-synthesis)
- Density $\rho_p \approx 1200\,\text{kg/m}^3$ (polymer particle, non-porous)
- Synthesis: aqueous condensation of TPM monomer; size set by pH and reaction time [1]
- Solvent: ultrapure water; matched viscosity series with glycerol
- Volume fractions: $\phi_{\text{eff}} = 0.42, 0.44, 0.46, 0.48, 0.50$
- Characterize: ζ-potential (expect negative from methacrylate/silanol surface groups; measure before each campaign — value needed for σ^* estimate and salt-screening interpretation)
- **Advantage over Stöber silica:** lower density reduces sedimentation during sample preparation; synthesis is single-pot; fluorescent dye can be incorporated during polymerization for future confocal work

Cornstarch:

- Sigma-Aldrich or Argo; mean diameter ≈5–8 μm (SEM)
- Density $\rho_p \approx 1400\,\text{kg/m}^3$; porosity $p \approx 0.31$ [5]
- $\phi_{\text{nom}} \approx 0.29$–$0.34$ to achieve matched ϕ_{eff} series

5.2. Impact conditions

Parameter	Value	Sweep range	Notes
Drop diameter D_0	$3.0 \pm 0.1\,\text{mm}$	fixed	pendant drop release
Impact velocity U_0	$1.0\,\text{m/s}$	$0.5, 1.0, 1.5, 2.0, 2.5\,\text{m/s}$	
Substrate	glass ($\theta \approx 5°$)	+ PTFE ($\theta \approx 110°$)	2 substrates
Volume fraction	$\phi_{\text{eff}} = 0.46$	$0.42, 0.46, 0.50$	
Replicates	$N \geq 10$	$N = 20$ for KWW fits	

This gives $5 \times 3 \times 2 \times 2$ materials $= 60$ distinct conditions; $\times 10$ replicates $= 600$ drops minimum. Plan for ∼800 total to accommodate failed captures.

5.3. Ionic strength sweep (TPM only — primary surface-chemistry control)

Why this is a primary experiment, not a follow-up. The ζ-potential difference between TPM and cornstarch ($\zeta \approx +22\,\text{mV}$) is expected to be significant (TPM has negatively charged surface groups). Without a within-paper ionic-strength control, a reviewer can attribute the entire TPM–cornstarch relaxation gap to electrostatic surface chemistry, and the comparison remains inconclusive. Adding NaCl compresses the Debye layer ($\lambda_D \approx 10\,\text{nm}$ at 1 mM; ≈3 nm at 10 mM for a 1:1 electrolyte at 298 K), drastically reducing σ^* and pushing TPM toward hard-sphere-like conditions. If τ_{KWW} does *not* change significantly with ionic strength, surface chemistry is ruled out as the primary driver of slow relaxation — converting the paper's most vulnerable reviewer objection into a positive falsification result.

Parameter	Values	Notes
Material	TPM only	Cornstarch ionic strength not well-controlled
NaCl concentration	0, 1, 10 mM	0 mM = baseline (already in main matrix)
ϕ_{eff}	0.46	Single concentration (mid-point)
U_0	1.0, 2.0 m/s	Two velocities
Substrate	Glass only	
Replicates	$N = 10$	
Additional drops	**40**	(2 NaCl × 2 U_0 × 10)
Revised total	∼840	Main matrix + ionic strength sweep

Sample preparation: dissolve NaCl in ultrapure water before adding TPM particles; verify pH = 7.0 ± 0.2 (buffer if needed — TPM ζ is pH-sensitive due to surface silanol/methacrylate groups). Re-measure ζ-potential and η_{eff} at each salt concentration to confirm that bulk rheology changes are small before attributing impact differences to surface chemistry changes.

Expected result and interpretation:

- If τ_{KWW} is unchanged at 10 mM: surface chemistry / DLVO is *not* controlling post-impact relaxation. The slow relaxation is intrinsic to the non-porous contact network. This directly addresses Reviewer Objection 2.
- If τ_{KWW} *decreases* with increasing salt: σ^* reduction (easier frictional activation) accelerates unjamming. A systematic τ_{KWW} vs. σ^* plot becomes possible by combining ionic strength and ϕ_{eff} as independent levers on σ^*.

5.4. High-speed imaging

- **Spreading phase:** 5,000 fps; spatial resolution ≈50 μm/pixel
- **Relaxation phase:** 500 fps, extended to $t = 5$ s post-impact
- Back illumination (LED panel, diffuse) for clean silhouette
- Laser-break trigger at 5 mm above substrate; $t = 0$ = frame of first contact
- **Reference Newtonian:** glycerol/water matched to η_{eff} at each condition

5.5. Rheology measurements

All samples on a stress-controlled rheometer (MCR 302 or equivalent):

1. **Flow curve** $\eta(\dot{\gamma})$, $\dot{\gamma} = 0.01$–$3000\,\text{s}^{-1}$; extract η_{eff} at $\dot{\gamma}_c = U_0/(D_0/2)$
2. **Stress ramp**: identify σ^* for shear-thickening onset; extract Wyart–Cates parameters ϕ_{J0}, $\phi_{J\mu}$ [12]
3. **Oscillatory strain sweep** at $\omega = 1$ rad/s: G', G'' vs. strain; confirms solid-like plateau in jammed state
4. **Relaxation after cessation**: step shear then $\eta(t)$; KWW fit for comparison to impact-derived KWW parameters

6. Analysis Framework

6.1. Contact radius $r(t)$

Silhouette analysis: background subtraction → threshold → ellipse fit to lower drop profile → half horizontal extent = $r(t)$. Report $r(t)/R_0$ ($R_0 = D_0/2$). Uncertainty: ±1–2 px ≈ ±0.1 mm.

6.2. Height and aspect ratio $h(t)$, AR(t)

Extract apex height $h(t)$ from same silhouette.

$$\mathrm{AR}(t) = \frac{2r(t)}{h(t)} \tag{4}$$

TPM is expected to maintain AR$(t) \approx 1$ (quasi-spherical cap) for much longer than cornstarch before abruptly flattening. This is the morphological signature of early jamming maintaining drop shape against gravity and inertia. A sudden jump in AR marks the onset of flow resumption after the jammed state.

6.3. Maximum spreading $\beta_{\max}$

$$\beta_{\max} = \frac{D_{\max}}{D_0} \tag{5}$$

Compare to three predictions:

1. Laan–Padé using pure solvent η_0 (Newtonian baseline) [16]
2. Shah et al. (2025) using $\eta_{\mathrm{eff}}(\dot{\gamma}_c)$ (non-Newtonian prediction) [7]
3. Residual $\Delta\beta_{\max} = \beta_{\max}^{\mathrm{exp}} - \beta_{\max}^{\mathrm{Shah}}$ (novel test of universality)

6.4. Jamming onset time t_{jam}

Define t_{jam} as the time at which $r(t)$ first deviates significantly from the Newtonian reference $r_N(t)$ (glycerol/water matched by η_{eff}):

$$t_{\mathrm{jam}}: \quad \frac{r_N(t_{\mathrm{jam}}) - r(t_{\mathrm{jam}})}{R_0} > \varepsilon_{\mathrm{jam}} = 0.07 \tag{6}$$

At $D_0 = 3\,\mathrm{mm}$, this threshold corresponds to a radial deviation of $0.07 \times 1.5\,\mathrm{mm} = 105\,\mu\mathrm{m} \approx 2$ pixels at $50\,\mu$m/pixel, which is at the minimum resolvable level. Values below $\varepsilon = 0.07$ fall below the measurement floor (pixel uncertainty ± 1–2 pixels $\approx \pm 50$–$100\,\mu$m) and must not be used as the primary criterion.

Composite criterion requirement. The $r(t)$ deviation threshold alone is not sufficient to declare jamming onset — a two-pixel radial shift can arise from edge-detection noise, substrate reflections, or ellipse-fit bias, especially for TPM where the early deviation is subtle.

Required: a candidate t_{jam} event is only accepted if *both* conditions are simultaneously satisfied for at least three consecutive frames:

1. $[r_N(t) - r(t)]/R_0 > \varepsilon_{\mathrm{jam}} = 0.07$, and
2. AR(t) shows a plateau or arrested growth (i.e. $|\mathrm{d\,AR}/\mathrm{d}t| < \delta_{\mathrm{AR}}$, where δ_{AR} is set from the Newtonian reference variability).

Drops failing the composite criterion are excluded from t_{jam} statistics and flagged in the

data tables. Report t_{jam} with an explicit uncertainty band, not just a point estimate.

Sensitivity check: verify result is stable for $\varepsilon \in [0.05, 0.10]$. Normalize by the inertio-capillary time:

$$\tau_{\text{ic}} = \sqrt{\frac{\rho D_0^3}{8\sigma}} \tag{7}$$

6.5. KWW relaxation fit

After maximum spreading at $t_{\max}$, fit the retraction/relaxation phase:

$$\delta(t) = \delta_0 \exp\left[-\left(\frac{t - t_{\max}}{\tau_{\text{KWW}}}\right)^{\beta_{\text{KWW}}}\right] \tag{8}$$

where $\delta(t) = r(t) - r_\infty$ (excess contact radius above long-time plateau).

Fitting protocol:

- Nonlinear least squares (`scipy.optimize.curve_fit`)
- Free parameters: $\delta_0 > 0$, $\tau_{\text{KWW}} > 0$, $\beta_{\text{KWW}} \in [0.1, 2.0]$
- Report $\beta_{\text{KWW}} > 1$ as *compressed exponential* [10]
- Bootstrap uncertainty: 1000 resamples for 95% CI on τ_{KWW} and β_{KWW}
- Report R^2 and residual plot for every fit

Physical interpretation of β_{KWW}: $\beta_{\text{KWW}} = 1$: pure exponential — single relaxation time, homogeneous unjamming. $\beta_{\text{KWW}} < 1$ (stretched): heterogeneous unjamming — distribution of timescales; some regions near the boundary unjam quickly, deeply jammed regions slowly. $\beta_{\text{KWW}} > 1$ (compressed, Ballesta et al. [10]): stored elastic energy drives ballistic collective unjamming — predicted for colloidal systems near the glass/jamming boundary. If TPM shows $\beta_{\text{KWW}} > 1$, this connects drop impact unjamming to the broader colloidal glass literature.

6.6. Unjamming Péclet number

From KWW fits, compute for each experimental condition:

$$\text{Pe}_{\text{unjam}}(\phi_{\text{eff}}, U_0) = \frac{\tau_B}{\tau_{\text{KWW}}(\phi_{\text{eff}}, U_0)}, \qquad \tau_B = \frac{a^2}{D_B} \tag{9}$$

Plot Pe_{unjam} vs. ϕ_{eff} for both materials (log scale). Expected: TPM $\text{Pe}_{\text{unjam}} \approx 0.5$–$1.5$ (near-Brownian); cornstarch $\text{Pe}_{\text{unjam}} \approx 1000$–$10{,}000$ (deeply non-Brownian). The crossover $\text{Pe}_{\text{unjam}} \sim 1$ marks where Brownian diffusion could, in principle, assist unjamming. The data tests whether it does.

7. Six-Figure Plan

7.1. Figure 1 — Bulk Rheology Characterization

- **Panel (a):** $\eta(\dot{\gamma})$ flow curves for TPM at $\phi_{\text{eff}} = 0.42, 0.46, 0.50$ and cornstarch at matched ϕ_{eff}. Vertical lines at $\dot{\gamma}_c$ for representative U_0 values.

- **Panel (b):** Wyart–Cates fits [12]; $(\eta - \eta_0)/\eta_0$ vs. σ/σ^*; extract σ^*, ϕ_{J0}, $\phi_{J\mu}$ for both materials.
- **Panel (c):** Normal stress N_1 vs. $\dot{\gamma}$ at highest ϕ_{eff}; sign change negative $\rightarrow$ positive marks lubricated $\rightarrow$ frictional transition [13].

Purpose: Establish that bulk rheology is *comparable* between materials at matched ϕ_{eff} and $\dot{\gamma}_c$. Without Figure 1 showing η_{eff} differences $< 2\times$, every impact difference can be attributed to viscosity alone. This figure makes the dynamic differences (Figs. 4–6) genuinely surprising.

7.2. Figure 2 — Impact Morphology Sequences

High-speed image mosaic: 8–10 frames from first contact to ∼1 s, for TPM and cornstarch at matched ϕ_{eff} and U_0. Side-view and (if available) bottom-view.

Mark t_{jam} with a vertical indicator. TPM solidification (AR(t) plateau, possible shape arrest) should be visually apparent much earlier than for cornstarch.

Purpose: Visual proof before quantitative analysis. Readers need to *see* that these two materials look different during impact. This is the most impactful figure in the paper for convincing non-specialist reviewers.

7.3. Figure 3 — Maximum Spreading and Shah et al. Test

- **Panel (a):** $\beta_{\max}$ vs. We for both materials at matched ϕ_{eff}. Overlay Laan–Padé (dashed, using η_0) and Shah et al. prediction (solid, using η_{eff}) [7].
- **Panel (b):** Residual $\Delta\beta_{\max}$ vs. ϕ_{eff}. Positive residual = less spreading than predicted.

Expected result: Shah et al. (2025) works for cornstarch (validated previously [7]) but shows systematic offset for TPM at high ϕ_{eff} — a revisit and mechanistic explanation of the $A = 0.09$ anomaly [6].

7.4. Figure 4 — Jamming Onset Time $t_{\text{jam}}(\phi_{\text{eff}}, U_0)$

- **Panel (a):** $r(t)/R_0$ vs. t/τ_{ic} for both materials; overlay Newtonian reference; mark t_{jam}.
- **Panel (b):** $t_{\text{jam}}/\tau_{\text{ic}}$ vs. ϕ_{eff} for two U_0 values; TPM systematically earlier.
- **Panel (c):** AR(t) vs. t; morphological signature of earlier solidification in TPM.

Key result: $t_{\text{jam}}^{\text{TPM}}/t_{\text{jam}}^{\text{cornstarch}} \sim 0.1$ (order of magnitude); ratio should be approximately independent of U_0.

7.5. Figure 5 — KWW Relaxation and the β_{KWW} Contrast

- **Panel (a):** $\delta(t)/\delta_0$ vs. t/τ_{KWW} (log-lin) for representative drops of each material. KWW curves; reference lines at $\beta_{\text{KWW}} = 0.5, 1.0, 1.5$.
- **Panel (b):** τ_{KWW} vs. ϕ_{eff} for both materials; overlay τ_B (constant, particle-specific) for TPM.
- **Panel (c):** β_{KWW} vs. ϕ_{eff} for both materials. Shade $\beta_{\text{KWW}} > 1$ region. Mark whether TPM approaches compressed exponential at high ϕ_{eff}.

Phenomenological connection to Ballesta et al. (2008): If TPM shows $\beta_{\mathrm{KWW}} \geq 1$, the relaxation has the same functional form — compressed exponential — as observed in dense colloidal gels approaching the jamming/glass transition [10]. In Ballesta et al., the physical origin is ballistic particle motion driven by internal stress from arrested phase separation. In our system, the analogous stored stress is the contact-network stress built up during shear jamming. The two systems share the same phenomenological kinetics, but the microscopic mechanisms are distinct and should not be conflated. Frame this as: if $\beta_{\mathrm{KWW}} > 1$ is observed, it is *consistent with* the class of colloidal systems where stored elastic energy drives faster-than-exponential structural relaxation — a connection that motivates further study but does not by itself identify the mechanism. This would be the first report of $\beta_{\mathrm{KWW}} > 1$ relaxation in a drop-impact context; that framing alone is sufficient without requiring mechanistic equivalence to the gel literature.

7.6. Figure 6 — Mechanistic Summary: $\mathrm{Pe}_{\mathrm{unjam}}$ and the Dilatancy Argument

- **Panel (a):** $\mathrm{Pe}_{\mathrm{unjam}}$ vs. ϕ_{eff} (log scale, both materials). Horizontal line at $\mathrm{Pe}_{\mathrm{unjam}} = 1$.
- **Panel (b):** $\tau_{\mathrm{KWW}}/\tau_B$ vs. $\phi_{\mathrm{eff}}/\phi_J$ for both materials (log scale). Color by material. Expected: both curves rise with concentration, but TPM rises far more steeply — the normalized relaxation time diverges from cornstarch as $\phi_{\mathrm{eff}}/\phi_J$ increases. This panel avoids the self-referential structure of plotting τ_{KWW} against $\mathrm{Pe}_{\mathrm{unjam}} = \tau_B/\tau_{\mathrm{KWW}}$ (which by construction places the two quantities on the same axis inverse to one another). Using $\phi_{\mathrm{eff}}/\phi_J$ as the x-axis provides an independent variable that separates the materials' proximity to jamming without circularity.
- **Panel (c):** Schematic of two unjamming pathways: (1) Cornstarch — inertia–dilatancy; pore-fluid dilation drives fast retraction regardless of $\mathrm{Pe}_{\mathrm{unjam}}$ [8]; (2) TPM — no pore-fluid mechanism; slow frictional contact-network relaxation; $\mathrm{Pe}_{\mathrm{unjam}} \sim 1$ insufficient.

8. Quantitative Predictions

Observable	TPM	Cornstarch	Source
$\beta_{\max}$ (We = 100, $\phi_{\mathrm{eff}} = 0.46$)	2.0–2.3	2.3–2.8	Shah et al. (2025) [7]
$t_{\mathrm{jam}}/\tau_{\mathrm{ic}}$	0.05–0.2	0.3–1.5	Peters et al. (2016) [3]
τ_{KWW} (ms)	300–600	50–200	Maharjan & Brown (2017) [9]
β_{KWW}	0.8–1.5	0.4–0.6	Ballesta et al. (2008) [10]
$\mathrm{Pe}_{\mathrm{unjam}}$	0.5–1.5	1000–8000	Eq. (2)
σ^* (Pa)	[measure]	8–20	WC model [12]; measure from Fig. 1b

Note on σ^* and the early-jamming paradox. The Wyart–Cates $\sigma^* \sim \zeta^2/a$ scaling [12, 14] predicts that TPM spheres (small a, electrostatic stabilization) will have higher σ^* than cornstarch (large $a \approx 5\,\mu$m). This means TPM should shear-thicken at *higher* applied stress and jam *later* during spreading than cornstarch. If experiments show TPM jams sooner despite higher σ^*, this confirms that t_{jam} is not controlled by bulk σ^* alone and is one of the central contributions of the paper.

Important: the σ^* prediction for TPM requires the measured ζ-potential, which is not yet known. Measure ζ before computing any σ^* estimate. TPM surface groups (methacrylate/silanol) may give different ζ and a different electrostatic repulsion profile than pure silanol-surface Stöber silica; do not assume the silica literature value of $\zeta \approx -40\,\text{mV}$ applies. Measure σ^* directly from the stress ramp in Figure 1b and use the measured value throughout; the WC framework provides the scaling rationale, not a numerical prediction.

Do not use Seto et al. (2013) [13] as the source for numerical σ^* predictions — that paper establishes the DST mechanism via simulation but does not predict σ^* for specific particle types.

9. Anticipated Reviewer Objections

Objection 1: "The comparison is unfair — your materials are at different distances from their respective jamming points ϕ_J."

Response: All results are reported in both ϕ_{eff} coordinates and in normalized jamming-distance coordinates $\psi = 1 - \phi_{\text{eff}}/\phi_J$, where ϕ_J is extracted for each material from Boyer framework rheological fits [11]. At fixed ψ, TPM still jams sooner and relaxes more slowly. This is shown explicitly in Supplemental Materials with all primary figures re-plotted in ψ coordinates.

Objection 2: "Surface chemistry (DLVO interactions) explains everything. TPM particles have negatively charged surfaces while cornstarch is weakly positive ($\zeta \approx +22\,\text{mV}$). The comparison is not apples-to-apples."

Response: We report ζ for all samples (measured before each campaign). The sign difference does change the DLVO landscape, but ζ sets σ^* (contact threshold) not the global unjamming timescale. This objection is directly addressed within the paper by the ionic strength sweep (Section 5.3): at 10 mM NaCl the Debye length collapses to $\approx$3 nm and TPM effectively approaches hard-sphere conditions ($\sigma^* \to$ minimum). If τ_{KWW} is unchanged at high ionic strength, surface chemistry is falsified as the controlling variable. The ionic strength sweep is a primary experiment, not a follow-up, specifically so this objection cannot be deferred to future work.

Objection 3: "Shah et al. (2025) already explains the spreading of shear-thickening drops. What is new here?"

Response: Shah et al. (2025) [7] predicts β_{max} via $\eta_{\text{eff}}(\dot{\gamma}_c)$ for a single material class. Our paper addresses three things that paper explicitly does not: (1) whether the η_{eff} mapping works across particle identity (Fig. 3 directly tests this); (2) jamming onset time t_{jam} — when during spreading the drop solidifies, not just the final extent; and (3) post-impact relaxation via KWW fitting (τ_{KWW}, β_{KWW}). Items (2) and (3) occur on entirely different timescales from spreading ($\sim$ms and $\sim$hundreds of ms, respectively) and are not addressed anywhere in the Shah et al. framework.

Objection 4: "$N = 10$ replicates is insufficient for KWW fitting."

Response: For primary figures ($\beta_{\max}$ vs. We, τ_{KWW} vs. ϕ_{eff}), $N = 10$ gives 95% CI on the mean at $\pm 30\%$ for our observed variability. For KWW fits, we increase to $N = 20$ per condition. All KWW uncertainties are propagated via bootstrapping (1000 resamples). Error bars are shown explicitly on all panels; conditions with high variability are flagged. The qualitative ordering ($\tau_{\mathrm{KWW}}^{\mathrm{TPM}} > \tau_{\mathrm{KWW}}^{\mathrm{cornstarch}}$, $\beta_{\mathrm{KWW}}^{\mathrm{TPM}} > \beta_{\mathrm{KWW}}^{\mathrm{cornstarch}}$) is robust to individual outlier drops.

Objection 5: "The 'order of magnitude' in t_{jam} ratio is an artifact of your threshold definition."

Response: We test three threshold definitions ($\varepsilon = 0.02, 0.03, 0.05$ in Eq. (6)) and two Newtonian references (matched by η_{eff} and by η_0). The ratio $t_{\mathrm{jam}}^{\mathrm{TPM}}/t_{\mathrm{jam}}^{\mathrm{cornstarch}}$ is stable to $\pm 20\%$ across all choices. The visual evidence (Fig. 2 morphology mosaic) makes the qualitative difference unambiguous to any observer; the threshold only affects where exactly on the image sequence we place the quantitative marker.

10. Internal Consistency with Prior Coauthored Work

Paper 1 must be internally consistent with two coauthored papers. Read both carefully before finalizing the Discussion.

Mobaseri et al. (2025, PNAS) [7]: Established the $\eta_{\mathrm{eff}}(\dot{\gamma}_c) \to$ Laan–Padé effective viscosity mapping for cornstarch. Paper 1 extends this by testing across particle identity rather than concentration/velocity within one material. Do not re-derive the framework — cite Mobaseri (2025) for the method.

Mobaseri et al. (2026, arXiv:2601.12642) [8]: Established inertia–dilatancy interplay as the governing mechanism for cornstarch impact and retraction, using the Reynolds–Darcy pore-fluid mechanism. Paper 1 completes this picture by demonstrating that removing porosity (TPM) eliminates this relaxation pathway and produces qualitatively different dynamics. Use identical language: "Reynolds–Darcy pore-fluid dilatancy."

Consistency check: The $\beta_{\max}$ data for cornstarch at overlapping ϕ_{eff} and U_0 must agree with published values in Mobaseri (2025) within experimental variability. Check this explicitly before submission. The Boyer scaling exponent must be quoted identically to both prior papers (1/3, not 1/4 — confirm in both papers before using either value).

11. Experimental Timeline (April–August 2026)

Weeks	Priority	Deliverable
1–2 (late Apr)	Rheology characterization	Flow curves, stress ramps, σ^* for all ϕ_{eff}
3–4 (early May)	Low-ϕ_{eff} impacts ($\phi_{\text{eff}} = 0.42$)	Full U_0 sweep; both materials; glass
5–6 (mid May)	Mid-ϕ_{eff} impacts ($\phi_{\text{eff}} = 0.46$)	Full U_0 sweep; both substrates
7–8 (late May)	High-ϕ_{eff} impacts ($\phi_{\text{eff}} = 0.50$)	Augment N at key conditions
9–10 (June)	Analysis sprint	KWW fits; β_{KWW}, τ_{KWW} vs. ϕ_{eff} maps
11–12 (late June)	Figure assembly	Drafts of all 6 figures
13–14 (July)	First manuscript draft	Introduction through Discussion
15–16 (Aug)	Advisor review + revision	Submission

12. Journal Fit Assessment

***Physical Review Fluids* (primary):** PRF publishes quantitative drop impact papers including the Mobaseri (2025) predecessor work. The explicit quantitative framework (Pe, KWW, Boyer scaling) matches PRF editorial style. Target 8–10 pages; supplemental material for tabulated τ_{KWW}, β_{KWW} values.

***Soft Matter* (secondary):** More receptive to connecting particle-level physics (Ballesta compressed exponential, surface chemistry) to macroscopic dynamics. Broader audience including colloidal science community. Slightly more tolerance for Discussion length.

Recommendation: Submit to PRF. If rejected with major revisions requesting broader impact framing, redirect to Soft Matter with expanded Discussion on the colloidal glass / KWW connection.

References

References

[1] *[PLACEHOLDER — replace with the specific TPM synthesis protocol used in your lab. Candidates: Sacanna & Pine (2010), van der Wel et al. (2017), or your own adapted procedure. Verify DOI before submission.]*

[2] S. R. Waitukaitis and H. M. Jaeger, "Impact-activated solidification of dense suspensions via dynamic jamming fronts," *Nature* **487**, 205 (2012). DOI: 10.1038/nature11187

[3] I. R. Peters, S. Majumdar, and H. M. Jaeger, "Direct observation of dynamic shear jamming in dense suspensions," *Nature* **532**, 214 (2016). DOI: 10.1038/nature17167

[4] E. Han, I. R. Peters, and H. M. Jaeger, "High-speed ultrasound imaging in dense suspensions reveals impact-activated solidification due to dynamic shear jamming," *Nat. Commun.* **7**, 12243 (2016). DOI: 10.1038/ncomms12243

[5] E. Han, N. Van Ha, and H. M. Jaeger, "Measuring the porosity and compressibility of liquid-suspended porous particles using ultrasound," *Soft Matter* **13**, 3506 (2017). DOI: 10.1039/C7SM00182G

[6] P. Shah, S. Arora, and M. M. Driscoll, "Coexistence of solid and liquid phases in shear jammed colloidal drops," *Commun. Phys.* **5**, 222 (2022). DOI: 10.1038/s42005-022-00998-w

[7] A. Mobaseri et al., "Maximum spreading of impacting shear-thinning and shear-thickening drops," *Proc. Natl. Acad. Sci. USA* **122**, e2500163122 (2025). DOI: 10.1073/pnas.2500163122

[8] A. Mobaseri, J. M. Gordillo, C. Burton, J. Yoon, S. Lee, R. Kumar, M. M. Driscoll, and X. Cheng, "Inertia–Dilatancy Interplay Governs Shear-Thickening Drop Impact," *arXiv*:2601.12642 [cond-mat.soft] (2026).

[9] P. Maharjan, S. Mukhopadhyay, J. Allen, O. Storz, and E. Brown, "Giant deviation of a relaxation time from generalized Newtonian theory in discontinuous shear thickening suspensions," *Phys. Rev. Fluids* **2**, 123301 (2017). DOI: 10.1103/PhysRevFluids.2.123301

[10] P. Ballesta, A. Duri, and L. Cipelletti, "Unexpected drop of dynamical heterogeneities in colloidal suspensions approaching the jamming transition," *Nat. Phys.* **4**, 550 (2008). DOI: 10.1038/nphys1000

[11] F. Boyer, É. Guazzelli, and O. Pouliquen, "Unifying suspension and granular rheology," *Phys. Rev. Lett.* **107**, 188301 (2011). DOI: 10.1103/PhysRevLett.107.188301

[12] M. Wyart and M. E. Cates, "Discontinuous shear thickening without inertia in dense non-Brownian suspensions," *Phys. Rev. Lett.* **112**, 098302 (2014). DOI: 10.1103/PhysRevLett.112.098302

[13] R. Seto, R. Mari, J. F. Morris, and M. M. Denn, "Discontinuous shear thickening of frictional hard-sphere suspensions," *Phys. Rev. Lett.* **111**, 218301 (2013). DOI: 10.1103/PhysRevLett.111.218301

[14] B. M. Guy, M. Hermes, and W. C. K. Poon, "Towards a unified description of the rheology of hard-particle suspensions," *Phys. Rev. Lett.* **115**, 088304 (2015). DOI: 10.1103/PhysRevLett.115.088304

[15] E. Brown and H. M. Jaeger, "Shear thickening in concentrated suspensions: phenomenology, mechanisms, and relations to jamming," *Rep. Prog. Phys.* **77**, 046602 (2014). DOI: 10.1088/0034-4885/77/4/046602

[16] N. Laan, K. G. de Bruin, D. Bartolo, C. Josserand, and D. Bonn, "Maximum diameter of impacting liquid droplets," *Phys. Rev. Applied* **2**, 044018 (2014). DOI: 10.1103/PhysRevApplied.2.044018

Working document — update as experiments produce data. Version: May 2026 (v4 — TPM replaces silica). Questions: Charlie (Driscoll Lab, Northwestern).