Hydrogel Drying-Failure Research Roadmap

Mode Selection — Crack, Peel, and Curl — in Drying PEGDA/PEGMEA Gels

A ground-zero rebuild for a one-month, equipment-light campaign

Charlie Burton — Driscoll Lab, Northwestern University

June 2026

Contents

Purpose and Scope 1

1 The Central Question and Thesis 1

2 What Changed, and the Shamah Quarantine 2

3 Novelty and Positioning 2

4 Design: Control Axes and Observables 3
- 4.1 Control axes . . . 3
- 4.2 Camera-measured observables (per run) . . . 3

5 The One-Month Plan 3

6 Camera-First Mechanics: Measuring E, Γ, and ℓ_Γ 4

7 Protocol A: Diffusivity and Biot Number from the Equilibration Curves 5

8 Protocol B: Does Crack Precede Peel, Universally? 5
- 8.1 Side-view observables (all from a high-speed profile) . . . 6
- 8.2 Rig, practice, and a causal test . . . 6

9 Length Ledger and the Operational Biot Number 7

10 Falsifiable Predictions 7

11 Risks and Mitigations 8

Key References 8

Purpose and Scope of This Document

This is the working research plan for the next hydrogel paper, rebuilt from the ground up in June 2026. Two facts force the rebuild. First, *all data from the Shamah thesis are quarantined* — untrusted and to be recollected — which removes the empirical spine (the $h \approx 0.5$ mm peel "plateau," the 14× acetone/ethanol velocity ratio, the swelling-fracture table) on which the previous roadmap and outlook leaned. Second, the campaign is now *equipment-light*: a high-speed camera, a temperature-controlled box, an analytical balance, UV cure with PEG monomers, and simple dead loads, with only *occasional* rheometer/tensile access for cross-validation. The prior Aim 3 (routine rheometer + pure-shear rig) is replaced by camera-and-dead-load mechanics.

The document is scoped to a ∼**one-month** experimental push whose **headline deliverable is the first quantitative crack/peel/curl mode-selection phase diagram for a drying *covalent* PEG gel**, with the controlling length scales measured independently and camera-first. Risk posture is "balanced": a clean descriptive dataset is locked early (Week 1), and the predictive/quantitative claims are pushed with the remaining time.

1 The Central Question and Thesis

Definitive question. When a swollen covalent PEG network dries, what selects whether it relieves stress by *vertical channel cracks*, *horizontal peeling/exfoliation*, or *whole-layer curling* (the "cinnamon roll"), and can that selection be predicted from independently measured material and transport length scales rather than described after the fact?

Three sharpened sub-questions organize the work:

Q1. Mode selection. What sets crack vs. peel vs. curl?

Q2. Network control. How do crosslink density, modulus, and toughness set the emergent lengths (peel thickness, crack spacing, curl radius)?

Q3. Solvent control. How do volatility, viscosity, and solvent quality χ move those lengths?

Central thesis. Morphology is a competition between two lengths. The *network* fixes a material length $\ell_\Gamma \equiv \Gamma/E$ (fracture energy over modulus; units of length). The *solvent and drying* fix a kinetic length — the drying-front width w. Every observable length (peel thickness, crack spacing, curl radius) is a function of ℓ_Γ and w, and every mode transition is a threshold in their ratio together with the wet/dry toughness gradient. Measure ℓ_Γ and the front, and the phase diagram becomes predictive. The point of an equipment-light program is that both quantities are obtainable from a camera, a balance, and dead weights.

2 What Changed, and the Shamah Quarantine

Data provenance. Every Shamah-thesis quantity is treated as a *hypothesis to test*, not a fact, until independently remeasured: the constant peel thickness $h \approx 0.5$ mm; the $\approx 13.7\times$

acetone/ethanol crack-velocity ratio; the swelling-fracture table (which crosslink ratios survive water); crack-initiation times; and the "flux is everything" conclusion. Consequence: the previously celebrated agreement between $D_p Bi^2$ and the 14× ratio was a *fit* to Shamah's number and is now void; the corresponding figure must be regenerated from fresh data.

The earlier framing also inherits a **dimensional error** that is corrected throughout this document: the drying-front width is $w \sim D_p/v_f$ (with v_f a velocity), *not* $w \sim \sqrt{D_p/v_f}$; the square-root form is valid only for a boundary-layer thickness $\sim \ell/\sqrt{\mathrm{Pe}}$.

3 Novelty and Positioning

The open seam. Chung, Regev & Mahadevan (*Soft Matter* 2016), the foundational drying-exfoliation paper (PDMS/hexanes), has ∼8 citations and *zero experimental follow-ups on drying exfoliation of a covalent gel*. No PEG drying-fracture paper exists. A three-mode (crack/peel/curl) selection map for a drying *covalent, poroelastic* PEG network — with stress from network osmotic deswelling rather than capillary/granular pressure, and with *peeling/exfoliation as the under-mapped third mode* — is open.

The novelty is moderate but defensible, and must be carved explicitly against two neighbors:

- **Scoop risk (colloidal).** Meng, Liu, Gan, Pauchard & Chen, "Cracking to curling transition in drying colloidal films," *EPJE* **43**, 64 (2020) — a crack↔curl phase diagram, but for *particulate* films (capillary stress, only two modes). Differentiate on material physics (covalent/poroelastic) and the third (peel) mode.
- **In-house overlap (swelling).** The Driscoll/Szczepanski program owns the *swelling* direction and crack *initiation* — VanZanten et al., *Soft Matter* **20**, 6742 (2024); Wu et al., *SSRN* 5644468 (2025), "Control Parameters for Swelling-induced Fracture." Position this work as the **deswelling mirror**: failure-*mode selection*, not transient elastic surface patterns.

Framing. Lead with (i) the deswelling mirror of the well-mapped swelling-instability canon, and (ii) failure-mode selection in a covalent poroelastic gel with exfoliation as a new regime. Do *not* sell "camera + balance" as a method novelty — it is the standard desiccation-crack toolkit; sell the minimal-equipment angle as accessibility/reproducibility and the science as a *predictive collapse* of camera-measured lengths onto a covalent-gel mode boundary. (Watch: Yang/Style/Dufresne, "Dehydration drives damage in freezing of brittle hydrogels," *Sci. Adv.* 2024 — an elite group circling hydrogel dehydration-fracture.)

4 Design: Control Axes and Observables

4.1 Control axes

- **Crosslink density** (PEGDA:PEGMEA molar ratio) — highest leverage; sets swelling ratio Q, modulus E, brittleness, and ℓ_Γ at once. Levels 1:99, 2:98, 5:95, 10:90, 20:80, 30:70.

- **Solvent** — acetone, ethanol, water, and acetone/ethanol *blends* (0/25/50/75/100 vol% acetone).
- **Drying rate** — box temperature 20/40/60/80 °C (raises evaporative flux J_0).
- **Thickness** (secondary) — 0.5/1/2 mm for length-scale scalings.
- Replicates $n = 3$–4.

4.2 Camera-measured observables (per run)

Mode (crack/peel/curl); onset time t_c; **peel thickness** h (side-view); **crack spacing / polygon area** Λ, A_p (top-view); **curl radius** ρ (arc fit); fragment size L; crack velocity v_c (high-speed); mass-loss $m(t)$ (balance); side-view half-thickness $H(t)$.

5 The One-Month Plan

Week	Action	Unlocks / output
0	Synthesis SOP; thickness molds; camera/box/balance/backlight setup; **solvent-compatibility check** (acetone is marginal for high-MW PEG); gravimetric flux calibration $J_0(T, \text{blend})$; swelling-equilibration curves $Q(t)$ (§7); recalibrate the in-house model.	J_0, Q_{eq}, ε_0, D_{p}; re-baseline
1	**Safe deliverable:** crosslink sweep in *acetone* at fixed thickness/T; record all observables; high-speed on fast events.	Crack→peel→curl backbone (guaranteed result)
2	Add ethanol, water, 2–3 blends; add the T/drying-rate axis on a reduced set; thickness sub-series; begin the mechanism (crack-vs-peel) imaging (§8).	Fill $(J_0, \text{crosslink})$ and (T) planes; test $A_p \propto h^{4/3}$, $\rho \approx h/3\bar{\varepsilon}$
3	**Mechanics linchpin:** camera E (gravity-sphere indentation), dead-load Γ (pure shear), camera-only fractocohesive length; compute ℓ_Γ; cross-check on rheometer/tensile.	$\ell_\Gamma = \Gamma/E$ per crosslink
4	Synthesis: does ℓ_Γ predict h and the boundaries (no free parameter)? Build $\text{Bi}(t)$ trajectories; test $J_0\mu$ scaling via blends; assemble phase diagram and collapse plots.	Predictive tests; figures; draft

6 Camera-First Mechanics: Measuring E, Γ, and ℓ_Γ

Why this is possible without a rheometer. A hanging dead weight is a drift-free absolute force ($F = mg$), so pure-shear toughness needs no load cell; what dead loads cannot give is controlled *velocity*, which only rules out the cutting-toughness family. And

the *fractocohesive length* is obtainable from images alone — a ratio of lengths, no force at all.

Quantity	Method	Equation	Accuracy
E	Gravity-sphere indentation, optical (Gandin 2021) + finite-thickness ψ-correction (Long 2011)	$E = 9F/(16R^{1/2}\delta^{3/2}) \cdot \psi$, $F = (\rho_s - \rho_f)Vg$	∼10%
Γ	Pure shear / planar tension, dead-load step-loading + camera fiducials (Rivlin–Thomas)	$\Gamma = W(\lambda_c)\, H_0$	±15%
ℓ_{fc}	Notch-length series, rupture stretch vs. notch length (camera-only, *no force*)	knee of $\lambda_c(c) \approx \ell_{fc}$	factor ∼2
ε_0	Equilibrium swelling ratio	$\varepsilon_0 = 1 - Q_{\mathrm{eq}}^{-1/3}$ (linear)	good

Key relation: $\ell_\Gamma = \Gamma/E = \ell_{fc} \cdot f(\lambda_c)$, with neo-Hookean $f = (\lambda_c^2 + 2/\lambda_c - 3)/6$. For brittle low-stretch PEGDA ($\lambda_c \approx 1.1$–1.5), $\ell_\Gamma \approx \ell_{fc}$; for stretchy gels ℓ_Γ is 4–16× larger. Expect $\ell_\Gamma \approx 0.1$–1 mm.

Mechanics pitfalls. Finite-thickness artifact can reach ∼600% if ignored (keep $\delta/h \approx 0.1$–0.4, $R/h \approx 0.3$–6). Equilibrium reads give the *drained* modulus (∼10–40% below a high-frequency rheometer G' — a real offset to reconcile on the cross-check). Swelling→Flory–Rehner modulus is *relative only* unless χ is calibrated ($G \propto \frac{1}{2} - \chi$ diverges at $\chi = 0.5$).

7 Protocol A: Diffusivity and Biot Number from the Equilibration Curves

The Week-0 curves do double duty: they yield the collective (poroelastic) diffusivity D_p *and* the surface transfer k_m, and they calibrate the in-house solver (`swelling_model/diffusion2d.py`), whose $D(\phi_\mathrm{p}) = (k/\mu)\, M_{os}$, `calibrate_Kperm`, Tanaka–Fillmore form, and $\sqrt{t}$/Bi variants already exist.

The gravimetric curve gives the *collective* D_p, which is ϕ_p-dependent, so any single number is an average over the traversed range. Collect *both* swelling-in-bath and drying-in-air curves; the deswelling (high-ϕ_p, low-k) value is the fracture-relevant one. Report a bracket.

Two model-free extractions (do both; agreement is the Fickian check). For a disc of full thickness ℓ, radius ≫ thickness (axial-1D) or rim-sealed:

$$\text{Early-time } (M_t/M_\infty \lesssim 0.6): \quad \frac{M_t}{M_\infty} = \frac{4}{\ell}\sqrt{\frac{Dt}{\pi}} \;\Rightarrow\; D = \pi\left(\frac{\text{slope}\cdot\ell}{4}\right)^2, \tag{1}$$

$$\text{Long-time (Tanaka–Fillmore):} \quad \ln\!\left(1 - \frac{M_t}{M_\infty}\right) = \text{const} - \frac{\pi^2 D}{\ell^2}\, t. \tag{2}$$

If $D_{\text{short}} \neq D_{\text{long}}$, that is the signature of ϕ_{p}-dependence (quote both ends). Fitting $M_t/M_\infty \propto t^n$ diagnoses the mechanism: $n \approx 0.5$ Fickian; $n \approx 1$ Case II (a moving sharp front — direct evidence of the self-sharpening the theory needs); intermediate is anomalous.

Bath vs. air — where Bi hides. In a solvent *bath* the surface sits at liquid equilibrium (Bi $\to \infty$, diffusion-limited): the initial $\sqrt{t}$ slope is effectively infinite and gives clean internal D. Drying in *air* has finite k_m: the initial slope is *finite*, and a naïve $\sqrt{t}$ fit returns a too-small D. Fit both parameters — D and k_m — and obtain Bi $= k_m \ell / D$ as a byproduct, feeding the dynamic-Biot thread (§9). Tell the two regimes apart by whether the initial slope is infinite or curves finitely from the origin.

Decompose. Calibrating K_{perm} to each curve returns $D(\phi_{\text{p}}) = (k/\mu)M_{os}$, splitting each solvent's D into a viscosity factor ($\propto 1/\mu$) and a thermodynamic factor (M_{os}, carrying the activity correction $(1 - 2\chi\phi_{\text{p}})$). This directly tests $D \propto 1/\mu$ across acetone/ethanol/water, the χ-dependence (and exposes acetone's marginal-solvent risk if $M_{os} \to 0$), and D vs. crosslink through $k \propto \xi^2 \propto \phi_{\text{p}}^{-m}$. *Pitfalls:* moving boundary (ℓ changes on swelling — reference to the dry frame / use the Lagrangian solver); edge effects (thin disc or Crank finite-cylinder product solution); consistent blot protocol, or a continuous balance for the air curves.

8 Protocol B: Does Crack Precede Peel, Universally?

The claim under test. Chung–Mahadevan assert a *causal sequence at one site*: a vertical/radial crack nucleates at the free surface *first*, is arrested by the wet/dry toughness gradient, and *deflects* into a horizontal peel — one continuous, surface-initiated crack. Three commitments: (1) *order* (vertical before horizontal); (2) *continuity* (the peel is the deflected continuation, not an independent subsurface crack); (3) *initiation depth* (top surface, not subsurface).

Falsify against: **H1** peel-first/blister (subsurface delamination first; cracks segment it later); **H2** independent nucleation; **H3** *regime-dependent switching* — the order is not universal. H3 is the "agnostic of geometry/solvent/crosslinker?" question and the likely real answer.

8.1 Side-view observables (all from a high-speed profile)

- **Kymograph (workhorse).** A vertical pixel-line through a peel site → a depth–time (z, t) image. It timestamps t_{crack} and t_{deflect} and reveals whether the crack line *bends* (continuity, H0) or a horizontal feature *appears independently* at depth (H1).
- **Crack-tip trajectory.** A continuous down-then-turn path confirms deflection; a horizontal opening with no prior descent denies it.
- **Initiation depth.** Surface vs. subsurface, read directly in profile.
- **Front co-location.** The dry skin differs optically from the wet interior (enhance with a partitioning dye or crossed polarizers). If the deflection depth equals the front position at t_{deflect}, that is quantitative support for the toughness-gradient mechanism, not merely the kinematic order.

8.2 Rig, practice, and a causal test

Backlit profile; slow the process first (ethanol / low box-T) to establish the kymograph signatures, then use the Phantom pre-trigger circular buffer for fast acetone; auto-trigger on a frame-difference / intensity spike; *synchronize a top view* (shared trigger or an LED flash fiducial) so the radial crack (top) and the deflection (side) share one clock; fix px/mm per run (no hardcoded scale). **Best geometry:** a "2.5-D" drying cell — a gel slab between two glass plates with one open edge, drying laterally — gives an unobstructed, in-focus profile of the front and crack tip under controlled 1-D drying (also ideal for Protocol A). **Causal test (razor + camera):** pre-cut a shallow vertical notch; if peels reliably initiate at the notch, vertical-crack-first causality is supported; if they are independent of it, that argues for H1.

Deliverable: a mechanism map. Classify each run's ordering (*crack→peel / peel→crack / simultaneous / curl-without-crack*) across geometry × solvent × crosslink and overlay it on the morphology phase diagram. *Predicted (falsifiable):* the crack→peel order is regime-specific — it holds in the peel regime, breaks in the curl regime (compressive buckling, no preceding vertical crack), and degenerates in the brittle/high-crosslink regime (cracks that never deflect). Mapping the *boundary of validity* of Chung's mechanism is a cleaner result than a flat confirm/deny.

9 Length Ledger and the Operational Biot Number

Length	Scaling	Set by
Network length ℓ_Γ	Γ/E	crosslink (Γ, E)
Front width w	D_p/v_f *(corrected; not $\sqrt{\cdot}$)*	D_p (network), v_f (solvent flux)
Peel thickness h	$\ell_\Gamma^{1/3} w^{2/3}$ (Chung)	$\ell_\Gamma \times w$
Crack spacing / area	$\Lambda \propto h^{2/3-1}$, $A_p \propto h^{4/3}$	thickness (modulus-set)
Curl radius ρ	$\approx h/3\bar{\varepsilon}$ (locked)	h, differential strain

The three solvent knobs collapse into one measurable number, the drying Biot number $\mathrm{Bi} = k_m H/D_\mathrm{p}$, extracted on the fly from $m(t)$ and $H(t)$. With the corrected front width, $w \approx H/\mathrm{Bi}$, so $h \propto \mathrm{Bi}^{-2/3}$; the peeling threshold becomes a network-set critical value $\mathrm{Bi}_c \sim (H/\varepsilon_0 R)\sqrt{\ell_\Gamma/R}$, and the failure rate carries an extra D_p: rate $\sim D_\mathrm{p}\mathrm{Bi}^2/H^2$.

The $J_0\mu$ trap (design-critical). The drying-stress gradient scales as $\nabla\varepsilon \propto J_0\mu/(Ek)$ (Scherer; Hennessy–Craster–Matar's "drying number" $Q \propto J_0\eta/kE$). But pure acetone and pure ethanol *nearly cancel* on this group: (flux ratio ≈ 3.9)×(viscosity ratio $0.32/1.07$) ≈ 1.2 — the two pure solvents sit on the *same* $J_0\mu$ contour. **Blends are therefore essential** to move off the contour and test the scaling. Matched surface tensions (∼22–23 mN/m) make the pair unusually clean; the confound to model is surface enrichment in ethanol during drying (both μ and J_0 drift).

10 Falsifiable Predictions

P1. Length scale. Measured ℓ_Γ (no free parameter) predicts the observed peel thickness h and the crack↔peel boundary; if h instead tracks $J_0^{-2/3}$ over the blend range, the ℓ_Γ-dominated picture is wrong (and that is the headline instead).

P2. Mode boundary. Crack→peel occurs where ε_0 (from measured Q) drops below the $\sqrt{\ell_\Gamma/h^3}$ threshold.

P3. Flux/viscosity. Lengths collapse on $J_0\mu$, not J_0 alone — requires blends.

P4. Curl identity. Curl curvature obeys $\rho \approx h/3\bar{\varepsilon}$ (mud peel) or the Euler buckling L_c; either is a result.

P5. Toughness gradient. UV-cure-asymmetric gels peel on the steeper-gradient face; uniformly cured controls crack symmetrically.

P6. Universal Bi_c. $\mathrm{Bi}(t^\star)$ at failure collapses to one solvent-independent value; if each solvent fails at a different Bi, the threshold model is wrong.

P7. Mechanism ordering (§8). The crack→peel sequence is regime-specific, not universal; a single universal ordering across all conditions would refute this.

11 Risks and Mitigations

Risk	Mitigation
Acetone may be a poor solvent/precipitant for high-MW PEG ($\chi \approx 0.5$, MW-dependent)	Week-0 compatibility check; swap solvent or restrict crosslink range if it precipitates
χ for PEG–ethanol/–acetone untabulated	Measure Q_{eq} directly; do not rely on literature χ
Drying reproducibility (humidity, esp. water)	Box for T (+ humidity if possible); log ambient RH every run
Slow water/curl runs	Overnight time-lapse; accelerate with box T
Pure-shear on swollen strips dries mid-test / grips slip	Solvent-saturated atmosphere; wide bonded grips, width $\geq$ 5–10 $\times$ H_0; report equilibrium values
Drained vs. dynamic modulus offset	Reconcile camera-E (drained) with rheometer G' on the cross-check subset
One month is tight	Week-1 acetone mode map is the guaranteed deliverable; everything after is upside

Key References

- Chung, Regev & Mahadevan, *Spontaneous exfoliation of a drying gel*, Soft Matter **12**, 7855 (2016). — backbone.
- Meng, Liu, Gan, Pauchard & Chen, *Cracking to curling transition in drying colloidal films*, EPJE **43**, 64 (2020). — scoop #1.

- VanZanten, Chen, Driscoll & Szczepanski, Soft Matter **20**, 6742 (2024); Wu et al., SSRN 5644468 (2025). — in-house swelling lineage.
- Style, Peppin & Cocks, *Mud peeling…*, JGR Earth Surf. **116**, F01025 (2011). — $\rho \approx h/3\bar{\varepsilon}$.
- Ma, Lowensohn & Burton, *Universal scaling of polygonal desiccation cracks*, PRE **99**, 012802 (2019). — $A_p \propto h^{4/3}$.
- Singh & Tirumkudulu, PRL **98**, 218302 (2007); Tirumkudulu & Russel, Langmuir **21**, 4938 (2005). — CCT, $\sigma_c \propto h^{-2/3}$.
- Lilin, Ibrahim & Bischofberger, *Crack densification…*, Sci. Adv. **10**, eadp3746 (2024). — crack kinetics.
- Chen, Wang & Suo, Extreme Mech. Lett. **10**, 50 (2017); Yang, Yin & Suo, JMPS **131**, 43 (2019); Ma et al., Adv. Mater. 2311795 (2024). — fractocohesive length.
- Gandin et al., Sci. Rep. **11**, 22668 (2021); Long et al., Biophys. J. **101**, 643 (2011). — camera indentation + finite-thickness.
- Rivlin & Thomas, J. Polym. Sci. **10**, 291 (1953); Long & Hui, Soft Matter **12**, 8069 (2016). — pure-shear toughness.
- Flory & Rehner (1943); Merrill et al., Biomaterials **14**, 1117 (1993, $\chi_{\text{PEG-water}} \approx 0.43$); Akalp & Bryant, Polymer **66**, 135 (2015). — swelling thermodynamics.
- Tanaka & Fillmore, JCP **70**, 1214 (1979); Offeddu et al., AIP Adv. **8**, 105006 (2018, $k \propto \xi^2$). — poroelastic D_{p}.
- Hennessy, Craster & Matar, PRE **105**, 054602 (2022, drying number); Boulogne, Pauchard & Giorgiutti-Dauphiné, Soft Matter **8**, 8505 (2012); Tan et al. (2025). — solvent/cosolvent control.