FH2FHFH$\Delta 0\chi_{\mathrm{FH}}$

Driscoll Laboratory · Department of Physics & Astronomy · Northwestern University · Evanston, IL

Structural Failure in Polymer Hydrogels During Solvent Evaporation

A Research Roadmap Toward Publication

Building on:	Shamah (2026) undergraduate thesis; Chung, Regev & Mahadevan, *Soft Matter* **12**
System:	PEG-based hydrogels (PEGDA / PEGMEA)
Solvents:	Acetone, ethanol, water, and binary mixtures thereof
Date:	May 2026
Status:	Internal planning document

Abstract

We present a comprehensive research roadmap for the next publication arising from ongoing work on drying-induced delamination in poly(ethylene glycol)-based (PEG) hydrogels in the Driscoll Laboratory at Northwestern University. The roadmap synthesizes the prior art landscape, identifies unexplored theoretical and experimental space, and proposes three interconnected research aims: (1) a binary-solvent phase diagram that decouples evaporative flux from solvent–polymer thermodynamics; (2) a mechanistic characterization of the qualitatively new "cinnamon-roll" fracture mode observed in water-swollen PEG gels; and (3) a test and extension of the Chung–Mahadevan poroelastic scaling law to PEG systems, incorporating the Flory–Huggins interaction parameter χ_{FH} and a modified strain-gradient relation. The roadmap includes detailed theoretical derivations and extensions, experimental protocols, expected outcomes, and a ten-month timeline toward submission to *Soft Matter* or *Physical Review E*.

Contents

1. Introduction and Framing

When a soft, swollen polymer gel is removed from its solvent bath and exposed to air, the competition between elastic network forces, solvent chemical potential, and capillary stresses at receding liquid–air interfaces drives a rich array of mechanical instabilities: smooth deswelling, surface wrinkling, vertical cracking, layer exfoliation, or catastrophic fracture into large curved fragments. Understanding which mode is selected – and why – is both a fundamental question in non-equilibrium soft matter and practically important for the design of hydrogel-based drug delivery systems, tissue scaffolds, and wearable sensors.

The foundational experimental and theoretical work by **Chung, Regev, and Mahadevan ?** established a minimal framework for the exfoliation instability in PDMS gels swollen in hexanes. They demonstrated that: (i) a critical evaporative flux J_{0c} must be exceeded for exfoliation to occur; (ii) the emergent peel thickness h scales as $h \sim (\Gamma/E(\nabla\varepsilon)^2)^{1/3}$; and (iii) both a sharp strain gradient *and* a coincident toughness gradient – both produced by the advancing drying front – are necessary conditions. The model was later connected to the earlier theory of thermal spalling and mud peeling **??**.

More recently, **Shamah ?** extended this phenomenology to PEG-based hydrogels (PEGDA/PEGMEA), using acetone, ethanol, and water as solvents. The central finding is that *evaporative flux is the primary control parameter*: gel thickness and crosslinker concentration produce no measurable change in crack or peel morphology, only in the timescale on which behaviors occur. Qualitatively, PEG gels in acetone and ethanol show similar exfoliation patterns to PDMS. However, water-swollen PEG gels exhibit an entirely distinct fracture mode – fragments curl into large curved pieces resembling a cinnamon roll – that has no analog in the PDMS system and remains completely uncharacterized.

The central tension for the next publication is this: Shamah has shown that flux governs behavior, but her data show peel thickness $h \approx 0.5\,\text{mm}$ regardless of all tested conditions, apparently inconsistent with the Chung scaling law which predicts a strong dependence of h on J_0 and . The binary-solvent experiments proposed here are designed to resolve this tension by greatly widening the accessible range of J_0 at room temperature, while simultaneously providing the platform from which the theoretical framework can be tested, extended, and applied to the water mode.

This document is organized as follows. **??** provides a thorough review of the theoretical foundations – poroelastic fracture, the Chung scaling derivation, the Style–Peppin mud-peeling model, and the Flory–Rehner framework for swelling thermodynamics – together with new theoretical developments relevant to the proposed work. **??** surveys the prior art landscape. **??** presents the three research aims in experimental and theoretical detail. **??** gives the project timeline. **??** summarizes how this work is differentiated from existing literature.

2. Theoretical Background and New Developments

2.1. Poroelasticity: The Governing Framework

A swollen polymer gel is naturally described as a biphasic poroelastic solid: an elastic polymer network pervaded by a mobile fluid **??**. In the linear poroelastic formulation, the network displacement field $\mathbf{u}$ and the fluid pore pressure p are coupled through:

$$\nabla^2\mathbf{u} + \frac{1}{1-2\nu}\nabla(\nabla\cdot\mathbf{u}) = \frac{2(1-2\nu)}{E(1-\nu)}\nabla p \tag{1}$$

$$\frac{\partial p}{\partial t} = D_{\mathrm{p}}\nabla^2 p - \frac{D_{\mathrm{p}}B}{\kappa_u}\frac{\partial(\nabla\cdot\mathbf{u})}{\partial t} \tag{2}$$

where ν is the drained Poisson ratio, B is Skempton's coefficient, κ_u is the undrained bulk modulus, and

$$D_{\mathrm{p}} = \frac{kE(1-\nu)}{(1-2\nu)(1+\nu)} \tag{3}$$

is the poroelastic diffusivity with permeability k (Darcy). The characteristic timescale for poroelastic equilibration over a length scale ℓ is

$$\tau_p = \frac{\ell^2}{D_{\mathrm{p}}}. \tag{4}$$

For PDMS in hexanes, Chung et al. **?** estimated $D_{\mathrm{p}} \approx 10^{-8}\,\mathrm{m^2\,s^{-1}}$, giving $\tau_p \approx 400\,\mathrm{s}$ for a crack depth $\delta \approx 2\,\mathrm{mm}$, in agreement with the observed time to peeling. For PEG gels in water, the relevant diffusivity is expected to differ substantially due to the much smaller mesh size and stronger polymer–solvent affinity.

2.1.1. Poroelastic toughening and rate-dependent fracture

A key insight, developed rigorously for polymer gels in **??**, is that fracture in a gel is inherently rate-dependent: the apparent fracture toughness Γ_{app} exceeds the intrinsic value Γ_0 by the energy dissipated as solvent flows toward the opening crack tip. In the slow-crack limit (crack tip velocity $V \ll D_{\mathrm{p}}/a$, where a is a crack-tip length scale):

$$\Gamma_{\mathrm{app}} \approx \Gamma_0 + \frac{2D_{\mathrm{p}}\sigma_\infty^2}{E\,V}, \tag{5}$$

where σ_∞ is the far-field tensile stress. This implies that as a crack slows due to increasing local toughness (the wet–dry toughness gradient), the *apparent* toughness increases further, providing a strong positive feedback that arrests radial crack growth – which is precisely the mechanism invoked by Chung et al. for the crack arrest that precedes lateral peeling.

Implication for PEG: In PEG/water, the intrinsic Γ_0 is substantially higher than in PDMS/hexanes (PEG networks are tougher due to chain extensibility), but D_{p} is lower. The combination determines whether the crack will arrest in the wet region and peel, or propagate fully through the material in the catastrophic manner observed with water gels at room temperature (Shamah's "cinnamon roll"). This motivates measuring Γ_0, E, and D_{p} directly for PEG/water gels across concentrations.

2.2. The Chung–Mahadevan Scaling Law: Derivation and Limits

We reproduce the key derivation from **?** here to make explicit the assumptions and identify where they may break down for PEG systems.

2.2.1. Flat-surface limit

Consider a gel occupying the half-space $z > 0$, drying from the surface $z = 0$. The drying front propagates inward at velocity v_f, and the width of the front (the region over which the volumetric strain transitions from fully shrunk to fully swollen) is w. Across this front, the tangential strain $\varepsilon_{\theta\theta}$ varies as

$$\varepsilon_{\theta\theta}(z,t) = \varepsilon_0 \left[1 + \tanh\left(\frac{z - v_f t}{w}\right)\right], \tag{6}$$

so that the strain gradient scales as

$$\nabla\varepsilon \sim \frac{\varepsilon_0}{w}. \tag{7}$$

The strain ε_0 is set by the shrinkage of the gel upon complete drying; w is determined by the competition between evaporation and internal solvent diffusion. Using Darcy's law with a steady evaporation flux J_0 at the surface:

$$J_0 = -k\frac{\partial p}{\partial z}\bigg|_{z=0} \quad \Rightarrow \quad \nabla\varepsilon \sim \frac{J_0\mu}{Ek}, \tag{8}$$

where μ is the solvent dynamic viscosity. The stored elastic energy density in the surface layer of thickness h and lateral extent ℓ scales as

$$\mathcal{U} \sim E(\nabla\varepsilon)^2 \cdot \ell. \tag{9}$$

Setting this equal to the fracture energy $\Gamma\ell$ to open a lateral (horizontal) crack of length ℓ at depth h:

$$E(\nabla\varepsilon)^2\ell \sim \Gamma\ell \quad \Rightarrow \quad {}^3 \sim \frac{\Gamma}{E(\nabla\varepsilon)^2}. \tag{10}$$

Substituting **??**:

$$\boxed{\sim \left[\frac{(\Gamma E)^{1/2}k}{J_0\mu}\right]^{2/3}}. \tag{11}$$

2.2.2. Cylindrical geometry correction

For a cylinder of initial radius , the strain energy in polar coordinates becomes (see Appendix of **?**):

$$\mathcal{U} = E\ell(\eta - 1)^2\Big(1 - \Big), \tag{12}$$

where η is the tangential stretch. Balancing with fracture energy:

$$^{3}\Big(1 - \Big) \sim \frac{\Gamma}{E(\nabla\varepsilon)^2}. \tag{13}$$

This cubic equation has a nontrivial solution only when

$$\nabla\varepsilon \gtrsim \left(\frac{\Gamma}{E^3}\right)^{1/2}, \tag{14}$$

which defines the critical evaporative flux J_{0c} below which no exfoliation occurs. As $\to \infty$ (flat geometry), the correction factor $(1 - h/R) \to 1$ and **??** is recovered.

2.2.3. Why the scaling may not hold for PEG

Shamah's data show $\approx 0.5\,\mathrm{mm}$ essentially independent of J_0 and gel geometry. There are at least three non-exclusive explanations:

(i) **Measurement noise:** The fractional variation of h in Chung's data is about a factor of 4 over a decade of flux variation (**??** predicts $h \propto J_0^{-2/3}$). If the absolute value of h in PEG sits near the measurement resolution, the variation may simply be masked. This is addressable by widening the accessible flux range via binary solvent mixtures.

(ii) G/E **mismatch:** For PDMS, $\Gamma/E \approx 10^{-4}\,\mathrm{m}$ (the value used by Chung). PEG hydrogels have substantially different Γ and E; their ratio Γ/E must be measured. If it is much smaller than the PDMS value, h will be smaller and the absolute variation in h over accessible J_0 values will be below resolution.

(iii) **Modified strain gradient:** The relation **??** assumes a linear poroelastic response with constant permeability k. In PEG gels, the mesh size ℓ_p and hence k changes dramatically during drying (from $\ell_\mathrm{p} \approx 10\,\mathrm{nm}$ in the swollen state to essentially zero at the dry front), making the effective k a strong function of local solvent content. This is discussed further in **??**.

2.3. Style–Peppin Mud-Peeling Model

The first quantitative theory of horizontal cracking and peeling in drying media was developed for clays by Style, Peppin, and Cocks **?**. Treating the clay as a poroelastic solid with surface evaporation flux J_0, they showed that the pore pressure satisfies:

$$\frac{\partial p}{\partial t} = D_\mathrm{p}\,\frac{\partial^2 p}{\partial z^2}, \quad z > 0; \qquad -k\frac{\partial p}{\partial z}\bigg|_{z=0} = J_0, \quad p \to 0 \text{ as } z \to \infty. \tag{15}$$

The tensile stress in the horizontal (tangential) direction develops as

$$\sigma_{xx}(z,t) = \frac{E}{1-\nu}\int_0^t \alpha\frac{\partial p}{\partial t'}\,\mathrm{d}t', \tag{16}$$

where α is the Biot coefficient. The depth h at which a horizontal crack nucleates is determined by the condition that the stress intensity factor at the crack tip exceeds the fracture toughness:

$$K_I = F\,\sigma_{\max}\sqrt{\pi h} \geq K_{Ic}, \tag{17}$$

where F is a geometric correction factor and $K_{Ic} = \sqrt{E\Gamma_0/(1-\nu^2)}$ is the critical stress intensity factor. Style et al. further show that the radius of curvature ρ of the peeled layer is related to the depth of peeling h by:

$$\rho \approx \frac{h}{3\bar{\varepsilon}}, \tag{18}$$

where $\bar{\varepsilon}$ is the mean strain through the layer thickness at the time of peeling. **This equation provides a direct prediction for the curvature of Shamah's "cinnamon roll" fragments** – if they are indeed the same instability operating in a different regime, their curvature should be quantitatively predictable from **??** using measured h and $\bar{\varepsilon}$.

2.4. Flory–Rehner Thermodynamics and the Strain Gradient

The driving force for drying is the chemical potential difference between solvent in the gel and in the surrounding vapor. In the Flory–Rehner framework **??**, the chemical potential of solvent in the swollen network is

$$\mu_s = \mu_s^0 + RT\left[\ln(1-\phi_\mathrm{p}) + \phi_\mathrm{p} + \chi_\mathrm{FH}\phi_\mathrm{p}^2\right] + V_1\left[\frac{\rho_2}{M_c}\left(\frac{\phi_\mathrm{p}^{1/3}}{2} - \frac{\phi_\mathrm{p}}{2}\right)\right], \tag{19}$$

where ϕ_p is the polymer volume fraction, χ_FH is the Flory–Huggins solvent–polymer interaction parameter, V_1 is the molar volume of solvent, ρ_2 is the polymer density, and is the average molecular weight between crosslinks. The first three bracketed terms constitute the mixing contribution Π_mix and the last term is the elastic contribution Π_el.

The critical connection to drying: The local evaporation rate at the gel surface is determined by the vapor pressure of solvent above the gel, which equals the saturation pressure multiplied by the activity $a_s = \exp(\mu_s/RT)$. When the surface dries, ϕ_p increases there, μ_s decreases, and the surface vapor pressure drops. However, for solvents with large χ_FH (poor solvents), the chemical potential μ_s drops more steeply with ϕ_p, meaning the vapor pressure remains high even as the gel surface dries – driving continued fast evaporation. Conversely, for solvents with $\chi_\mathrm{FH} \ll 0.5$ (good solvents), the vapor pressure of solvent above the gel drops more quickly as the surface dries, providing a natural self-limiting mechanism.

Connecting χ_FH to the Strain Gradient

The equilibrium swelling ratio $Q_\mathrm{eq} = V_\mathrm{swollen}/V_\mathrm{dry}$ is determined by setting $\mu_s = \mu_s^0$ in **??**. The resulting volumetric strain upon complete drying from equilibrium is $\varepsilon_0 = 1 - Q_\mathrm{eq}^{-1}$. For the strain gradient **??**, modifying for the activity correction, Darcy's

law in the presence of a non-ideal solvent gives

$$\nabla\varepsilon \approx \frac{J_0\,\mu}{E\,k_{\text{eff}}} \cdot \frac{1}{1 - 2\chi_{\text{FH}}\phi_{\text{p}}^2/[\ln(1-\phi_{\text{p}}) + \phi_{\text{p}}]}, \tag{20}$$

where $k_{\text{eff}} \propto \ell_{\text{p}}^2$ is the effective permeability and the second factor – which we call the *activity correction* $\mathcal{A}(\chi_{\text{FH}}, \phi_{\text{p}})$ – captures how the chemical potential gradient driving internal solvent flow is modified by solvent–polymer thermodynamics. For hexanes in PDMS ($\chi_{\text{FH}} \approx 0$, near-ideal), $\mathcal{A} \approx 1$ and the Chung gradient is recovered. For water in PEG ($\chi_{\text{FH}} \approx 0.43$), $\mathcal{A} > 1$ at moderate ϕ_{p}, increasing the effective strain gradient and predicting a larger driving force for fracture at the same nominal J_0 – consistent with the more dramatic fracture behavior ("cinnamon roll") observed in water.

Substituting **??** into **??**, the modified scaling law becomes:

$$\boxed{\sim \left[\frac{(\Gamma E)^{1/2}\,k_{\text{eff}}}{J_0\,\mu\,\mathcal{A}(\chi_{\text{FH}}, \phi_{\text{p}})}\right]^{2/3}.} \tag{21}$$

This reduces to the Chung result for ideal solvents. **Testing ?? for acetone, ethanol, and binary mixtures – where χ_{FH} varies continuously – is the central theoretical objective of the proposed work.** Tabulated and estimated χ_{FH} values for relevant PEG–solvent pairs are given in **??**.

Table 1: Estimated Flory–Huggins parameter χ_{FH} and relevant physical properties for PEG with relevant solvents at $T = 20°\text{C}$. Vapor pressures P_v from standard references. χ_{FH} values from literature compilations (see, e.g., VanZanten et al. **?** and references therein).

Solvent	χ_{FH}	P_v (kPa)	μ (mPa s)	V_1 ($\text{cm}^3\,\text{mol}^{-1}$)
Water	≈ 0.43	2.3	1.00	18
Ethanol	≈ 0.3	5.95	1.20	58
Acetone	≈ 0.1	24.5	0.32	74
Hexanes	≈ 0.0	17.6	0.31	132

2.5. The Drying Front: Width, Velocity, and Localization

The drying front width w controls the strain gradient via **??**. For drying in porous media, the front width is set by the competition between evaporative flux and diffusive transport. Following Pel et al. **?** and Lehmann et al. **?**, the front width scales as

$$w \sim \sqrt{\frac{D_{\text{p}}}{v_f}}, \tag{22}$$

where v_f is the front velocity. The front velocity is set by global mass balance:

$$v_f = \frac{J_0}{\rho_s(\phi_{\mathrm{p}}^{\mathrm{dry}} - \phi_{\mathrm{p}}^{\mathrm{wet}})}, \tag{23}$$

where $\phi_{\mathrm{p}}^{\mathrm{dry}}$ and $\phi_{\mathrm{p}}^{\mathrm{wet}}$ are the polymer volume fractions in the dry and wet regions. Combining:

$$w \sim \sqrt{\frac{D_{\mathrm{p}}\rho_s\Delta\phi_{\mathrm{p}}}{J_0}}. \tag{24}$$

Importantly, as J_0 increases, w decreases: the front sharpens. This is consistent with **??**, which predicts that exfoliation requires $J_0 > J_{0c}$ (because only at high enough flux is the front sharp enough to generate a sufficient strain gradient). It also explains why water at room temperature – where J_0 is very low – produces no exfoliation in PEG gels: the drying front is too diffuse.

Permeability changes during drying are a complication absent from the Chung treatment. In PEG gels, the mesh size scales as $\ell_{\mathrm{p}} \sim N^{3/5} b \phi_{\mathrm{p}}^{-3/4}$ (in good solvent) **?**, so as the gel dries and ϕ_{p} increases, ℓ_{p} decreases dramatically and the permeability $k \propto \ell_{\mathrm{p}}^2$ drops. This means the strain gradient is steeper than **??** predicts for a constant-k model, and the front width **??** narrows as drying proceeds. This positive feedback may contribute to the catastrophic nature of fracture in water-swollen PEG gels.

2.6. Griffith Criterion and Crack Path Selection

The competition between vertical (radial in a cylinder) and horizontal (lateral) crack propagation determines whether exfoliation or through-cracking occurs. In the Chung framework, this competition is encoded in the toughness gradient: horizontal crack propagation is favored because the advancing wet front makes radial growth *harder* (higher Γ in the wet region) while bending stresses drive the peel torque.

More formally, the energy release rate for a crack of length c propagating at angle θ from the vertical is

$$G(\theta) = G_I \cos^4\left(\frac{\theta}{2}\right) + G_{II} \sin^2\left(\frac{\theta}{2}\right)\cos^2\left(\frac{\theta}{2}\right), \tag{25}$$

where G_I and G_{II} are the Mode I and Mode II contributions. For a crack propagating in a material with a spatial toughness gradient $\partial\Gamma/\partial z > 0$ (tougher deeper), the energy available from Mode I at the crack tip equals the local toughness at some finite depth, while the toughness ahead is higher. This forces crack deflection toward the direction of maximum bending energy release – which is horizontal – provided the bending stiffness of the incipient peel layer is sufficient.

Neither the Chung model nor any subsequent theoretical work has examined how crack path selection depends on the Flory–Huggins parameter χ_{FH} or on the non-ideal

activity correction $\mathcal{A}$ derived in **??**. In particular, for χ_{FH} near or above 0.5 (poor solvent), the osmotic driving force for solvent flow ahead of the crack tip is weaker, potentially altering the toughening feedback that arrests radial cracks. This could explain the transition to catastrophic fracture in water-swollen PEG gels.

3. Prior Art Landscape

3.1. Directly Related Work

Chung, Regev & Mahadevan (2016). The foundational study **?** on PDMS gels in hexanes. Established the scaling law **??**, confirmed via experiments over three temperatures (21–57°C) and two cylinder radii. Numerical simulations using a spring-network model confirmed that *both* strain and toughness gradients are required for exfoliation. The paper also identified a "controlled release" application: a pre-notched gel maintains nearly constant evaporation rate as it exfoliates, because each peeling event exposes fresh surface. The main limitations are: (i) a single material and solvent pair; (ii) $\chi_{\mathrm{FH}} \approx 0$ (no thermodynamic complication); (iii) no measurement of G or E independently; (iv) G/E taken from literature, not from this specific system.

Shamah (2026). Extends Chung's phenomenology to PEG/PEGMEA hydrogels in acetone, ethanol, and water **?**. Demonstrates the universality of the flux-driven instability across gel and solvent chemistry. Key quantitative findings: (i) crack initiation time is $\approx 200\,\mathrm{s}$ faster in acetone than ethanol, independent of thickness (0.5–3 mm) and PEGDA concentration (1–50 mol%); (ii) peel thickness $h \approx 0.5\,\mathrm{mm}$, showing no measurable dependence on any tested variable; (iii) crack velocity is approximately 14× higher in acetone ($5950 \pm 2122\,\mathrm{mm/s}$) than ethanol ($434 \pm 511\,\mathrm{mm/s}$); (iv) water gels show a qualitatively distinct "cinnamon-roll" fracture uncharacterized by existing theory. Limitations: only three solvents, each used at a single composition; no measurement of Γ, E, or D_{p} for PEG gels; no theoretical explanation for the $h \approx$ const finding; water experiments incomplete.

Style, Peppin & Cocks (2011). Developed the first quantitative poroelastic theory of horizontal crack formation (mud peeling) **?**, which the Chung model was explicitly inspired by. Predicts peel depth and curvature as functions of evaporation rate for clays. The key additional prediction – that the radius of curvature of peeled layers is $\rho \approx h/3\bar{\varepsilon}$ **??** – has never been tested in synthetic hydrogel systems.

3.2. Related Experimental Work

VanZanten et al. (2024). Characterized transient surface deformations during unconstrained swelling of PEG hydrogels in water and ethanol **?**. Found that swelling creates large, non-equilibrium surface stresses and instabilities, connected via Flory–Rehner theory (**??**). Directly relevant because it characterizes the same PEG/PEGMEA system, and

because swelling and drying are the forward and reverse of the same process – yet they produce different behaviors (swelling-induced fracture vs. drying-induced exfoliation), which itself is a theoretically interesting asymmetry.

Augustine et al. (2023). Studied delamination of thin ($\sim \mu$m) PDMA hydrogel films grafted to silicon substrates under swelling **?**. Found a threshold film thickness for delamination onset and discussed results within a nonlinear fracture mechanics framework. Complementary to our work (swelling-driven delamination rather than drying-driven), with the important difference that their system is constrained (grafted) while ours is free-standing.

Tan et al. (2025). Explored critical cracking thickness of colloidal suspensions in binary alcohol–water mixtures **?**. Found two distinct cracking regimes depending on alcohol fraction. This is the closest analog to our proposed Aim 1 (binary solvent mixtures), but applies to a colloidal gel (particle-based, no polymer network) rather than a covalently crosslinked polymer. The physics of the binary-front evaporation and its effect on crack patterns is qualitatively different, making the PEG case a distinct and open problem.

Boulogne, Pauchard & Giorgiutti-Dauphine (2012). Showed that addition of a non-volatile cosolvent (glycerol) to a drying colloidal gel suppresses crack formation **?** by reducing the capillary pressure gradient. This is a binary "solvent + non-evaporating additive" system, distinct from our proposed binary system of two volatile solvents with differing vapor pressures.

Bouchbinder et al. (2020) and Hui & collaborators (2018–present). A series of theoretical papers **??** on poroelastic fracture in gels, developing the rate-dependent toughening mechanism discussed in **??**. These set the theoretical standard against which our results should be interpreted.

Zhang, Qu et al. (2025). Reported "poroelastic fracture" in polyacrylamide gels – enhanced crack tip swelling driven by chain scission **?**. Demonstrated that fracture in gels involves a coupled mechano-chemical process at the crack tip that is absent in classical fracture mechanics. Relevant because it provides a modern, quantitative description of poroelastic crack growth that could be applied to our system.

3.3. Summary of Open Space

?? summarizes the landscape.

Table 2: Landscape of prior art relative to the proposed work. "✓" = addressed; "–" = not addressed; "⋆" = open and proposed here.

Topic	Chung	Shamah	Status
Single-solvent, single-gel exfoliation	✓	✓	Established
Flux as primary control parameter	✓	✓	Established
Peel thickness scaling law (theory + data)	✓	–	⋆ Test in PEG
Binary solvent / tunable flux	–	–	⋆ Open
Solvent–polymer χ_{FH} in theory	–	–	⋆ Open
Water fracture mode ("cinnamon roll")	–	Observed	⋆ Uncharacterized
Curvature of peels (**??**)	–	–	⋆ Open
Direct measurement of G, E, D_p in PEG	–	–	⋆ Needed
Humidity-controlled ambient environment	–	–	Open (not proposed)
Re-swelling and cyclic delamination	–	–	Open (not proposed)
Spatial patterning of delamination	–	–	Open (not proposed)

4. Research Aims

The three aims described below are designed to be internally coherent: Aim 1 generates the quantitative dataset and the extended flux range needed to test the theory; Aim 2 characterizes the water mode that Aim 1 cannot reach at room temperature; and Aim 3 synthesizes both into a theoretical framework. We envision Aims 1 and 2 as the two main experimental contributions of a single publication, with Aim 3 as the theoretical backbone.

4.1. Aim 1: Binary Solvent Phase Diagram

Aim 1 — Central Hypothesis

The behavioral phase diagram for PEG gel fracture and exfoliation is a function of evaporative flux J_0 alone, regardless of which particular solvent (or mixture) is used to achieve that flux. This hypothesis is tested by continuously varying J_0 via binary acetone/ethanol blends, holding all other variables fixed.

4.1.1. Rationale

Acetone and ethanol have vapor pressures of 24.5 kPa and 5.95 kPa at 20°C respectively – a factor of ~ 4. Crucially, both are good solvents for PEG ($\chi_{\mathrm{FH}} \lesssim 0.3$ for both; see **??**), so their equilibrium swelling ratios in PEG are broadly similar, minimizing confounds from χ_{FH} variation when the mixture is dilute in one component. By blending them in proportions from 0% to 100% acetone (by volume), we span a factor of ~ 4 in J_0 continuously at room temperature – a range comparable to Chung's temperature variation but without any confounding effect of temperature on modulus, toughness, or network dynamics.

This is significant because Shamah's comparison of acetone vs. ethanol involved *discrete* solvents that differ not only in vapor pressure but also in viscosity ($\mu_{\mathrm{acetone}} = 0.32\,\mathrm{mPa\,s}$ vs. $\mu_{\mathrm{ethanol}} = 1.20\,\mathrm{mPa\,s}$), molar volume ($V_1$), and χ_{FH}. A binary blend allows these to be varied quasi-continuously, enabling proper curve fitting to the scaling law **??** or its modified form **??**.

4.1.2. Experimental protocol

Gel preparation. Cylindrical PEG gels at fixed 20:80 (PEGDA:PEGMEA) molar ratio, initial thickness 1.0 mm (as in Shamah **?**). This concentration is well within the exfoliation regime for both acetone and ethanol. Four samples per condition.

Solvent blends. Eight blend compositions: $f_{\mathrm{ac}} \in \{0, 12.5, 25, 37.5, 50, 62.5, 75, 100\}\%$ (vol.% acetone). Gels are swollen to equilibrium in the desired blend for at least 3 h (acetone equilibration time) before imaging.

Effective vapor pressure. The effective vapor pressure of each mixture is not simply the mole-fraction-weighted average of the pure-component values; activity coefficients must be accounted for (e.g., using Wilson's equation for the acetone–ethanol system, which is nearly ideal). We calibrate the effective evaporation flux J_0 directly from the pre-gel mass-loss curve (rate of weight loss from a known area of solvent before placing the gel), thereby converting blend composition to an effective J_0 without theoretical assumptions.

Observables. For each condition, we record with the existing dual-camera setup:

- Crack initiation time t_c (top-view camera)
- Peel initiation time t_p (side-view camera)
- Peel thickness h (ImageJ, side-view, first visible peel)
- Maximum "fluff" height, normalized by swollen thickness
- Light intensity at peak cracking (proxy for crack density)
- Relaxation time T_{relax}
- Crack velocity v_c (high-speed camera, Phantom, for at least three blend compositions)

Additionally, we measure the *equilibrium swelling ratio* Q_{eq} for each blend (separately from the drying experiment) as a check on χ_{FH} variation.

Critical test. If the central hypothesis holds, all observables should collapse onto smooth curves as functions of J_0, regardless of whether the same J_0 is achieved by a dilute or concentrated acetone blend. If deviations from collapse occur at compositions where χ_{FH} changes significantly (near the ethanol-rich end), this indicates the activity correction $\mathcal{A}$ in **??** is necessary.

4.1.3. Expected outcomes and publishable findings

A. Phase diagram with continuous onset threshold. We expect a sharp transition in t_c, t_p, and crack density as J_0 crosses a critical value J_{0c}. Identifying J_{0c} for PEG gels in a solvent-independent manner would be the first such measurement in a synthetic hydrogel system. Comparing it to Chung's J_{0c} via **??** would yield an estimate of Γ/E independently of direct mechanical measurement.

B. Peel thickness vs. J_0 curve. If h does vary with J_0 over the extended range of binary mixtures, the data can be fit to **??** or **??**. If h remains $\approx 0.5\,\mathrm{mm}$ even at the extremes, this is itself a significant finding: it implies that Γ/E for PEG is such that the variation in h over accessible flux ranges is unmeasurably small, and the system operates in the "saturated" regime of **??**.

C. Crack velocity vs. J_0. Shamah observed a $\sim$14$\times$ velocity difference between acetone and ethanol. With binary mixtures, we can determine whether velocity scales with J_0 (or v_f, the drying front velocity) continuously. Crack velocity in gels is governed by poroelastic toughening **??**; a velocity–flux curve provides an indirect measurement of the poroelastic diffusivity D_{p} via $v_c \sim D_{\mathrm{p}}/\ell$ (where ℓ is the crack length scale).

4.2. Aim 2: Characterizing the Water Fracture Mode

Aim 2 — Central Hypothesis

The "cinnamon roll" fracture mode in water-swollen PEG gels is a distinct instability arising from the combination of: (i) very low evaporative flux at ambient conditions, causing a diffuse drying front that is insufficient for exfoliation; and (ii) the hygroscopic mismatch between the highly water-compatible PEG network and the ambient air, which creates a large osmotic prestress that drives catastrophic, globally-initiated fracture rather than locally-initiated exfoliation. At sufficiently high temperature (and hence J_0), we hypothesize that water gels will transition to standard exfoliation, unifying the water mode with the acetone/ethanol behavior.

4.2.1. Why this mode is mechanistically distinct

Water is simultaneously the worst solvent for fast drying (vapor pressure 2.3 kPa at room temperature, the lowest of the three solvents) and the one most intimately associated with

PEG (PEG is famously hygroscopic, with $\chi_{\mathrm{FH}} \approx 0.43$, close to but below the critical value of 0.5). As a result:

1. The drying front width $w \propto \sqrt{D_{\mathrm{p}}/v_f}$ (**??**) is *very large* at room temperature because v_f is small (the gel barely dries over 24 h). The strain gradient $\nabla\varepsilon \sim \varepsilon_0/w$ is therefore far below the critical gradient (**??**), and no exfoliation should occur – consistent with Shamah's observations.
2. However, the large osmotic potential gradient between the bulk gel and the surface (driven by the low vapor pressure of water over the partially-dried surface) creates a tensile prestress in the outermost layer that is *not* relieved by vertical cracking (vertical cracks relieve tangential stress, not normal prestress). Eventually, the surface layer buckles or fractures catastrophically in a mode driven by global bending of the disk, producing the large curved fragments.
3. At elevated temperature (e.g., 60°C, where water's vapor pressure matches acetone at 20°C), the drying front sharpens sufficiently that $\nabla\varepsilon >$, and standard exfoliation should replace the cinnamon-roll mode.

4.2.2. Connection to the Style–Peppin model

In mud peeling, the radius of curvature of peeled fragments is $\rho \approx h/3\bar{\varepsilon}$ **??**. If the "cinnamon roll" fragments obey this relation, they are properly described as mud peels in the poroelastic framework. If not – if the curvature is much larger or smaller than predicted – it suggests a different instability mechanism, possibly related to the Euler buckling of a swollen elastic sheet under biaxial compression.

The critical Euler buckling stress for a thin plate of thickness h_0, modulus E, and Poisson ratio ν subject to a biaxial compressive prestress σ_0 is:

$$\sigma_c = \frac{\pi^2 E h_0^2}{12(1-\nu^2)L^2}, \tag{26}$$

where L is the lateral extent of the fragment. If the prestress $\sigma_0 > \sigma_c$, the fragment buckles out of plane and detaches. The characteristic fragment size L_c is set by the condition $\sigma_0 = \sigma_c$:

$$L_c \sim h_0 \sqrt{\frac{\pi^2 E}{12(1-\nu^2)\sigma_0}}. \tag{27}$$

Measuring the fragment size and curvature of "cinnamon roll" pieces will allow us to distinguish between the mud-peel (??) and buckling-delamination (??) mechanisms.

4.2.3. Experimental protocol

Infrastructure. Complete construction of the temperature-controlled oven with a clear optical window (in progress per Shamah's conclusion **?**). The oven must maintain temperature to ±1°C and allow continuous imaging from above.

Sample conditions.

- PEGDA concentrations: 1:99, 2:98 (only these survive water swelling without fracturing per **??**)
- Temperatures: $20, 40, 50, 60, 70, 80°\mathrm{C}$ (spanning $P_v = 2.3$ to $47.4\,\mathrm{kPa}$)
- Thickness: $1\,\mathrm{mm}$ (fixed)

New observables (beyond Aim 1).

- **Fragment curvature radius** ρ: ImageJ, measured by fitting a circular arc to the curved fragment edge in side-view images.
- **Fragment length** L: major axis of detached fragments, top-view.
- **Number of fragments per gel**: a proxy for the characteristic fragmentation length scale.
- **Time to first fracture**: analogous to t_c in Aim 1; in the water case this is likely very long at low T and sharply decreases at high T.
- **Mode transition temperature** T^*: the temperature (if any) above which the water gel transitions from cinnamon-roll to standard exfoliation.

Table: Swelling fracture rate in water. To guide sample selection, we reproduce Shamah's swelling-fracture data **?**:

Table 3: Percentage of PEG gels that fracture during swelling in room-temperature Milli-Q water (4 samples per concentration). Only 1:99 and 2:98 are suitable for drying experiments.

Concentration (PEGDA:PEGMEA)	% fractured during swelling
1:99	0%
2:98	25%
3:97	0%
4:96	0%
5:95	50%
10:90	100%
20:80	100%
30:70	100%

4.2.4. Expected outcomes and publishable findings

A. Mode transition. If a transition from cinnamon-roll to exfoliation exists at some temperature T^*, this defines a new critical flux J_{0c}^{water}. Comparing it to J_{0c} measured from acetone/ethanol blends in Aim 1 tests whether J_{0c} is truly material-independent.

B. Mechanism identification. Comparing measured curvature ρ and fragment size L to the predictions of **??** (poroelastic mud peeling) and **??** (buckling delamination) will identify the operative mechanism. This could yield a standalone letter if the mechanism is clean.

C. Vapor pressure control validation. The oven experiment at 60°C (water vapor pressure ≈ acetone vapor pressure at 20°C) tests Shamah's preliminary observation that the two solvents behave similarly when their vapor pressures are matched **?**. If confirmed quantitatively (same t_c, t_p, h, fragment morphology), this is the strongest possible confirmation that J_0 is the sole control parameter.

4.3. Aim 3: Testing and Extending the Chung Scaling Law

Aim 3 — Central Hypothesis

The failure of the Chung scaling law **??** to predict a measurable variation in h for PEG gels arises from either (a) a very different Γ/E ratio in PEG that places h deep in a plateau regime, or (b) a breakdown of the constant-k assumption due to the strong permeability change during drying in PEG. Direct measurement of Γ, E, and D_p will resolve the discrepancy and, combined with the binary-mixture data from Aim 1, will allow formulation of a modified scaling law that includes the Flory–Huggins parameter as an additional control.

4.3.1. Direct mechanical measurements

The following measurements should be made for all concentrations used in Aims 1 and 2 in the *swollen* state (i.e., immediately after removal from solvent, before any drying):

Elastic modulus E. Using the Anton Paar rheometer available in the Driscoll lab (per Shamah's methods **?**), measure the shear modulus G^* via oscillatory rheology at 1 Hz. The drained Young's modulus is approximately $E \approx 3G'$ for incompressible networks.

Fracture toughness Γ_0. The standard method for soft gels is the "trouser tear" or "pure shear" test. Cut a thin sample (1 mm thick) into a rectangular strip of width W and height H, with a pre-cut notch of length $a_0 = H/2$. Apply quasi-static displacement δ at the crack mouth and record force F. The energy release rate is:

$$G_c = \frac{F_c}{W} \quad \text{(for the pure-shear geometry)}, \tag{28}$$

where F_c is the critical force at fracture onset. Three to five measurements per concentration.

Poroelastic diffusivity D_p. Estimated from the pre-exfoliation mass-loss curves using the method of Chung et al. **?**: fit the drying data (before the first kink indicating exfoliation) to

$$\frac{m_0 - m(t)}{m_0 - m_\infty} = \exp\left[-\left(\frac{\alpha_1^2 D_\mathrm{p} t}{R^2}\right)^\beta\right], \tag{29}$$

where $\alpha_1 = 2.405$ is the first zero of J_0, and $\beta \approx 1$ (Fickian diffusion limit). This yields D_p for each solvent and concentration combination as a by-product of the Aim 1 experiments.

4.3.2. Theoretical comparison

With Γ_0, E, D_p, and J_0 all measured, we can compute the predicted peel thickness from

$$_{\mathrm{pred}} = \left[c \cdot \frac{(\Gamma_0 E)^{1/2} k_\mathrm{eff}}{J_0\, \mu\, \mathcal{A}(\chi_\mathrm{FH}, \phi_\mathrm{p})}\right]^{2/3} \tag{30}$$

where $k_\mathrm{eff} = \ell_\mathrm{p}^2/\mu$ is estimated from measured D_p (since $D_\mathrm{p} \approx k_\mathrm{eff} E/\mu$) and $c \approx 0.2$ is the numerical prefactor from Chung et al. **?**. If $_{\mathrm{pred}}$ agrees with $_{\mathrm{meas}} \approx 0.5\,\mathrm{mm}$ at all conditions, the theory is validated in PEG; the apparent insensitivity of h to conditions is explained by the particular values of Γ_0 and E in PEG placing it in the plateau. If $_{\mathrm{pred}}$ disagrees, the modified gradient relation **??** with $\mathcal{A} \neq 1$ should be tested.

4.3.3. A dimensionless parameter for mode selection

Combining **????????**, the key dimensionless group governing whether exfoliation occurs is

$$\Pi = \frac{J_0^2\, \mu^{2\,3}\, \mathcal{A}^2(\chi_\mathrm{FH}, \phi_\mathrm{p})}{\Gamma_0\, E\, k_\mathrm{eff}^2}, \tag{31}$$

with exfoliation occurring when $\Pi > \Pi_c \sim O(1)$. This generalizes the Chung criterion **??** to include solvent–polymer thermodynamics. The binary-mixture experiments of Aim 1 probe Π by varying J_0 and k_eff (through μ) continuously; the water-temperature experiments of Aim 2 probe Π by varying J_0, $\mathcal{A}$, and k_eff (because D_p is temperature-dependent). A plot of behavioral mode vs. Π should collapse all data onto a single phase boundary – the central theoretical result of the paper.

4.3.4. Expected outcomes

A. Validated or falsified scaling law. Either the Chung law (with or without the activity correction) explains the data, or it does not. Either outcome is publishable.

B. Measured Γ_0, E, D_p for PEG hydrogels in acetone and ethanol. These values are currently absent from the literature and will be useful to the broader community independent of the specific application here.

C. Universal phase diagram Π. A single plot of behavioral mode (no fracture / cracking only / exfoliation / cinnamon roll) as a function of the dimensionless parameter Π unifying all solvents, temperatures, and concentrations would be the central figure of the publication.

5. Proposed Timeline

Table 4: Ten-month roadmap to manuscript submission. Milestones are cumulative.

Period	Milestones
Months 1–2	Complete oven build with optical window and temperature control (±1°C). Calibrate evaporation flux J_0 for all 8 acetone/ethanol blends by gravimetric measurement. Measure E and G_c for 10:90, 20:80, 30:70 PEG gels in acetone and ethanol by rheology and pure-shear testing. Pilot Aim 1 experiment at $f_{\mathrm{ac}} = 0, 50, 100\%$.
Months 3–4	Full Aim 1 data collection: all 8 binary blend compositions, $n = 4$ per condition, dual camera, high-speed camera at three compositions. Estimate D_{p} for each blend from pre-exfoliation mass-loss curves. Begin phase-diagram analysis and comparison to Chung law (Aim 3).
Months 5–6	Full Aim 2 data collection: water-swollen 1:99 and 2:98 gels at six temperatures (20–80°C). Measure fragment curvature ρ, fragment size L, and mode transition temperature T^*. Compare to Style–Peppin **??** and buckling **??** predictions.
Months 7–8	Finalize Aim 3 analysis: compute Π for all experiments, plot universal phase diagram. Draft manuscript. Internal group review.
Months 9–10	Address reviewer-anticipated comments, refine figures, finalize theory. Submit to *Soft Matter* (primary target) or *Physical Review E* (if theoretical content warrants). Simultaneously evaluate whether Aim 2 has standalone novelty for a letter to *Soft Matter Letters* or *EPL*.

6. Differentiation from Existing Work

The following table summarizes, axis by axis, how this work is distinguished from the two closest prior studies.

Table 5: Differentiation summary.

Dimension	Chung 2016	Shamah 2026	This work
Material	PDMS	PEG	PEG
Solvent(s)	Hexanes	Acetone, EtOH, water	Binary blends + water at T
Flux control knob	Temperature	Solvent identity	Blend composition / temperature
J_0 range	$\sim 4\times$	Discrete	Continuous, $\sim 4\times$
χ_{FH} variation	None (ideal)	Discrete 3-point	Continuous + explicit
Peel thickness theory	Confirmed	Not confirmed	Tested / extended
G, E, D_p measured	No	No	Yes
Activity correction	Not needed	Not considered	Derived and tested
Water mode	Absent	Observed, uncharacterized	Characterized, mechanism ID'd
Universal Π parameter	Not formulated	Not formulated	Derived and plotted

7. Supplementary Theoretical Notes

7.1. Estimating χ_{FH} for Binary Solvent Mixtures

For a binary solvent mixture of components 1 (acetone) and 2 (ethanol) at volume fraction ϕ_1, the effective χ_{FH} for interaction with PEG is approximately **?**:

$$\chi_{\mathrm{FH}}^{\mathrm{eff}} \approx \phi_1\chi_1 + (1-\phi_1)\chi_2 - \phi_1(1-\phi_1)\chi_{12}, \tag{32}$$

where χ_{12} is the interaction parameter between the two solvents. For the acetone–ethanol pair, which is nearly ideal, $\chi_{12} \approx 0$, and so $\chi_{\mathrm{FH}}^{\mathrm{eff}} \approx \phi_1 \times 0.1 + (1-\phi_1) \times 0.3$. This varies by only 0.2 units across the full blend range, much less than the variation from PEG/ethanol to PEG/water (from ≈ 0.3 to ≈ 0.43). The activity correction $\mathcal{A}$ is therefore expected to be nearly constant across the acetone/ethanol blends, validating the strategy of using these blends as a clean flux-only knob.

7.2. Bending Stiffness and Peeling Torque

Once a crack has propagated to depth h, the superficial layer behaves as an elastic beam of thickness h subject to a bending moment from the strain gradient $\nabla\varepsilon$. The bending stiffness is $D = Eh^3/12(1-\nu^2)$. The bending moment per unit length is

$$M = \int_0^h \sigma_{\theta\theta}(z)\,(z - h/2)\,\mathrm{d}z \approx \frac{E(\nabla\varepsilon)h^3}{12(1-\nu^2)}. \tag{33}$$

The crack deflects from vertical to horizontal when M is sufficient to open a lateral crack, i.e., when $M \sim \Gamma_0 h$, which gives

$$\frac{E(\nabla\varepsilon)h^2}{12(1-\nu^2)} \sim \Gamma_0. \tag{34}$$

This can be rearranged to $h^2 \sim 12(1-\nu^2)\Gamma_0/(E\nabla\varepsilon)$, which differs from the energy-balance estimate **??** by a factor involving $\nabla\varepsilon$ in a different power. The two estimates agree in order of magnitude for $\nabla\varepsilon h \sim \varepsilon_0 \sim O(1)$. However, for very thin layers (h small) or weak strain gradients, the energy balance and torque criteria select different h, and the *smaller* of the two will set the actual peel thickness. This provides a more refined prediction that could explain the near-constant $h \approx 0.5\,\mathrm{mm}$ if the bending-moment criterion **??** is the operative one in PEG.

7.3. Drying-Front Localization in PEG: A Perturbative Analysis

Assume that permeability decreases with polymer volume fraction as $k = k_0(\phi_{\mathrm{p}0}/\phi_{\mathrm{p}})^\alpha$ (a power-law form consistent with mesh-size scaling **?**). Then the poroelastic diffusivity $D_{\mathrm{p}}(\phi_{\mathrm{p}}) = kE(\phi_{\mathrm{p}})/\mu$ is also ϕ_{p}-dependent. The drying-front PDE **??** becomes nonlinear:

$$\frac{\partial\phi_{\mathrm{p}}}{\partial t} = \frac{\partial}{\partial z}\left[D_{\mathrm{p}}(\phi_{\mathrm{p}})\frac{\partial\phi_{\mathrm{p}}}{\partial z}\right]. \tag{35}$$

For a traveling-wave solution $\phi_{\mathrm{p}} = \phi_{\mathrm{p}}(z - v_f t)$, the front width scales as **?**

$$w \sim \frac{D_{\mathrm{p}}(\phi_{\mathrm{p}}^{\mathrm{wet}})}{v_f}, \tag{36}$$

where $\phi_{\mathrm{p}}^{\mathrm{wet}}$ is the polymer fraction in the wet interior. Since $D_{\mathrm{p}}(\phi_{\mathrm{p}}^{\mathrm{wet}}) \sim D_{\mathrm{p}}^0$ is approximately the equilibrium-swollen value, but $D_{\mathrm{p}}(\phi_{\mathrm{p}}^{\mathrm{dry}}) \ll D_{\mathrm{p}}^0$ (the dry surface layer is essentially impermeable), the front actually becomes *self-sharpening* as drying progresses: the front stiffens from behind, reducing the effective w and *increasing* the strain gradient. This positive feedback may explain why peeling events in PEG can be sudden and vigorous compared to PDMS.

8. Future Directions Not Proposed Here

Several additional directions are scientifically interesting but are excluded from the current proposal to maintain a publishable scope. They are recorded here for future project planning.

Humidity-controlled drying. Varying ambient relative humidity (RH) provides another knob on J_0 (since $J_0 \propto P_v(1 - \mathrm{RH})$) without changing solvent identity. This would provide a third, independent axis in the phase diagram.

Cyclic swelling and drying. PEG gels can be re-swollen after drying. A gel that has delaminated may exhibit different mechanics upon re-swelling (the delaminated layers may re-adhere or remain separated). This connects to re-swelling literature **?** and has implications for cyclic drug-release applications.

Spatial programming of delamination. Chung et al. **?** noted that pre-notching a gel allows controlled initiation of exfoliation, yielding near-uniform drying rate. One could extend this to two-dimensional notch patterns (using laser cutting or photolithography of the mold) to spatially program the peeling sequence. This is a clear engineering application.

Thin-film geometry. All existing work uses gels in the range $h_0 \sim 0.5$–$13\,\mathrm{mm}$. The theory predicts that for very thin gels ($h_0 \lesssim h_{\mathrm{pred}}$), no peeling is possible because the gel is too thin to accumulate sufficient elastic energy. Testing this limit (using gels in the 50–200 μm thickness range fabricated by spin-coating) would set a hard constraint on the theory.

Double-network and interpenetrating-network gels. Toughened DN gels have dramatically different Γ_0 (up to 100 $\mathrm{J/m^2}$ vs. ~ 1 $\mathrm{J/m^2}$ for single-network PEG), which would shift the peel thickness to much larger values and potentially allow the h vs. J_0 dependence to be resolved experimentally.

Acknowledgments

This roadmap was developed by the Driscoll Laboratory with financial support from the Northwestern Office of Undergraduate Research, NSF/DMR Award 2311698, and the Baker Program in Undergraduate Research. The experimental foundations of this work were established by Haley Shamah in her 2026 undergraduate thesis under the supervision of Samira Khan and Professor Michelle Driscoll.

References

J. Y. Chung, I. Regev, and L. Mahadevan. Spontaneous exfoliation of a drying gel. *Soft Matter*, **12**:7855–7862, 2016.

H. Shamah. Hydrogel delamination during solvent evaporation. Undergraduate thesis, Northwestern University, April 2026.

R. W. Style, S. S. L. Peppin, and A. C. F. Cocks. Mud peeling and horizontal crack formation in drying clays. *J. Geophys. Res.*, **116**:F01025, 2011.

J. W. Hutchinson and Z. Suo. Mixed mode cracking in layered materials. *Adv. Appl. Mech.*, **29**:63–191, 1991.

M. A. Biot. General theory of three-dimensional consolidation. *J. Appl. Phys.*, **12**:155–164, 1941.

E. Detournay and A. H. D. Cheng. Fundamentals of poroelasticity. In *Comprehensive Rock Engineering*, volume 2, pages 113–171. Pergamon, 1993.

C. Y. Hui, Z. Long, and J. Guo. A poroelastic signature of the dry/wet state of a crack tip propagating steadily in a physical hydrogel. *Soft Matter*, **14**:386–400, 2018.

Y. Yu and C. Y. Hui. Poroelastic effects on steady state crack growth in polymer gels under plane stress. *Mech. Mater.*, **143**:103320, 2020.

A. VanZanten, S. Khan, and M. Driscoll. Unconstrained dynamic gel swelling generates transient surface deformations. *Soft Matter*, **20**:6742–6753, 2024.

P. J. Flory and J. Rehner. Statistical mechanics of cross-linked polymer networks. *J. Chem. Phys.*, **11**:512–520, 1943.

P. J. Flory. *Principles of Polymer Chemistry*. Cornell University Press, 1953.

M. Rubinstein and R. H. Colby. *Polymer Physics*. Oxford University Press, 2003.

L. Pel, K. A. Landman, and E. F. Kaasschieter. Analytic solution for the non-linear drying problem. *Int. J. Heat Mass Transfer*, **45**:3173–3180, 2002.

P. Lehmann, S. Assouline, and D. Or. Characteristic lengths affecting evaporative drying of porous media. *Phys. Rev. E*, **77**:056309, 2008.

L. Goehring, L. Mahadevan, and S. W. Morris. Nonequilibrium scale selection mechanism for columnar jointing. *Proc. Natl. Acad. Sci.*, **106**:387–392, 2009.

E. R. Dufresne, D. J. Stark, N. A. Greenblatt, J. X. Cheng, J. W. Hutchinson, L. Mahadevan, and D. A. Weitz. Dynamics of fracture in drying suspensions. *Langmuir*, **22**:7144–7147, 2006.

A. Augustine, Y. Tran, E. Verneuil, A. Chateauminois, N. Gauthier, M. Veillerot, B. Zhu, and C. Y. Hui. Swelling induced debonding of thin hydrogel films grafted on silicon substrates. Preprint, arXiv:2306.16166, 2023.

B. T. Tan et al. Manipulating cracks with selective drying in binary solvent mixture suspensions. *J. Chem. Soc. Jpn.*, 2025. DOI:10.1080/00219592.2025.2545622.

F. Boulogne, L. Pauchard, and F. Giorgiutti-Dauphine. Effect of a non-volatile cosolvent on crack pattern induced by desiccation of a colloidal gel. *Soft Matter*, 2012. DOI:10.1039/C2SM25663K.

Q. Zhang, J. Liu, G. Zhang, Y. Li, N. Hu, J. Yang, Y. Yang, S. Qu, Q. Kan, and G. Kang. Poroelastic fracture of polyacrylamide hydrogels: enhanced crack tip swelling driven by chain scission. *J. Mech. Phys. Solids*, **194**:105954, 2025.

X. Wang and W. Hong. Delayed fracture in gels. *Soft Matter*, **8**:8171–8178, 2012.

K. A. Leslie et al. Gel rupture during dynamic swelling. *Soft Matter*, **17**:1513–1520, 2021.