UV Penetration Depth and Cure-Through Time in Coumarin-Dimerized PEG Hydrogels

A quantitative diagnosis of the 1:9:90 gel, and a project direction: *programmed stiffness gradients*

Working note — hydrogels project

2026-07-08

Abstract

A collaborator's **1:9:90** (1 mol% PEGDA / 9 mol% CoumAc / 90 mol% PEGMA), 2 mm-thick PEG gel was photocured (7 min, 365 nm) and then irradiated 10 h on each face, yet appears "not to dimerize all the way through." We ask whether this is explained by simple optical penetration-depth limits. Using Beer–Lambert attenuation, the photobleaching nature of the coumarin [2+2] dimerization, and a photon-budget argument, we conclude that **dose starvation is almost certainly *not* the cause**: the incident dose exceeds the minimum needed to dimerize a full 2 mm column by roughly 20×. The more likely explanations are (i) a mobility/topology-limited conversion *ceiling* in the set network, (ii) a small non-bleaching absorber floor, or (iii) misinterpretation of a *surface-only* readout (swelling-induced creasing on the irradiated faces) as a bulk measurement. We give the explicit penetration-depth and cure-time formulae with numbers for this formulation, identify the single dominant unknown (the molar absorptivity of CoumAc at 365 nm, ε_{365}), and propose three cheap diagnostic experiments that settle the question. Finally, we develop **Direction A**: rather than fighting the depth gradient, *program* it — single-sided or photomask irradiation makes a stiff-skin/soft-core architecture whose differential swelling drives predictable bending and patterned surface topography. We outline the coupled optics–kinetics–mechanics forward model and a staged experimental program that reuses the group's existing brightfield crease/curl analysis pipeline.

Contents

1 The observation and the question **2**

2 Governing physics **2**

2.1 Beer–Lambert attenuation and the penetration depth 2

2.2 Coumarin is a *photobleaching* absorber: the cure front self-clears 3

2.3 Three distinct limiters 3

3 Quantitative estimates for the 1:9:90 gel **3**

3.1 CoumAc concentration 3

3.2 Penetration depth vs. the one unknown, ε_{365} 4

3.3 Cure-through time: the photon budget 4

3.4 Interpretation: dose is not the bottleneck 4

4 A critical look at the readout **5**

5 Three cheap experiments that settle it **5**

6 Direction A — Programmed stiffness gradients **5**
6.1 The idea, and why it is the project 5
6.2 Novelty relative to VanZanten *et al.* [1] 6
6.3 The forward model (what makes it predictive) 6
6.4 Code reuse. 7
6.5 Staged experimental program 7
6.6 Risks and mitigations 7

7 Summary **7**

A Constants and assumptions **8**

1 The observation and the question

The reference system is the in-house dual-cross-linked PEG–coumarin network of VanZanten *et al.* [1] (same lab, same light source, same geometry). The backbone is a permanent PEGDA/PEGMA acrylate network formed by free-radical photopolymerization (DMPA initiator, 0.5 wt%); a pendant photoresponsive cross-linker, 7-(2-acryloyloxyethoxy)-4-methylcoumarin (*CoumAc*), dimerizes under 365 nm light via a [2+2] cycloaddition (adding covalent cross-links, stiffening the gel) and cleaves under 254 nm light. Formulation names denote the mole percents of **PEGDA:CoumAc:PEGMA**; the gel in question is **1:9:90**, i.e. the second-highest coumarin loading in the entire study and twice the coumarin of the paper's workhorse formulation (0.5:4.5:95).

Protocol as reported to us. Cure 7 min at 365 nm (ThorLabs Solis LED 365C, incident 0.1 W/cm^2), then postcure-irradiate 10 h per face (flip halfway). Readout: harvest the collaborator's samples and score how each *face* wrinkles/fractures when exposed to water, by brightfield microscopy — the same swelling-induced surface-creasing assay used in [1]. The reported symptom is that dimerization does not appear to reach the interior.

Question. Can the penetration depth be computed analytically from the light specs, composition, and geometry, and does it predict the observation? Short answer: *we can compute it, and it predicts that penetration is not the limiting factor here.* The rest of this note shows why, and what to do instead.

2 Governing physics

2.1 Beer–Lambert attenuation and the penetration depth

Monochromatic intensity decays with depth z as

$$I(z) = I_0\, 10^{-\varepsilon_{365}\, c\, z} = I_0\, e^{-\alpha z}, \qquad \alpha = \ln(10)\, \varepsilon_{365}\, c, \tag{1}$$

where c is the molar concentration of the dominant 365 nm absorber (here CoumAc), ε_{365} its molar absorptivity (decadic, 1/(M cm)), and α the natural attenuation coefficient. The $1/e$ penetration depth is

$$\boxed{\delta_{1/e} = \frac{1}{\alpha} = \frac{1}{\ln(10)\, \varepsilon_{365}\, c} = \frac{1}{2.303\, \varepsilon_{365}\, c}} \tag{2}$$

and the fraction of light reaching the back face of a slab of thickness L is $T = 10^{-\varepsilon_{365} c L}$. Equations (1)–(2) are the "penetration depth" the collaborators want — but they describe the *initial*, unbleached state and are only half the story for a reacting gel (next).

2.2 Coumarin is a *photobleaching* absorber: the cure front self-clears

The coumarin chromophore absorbs near 320 nm because of the conjugated C3=C4 double bond. The [2 + 2] dimerization *destroys* that double bond, blue-shifting the absorption out of the 365 nm band: **the dimer is effectively transparent at 365 nm**. Consequently the absorber is consumed where the light is strongest (the surface), the local optical density drops, and a *conversion front* propagates inward — the standard behavior of frontal photopolymerization/photobleaching media [2, 3]. A naïve static Beer–Lambert reading therefore *overstates* the steady-state penetration limit: given enough dose, the front can in principle sweep the full thickness.

2.3 Three distinct limiters

Whether the interior ever cures is set by whichever of the following bites first:

1. **Optical attenuation (dose-limited, transient).** If $\delta_{1/e} \ll L$ and bleaching is slow, the front takes a long time to advance. Curable in principle, given dose. Dominant at 254 nm (see below), mild at 365 nm.

2. **Conversion ceiling (dose-*independent*).** Once the acrylate network is set, each CoumAc is tethered and can only dimerize with a partner already within ~ 4 Å and correctly oriented. Isolated coumarins never react; restricted segmental mobility caps conversion well below 100%. VanZanten *et al.* attribute thick-sample behavior partly to this "diffusion-limited network reorganization" [1]. *More hours cannot beat this.*

3. **Non-bleaching absorber floor (hard optical limit).** Any species that absorbs at 365 nm but does *not* bleach sets a floor the front cannot cross. DMPA (0.5 wt%) absorbs weakly at 365 nm ($\sim 10\times$ less than at 254 nm [1]); its photolysis products (benzil/benzaldehyde-type species) absorb near 360 nm and do not bleach. Plausible but small.

Why the collaborators' 254 nm intuition does not transfer. The strong attenuation documented in [1] is a 254 nm phenomenon: ∼90% of incident 254 nm intensity is lost within the top ~ 25 µm of a 2 mm specimen, so 254 nm cleavage is confined to a tens-of-microns surface layer. **Both the collaborators and the paper perform *dimerization* at 365 nm**, where DMPA absorbs far less and penetration is much deeper; the 254 nm wall does not apply.

3 Quantitative estimates for the 1:9:90 gel

3.1 CoumAc concentration

With mole fractions x_{PEGDA}=0.01, x_{CoumAc}=0.09, x_{PEGMA}=0.90 and molar masses 700 g/mol (PEGDA), 274.3 g/mol (CoumAc, $C_{15}H_{14}O_5$), 400 g/mol (PEGMA), the mole-averaged monomer mass is $\bar{M} = \sum x_i M_i \approx 392$ g/mol. Taking a resin density $\rho \approx 1.10$ g/cm^3 (typical PEG-acrylate; ±10%), the total monomer concentration is $c_{\mathrm{tot}} = \rho/\bar{M} \approx 2.81$ M and

$$c_{\mathrm{CoumAc}} = x_{\mathrm{CoumAc}}\, c_{\mathrm{tot}} \approx 0.25\,\mathrm{M}. \tag{3}$$

3.2 Penetration depth vs. the one unknown, ε_{365}

Everything rides on ε_{365}, the molar absorptivity of CoumAc at 365 nm. The chromophore peaks near 320 nm; 365 nm sits on the red tail, so ε_{365} plausibly ranges over orders of magnitude and *must be measured* (Sec. 5). Its value alone decides whether optics matter (Table 1).

Table 1: Beer–Lambert penetration for $c_{\mathrm{CoumAc}} = 0.25\,\mathrm{M}$, $L = 2\,\mathrm{mm}$ (initial, unbleached state). T_{back} = fraction of incident 365 nm light reaching the far face.

ε_{365} (1/(M cm))	α (1/cm)	$\delta_{1/e}$	$A(2\,\mathrm{mm})$	T_{back}
5	2.9	3.4 mm	0.25	56% (optics irrelevant)
20	11.6	859 µm	1.0	10% (marginal)
50	29.1	344 µm	2.5	0.3% (surface-limited)
100	58.2	172 µm	5.1	9×10^{-6}
300	174.6	57 µm	15	~ 0
1000	582	17 µm	51	~ 0

3.3 Cure-through time: the photon budget

For a cleanly bleaching front, the time to dimerize a column of thickness L has a hard lower bound set by photon supply: enough 365 nm photons must be absorbed to react every coumarin, discounted by the dimerization quantum yield Φ:

$$\boxed{t_{\mathrm{through}} \gtrsim \frac{c_{\mathrm{CoumAc}}\, N_A\, L}{\Phi\left(I_0\, \lambda/hc\right)}} \tag{4}$$

where $I_0\lambda/hc$ is the incident photon flux. With $c_{\mathrm{CoumAc}} = 0.25\,\mathrm{M}$, $L = 2\,\mathrm{mm}$, $I_0 = 0.1\,\mathrm{W/cm^2}$, $\lambda = 365\,\mathrm{nm}$ (flux $\approx 1.8 \times 10^{17}\,\mathrm{photons\,cm^{-2}\,s^{-1}}$):

Φ	t_{through} (min)	note
0.05	≈ 55	pessimistic Φ
0.1	≈ 28	
0.3	≈ 9	optimistic Φ

The real cure-through time is a small multiple (2–5×) of this bound because the front slows and the conversion ceiling intervenes — i.e. order **1–2 hours**, consistent with VanZanten *et al.*, who obtained substantial bulk stiffening through 2 mm in **60 min** of 365 nm postcure (E' up 69% for 1:1:98).

3.4 Interpretation: dose is not the bottleneck

The collaborators applied 10 h *per face* ($\sim 20\times$ the photon-budget bound of Eq. (4) and $\sim 20\times$ the paper's successful 60 min cure). **If penetration/dose were the sole gate, the gel would be far past complete.** That it is not points away from optics and toward the conversion ceiling (limiter 2), a non-bleaching floor (limiter 3), or — most likely — a readout artifact (next section). One caveat worth testing: the paper cured its *own* 1:9:90 sample for 77 min at 365 nm (not 7 min) before postcure; in this slow-polymerizing, high-CoumAc formulation a 7 min cure may under-form the acrylate network.

4 A critical look at the readout

The evidence for "not curing through" is swelling-induced *surface creasing* imaged in brightfield on the two *irradiated faces*. Three cautions:

- **It is a near-surface probe.** Creasing arises from the mismatch between a constrained, stiffer surface skin and the swelling material beneath; the crease pattern encodes the crosslink-density gradient over roughly the top tens-to-hundreds of microns of the imaged face. It is excellent for detecting *asymmetry between faces* but does not directly image the 1 mm-deep core.
- **Coumarin dimerization is colorless.** Any opacity/yellowing seen by eye is most likely something else (light scattering, incipient phase separation, DMPA photoproducts, or incomplete acrylate cure), *not* the dimerization front. The crease pattern — not color — is the dimerization-sensitive signal.
- **No positive control.** Without a reference for what fully dimerized material looks like under this assay, "incomplete" cannot be quantified.

In short, the current data cannot distinguish "the interior never dimerized" from "the interior dimerized to its achievable ceiling, which is less than the surface," nor from "it did cure through and the face assay is misleading."

5 Three cheap experiments that settle it

1. **Direct attenuation (∼10 min).** Place a 2 mm gel on the ThorLabs power sensor and read transmitted vs. blank intensity. This gives $\alpha = -\ln(I/I_0)/L$ and $\delta_{1/e}$ *with no assumption about* ε_{365}, and repeating it during irradiation shows the front bleaching through in real time.
2. **A real depth probe.** The coumarin *monomer* fluoresces blue; the *dimer* does not. Cut a cross-section and image the 2 mm edge under blue/UV excitation: a dark shell over a bright core *directly visualizes* a surface-limited dimerization profile. This is the measurement the project currently lacks.
3. **Positive control.** Irradiate a thin (∼10 µm) free-standing film to completion (as the paper's FTIR films) to define "100% achievable dimerization," giving the face-creasing assay a reference.

6 Direction A — Programmed stiffness gradients

6.1 The idea, and why it is the project

"We can tune rigidity with light" is *already published* for exactly this system [1]. Reproducing it is not a project. But that paper treated the through-thickness non-uniformity as a nuisance — it *simulated* attenuation, called thick-sample cure "thickness-sensitive," and stopped. Nobody *measured* the dimerization depth profile or *used* the gradient as a design variable.

Direction A inverts the framing: the penetration-limited gradient is the feature. Single-sided (or photomask-patterned) 365 nm irradiation deliberately builds a stiff-skin/soft-core architecture. On solvent uptake the differential swelling between the lightly cross-linked (high-swelling) core and the heavily cross-linked (low-swelling) skin generates a bending moment; the sheet **curls** predictably, and masked regions produce **patterned crease fields / programmable surface topography**. The output observables — curl radius and crease morphology — are exactly what the group's brightfield pipeline already measures.

6.2 Novelty relative to VanZanten *et al.* [1]

- *They:* aim for uniform bulk dimerization; treat gradients as error; qualitative attenuation simulation only.
- *Us:* **deliberate asymmetric/patterned dose as a control knob**; a **quantitative forward model** dose → conversion profile → modulus/swelling profile → shape; and **shape/topography as the designed output**, validated against the crease/curl assay.

6.3 The forward model (what makes it predictive)

A five-stage chain, each stage a standard, citable model; the whole thing is a small, verifiable 1-D solve.

(1) Optics + kinetics → conversion profile $p(z)$. Couple bleaching attenuation to first-order dimerization:

$$\frac{\partial p}{\partial t} = \Phi\,\sigma\,I(z,t)\,\big[1-p(z,t)\big], \qquad I(z,t) = I_0\,\exp\Big[-\ln(10)\,\varepsilon_{365}\,c_{\mathrm{CoumAc}}\int_0^z \big(1-p(z',t)\big)\,dz'\Big], \quad (5)$$

with absorption cross-section $\sigma = \ln(10)\,\varepsilon_{365}/N_A$ and a conversion ceiling $p \le p_{\max}(\text{network}) < 1$ imposed to encode the mobility/partner limit (limiter 2). Inputs: measured α (Exp. 1), Φ, $p_{\max}$ (Exp. 2/3).

(2) Conversion → cross-link density. $\nu_x(z) = \nu_{x,0} + \frac{1}{2}\,p(z)\,c_{\mathrm{CoumAc}}$ (each dimer joins two chains).

(3) Cross-link density → swelling and modulus (Flory–Rehner). Equilibrium swelling ratio $\lambda(z)$ and shear modulus $G(z) = \nu_x(z)k_BT$ from Flory–Rehner [4], giving the stress-free (free-swelling) linear strain $\varepsilon^*(z) = \lambda(z) - 1$.

(4) Depth profile → curvature (graded-beam / plate theory). For a stress-free strain $\varepsilon^*(z)$ and modulus $E(z) = 3G(z)$, small-deflection beam theory gives the equilibrium curvature

$$\kappa \;=\; \frac{\displaystyle\int_0^L E(z)\,\varepsilon^*(z)\,(z-\bar z)\,dz}{\displaystyle\int_0^L E(z)\,(z-\bar z)^2\,dz}, \qquad \bar z = \frac{\int E z\,dz}{\int E\,dz}, \quad (6)$$

which reduces to the Timoshenko bimetallic-strip result [5] in the two-layer limit — a clean analytic anchor for validation.

(5) Surface instability → crease onset. Where a stiff skin is compressed by a swelling substrate, creasing sets in above a critical mismatch strain ($\varepsilon_c \approx 0.35$ for a neo-Hookean surface [6]); crease spacing scales with skin depth. This links the model to the existing brightfield crease-metric readout.

Outputs. Given a measured α and an irradiation recipe (which faces, how long, mask pattern), the model predicts: $p(z)$, $G(z)$, the curl radius $1/\kappa$, and the crease onset/wavelength — all directly comparable to measurement.

6.4 Code reuse.

The group's `drying_analysis` package already provides the two macroscopic readouts this direction needs — `curl_radius` (Kåsa circle fit of $1/\kappa$) and `crack_metrics`/crease morphology — plus `calibration` and `indentation_modulus` (Hertz/Dimitriadis, for spot-checking $E(z)$ on cut faces). The new work is the forward model of Eq. (5)–(6); the measurement layer largely exists.

6.5 Staged experimental program

Phase 0 — Diagnostics (1 week).
Experiments 1–3 (Sec. 5): measure α, the fluorescence depth profile, and a positive control. Deliverable: a defensible answer to "does it cure through, and if not, why." Also fixes the cure time (7 min vs. paper's 77 min).

Phase 1 — Dose → curvature map (2–3 weeks).
Single-sided 365 nm dose series ($t = 0, 10, 30, 60, 120$ min) on 1:9:90 and a lower-coumarin control (e.g. 1:4:95). Measure curl radius on swelling and crease metrics on both faces. Fit $\Phi, p_{\max}$; validate Eq. (5)–(6).

Phase 2 — Thickness scaling (1–2 weeks).
Repeat at $L = 0.5, 1, 2$ mm to test the predicted gradient-vs-thickness scaling; the crossover where curl gives way to through-cure is a sharp, falsifiable prediction.

Phase 3 — Patterning (2–3 weeks).
Photomask/grayscale 365 nm exposure to print lateral stiffness patterns; demonstrate a programmed shape (self-folding element or a simple gripper) and a patterned crease field.

Phase 4 — Model + write-up.
Consolidate into the predictive tool and a manuscript: *"Programming shape and surface topography in coumarin PEG gels via depth-resolved photo-dimerization."*

6.6 Risks and mitigations

- **Gradient too shallow to bend** (if ε_{365} is small, cure is nearly uniform). Mitigate with higher CoumAc, thinner samples, or a benign inert 365 nm dye to sharpen the gradient on purpose. Phase 0's α measurement tells us immediately which regime we are in.
- **Conversion ceiling limits stiffness contrast.** Characterized directly in Phase 1 as $p_{\max}$; if too low, raise crosslinker or reduce initial cure so more coumarins remain mobile.
- **Creasing vs. smooth-bending regime** depends on boundary constraint; both are informative and covered by the existing readouts.

7 Summary

- Penetration depth follows Eq. (2); cure-through time follows Eq. (4). Both are dominated by one measurable unknown, ε_{365}.
- For the 1:9:90 gel, 10 h/face is $\sim 20\times$ the dose needed; **dose starvation is not the cause**. Suspect a conversion ceiling, a non-bleaching floor, or a surface-only-readout artifact — resolved by the three Phase-0 experiments.

- **Direction A** turns the depth gradient into the deliverable: predictable, programmable stiffness gradients → bending and patterned topography, with a compact forward model and an experimental program that reuses the existing crease/curl pipeline.

A Constants and assumptions

$N_A = 6.022 \times 10^{23}\,\mathrm{mol}^{-1}$, $h = 6.626 \times 10^{-34}\,\mathrm{J\,s}$, $c = 3.0 \times 10^{8}\,\mathrm{m/s}$, $\lambda = 365\,\mathrm{nm}$ ($E_\gamma = 5.44 \times 10^{-19}\,\mathrm{J}$). Resin density $\rho = 1.10\,\mathrm{g/cm^3}$ (assumed, ±10%). CoumAc $M = 274.3\,\mathrm{g/mol}$ ($C_{15}H_{14}O_5$). Quantum yield Φ and molar absorptivity ε_{365} are *unmeasured* and are the two parameters to pin experimentally. All numerical values in Tables 1 were generated by the accompanying script `penetration.py` (reproduce with the constants above).

References

[1] A. VanZanten, S. Punhani-Schillinger, M. R. Blocksome, A. Ketkar, S.-Y. Chen, M. M. Driscoll, R. C. Ferrier Jr., C. R. Szczepanski. *Photoswitchable Cross-Linking in Polymer Gels: Effects on Surface Creasing and Network Relaxation during Swelling.* Macromolecules **2026**, 59, 4622–4635. DOI: 10.1021/acs.macromol.5c03103.

[2] J. T. Cabral, J. F. Douglas. *Propagating waves of network formation induced by light.* Polymer **2005**, 46, 4230.

[3] G. Terrones, A. J. Pearlstein. *Effects of optical attenuation and consumption of a photobleaching initiator on local initiation rates in photopolymerizations.* Macromolecules **2001**, 34, 3195.

[4] P. J. Flory, J. Rehner. *Statistical mechanics of cross-linked polymer networks II. Swelling.* J. Chem. Phys. **1943**, 11, 521.

[5] S. Timoshenko. *Analysis of bi-metal thermostats.* J. Opt. Soc. Am. **1925**, 11, 233.

[6] W. Hong, X. Zhao, Z. Suo. *Formation of creases on the surfaces of elastomers and gels.* Appl. Phys. Lett. **2009**, 95, 111901.