Pore draining and pore relaxation in a dense suspension

What the quantities mean, how to calculate them, and how to measure them, for 800 nm silica and for cornstarch

Working brief, Driscoll lab

2026-08-10

Contents

0. What this document is for **2**

1. Three different things get called "pore relaxation" **3**

2. Deriving the consolidation equation **4**
2.1 The two mass balances . . . 4
2.2 Darcy's law . . . 4
2.3 Effective stress . . . 4
2.4 The storage coefficient . . . 5
2.5 The relaxation time, exactly . . . 5

3. The drainage length is a modelling choice **7**

4. Reynolds dilatancy **8**
4.1 The dilatancy law . . . 8
4.2 Coupling to Darcy . . . 8
4.3 The identity, and the ceiling . . . 8
4.4 Why the ceiling matters . . . 9

5. How to know the permeability **10**
5.1 Carman–Kozeny . . . 10
5.2 Where it breaks for 800 nm silica: the double layer in the pore throat . . . 10
5.3 Three ways to measure κ . . . 11

6. How to know the network modulus **12**
6.1 What it is . . . 12
6.2 The Brownian regime, $\phi < \phi_c$ . . . 12
6.3 The double-layer regime: the silica case . . . 12
6.4 The Hertzian regime: cornstarch and glass beads . . . 13
6.5 Four ways to measure K_p . . . 13

7. The shortcut: you do not need κ and K_p separately **14**

8. The dimensionless groups, and what each is for **15**

9. Worked calculations **16**
9.1 800 nm silica at $\phi = 0.50$ . . . 16
9.2 Cornstarch at $\phi = 0.42$ . . . 17
9.3 The validation: Jérôme's glass beads . . . 17

9.4 The one prediction that is anchor-free 17

10. How each assumption fails **19**

11. What to do about it, cheapest first **20**

12. Symbols **21**
Formula card 21

13. Sources **21**

0. What this document is for

The lab needs two numbers for its 800 nm silica at high volume fraction: how long the pore pressure takes to relax, and how large a pressure Reynolds dilatancy can generate. Both have closed forms. Neither can be evaluated without inputs the project does not yet measure.

This document works the physics from the two-phase mass balances up, so that every assumption is visible and every input can be traced to something measurable. It then gives the measurement routes in order of cost, including one that skips the hardest input entirely.

Companion documents:

File	What it holds
`PORE_RELAXATION_BRIEF.md`	The answer and the comparison, four pages
`STRESS_AND_DILATANCY_BRIEF.pdf`	The 2026-08-06 stress ladder and the ID number
`pore_relaxation.py`	Every formula here, executable
`test_pore_relaxation.py`	33 tests, including the validation against measured data
`out/pore_relaxation.json`	Every number here, machine-readable

Notation, fixed once. a is a particle **diameter**. It is a radius in the Wyart–Cates literature and a diameter in Carman–Kozeny, and mixing them costs a factor of four in the permeability. ϕ is the solid volume fraction, ϕ_c the dilatancy onset, $\Delta\phi = \phi - \phi_c$. Pressures are in Pa, lengths in m, and μ_f is the pore fluid's viscosity. A full symbol table is in §12.

1. Three different things get called "pore relaxation"

Before deriving anything it is worth separating three times that all have units of seconds and all get called the pore relaxation time. They differ by up to nine decades for the same material, so picking the wrong one is not a rounding error.

(i) The acoustic time, $\tau_{\mathrm{ac}} \sim L/c$. How long a pressure signal takes to cross the sample at the speed of sound in the mixture. For a 2.5 mm drop with $c \approx 1630$ m/s this is 1.5 µs. It governs the water-hammer stage of impact and nothing else here.

(ii) The fluid-compressibility time, $\tau_\chi = \mu_f \chi_f L^2/\kappa$. How long it takes to drain a pore-pressure increment when the *only* thing storing that increment is the pore water squeezing. This is the rigid-skeleton limit: rigid grains, rigid network, compressible fluid. It is the time that appears in Jérôme, Vandenberghe and Forterre's validity condition for treating the pore fluid as incompressible, and it is what `inertial_dilatant.poroelastic_time_ratio` computes.

(iii) The poroelastic consolidation time, $\tau_p = \mu_f L^2/(\kappa K_p)$. How long it takes to drain a pore-pressure increment when the storage is provided by the *particle network* deforming. This is the pore relaxation time in the sense that matters for dilatancy, and it is the one this document is about.

The three differ because they use different storage terms. Water's compressibility gives an effective stiffness of $1/\chi_f = 2.2$ GPa. The particle network of a colloidal suspension at $\phi = 0.5$ has a bulk modulus of order 10^2–10^3 Pa. The ratio is six to seven decades, and it is the whole reason (ii) and (iii) disagree so violently.

Both (ii) and (iii) are correct answers to their own questions. Neither substitutes for the other. §2 derives a single equation containing both.

2. Deriving the consolidation equation

2.1 The two mass balances

Treat the suspension as two interpenetrating continua. The solid phase occupies volume fraction ϕ and moves at $\mathbf{v}_s$; the fluid occupies $1-\phi$ and moves at $\mathbf{v}_f$. With incompressible grains,

$$\frac{\partial \phi}{\partial t} + \nabla\cdot(\phi\,\mathbf{v}_s) = 0, \tag{2.1}$$

$$\frac{\partial}{\partial t}\big[(1-\phi)\rho_f\big] + \nabla\cdot\big[(1-\phi)\rho_f \mathbf{v}_f\big] = 0. \tag{2.2}$$

Let the fluid be slightly compressible, $\rho_f = \rho_{f0}(1+\chi_f p)$, with χ_f the isothermal compressibility and p the pore pressure. Expanding (2.2) and keeping terms to first order in $\chi_f p$:

$$\frac{\partial (1-\phi)}{\partial t} + \nabla\cdot\big[(1-\phi)\mathbf{v}_f\big] + (1-\phi)\chi_f \frac{\partial p}{\partial t} = 0. \tag{2.3}$$

Adding (2.1) and (2.3), the $\partial\phi/\partial t$ terms cancel and we are left with a statement about the total volume flux:

$$\nabla\cdot\mathbf{v}_s + \nabla\cdot\mathbf{q} + (1-\phi)\chi_f\frac{\partial p}{\partial t} = 0, \qquad \mathbf{q} \equiv (1-\phi)(\mathbf{v}_f - \mathbf{v}_s). \tag{2.4}$$

$\mathbf{q}$ is the **filtration flux**, also called the superficial or Darcy velocity: the volume of fluid crossing unit total area per unit time, measured in the frame of the moving solid. It is not the interstitial fluid velocity, and the factor $(1-\phi)$ between them is a standard place to lose a factor.

2.2 Darcy's law

Darcy's law closes $\mathbf{q}$:

$$\mathbf{q} = -\frac{\kappa}{\mu_f}\nabla p. \tag{2.5}$$

This is the Stokes-flow drag of the fluid through the pore network, coarse-grained. It assumes: creeping flow through the pores (pore Reynolds number $\ll 1$), a pore geometry large compared with any molecular or electrostatic length, no slip at the particle surfaces, and a representative volume containing many pores. §5.2 shows the third of these is the one that bites for 800 nm silica at low salt.

The pore Reynolds number for the lab's system is reassuringly small. With a pore velocity of order $q/(1-\phi)$ and a pore length of order a, even a filtration flux of 1 mm/s gives $\mathrm{Re}_{\mathrm{pore}} \sim \rho\, q\, a/\mu_f \sim 10^{-3}$. Creeping flow is safe.

2.3 Effective stress

The last ingredient is how the skeleton responds. Terzaghi's principle: the deformation of a saturated granular skeleton is controlled not by the total stress σ but by the **effective stress** carried by the contacts,

$$\sigma' = \sigma - p. \tag{2.6}$$

This is why the distinction matters physically. Load a saturated packing fast enough that no fluid can move and the pore pressure rises to carry essentially the whole increment, so σ' barely changes and the particles barely feel it. That is the undrained limit. Wait long enough for the fluid to drain and p returns to ambient, so the entire increment transfers onto the contacts. Consolidation is the transfer, and τ_p is how long it takes.

Define the drained bulk modulus of the skeleton by

$$K_p \equiv -V\frac{\partial \sigma'}{\partial V}\bigg|_p = \phi\,\frac{\partial \sigma'}{\partial \phi}, \tag{2.7}$$

where the second form uses incompressible grains: the particle volume ϕV is fixed, so $V = V_s/\phi$ and $\mathrm{d}V/V = -\mathrm{d}\phi/\phi$. **This is the same ϕ, not $1-\phi$, that reappears in the dilatancy ceiling in §4.3, and getting it wrong there is a mistake this project made and corrected.**

At constant total stress, $\partial\sigma'/\partial t = -\partial p/\partial t$, so the skeleton's volumetric strain rate is

$$\nabla\cdot\mathbf{v}_s = \frac{1}{V}\frac{\partial V}{\partial t} = -\frac{1}{K_p}\frac{\partial \sigma'}{\partial t} = \frac{1}{K_p}\frac{\partial p}{\partial t}. \tag{2.8}$$

2.4 The storage coefficient

Substituting (2.5) and (2.8) into (2.4):

$$\boxed{S\,\frac{\partial p}{\partial t} = \nabla\cdot\left[\frac{\kappa}{\mu_f}\nabla p\right], \qquad S = \underbrace{\frac{1}{K_p}}_{\text{skeleton}} + \underbrace{(1-\phi)\chi_f}_{\text{pore fluid}}} \tag{2.9}$$

The two storage terms **add**, which means the *larger compliance wins*. This is worth dwelling on, because the intuition runs the other way: one might expect the stiffer element to dominate, as it does for springs in parallel. Here the elements are in series as far as storing a pressure increment goes, and the softer one absorbs almost all of it.

For the lab's silica at $\phi = 0.50$: $1/K_p = 1.7\times10^{-3}$ Pa^{-1} against $(1-\phi)\chi_f = 2.3\times10^{-10}$ Pa^{-1}. The skeleton carries 99.99999% of the storage. For cornstarch it carries 99.97%. Only for a genuinely stiff pack such as glass beads does the fluid term reach a percent.

So in every case of interest, (2.9) simplifies to a plain diffusion equation:

$$\frac{\partial p}{\partial t} = D_p\nabla^2 p, \qquad \boxed{D_p = \frac{\kappa K_p}{\mu_f}} \tag{2.10}$$

D_p is the pore-pressure diffusivity, also called the consolidation coefficient in soil mechanics and, in colloid science, the **collective (or gradient) diffusion coefficient**. Those are the same quantity under three names, and §7 turns that fact into the cheapest available measurement.

2.5 The relaxation time, exactly

Solve (2.10) in one dimension for a layer of thickness L drained at $x = 0$ and sealed at $x = L$, starting from a uniform overpressure p_0. Separating variables gives a cosine series whose slowest mode decays as $\exp(-t/\tau_1)$ with

$$\tau_1 = \frac{4L^2}{\pi^2 D_p} = 0.405\,\frac{L^2}{D_p}. \tag{2.11}$$

Throughout the brief and the code we quote the **scaling**

$$\tau_p = \frac{L^2}{D_p} = \frac{\mu_f L^2}{\kappa K_p} \tag{2.12}$$

and report the $4/\pi^2$ factor separately (`slowest_mode_time`) rather than folding it in. The reason is arithmetic hygiene: every conclusion in this analysis is a statement about decades, and a formula you can check on the back of an envelope is worth more than one that is $2.5\times$ more accurate. If a number is ever needed to better than a factor of two, use (2.11) and state the boundary conditions it assumes.

3. The drainage length is a modelling choice

L is the distance pore fluid must actually travel to equilibrate. It is not a material property, and quoting τ_p without L is meaningless. Three lengths matter for a drop impact.

The particle length, $L = a$. Equilibration between neighbouring pores. Note what happens to the formula: $\kappa \propto a^2$, so L^2/κ is independent of a, and

$$\tau_p(L = a) = \frac{180\,\mu_f\,\phi^2}{(1-\phi)^3 K_p} \tag{3.1}$$

contains no particle size at all. Small particles do not drain more slowly at the pore scale. They drain more slowly across a *fixed geometric* length, because it takes more pores to span it. This is the single most common confusion in this area and it is worth stating in any talk on the subject.

The contact length, $L = 0.49\,D_0$. The contact-patch radius at the force peak, taken from the Wagner analysis in `stress.py`, where it is the computed r_c at peak force rather than an assumption. This is the length that governs whether the spreading lamella can drain, and it is the length implied by Mobaseri *et al.*'s Eq. 3.

The drop length, $L = D_0$. Global drainage.

For the lab's silica these give $\tau_p = 0.6$ ms, 1430 s, and 5960 s at $\phi = 0.50$. The spread is seven decades, from a single material, purely through L.

The right choice depends on the question. For *whether frustrated dilatancy can raise the particle pressure in the spreading film*, the contact length is correct: the fluid must be drawn from somewhere in the film to fill the dilating region, and the film's own radius bounds that distance. For *whether the packing is locally in mechanical equilibrium at the pore scale*, the particle length is correct.

4. Reynolds dilatancy

4.1 The dilatancy law

A packing denser than its critical state cannot shear without expanding: the particles have to ride up over one another. Reynolds observed this in 1885. The modern statement, following Roux and Radjai and used in the two-phase form by Pailha and Pouliquen, is that the solid fraction relaxes toward a shear-rate-dependent equilibrium value:

$$\frac{1}{\phi}\frac{\mathrm{D}\phi}{\mathrm{D}t} = -\tan\psi\,\dot{\gamma}, \qquad \tan\psi = K_{\mathrm{dil}}(\phi - \phi_{\mathrm{eq}}(I)) \approx \alpha\,\Delta\phi. \tag{4.1}$$

ψ is the dilatancy angle. The linear closure $\tan\psi = \alpha\Delta\phi$ with $\alpha \sim 1$ is what Mobaseri *et al.* use and what this analysis inherits. It is a one-parameter model of a genuinely more complicated constitutive response, and α is not measured for either system here.

4.2 Coupling to Darcy

Dilation creates pore volume that must be filled by fluid drawn in from outside. Using (2.4) in the incompressible-fluid limit, $\nabla\cdot\mathbf{q} = -\nabla\cdot\mathbf{v}_s$, and from (4.1) the skeleton's volumetric expansion rate is $\tan\psi\,\dot{\gamma}$. So

$$\nabla\cdot\left[\frac{\kappa}{\mu_f}\nabla p\right] = \tan\psi\,\dot{\gamma}. \tag{4.2}$$

This is a Poisson equation for the pore pressure with the dilation as its source. Over a region of size L_d it scales as $(\kappa/\mu_f)(p/L_d^2) \sim \tan\psi\,\dot{\gamma}$, giving

$$\boxed{p_{\mathrm{dil}} = \frac{\mu_f}{\kappa}\,\Delta\phi\,L_d^2\,\dot{\gamma}} \tag{4.3}$$

taking $\alpha = 1$. The sign is a **suction**: the fluid pressure drops, and by Terzaghi (2.6) the effective stress on the contacts rises by the same amount. That rise is the mechanism. Frustrated dilation does not push the particles apart, it sucks them together.

Equation (4.3) is Mobaseri *et al.*'s Eq. 3 with $|\mathrm{d}h/\mathrm{d}t| = L_d\dot{\gamma}$, and it is the same closure the DNS runs behind `DIL_COEFF` in `wc_drop_impact.c`, where it appears as $p_{\mathrm{dil}} = (\eta_f/k)\,\epsilon_{\mathrm{dil}}L_d^2\dot{\gamma}$. Three independent statements of one relation, which is a good sign.

4.3 The identity, and the ceiling

Divide (4.3) by K_p and use $\tau_p = \mu_f L_d^2/(\kappa K_p)$:

$$p_{\mathrm{dil}} = K_p\,\Delta\phi\,(\dot{\gamma}\,\tau_p). \tag{4.4}$$

The dilatant pressure is the network modulus times the dilation strain accumulated in one pore-relaxation time. This form is more useful than (4.3) because it makes the saturation obvious. $\dot{\gamma}\tau_p$ is a strain, and the packing does not have unlimited strain available: once it has expanded from ϕ to ϕ_c there is no further dilation left to frustrate. From (2.7) that maximum volumetric strain is $\Delta\phi/\phi$, so

$$\boxed{p_{\mathrm{dil}}^{\max} = \frac{K_p\,\Delta\phi}{\phi}} \tag{4.5}$$

A correction on the record. The first version of this analysis wrote (4.5) with $\Delta\phi/(1-\phi)$, reasoning from the porosity. That is wrong, and the derivation in §2.3 is why: with incompressible grains the volumetric strain is referenced to the solid fraction, $\mathrm{d}V/V = -\mathrm{d}\phi/\phi$, and the same ϕ appears in the definition of K_p itself. Using the porosity in one and the solid fraction in the other mixes conventions. The two forms coincide *exactly* at $\phi = 0.5$, which is precisely the operating point the analysis was first evaluated at, so nothing caught it until the derivation was written out longhand. The error is 27% at $\phi = 0.44$ and 38% at $\phi = 0.58$. It changes no conclusion and it moves every printed ceiling. `test_pore_relaxation.py` now pins the corrected form, including the coincidence at $\phi = 0.5$ that hid it.

4.4 Why the ceiling matters

Uncapped, (4.3) predicts 6×10^7 Pa of pore suction for 800 nm silica at $\phi = 0.50$. That is 600 atmospheres of tension in water. The 2026-08-06 brief flagged this as an open problem, proposed a cavitation cap, and then withdrew the cap for four reasons, the strongest being that once the pore-throat radius is computed correctly the capillary ceiling never binds and the capped expression loses all particle-size dependence.

(4.5) is a better answer because it is a statement about what the *material* can do rather than about what the *fluid* can survive, and because it keeps a size dependence through K_p. It also has the right structure: it says the Darcy expression (4.3) describes a *transient build-up rate*, valid until the packing runs out of dilation, at which point the pressure plateaus. The physical picture is a spring being wound up, not a pressure vessel being burst.

It can be checked against data. Jérôme, Vandenberghe and Forterre measured pore suctions of -10 to -100 kPa in 170 µm glass beads under impact. That is the one system in this comparison where the suction was measured rather than extrapolated. §6.4 and §9.3 show what (4.5) gives there, and what had to be fixed to make it agree.

5. How to know the permeability

5.1 Carman–Kozeny

The standard estimate treats the pore space as a bundle of tortuous channels and applies Poiseuille flow. The hydraulic radius of the pore space is

$$R_h = \frac{\text{void volume}}{\text{wetted area}} = \frac{1-\phi}{S_v\,\phi}, \qquad S_v = \frac{6}{a} \text{ for spheres,} \tag{5.1}$$

and folding the Kozeny constant and the tortuosity into a single empirical factor of 180 gives

$$\boxed{\kappa = \frac{(1-\phi)^3\,a^2}{180\,\phi^2}} \tag{5.2}$$

Validity. (5.2) works well for packings of roughly equal spheres over $0.25 \lesssim \phi \lesssim \phi_{\mathrm{RCP}}$. It returns $\kappa = 1.0\times10^{-3}a^2$ at random close packing, which is the standard measured value, and the test suite checks that. It degrades for high-porosity fibrous media, for strongly non-spherical particles, and for broad size distributions, where the Sauter mean diameter should be used instead of the arithmetic mean. For a monodisperse silica this is the right formula.

The size dependence is the whole story. $\kappa \propto a^2$, so the lab's 800 nm silica is $(10\,\mu\mathrm{m}/800\,\mathrm{nm})^2 = 156$ times less permeable than cornstarch at matched ϕ, and about 256 times at the volume fractions the two experiments actually use. Everything downstream inherits this factor.

5.2 Where it breaks for 800 nm silica: the double layer in the pore throat

Carman–Kozeny treats the pore space as inert plumbing. That requires the electrical double layer to be thin compared with the pore throat. The throat radius of a dense sphere pack is the largest sphere that fits between three touching particles, $r_{\mathrm{throat}} = 0.155\,R = 0.0775\,a$, which is **62 nm** for 800 nm silica.

Comparing that with the Debye length across the lab's salt range (`debye_to_throat_ratio`):

added salt	λ_D	$\lambda_D/r_{\mathrm{throat}}$	continuum Darcy?
100 mM	1.0 nm	0.016	fine
1 mM	9.6 nm	0.16	fine
nominal 0 (0.01 mM residual)	95 nm	**1.5**	**no**

At the low-salt end the double layers of opposing pore walls overlap across the entire throat. Two things follow. The counterion cloud is dragged along by the flow and generates a streaming potential whose back-conduction opposes the flow, which is the **electroviscous effect** and raises the apparent viscosity. And the geometric pore area available to bulk flow is reduced.

Both reduce the *effective* permeability below the geometric one, so the low-salt end of the salt series is **less** permeable than (5.2) says, not more. That strengthens the undrained conclusion rather than threatening it, which is why no correction is applied here. But it does mean that a measured κ at 0 mM should not be expected to match Carman–Kozeny, and that the salt axis moves the permeability as well as the contact stiffness. Anyone fitting κ across the salt series should expect two effects, not one.

A caution on the residual ionic strength itself. The 95 nm figure assumes 10^{-5} M from dissolved CO_2. A concentrated silica suspension also releases its own counterions, which at $\phi = 0.5$ can push the ionic strength considerably higher and λ_D correspondingly lower. The bracket used in the calculations (30 nm) is a compromise between these. **The ionic strength of the nominally salt-free samples is not measured,**

and it should be: a conductivity probe reading takes minutes and removes a factor that currently spans a decade.

5.3 Three ways to measure κ

Constant-flux filtration (a Darcy cell). Push fluid through a packed bed at a known volumetric flux and measure the pressure drop; $\kappa = \mu_f q L_{\mathrm{bed}}/\Delta p$. This is the definitional measurement. For a colloid it is awkward: the required pressures are high, the bed consolidates during the measurement (so ϕ is not the ϕ you set), and you need a membrane fine enough to retain 800 nm particles without dominating the resistance.

Hindered settling. Let the suspension sediment and track the interface. At steady state the buoyant weight of the particles is balanced by Darcy drag, giving

$$\kappa = \frac{\mu_f \, (1-\phi) \, U_{\mathrm{settle}}}{\phi \, \Delta\rho \, g}. \tag{5.3}$$

For the lab's silica at $\phi = 0.50$ this predicts $U_{\mathrm{settle}} \approx 1.5$ mm per day. Slow, but a cathetometer or a photograph a day for a week measures it, and it needs no equipment the lab does not have. The caveat is that at high ϕ the suspension may not settle as a clean interface, and the network can support itself against gravity entirely if it has yielded.

Infer it from the collective diffusivity. See §7. This is the cheapest route and it measures the product κK_p, which is what τ_p actually needs.

6. How to know the network modulus

K_p is the input with the widest uncertainty and the least literature support. This section gives three physical regimes and four measurement routes.

6.1 What it is

From (2.7), $K_p = \phi\,\partial\sigma'/\partial\phi$: the change in effective particle pressure per unit fractional compression, at fixed pore pressure. In colloid science the same quantity, measured under quiescent conditions, is the **osmotic bulk modulus** $K = \phi\,\partial\Pi/\partial\phi$. The two coincide when the particle pressure is thermodynamic in origin, and diverge once contacts form, because contact forces are not in equilibrium with a reservoir.

That distinction sets up the three regimes.

6.2 The Brownian regime, $\phi < \phi_c$

Below the contact onset the particles are held apart by thermal pressure. For hard spheres the Carnahan–Starling equation of state gives

$$\Pi = nk_BT\,Z(\phi), \qquad Z = \frac{1+\phi+\phi^2-\phi^3}{(1-\phi)^3}, \qquad n = \frac{6\phi}{\pi a^3}. \tag{6.1}$$

Its worth as an anchor is that it is exact to fourth order in ϕ and reproduces the hard-sphere freezing pressure to a few percent, which the test suite checks.

For 800 nm silica at $\phi = 0.50$ this gives $K = 0.43$ Pa. That number deserves a moment. It is *tiny*: the entire osmotic stiffness of a concentrated colloidal suspension is well under a pascal, because nk_BT for 800 nm particles is only 7.6×10^{-3} Pa. This is why colloidal consolidation takes days, why these suspensions do not settle, and why any network stiffness above a few pascals must come from contacts rather than from thermal pressure.

For cornstarch, $K_{\text{osm}} = 9 \times 10^{-5}$ Pa. Thermal pressure is irrelevant. The shear Péclet number confirms it from the other side: $\mathrm{Pe} = 7 \times 10^5$ for cornstarch under impact against $\mathrm{Pe} = 274$ for the silica. Both are athermal in flow, but the silica only by two decades, and its *equilibrium* modulus is Brownian.

6.3 The double-layer regime: the silica case

Once particles are pressed into contact the stiffness is set by whatever repulsion holds them apart. For electrostatically stabilised silica that is the double layer, and a screened-Coulomb repulsion decays exponentially with surface separation h:

$$F(h) = F^* e^{-h/\lambda_D} \quad\Longrightarrow\quad k_n = -\frac{\mathrm{d}F}{\mathrm{d}h} = \frac{F}{\lambda_D}. \tag{6.2}$$

The stiffness is set by the load the contact already carries, divided by the screening length. There is no particle modulus in it, correctly, since these surfaces never touch.

The mean contact force in a packing at isotropic particle pressure P follows from summing $f\ell$ over the $Zn/2$ contacts per unit volume:

$$f = \frac{\pi P a^2}{Z\phi}. \tag{6.3}$$

The affine (Voigt) estimate of the packing's bulk modulus with normal springs is $K_p = Z\phi k_n/(6\pi a)$. Substituting (6.2) and (6.3), Z and ϕ **cancel exactly**:

$$\boxed{K_p = \frac{P\,a}{6\lambda_D}} \tag{6.4}$$

This is a satisfying result. It has one free parameter, λ_D, which is set by a measurable salt concentration. It says the network's stiffness *relative to its own confining pressure* is fixed by a pure geometric ratio, $a/6\lambda_D \approx 13$ at $\lambda_D = 10$ nm. And it predicts that **adding salt stiffens the network**, in the same direction as the measured rise of σ^* with salt.

Two caveats. The affine estimate is an upper bound; real packings relax non-affinely and measure two to five times softer near isostaticity. And (6.2) presumes a pure screened-Coulomb repulsion, whereas Ishibashi *et al.* fit these particles with a double-layer term *plus* a thermal term and find the double-layer contribution vanishing above a critical coagulation concentration. Above roughly 100 mM, (6.4) should not be trusted.

6.4 The Hertzian regime: cornstarch and glass beads

For solid grains in true contact the stiffness is Hertzian:

$$E^* = \frac{E}{2(1-\nu^2)}, \quad R^* = \frac{a}{4}, \quad \delta = \left(\frac{3f}{4E^*\sqrt{R^*}}\right)^{2/3}, \quad k_n = \frac{\mathrm{d}f}{\mathrm{d}\delta} = 2E^*\sqrt{R^*\delta}. \tag{6.5}$$

The essential feature is $k_n \propto P^{1/3}$: **a granular network has no pressure-independent modulus**, and quoting K_p for a granular pack without stating the confining pressure is meaningless.

This is not a fine point. The first version of this analysis used the pressure-free scale $k_n \sim Ea$, which corresponds to a contact squashed by $\delta \sim a$. For glass beads at 10 kPa confinement the real overlap is $\delta/a \approx 5 \times 10^{-5}$, and the pressure-free estimate is **three decades too stiff**. Fed into (4.5) it predicted 1.1×10^8 Pa of dilatant suction in Jérôme's beads against a measured 10^4 to 10^5 Pa, and the validation test failed. With (6.5) at the stated confinement the prediction is 4.2×10^5 Pa: within a decade, and on the expected side, since the affine modulus is an upper bound. The pressure-free form is retained in the code with a test that holds it to its three-decade error, so it cannot be quietly reinstated.

6.5 Four ways to measure K_p

Osmotic stress / dialysis. Equilibrate the suspension against a polymer solution of known osmotic pressure through a semipermeable membrane, and measure the resulting ϕ. Repeat at several pressures to get $\Pi(\phi)$, then differentiate. This is the gold standard for colloids and it directly returns the quantity in (2.7). It is slow: equilibration at $\phi \sim 0.5$ takes days to weeks, for exactly the reason this document is about.

Centrifugation to equilibrium. Spin to a known g, let the sediment reach equilibrium, and read the $\phi(z)$ profile. The profile *is* $\Pi(\phi)$, since at equilibrium $\mathrm{d}\Pi/\mathrm{d}z = -\phi\Delta\rho\, g(z)$. One tube gives the whole curve. Reading $\phi(z)$ non-destructively needs X-ray or NMR profiling; destructively, it needs careful sectioning.

Compressional rheology / filtration. Apply a step pressure to a suspension above a membrane and record the height against time. This is the most direct route because it returns K_p *and* the consolidation coefficient from one experiment, and the Buscall–White and Landman–White framework for extracting both is standard in the literature.

Confined oscillatory compression. Compress a suspension in a rheometer between a plate and a porous frit, oscillating at frequency ω, and measure the normal force. Below the drainage frequency the response is drained and returns K_p; above it the response is undrained. The crossover frequency is $1/\tau_p$, which makes this a measurement of both. The practical obstacle is that most rheometers do not have a normal-force resolution good enough for a network modulus of order 10^2 Pa.

7. The shortcut: you do not need κ and K_p separately

Look again at (2.10). The relaxation time depends on κ and K_p only through their product:

$$\tau_p = \frac{L^2}{D_p}, \qquad D_p = \frac{\kappa K_p}{\mu_f}.$$

D_p is a single measurable quantity. Splitting it into a permeability and a modulus is a modelling convenience, not a requirement. **If the goal is the relaxation time, measure D_p and stop.** Three routes, cheapest first.

Dynamic light scattering at small q. The collective diffusion coefficient is exactly D_p, and DLS measures it directly from the decay rate $\Gamma = D_c q^2$ in the limit $qa \ll 1$. The obstacle at $\phi = 0.5$ is multiple scattering: the sample is opaque. The standard fixes are refractive-index matching (feasible for silica in a water/glycerol/DMSO mix, though that changes μ_f and therefore τ_p, so the measurement must be corrected back), 3D cross-correlation DLS, or diffusing-wave spectroscopy. **This is the measurement to ask a collaborator for**, and it is a half-day on an instrument the lab may already have access to.

A consolidation (filtration) experiment. Load the suspension into a cell above a membrane, apply a step pressure, record the piston height $h(t)$. The approach to equilibrium is exponential with the time constant of (2.11), so a single fit returns D_p for a known cell height. This measures the actual physical process rather than a proxy, and it needs no optics. It is the most defensible number available.

A centrifuge consolidation run. The same experiment with centrifugal rather than mechanical loading. Faster, and it reaches higher effective pressures, at the cost of a non-uniform body force that has to be modelled.

All three measure the same D_p, and any two agreeing would be a genuine cross-check of the kind this project currently lacks.

8. The dimensionless groups, and what each is for

Four groups appear in this problem and they are routinely confused.

The drainage number, $\mathrm{De} = \tau_p/\tau_{\mathrm{imp}}$, with $\tau_{\mathrm{imp}} = D_0/U_0$. Asks whether the pore pressure can relax during the event. $\mathrm{De} \gg 1$ is undrained, so an imposed dilation is fully frustrated and generates the largest particle pressure the network can carry. $\mathrm{De} \ll 1$ is drained, and suction bleeds away as fast as dilation makes it. This is the group this document is built on.

The inertial–dilatant number, $\mathrm{ID} = \rho\kappa U_0/(A\mu_f \Delta\phi D_0)$, from Mobaseri *et al.*, Eq. 6. Asks whether inertia or dilatancy wins the *force* balance. Note it contains no K_p: it is a Reynolds–Darcy construct, and it compares $F_i \sim \rho U_0^2 D_0^2$ with $F_d \sim A\mu_f U_0 D_0^3 \Delta\phi/\kappa$. It answers a different question from De and the two must not be conflated. The 2026-08-06 brief documents two problems with Eq. 6 as printed, including that it does not evaluate to 1 at the regime boundary it is drawn at.

The fluid-compressibility ratio, $\tau_\chi/\tau_{\mathrm{imp}} = \mu_f \chi_f D_0 U_0/\kappa$**.** Asks only whether the pore fluid may be treated as incompressible in the Darcy–Reynolds equation. Jérôme *et al.*'s own validity condition. 0.014 for cornstarch, 0.81 for the lab's silica, which is marginal, and 17.6 with 0.1% entrained gas, which is not.

The Péclet number, $\mathrm{Pe} = 6\pi\mu_f (a/2)^3 \dot{\gamma}/k_B T$**.** Asks whether the suspension is athermal. 274 for the silica, 7×10^5 for cornstarch.

A table of what each one decides:

group	decides	silica	cornstarch
De	can pore pressure relax?	1×10^6	7.2
ID	inertia or dilatancy?	6×10^{-5}	1×10^{-2}
$\tau_\chi/\tau_{\mathrm{imp}}$	is the pore fluid incompressible?	0.81	0.014
Pe	is it athermal?	274	7×10^5

9. Worked calculations

9.1 800 nm silica at $\phi = 0.50$

Inputs: $a = 800$ nm, $\phi = 0.50$, $\phi_c = 0.42$ (assumed, see §10), $\mu_f = 10^{-3}$ Pa s, $\lambda_D = 10$ nm, $P_{\text{conf}} = \sigma^* = 44.2$ Pa, $D_0 = 2.5$ mm, $U_0 = 2.3$ m/s.

Permeability, (5.2):

$$\kappa = \frac{(0.50)^3 (8 \times 10^{-7})^2}{180(0.50)^2} = 1.78 \times 10^{-15} \text{ m}^2$$

Network modulus, (6.4):

$$K_p = \frac{44.2 \times 8 \times 10^{-7}}{6 \times 10^{-8}} = 590 \text{ Pa}$$

Storage, (2.9): $1/K_p = 1.70 \times 10^{-3}$ against $(1-\phi)\chi_f = 2.3 \times 10^{-10}$. The skeleton carries all of it, to seven figures.

Diffusivity, (2.10):

$$D_p = \frac{1.78 \times 10^{-15} \times 590}{10^{-3}} = 1.05 \times 10^{-9} \text{ m}^2/\text{s}$$

Relaxation, (2.12), at $L = 0.49 D_0 = 1.23$ mm:

$$\tau_p = \frac{(1.23 \times 10^{-3})^2}{1.05 \times 10^{-9}} = 1.43 \times 10^3 \text{ s}$$

against an impact time $\tau_{\text{imp}} = D_0/U_0 = 1.09$ ms. So

$$\text{De} = 1.3 \times 10^6.$$

Uncapped dilatant pressure, (4.3), with $\dot{\gamma} = U_0/D_0 = 920$ s^{-1}:

$$p_{\text{dil}} = \frac{10^{-3}}{1.78 \times 10^{-15}} \times 0.08 \times (1.23 \times 10^{-3})^2 \times 920 = 6.2 \times 10^7 \text{ Pa}$$

Ceiling, (4.5):

$$p_{\text{dil}}^{\max} = \frac{590 \times 0.08}{0.50} = 94 \text{ Pa}$$

The ceiling binds by six decades. Everything the material can do is bounded by 94 Pa, of the same order as $\sigma^* = 44$ Pa. That coincidence is not independent, since P_{conf} was set to σ^*; §9.4 removes the anchor.

9.2 Cornstarch at $\phi = 0.42$

Inputs: $a = 10$ µm, $\phi_c = 0.37$, $E_p = 10^8$ Pa, $\nu = 0.3$, $P_{\text{conf}} = 10^5$ Pa, $D_0 = 4$ mm, $U_0 = 5.1$ m/s.

$\kappa = 6.14 \times 10^{-13}$ m^2. Hertz, (6.5), gives $k_n = 83$ N/m at $\delta/a = 2.3 \times 10^{-2}$, and the affine modulus gives $K_p = 1.10 \times 10^6$ Pa. Then $D_p = 6.8 \times 10^{-4}$ m^2/s, and at $L = 1.96$ mm,

$$\tau_p = 5.7 \text{ ms}, \qquad \text{De} = 7.2.$$

Ceiling: $p_{\text{dil}}^{\max} = 1.10 \times 10^6 \times 0.05/0.42 = 1.3 \times 10^5$ Pa, against an uncapped Darcy value of 4.0×10^5 Pa. The ceiling binds, but only by a factor of 3, and the resulting number sits in the 10^5–10^6 Pa band Waitukaitis and Jaeger measured for jammed cornstarch columns under impact.

The contrast. Silica's D_p is 4.8×10^5 times smaller. That decomposes as ×257 from permeability and ×1854 from network stiffness, but the second factor is mostly an artefact of the two experiments operating at pressures 2000-fold apart. Put both at $P_{\text{conf}} = 10^5$ Pa and the moduli come out within 20% of each other, and the whole contrast collapses back onto the a^2 permeability factor. **The permeability contrast is the material difference; the stiffness contrast says where each experiment sits.**

9.3 The validation: Jérôme's glass beads

Inputs: $a = 170$ µm, $\phi = 0.58$, $\Delta\phi = 0.005$ (estimated), $E = 70$ GPa, $\nu = 0.25$, $P_{\text{conf}} = 10^4$ Pa, the low end of their measured suction.

$\kappa = 3.5 \times 10^{-11}$ m^2. Hertz gives $k_n = 4.5 \times 10^4$ N/m at $\delta/a = 5.1 \times 10^{-5}$, so $K_p = 4.9 \times 10^7$ Pa, and

$$p_{\text{dil}}^{\max} = \frac{4.9 \times 10^7 \times 0.005}{0.58} = 4.2 \times 10^5 \text{ Pa}$$

against a measured 10^4 to 10^5 Pa. Within a decade, and above rather than below, which is the expected direction for an affine upper bound. The dominant remaining uncertainty is $\Delta\phi$, which is not reported in their paper: $\Delta\phi = 0.001$ would put the prediction at 8×10^4 Pa, dead centre of the measurement.

Their drainage number is De = 0.003. Glass beads drain freely, which is why their suction is set by the Darcy build-up rate rather than by the ceiling.

9.4 The one prediction that is anchor-free

Divide (4.5) by the confining pressure. Using (6.4), P cancels:

$$\boxed{\frac{p_{\text{dil}}^{\max}}{P_{\text{conf}}} = \frac{a}{6\lambda_D} \cdot \frac{\Delta\phi}{\phi}} \tag{9.1}$$

No σ^*, no K_p, no permeability. Only a particle size, a Debye length, and the distance above the dilatancy onset. Below 1, frustrated dilation cannot raise the particle pressure above what already drives it, so Reynolds dilatancy is not available as a strengthening mechanism. Above 1, it is. Setting (9.1) to unity,

$$\phi^* = \frac{\phi_c}{1 - 6\lambda_D/a}. \tag{9.2}$$

added salt	λ_D	ϕ^*	ratio at $\phi = 0.44$	at $\phi = 0.50$
nominal 0 (residual)	30 nm	0.542	0.20	0.71

added salt	λ_D	ϕ^*	ratio at $\phi = 0.44$	at $\phi = 0.50$
1 mM	10 nm	0.454	0.61	2.13
100 mM	1 nm	0.423	6.06	21.3

At the volume fraction the drops are actually made at, $\phi = 0.44$, the silica is on the wrong side of the crossover at low salt. **Reynolds dilatancy cannot be the arrest mechanism there unless the salt is high.** That is consistent with what the DNS found by an entirely different route: at $\phi = 0.44$ the fitted Wyart–Cates closure cannot shear-jam at any stress either, and a free-surface mechanism is required in any case because a local constitutive law has no propagating-front solution.

ϕ^* moves from 0.54 to 0.42 across the salt range, which is a curve the existing salt-screening series can be replotted against at no experimental cost, provided the ϕ axis is trusted. Worth flagging without leaning on it: at 1 mM, (9.2) gives $\phi^* = 0.454$, and Shah, Arora and Driscoll report the first localised solid patches at $\phi = 0.47$ on the same 830 nm particles. $\lambda_D = 10$ nm was a default rather than a measurement on their samples, so that is a coincidence worth testing rather than evidence.

10. How each assumption fails

In rough order of how much damage it does.

ϕ_c is unmeasured. Every quantity containing $\Delta\phi$ scales with it, and ϕ^* moves with it roughly one-for-one. Three anchors exist and they cannot all sit on one ϕ axis: Shah's 0.47 for the first solid patches, the fitted $\phi_M = 0.5176$, and the lab's own observation of fronts at 0.42. Until the ϕ axis is settled, every absolute number here carries that spread. Nothing else on this list matters as much.

K_p is unmeasured for either system. Bracketed here by λ_D from 30 to 1 nm for the silica and E_p from 10^7 to 10^9 Pa for cornstarch. The undrained verdict survives the whole bracket by at least two decades; the absolute ceilings do not survive it at all.

The affine modulus is an upper bound. Real packings relax non-affinely, softening by two to five times near isostaticity. Every ceiling quoted here is correspondingly high.

The single-length scaling of (4.3). Replacing the Poisson problem (4.2) by $p \sim (\mu/\kappa)\Delta\phi L_d^2\dot{\gamma}$ is a scaling, not a solution. Mobaseri *et al.*'s own F_d carries the same substitution and it is where their factor-of-150 discrepancy most likely lives. If a factor of 3 ever matters, solve (4.2) on the actual contact geometry.

Carman–Kozeny at low salt. §5.2: the double layer fills the pore throat at the salt-free end, so the effective permeability is below the geometric one. Direction known, magnitude not.

Steady-state constitutive assumptions. (4.1) presumes the dilatancy law responds instantaneously. Under a 1 ms impact with $\mathrm{De} \sim 10^6$ that is not obviously true, and a rate-dependent ϕ_{eq} would change the transient.

Monodispersity. Assumed throughout, and true for this silica, which is why the analysis is cleaner for it than it would be for cornstarch. Cornstarch granules are polydisperse and faceted, so its κ carries an unquantified shape factor.

11. What to do about it, cheapest first

A conductivity reading on the salt-free samples. Minutes. Removes a factor spanning a decade in λ_D, which propagates directly into K_p, ϕ^* and the electroviscous correction. There is no reason not to have this number.

ϕ_c and the ϕ axis, by DLS and ζ. Half a day, already the top item on the open-problems slate, and already gating three other things. It is the same measurement in all four cases.

D_p by DLS at small q, or by a consolidation cell. §7. Returns the pore relaxation time directly, without needing κ and K_p separately. If only one new measurement is possible, this is the one, because it turns the central quantity of this document from an estimate into data.

Replot the salt series against $\phi^*(\lambda_D)$. No new experiments. Tests (9.2) against data the lab already owns.

A settling column. A week of passive observation gives κ from (5.3) and, with D_p, closes the system: $K_p = \mu_f D_p/\kappa$ with no micromechanical model at all. That combination would make every number in §9 a measurement rather than an estimate.

12. Symbols

symbol	meaning	units
a	particle **diameter**	m
ϕ, ϕ_c, $\Delta\phi$	solid fraction, dilatancy onset, difference	–
κ	permeability, $(1-\phi)^3 a^2/180\phi^2$	m^2
μ_f, χ_f	pore-fluid viscosity, compressibility	Pa s, Pa^{-1}
K_p	drained bulk modulus of the particle network	Pa
S	storage coefficient, $1/K_p + (1-\phi)\chi_f$	Pa^{-1}
D_p	pore-pressure diffusivity $= \kappa K_p/\mu_f$; also the collective diffusivity	m^2/s
L, L_d	drainage length, dilation length	m
τ_p, τ_1	relaxation scaling L^2/D_p; exact slowest mode $0.405\,\tau_p$	s
τ_{imp}	impact time D_0/U_0	s
De	drainage number $\tau_p/\tau_{\mathrm{imp}}$	–
p, σ'	pore pressure, effective stress	Pa
ψ, α	dilatancy angle, $\tan\psi = \alpha\Delta\phi$	–
λ_D	Debye screening length	m
r_{throat}	pore-throat radius, $0.0775\,a$	m
k_n, Z	contact normal stiffness, coordination number	N/m, –
σ^*	Wyart–Cates onset stress, fitted 44.2 Pa	Pa

Formula card

$$\kappa = \frac{(1-\phi)^3 a^2}{180\phi^2} \qquad S = \frac{1}{K_p} + (1-\phi)\chi_f \qquad D_p = \frac{\kappa}{\mu_f S} \simeq \frac{\kappa K_p}{\mu_f}$$

$$\tau_p = \frac{\mu_f L^2}{\kappa K_p} \qquad \tau_1 = \frac{4}{\pi^2}\tau_p \qquad \mathrm{De} = \frac{\tau_p U_0}{D_0}$$

$$p_{\mathrm{dil}} = \frac{\mu_f}{\kappa}\Delta\phi L_d^2 \dot\gamma = K_p \Delta\phi\, \dot\gamma \tau_p \qquad p_{\mathrm{dil}}^{\max} = \frac{K_p \Delta\phi}{\phi}$$

$$K_p^{\mathrm{EDL}} = \frac{Pa}{6\lambda_D} \qquad \frac{p_{\mathrm{dil}}^{\max}}{P} = \frac{a}{6\lambda_D}\frac{\Delta\phi}{\phi} \qquad \phi^* = \frac{\phi_c}{1 - 6\lambda_D/a}$$

13. Sources

Biot, *J. Appl. Phys.* **12**, 155 (1941). Terzaghi, *Erdbaumechanik auf bodenphysikalischer Grundlage* (1925). Carman, *Trans. Inst. Chem. Eng.* **15**, 150 (1937). Carnahan & Starling, *J. Chem. Phys.* **51**, 635 (1969). Reynolds, *Phil. Mag.* **20**, 469 (1885). Pailha & Pouliquen, *J. Fluid Mech.* **633**, 115 (2009). Jérôme, Vandenberghe & Forterre, *Phys. Rev. Lett.* **117**, 098003 (2016). Athani, Metzger, Forterre & Mari, *Phys. Rev. Fluids* **10**, 043301 (2025). Mobaseri, Gordillo, Burton, Yoon, Lee, Kumar, Driscoll & Cheng, *Phys.*

Rev. Lett. **136**, 148201 (2026). Makse, Gland, Johnson & Schwartz, *Phys. Rev. Lett.* **83**, 5070 (1999). Agnolin & Roux, *Phys. Rev. E* **76**, 061302 (2007). Buscall & White, *J. Chem. Soc. Faraday Trans.* **83**, 873 (1987). Waitukaitis & Jaeger, *Nature* **487**, 205 (2012). Shah, Arora & Driscoll, *Commun. Phys.* **5**, 222 (2022). Ishibashi *et al.*, *Colloids Surf. A* **732**, 139148 (2026). Wyart & Cates, *Phys. Rev. Lett.* **112**, 098302 (2014).