






























POLYMERS

S. No.	Name	Monomer(s)	Structure	Remark/ Catalyst
1.	Teflon	$CF_2 = CF_2$	$+CF_2-CF_2+_n$	Persulphate Or Free Radical as catalyst
2.	Polyacrylonitrile	$CH_2 = CH-CN$	$+CH_2-CH(CN)+_n$	Peroxide as catalyst
3.	Polyethene	$CH_2 = CH_2$	$+CH_2-CH_2+_n$	
a)	LDP			LOW => O2 as catalyst High Temp (350-570K) and pressure (1000-2000 atm)
b)	HDP			Zeigler Natta Catalyst : [TiCl4 + (C2H5)3Al] Low temp (333K) and Pressure (6-7 atm)
4.	PMMA (Polymethylmethacrylate)	$CH_2 = C(CH_3)-C(=O)-OCH_3$	$+CH_2-C(CH_3)(COOCH_3)+_n$	
5.	Nylon 5 ↳ 5 'C'	$NH_2(CH_2)_4COOH$	$+NH(CH_2)_4-C(=O)+_n$	
6.	Nylon 6 ↳ 6 'C'	$NH_2(CH_2)_5COOH$	$+NH(CH_2)_5-C(=O)+_n$	

Trulit Delhi

7.	Nylon 6,6			
8.	Nylon 6,10 6 'C' Ka amine 10 'C' waala acid			
9.	Nylon-2 Nylon-6			
10.	Dacron/ Terylene			Zinc Acetate and Antimony Trioxide
11.	Glyptal			
12.	Phenol Formaldehyde Resin			
a)	Novolec			
b)	Bakelite			Novalac + HCHO ↓ Δ Bakelite

TiruIITDelhi

13.	Malamine Formaldehyde Resin			
14.	Urea Formalehyde Resin			
15.	Isoprene (Natural Rubber)			Elastic Properties Latex - Colloidal soln of rubber in water Coiled (Spring) structure
	Vulcanised Rubber			Heat raw rubber with S.
16.	Neoprene (Synthetic Rubber)			
17.	Buna-N (Synthetic Rubber)			Peroxide
18.	Buna-S			
19.	PHBV (Biodegradable)			

Tinu IIT Delhi