Date: 2026-05-15
Request ID: 100048558

Hotplate		
Element(s)	Pt	
SOP#		
Cocktail	None	
sample(s)	**weight (g)**	**volume (mL)**
200128013_1	30.0225	50
200128013_2	30.0000	50
200128014_1	29.9969	50
200128014_2	29.9648	50

Date: 2026-05-15
Request ID: 100048558

Pt ICP analysis

sample	**Dilution**	**conc. [mg/L]**	**Pt_ppm**	**%Pt**
200128013_1	100/0.27	1.817	1120.76	0.11
200128013_2	100/0.27	1.833	1131.48	0.11

pt result: 1126.12 ppm
pt result: 0.11 %
pt oxide factor:
pt oxide result: 0.00 %
pt lot: *Manufacturer: Assurance, 28-2PTY exp: 2027-02-28*

Note(s):

Date: 2026-05-15
Request ID: 100048558

Pt ICP analysis

sample	Dilution	conc. [mg/L]	Pt_ppm	%Pt
200128014_1	100/0.27	1.974	1218.64	0.12
200128014_2	100/0.27	2.059	1272.48	0.13

pt result: 1245.56 ppm
pt result: 0.12 %
pt oxide factor:
pt oxide result: 0.00 %
pt lot: *Manufacturer: Assurance, 28-2PTY exp: 2027-02-28*

Note(s):

A = crucible
B = crucible + sample
C = crucible + sample after drying

%LOI = ([B-A]-[C-A])/(B-A)*100%

ppm M+ = [conc.][volume][dilution]/[weight]

%M+ = [conc.][volume][dilution]/([weight]*10,000)

%MO = [oxide factor]*%M+

ppm M+ [dried] = ppm M+/([1-(%LOI)/100])

%M+ [dried] = %M+/([1-(%LOI)/100])

%MO [dried] = %MO/([1-(%LOI)/100])

%Cr(VI) = (1.733[mL FAS][N FAS])/([weight])

%Cr2O3 = 1.462*[%Cr(VI)]

%Cr(III) = total_Cr - Cr(VI)