

Date: 2026-04-24

Request ID: 100048444

Microwave				
Element(s)	Cu, Fe, K			
SOP#				
Acid Cocktail	9 mL HCl, 3 mL HNO3, 3 mL H2SO4			
Rack	7			
Vessel	PTFE			
Stir	90%			
Time (min)	Power (W)	T1 (C)	T2 (C)	P (bar)
15	1200	180	65	110
15	1500	245	65	100
30	1500	245	65	100
sample(s)	weight (g)	volume (mL)		
200127624_1	0.2072	250		
200127624_2	0.2097	250		

Date: 2026-04-24

Request ID: 100048444

LOI temp: 900

sample	crucible (g)	crucible + sample (g)	after 900 °C	LOI (%)	correction
200127624	26.5718	28.5733	28.5442	1.45	0.9855

sample	Dilution	conc. [mg/L]	Cu_ppm [dried]	%Cu [dried]
200127624_1	100/1	4.269	522681.36	52.27
200127624_2	100/1	4.434	536411.24	53.64

result: 529546.30 ppm

result: 52.95 %

oxide factor: 1.252

oxide result: 66.30 %

lot: Manufacturer: Assurance, 28-83CUT exp: 2026-09-30

sample	Dilution	conc. [mg/L]	Fe_ppm [dried]	%Fe [dried]
200127624_1	100/1	1.83	224058.77	22.41
200127624_2	100/1	1.835	221992.47	22.20

result: 223025.62 ppm

result: 22.30 %

oxide factor: 1.43

oxide result: 31.89 %

lot: Manufacturer: Assurance, 28-75FEY exp: 2026-07-30

sample	Dilution	conc. [mg/L]	K_ppm [dried]	%K [dried]
200127624_1	1/1	6.268	7674.32	0.77
200127624_2	1/1	6.387	7726.79	0.77

result: 7700.55 ppm

result: 0.77 %

oxide factor: 1.205

oxide result: 0.93 %

lot: Manufacturer: Assurance, 28-6KY exp: 2026-08-30

Note(s):