

Date: 2026-04-29

Request ID: 100048453

Katanax		
Element(s)	Fe	
SOP#		
Acid Cocktail	50 mL 1:1 HCl	
sample(s)	weight (g)	volume (mL)
200127647_1	0.3045	250
200127647_2	0.3058	250

Date: 2026-04-29
Request ID: 100048453

Fe ICP analysis

sample	Dilution	conc. [mg/L]	Fe_ppm	%Fe
200127647_1	10/9	0.125	114.03	0.01
200127647_2	10/9	0.120	109.00	0.01

fe result: 111.52 ppm

fe result: 0.01 %

fe oxide factor:

fe oxide result: 0.00 %

fe lot: *Manufacturer: Assurance, 28-75FEY exp: 2026-07-30*

Note(s):

A = crucible

B = crucible + sample

C = crucible + sample after drying

$$\%LOI = ([B-A] - [C-A]) / (B-A) * 100\%$$

$$ppm\ M+ = [conc.][volume][dilution] / [weight]$$

$$\%M+ = [conc.][volume][dilution] / ([weight] * 10,000)$$

$$\%MO = [oxide\ factor] * \%M+$$

$$ppm\ M+ \ [dried] = ppm\ M+ / ([1 - (\%LOI) / 100])$$

$$\%M+ \ [dried] = \%M+ / ([1 - (\%LOI) / 100])$$

$$\%MO \ [dried] = \%MO / ([1 - (\%LOI) / 100])$$

$$\%Cr(VI) = (1.733[mL\ FAS][N\ FAS]) / ([weight])$$

$$\%Cr_2O_3 = 1.462 * [\%Cr(VI)]$$

$$\%Cr(III) = total_Cr - Cr(VI)$$