

Date: 2026-04-24
Request ID: 100048459

Microwave				
Element(s)	Co, Pt			
SOP#				
Acid Cocktail	9 mL HCl, 3 mL HNO3, 6 mL H2SO4			
Rack	7			
Vessel	PTFE			
Stir	90%			
Time (min)	Power (W)	T1 (C)	T2 (C)	P (bar)
15	1200	180	65	110
15	1500	240	65	100
30	1500	240	65	100
sample(s)	weight (g)	volume (mL)		
200127662_1	0.5059	100		
200127662_2	0.5073	100		

Date: 2026-04-24

Request ID: 100048459

LOI temp: 900

sample	crucible (g)	crucible + sam	after 900 °C	LOI (%)	correction
200127662	27.1479	29.1487	29.0837	3.25	0.9675

sample	Dilution	conc. [mg/L]	Co_ppm [dried]	%Co [dried]
200127662_1	250/1	3.431	175242.42	17.52
200127662_2	250/1	3.632	184996.78	18.50

result: #####

result: 18.01 %

oxide factor:

oxide result: 0.00 %

lot: Manufacturer: Assurance, 28-73COY exp: 2026-10-30

sample	Dilution	conc. [mg/L]	Pt_ppm [dried]	%Pt [dried]
200127662_1	10/5	0.664	271.32	0.03
200127662_2	10/5	0.681	277.50	0.03

result: 274.41 ppm

result: 0.03 %

oxide factor:

oxide result: 0.00 %

lot: Manufacturer: Assurance, 28-2PTY exp: 2027-02-28

Note(s):