

Date: 2026-06-03
Request ID: 100048609

Microwave				
Element(s)	Cu, Pt			
SOP#				
Acid Cocktail	9 mL HCl, 3 mL HNO3, 6 mL H2SO4			
Rack	7			
Vessel	Quartz			
Stir	90%			
Time (min)	Power (W)	T1 (°C)	T2 (°C)	P (bar)
15	1200	180	65	110
15	1500	240	65	110
30	1500	240	65	110
sample(s)	weight (g)	volume (mL)		
200128173_1	0.2026	200		
200128173_2	0.2035	200		

Hotplate		
Element(s)	Cl	
SOP#		
Cocktail	50 mL NaOH	
sample(s)	weight (g)	volume (mL)
200128173_1	1.0080	100
200128173_2	1.0042	100

Date: 2026-06-03
Request ID: 100048609

Cu ICP analysis

sample	Dilution	conc. [mg/L]	Cu_ppm	%Cu
200128173_1	25/7	2.094	7381.72	0.74
200128173_2	25/7	2.071	7267.46	0.73

cu result: 7324.59 ppm

cu result: 0.73 %

cu oxide factor:

cu oxide result: 0.00 %

cu lot: *Manufacturer: Assurance, 28-83CUT exp: 2026-09-30*

Pt ICP analysis

sample	Dilution	conc. [mg/L]	Pt_ppm	%Pt
200128173_1	10/5	1.991	3930.90	0.39
200128173_2	10/5	2.046	4022.11	0.40

pt result: 3976.51 ppm

pt result: 0.40 %

pt oxide factor:

pt oxide result: 0.00 %

pt lot: *Manufacturer: Assurance, 28-2PTY exp: 2027-02-28*

Cl IC analysis

sample	Dilution	conc. [mg/L]	Cl_ppm	%Cl
200128173_1	10/1	11.238	11148.61	1.11
200128173_2	10/1	11.215	11167.60	1.12

cl result: 11158.10 ppm

cl result: 1.12 %

cl lot: *Manufacturer: Ricca, 2502C26 exp: 2027-01-31*

Note(s): *Cl, Cu, Pt on carbon, whole pieces digestion.*

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}]*10,000)$$

$$\%MO = [\text{oxide factor}]*\%M+$$