

Date: 2026-06-15

Request ID: 100048628

Hotplate		
Element(s)	Pd	
SOP#		
Cocktail	Determination of Palladium in Catalyst with or without Ag present	
sample(s)	weight (g)	volume (mL)
200128248_1	1.0069	100
200128248_2	1.0028	100

Date: 2026-06-15

Request ID: 100048628

LOI temp: 900 °C

sample	crucible (g)	crucible + sample (g)	after 900 °C	LOI (%)	correction
200128248	27.1972	29.2142	28.9770	11.76	0.8824

Pd ICP analysis

sample	Dilution	conc. [mg/L]	Pd_ppm [dried]	%Pd [dried]
200128248_1	25/7	1.445	580.98	0.06
200128248_2	25/7	1.425	575.28	0.06

pd result: 578.13 ppm

pd result: 0.06 %

pd lot: *Manufacturer: Ricca, 841005E exp: 2027-11-30*

Note(s):

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}] * 10,000)$$

$$\%MO = [\text{oxide factor}] * \%M+$$

A = crucible

B = crucible + sample

C = crucible + sample after drying

$$\%LOI = ([B-A] - [C-A]) / (B-A) * 100\%$$

$$\text{ppm } M+ \text{ [dried]} = \text{ppm } M+ / ([1 - (\%LOI)] / 100)$$

$$\%M+ \text{ [dried]} = \%M+ / ([1 - (\%LOI)] / 100)$$

$$\%MO \text{ [dried]} = \%MO / ([1 - (\%LOI)] / 100)$$