

Date: 2026-06-16
Request ID: 100048650

Hotplate		
Element(s)	Cu, Pt	
SOP#		
Cocktail	15 mL HCl, 10 mL H2SO4, 5 mL HNO3	
sample(s)	weight (g)	volume (mL)
200128295_1	0.2016	200
200128295_2	0.2088	200

Date: 2026-06-16
Request ID: 100048650

Cu ICP analysis

sample	Dilution	conc. [mg/L]	Cu_ppm	%Cu
200128295_1	50/10	1.671	8288.69	0.83
200128295_2	50/10	1.782	8534.48	0.85

cu result: 8411.59 ppm

cu result: 0.84 %

cu lot: *Manufacturer: Assurance, 28-83CUT exp: 2026-09-30*

Pt ICP analysis

sample	Dilution	conc. [mg/L]	Pt_ppm	%Pt
200128295_2	10/6	2.959	4723.82	0.47

pt result: 4723.82 ppm

pt result: 0.47 %

pt lot: *Manufacturer: Assurance, 28-2PTY exp: 2027-02-28*

Note(s): *Cu, Pt on carbon, received as whole pieces. Samples were ground using a Spex SamplePrep Mixer/Mill.*

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}]*10,000)$$

$$\%MO = [\text{oxide factor}]*\%M+$$