

Date: 2026-06-18

Request ID: 100048659

Katanax		
Element(s)	Al, Ca, Ti	
SOP#		
Acid Cocktail	40 mL 1:1 HCl	
sample(s)	weight (g)	volume (mL)
200128311_1	0.2066	250
200128311_2	0.2049	250
200128312_1	0.2058	250
200128312_2	0.2088	250
200128313_1	0.2026	250
200128313_2	0.2104	250
200128314_1	0.2093	250
200128314_2	0.2084	250

Date: 2026-06-18

Request ID: 100048659

Al ICP analysis

sample	Dilution	conc. [mg/L]	Al_ppm	%Al
200128311_1	1/1		0.00	42.94
200128311_2	1/1		0.00	42.94

al result: 0.00 ppm

al result: 42.94 %

al oxide factor: 1.889

al oxide result: 81.11 %

al lot: Manufacturer: Assurance, 27-171ALT exp: 2026-07-30

Ca ICP analysis

sample	Dilution	conc. [mg/L]	Ca_ppm	%Ca
200128311_1	50/0.83	1.565	114105.99	11.41
200128311_2	50/0.83	1.549	113852.19	11.39

ca result: #####

ca result: 11.40 %

ca oxide factor: 1.399

ca oxide result: 15.95 %

ca lot: Manufacturer: Assurance, 28-35CAY exp: 2026-10-30

Ti ICP analysis

sample	Dilution	conc. [mg/L]	Ti_ppm	%Ti
200128311_1	50/6	1.750	17646.82	1.76
200128311_2	50/6	1.727	17559.38	1.76

ti result: 17603.10 ppm

ti result: 1.76 %

ti oxide factor: 1.668

ti oxide result: 2.94 %

ti lot: Manufacturer: Assurance, 27-189TIT exp: 2026-08-30

Note(s): Alumina analysis by mass balance.

Date: 2026-06-18

Request ID: 100048659

Al ICP analysis

sample	Dilution	conc. [mg/L]	Al_ppm	%Al
200128312_1	1/1		0.00	47.84
200128312_2	1/1		0.00	47.84

al result: 0.00 ppm

al result: 47.84 %

al oxide factor: 1.889

al oxide result: 90.37 %

al lot: *Manufacturer: Assurance, 27-171ALT exp: 2026-07-30*

Ca ICP analysis

sample	Dilution	conc. [mg/L]	Ca_ppm	%Ca
200128312_1	100/3	1.708	69161.00	6.92
200128312_2	100/3	1.717	68526.50	6.85

ca result: 68843.75 ppm

ca result: 6.88 %

ca oxide factor: 1.399

ca oxide result: 9.63 %

ca lot: *Manufacturer: Assurance, 28-35CAY exp: 2026-10-30*

Ti ICP analysis

sample	Dilution	conc. [mg/L]	Ti_ppm	%Ti
200128312_1	1/1		0.00	0.00
200128312_2	1/1		0.00	0.00

ti result: 0.00 ppm

ti result: 0.00 %

ti oxide factor:

ti oxide result: 0.00 %

ti lot: *Manufacturer: Assurance, 27-189TIT exp: 2026-08-30*

Note(s): *Alumina analysis by mass balance.*

Date: 2026-06-18

Request ID: 100048659

Al ICP analysis

sample	Dilution	conc. [mg/L]	Al_ppm	%Al
200128313_1	1/1		0.00	47.91
200128313_2	1/1		0.00	47.91

al result: 0.00 ppm

al result: 47.91 %

al oxide factor: 1.889

al oxide result: 90.50 %

al lot: Manufacturer: Assurance, 27-171ALT exp: 2026-07-30

Ca ICP analysis

sample	Dilution	conc. [mg/L]	Ca_ppm	%Ca
200128313_1	100/3	1.649	67826.59	6.78
200128313_2	100/3	1.710	67728.14	6.77

ca result: 67777.36 ppm

ca result: 6.78 %

ca oxide factor: 1.399

ca oxide result: 9.48 %

ca lot: Manufacturer: Assurance, 28-35CAY exp: 2026-10-30

Ti ICP analysis

sample	Dilution	conc. [mg/L]	Ti_ppm	%Ti
200128313_1	1/1		0.00	0.00
200128313_2	1/1		0.00	0.00

ti result: 0.00 ppm

ti result: 0.00 %

ti oxide factor:

ti oxide result: 0.00 %

ti lot: Manufacturer: Assurance, 27-189TIT exp: 2026-08-30

Note(s): Alumina analysis by mass balance.

Date: 2026-06-18

Request ID: 100048659

Al ICP analysis

sample	Dilution	conc. [mg/L]	Al_ppm	%Al
200128314_1	1/1		0.00	42.68
200128314_2	1/1		0.00	42.68

al result: 0.00 ppm

al result: 42.68 %

al oxide factor: 1.889

al oxide result: 80.62 %

al lot: Manufacturer: Assurance, 27-171ALT exp: 2026-07-30

Ca ICP analysis

sample	Dilution	conc. [mg/L]	Ca_ppm	%Ca
200128314_1	50/1	1.959	116997.13	11.70
200128314_2	50/1	1.955	117262.48	11.73

ca result: #####

ca result: 11.71 %

ca oxide factor: 1.399

ca oxide result: 16.39 %

ca lot: Manufacturer: Assurance, 28-35CAY exp: 2026-10-30

Ti ICP analysis

sample	Dilution	conc. [mg/L]	Ti_ppm	%Ti
200128314_1	50/7	2.067	17631.05	1.76
200128314_2	50/7	2.113	18103.49	1.81

ti result: 17867.27 ppm

ti result: 1.79 %

ti oxide factor: 1.668

ti oxide result: 2.98 %

ti lot: Manufacturer: Assurance, 27-189TIT exp: 2026-08-30

Note(s): Alumina analysis by mass balance.

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}]*10,000)$$

$$\%MO = [\text{oxide factor}]*\%M+$$