

Date: 2026-06-25

Request ID: 100048684

Hotplate		
Element(s)	Pd	
SOP#		
Cocktail	Determination of Palladium in Catalyst with or without Ag present	
sample(s)	weight (g)	volume (mL)
200128376_1	1.0102	100
200128376_2	1.0035	100
200128377_1	1.0027	50
200128377_2	1.0060	50
200128378_1	2.0055	50
200128378_2	2.0097	100
200128379_1	1.0080	50
200128379_2	1.0080	50

Date: 2026-06-25

Request ID: 100048684

LOI temp: 900 °C

sample	crucible (g)	crucible + sample (g)	after 900 °C	LOI (%)	correction
200128376	25.9842	27.9839	27.7760	10.40	0.8960

Pd ICP analysis

sample	Dilution	conc. [mg/L]	Pd_ppm [dried]	%Pd [dried]
200128376_1	25/3	1.758	1618.47	0.16
200128376_2	25/3	1.721	1594.99	0.16

pd result: 1606.73 ppm

pd result: 0.16 %

pd lot: *Manufacturer: Ricca, 841005E exp: 2027-11-30*

Note(s):

Date: 2026-06-25

Request ID: 100048684

LOI temp: 900 °C

sample	crucible (g)	crucible + sample (g)	after 900 °C	LOI (%)	correction
200128377	27.1495	29.1506	28.9658	9.23	0.9077

Pd ICP analysis

sample	Dilution	conc. [mg/L]	Pd_ppm [dried]	%Pd [dried]
200128377_1	25/8	1.713	294.09	0.03
200128377_2	25/8	1.707	292.10	0.03

pd result: 293.10 ppm

pd result: 0.03 %

pd lot: *Manufacturer: Ricca, 841005E exp: 2027-11-30*

Note(s):

Date: 2026-06-25

Request ID: 100048684

LOI temp: 900 °C

sample	crucible (g)	crucible + sample (g)	after 900 °C	LOI (%)	correction
200128378	15.5567	17.5653	17.4802	4.24	0.9576

Pd ICP analysis

sample	Dilution	conc. [mg/L]	Pd_ppm [dried]	%Pd [dried]
200128378_1	10/9	1.430	41.37	0.00
200128378_2	10/9	0.759	43.82	0.00

pd result: 42.59 ppm

pd result: 0.00 %

pd lot: *Manufacturer: Ricca, 841005E exp: 2027-11-30*

Note(s):

Date: 2026-06-25

Request ID: 100048684

LOI temp: 900 °C

sample	crucible (g)	crucible + sample (g)	after 900 °C	LOI (%)	correction
200128379	16.9755	18.9951	18.8190	8.72	0.9128

Pd ICP analysis

sample	Dilution	conc. [mg/L]	Pd_ppm [dried]	%Pd [dried]
200128379_1	25/9	1.702	256.91	0.03
200128379_2	25/9	1.749	264.01	0.03

pd result: 260.46 ppm

pd result: 0.03 %

pd lot: *Manufacturer: Ricca, 841005E exp: 2027-11-30*

Note(s):

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}] * 10,000)$$

$$\%MO = [\text{oxide factor}] * \%M+$$

A = crucible

B = crucible + sample

C = crucible + sample after drying

$$\%LOI = ([B-A] - [C-A]) / (B-A) * 100\%$$

$$\text{ppm } M+ \text{ [dried]} = \text{ppm } M+ / ([1 - (\%LOI)] / 100)$$

$$\%M+ \text{ [dried]} = \%M+ / ([1 - (\%LOI)] / 100)$$

$$\%MO \text{ [dried]} = \%MO / ([1 - (\%LOI)] / 100)$$