

Date: 2026-07-06
Request ID: 100048742

Hotplate		
Analyte(s)	Al, Si, Ti	
SOP#		
Cocktail		
sample(s)	weight (g)	volume (mL)
200128519_1	40.1555	50
200128519_2	40.0000	50

Date: 2026-07-06

Request ID: 100048742

Al ICP analysis

sample	Dilution	conc. [mg/L]	Al_ppm	%Al
200128519_1	100/0.81	2.164	332.66	0.03
200128519_2	100/0.81	2.163	333.80	0.03

al result: 333.23 ppm

al result: 0.03 %

al lot: *Manufacturer: Assurance, 27-171ALT exp: 2026-07-30*

Si ICP analysis

sample	Dilution	conc. [mg/L]	Si_ppm	%Si
200128519_1	50/50	2.866	3.57	0.00
200128519_2	50/50	2.889	3.61	0.00

si result: 3.59 ppm

si result: 0.00 %

si lot: *Manufacturer: Assurance, 28-87SIX exp: 2026-08-30*

Ti ICP analysis

sample	Dilution	conc. [mg/L]	Ti_ppm	%Ti
200128519_1	50/50	2.812	3.50	0.00
200128519_2	50/50	2.808	3.51	0.00

ti result: 3.51 ppm

ti result: 0.00 %

ti lot: *Manufacturer: Assurance, 27-189TIT exp: 2026-08-30*

Note(s): *Acidic solution post chemical attrition.*

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}]*10,000)$$

$$\%MO = [\text{oxide factor}]*\%M+$$