

**Date:** 2026-07-21

**Request ID:** 100048789

| Katanax       |                 |             |
|---------------|-----------------|-------------|
| Analyte(s)    | Co, Cr, Ni      |             |
| SOP#          |                 |             |
| Acid Cocktail | 30 mL conc. HCl |             |
| sample(s)     | weight (g)      | volume (mL) |
| 200128642_1   | 0.2540          | 250         |
| 200128642_2   | 0.2524          | 250         |

Date: 2026-07-21  
Request ID: 100048789

LOI temp: 900 °C

| sample    | crucible (g) | crucible + sample (g) | after 900 °C | LOI (%) | correction |
|-----------|--------------|-----------------------|--------------|---------|------------|
| 200128642 | 18.7325      | 20.7362               | 20.6399      | 4.81    | 0.9519     |

Co ICP analysis

| sample      | Dilution | conc. [mg/L] | Co_ppm [dried] | %Co [dried] |
|-------------|----------|--------------|----------------|-------------|
| 200128642_1 | 10/9     | 1.522        | 1748.51        | 0.17        |
| 200128642_2 | 10/9     | 1.558        | 1801.22        | 0.18        |

co result: 1774.87 ppm

co result: 0.18 %

co lot: *Manufacturer: Assurance, 29-22COY exp: 2027-06-30*

Cr ICP analysis

| sample      | Dilution | conc. [mg/L] | Cr_ppm [dried] | %Cr [dried] |
|-------------|----------|--------------|----------------|-------------|
| 200128642_1 | 10/9     | 0.559        | 642.19         | 0.06        |
| 200128642_2 | 10/9     | 0.584        | 675.17         | 0.07        |

cr result: 658.68 ppm

cr result: 0.07 %

cr lot: *Manufacturer: Ricca, 45120423 exp: 2027-05-31*

Ni ICP analysis

| sample      | Dilution | conc. [mg/L] | Ni_ppm [dried] | %Ni [dried] |
|-------------|----------|--------------|----------------|-------------|
| 200128642_1 | 100/10   | 1.559        | 16119.19       | 1.61        |
| 200128642_2 | 100/10   | 1.605        | 16700.01       | 1.67        |

ni result: 16409.60 ppm

ni result: 1.64 %

ni lot: *Manufacturer: Assurance, 28-130NIT exp: 2026-10-30*

Note(s): *OleMax 101 Ref26BB.*

$$\text{ppm } M+ = [\text{conc.}][\text{volume}][\text{dilution}]/[\text{weight}]$$

$$\%M+ = [\text{conc.}][\text{volume}][\text{dilution}]/([\text{weight}]*10,000)$$

$$\%MO = [\text{oxide factor}]*\%M+$$

*A = crucible*

*B = crucible + sample*

*C = crucible + sample after drying*

$$\%LOI = ([B-A]-[C-A])/(B-A)*100\%$$

$$\text{ppm } M+ \text{ [dried]} = \text{ppm } M+ / ([1-(\%LOI)/100])$$

$$\%M+ \text{ [dried]} = \%M+ / ([1-(\%LOI)/100])$$

$$\%MO \text{ [dried]} = \%MO / ([1-(\%LOI)/100])$$