

QUALITY SPECIFICATIONS

MEPCORE (CORE BOARD)



TYPICAL CHARACTERISTICS

GRADE -----▶▶

PARAMETERS	UNIT	STANDARD METHOD	200X										250X										350X									
			GRAMMAGE										GRAMMAGE										GRAMMAGE									
Nominal Basis Weight	g/m ²	T 410 om-19	200	250	300	350	400	450	500	550	200	250	300	350	400	450	500	550	200	250	300	350	400	450	500							
Nominal Moisture	%	T 412 om-22	6										6										6									
Thickness	µm	T 411 om-21	310	388	465	543	620	698	775	853	310	388	465	543	620	698	775	853	310	388	465	543	620	698	775							
Bulk	cc/g		1.55										1.55										1.55									
Internal Bond (Scott type)	j/m ²	T 569 om-22	200										250										350									
COBB ₆₀	g/m ²	T 441 om-20	300		450		500		300		450		500		300		450		500		300		450		500							

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE										GRAMMAGE										GRAMMAGE									
Nominal Basis Weight	g/m ²	T 410 om-19	200	250	300	350	400	450	500	550	200	250	300	350	400	450	500	550	200	250	300	350	400	450	500							
Mean Basis Weight	%		± 3 %										± 3 %										± 3 %									
Nominal Moisture	%	T 412 om-22	6										6										6									
Mean Moisture	%		± 1 %										± 1 %										± 1 %									
Thickness	µm	T 411 om-21	± 40 µm										± 40 µm										± 40 µm									
Bulk	cc/g		± 0.05										± 0.05										± 0.08									
Internal Bond (Scott type)	j/m ²	T 569 om-22	Min 200 j/m ² , Max 250 j/m ²										Min 250 j/m ² , Max 300 j/m ²										Min 350 j/m ² , Max 400 j/m ²									
COBB ₆₀	g/m ²	T 441 om-20	400		650		750		400		650		750		400		650		750		400		650		750							

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	As specified
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

* Test Method = TAPPI

QUALITY SPECIFICATIONS

MEPCORE (CORE BOARD)



TYPICAL CHARACTERISTICS

GRADE ----->>			450X			500X			600X			700X			800X		
PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE		
Nominal Basis Weight	g/m ²	T 410 om-19	400	450	500	400	450	500	400	450	500	400	450	500	400	450	500
Nominal Moisture	%	T 412 om-22	6			6			6			6			6		
Thickness	µm	T 411 om-21	620	698	775	620	698	775	620	698	775	620	698	775	620	698	775
Bulk	cc/g		1.55			1.55			1.55			1.55			1.55		
Internal Bond (Scott type)	j/m ²	T 569 om-22	450			500			600			700			800		
COBB ₆₀	g/m ²	T 441 om-20	450	500		450	500		450	500		450	500		450	500	

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE		
Nominal Basis Weight	g/m ²	T 410 om-19	400	450	500	400	450	500	400	450	500	400	450	500	400	450	500
Mean Basis Weight	%		± 3 %			± 3 %			± 3 %			± 3 %			± 3 %		
Nominal Moisture	%	T 412 om-22	6			6			6			6			6		
Mean Moisture	%		± 1 %			± 1 %			± 1 %			± 1 %			± 1 %		
Thickness	µm	T 411 om-21	± 40 µm			± 40 µm			± 40 µm			± 40 µm			± 40 µm		
Bulk	cc/g		± 0.08			± 0.08			± 0.08			± 0.08			± 0.08		
Internal Bond (Scott type)	j/m ²	T 569 om-22	Min 450 j/m ² , Max 500 j/m2			Min 500 j/m ² , Max 600 j/m2			Min 600 j/m ² , Max 700 j/m2			Min 700 j/m ² , Max 800 j/m2			Min 800 j/m ² , Max 900 j/m2		
COBB ₆₀	g/m ²	T 441 om-20	650	750		650	750		650	750		650	750		650	750	

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	As specified
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

* Test Method = TAPPI