



检测报告 Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 1 页 共 12 页
Page 1 of 12

委托单位 广州博雅新材料制造有限公司
Applicant Guangzhou Broadya New Materials Manufacturing Co.,Ltd
地 址 广州市花都区华侨经济开发试验区华植西路 10 号
Address No.10 Huazhi West Road,Huaqiao Economic Development Experimental Zone,Huadu District
Guangzhou City

样品信息：参照下页
Sample(s) information: Please refer to the following page(s).

测试信息：参照下页
Test(s) information: Please refer to the following page(s).

批 准 日期
Approved by 2025.06.17

Amy Jiang
授权签字人
Lab authorized signatory



上海华测品正检测技术有限公司

No. 190264240

上海市闵行区新骏环路 777 号 5 号楼

Centre Testing International (Shanghai) Co., Ltd. Building 5, No. 777, Xinjun Ring Road, Minhang District, Shanghai, China

检测报告
Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 2 页 共 12 页
Page 2 of 12

以下测试之样品及样品信息由申请者提供并确认

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

样品名称	低气味棉纸胶带
Sample Name(s)	Low Voc Double Sided Tape
零件号	LV120
Part No.	LV120
材质	离型纸+棉纸+丙烯酸胶水
Material	Release paper+tissue+acrylic adhesive
车型	/
Model	/
供应商	/
Supplier	/
买家	/
Buyer	/
主机厂	/
OEM	/
生产日期	/
Date of Manufacture	/
包装日期	/
Date of Package	/
备注	/
Remark	/
样品接收日期	2025.06.08
Sample Received Date	Jun.08,2025
实验室样品编号	A2250387173101002
CTI SH Sample No.	A2250387173101002
样品检测日期	2025.06.17-2025.06.17
Testing Period	Jun.17,2025-Jun.17,2025

检测项目	苯、甲苯、乙苯、二甲苯、苯乙烯、TVOC、甲醛、乙醛、丙烯醛、丙酮、丁酮、丁醛、环己酮。
Test Items	Benzene, Toluene, Ethylbenzene, Xylene, Styrene, TVOC, Formaldehyde, Acetaldehyde, Acrolein, Acetone, Butanone, Butyraldehyde, Cyclohexanone.

检测方法/检测结果	请参见下页。
Test Method/Test Result(s)	Please refer to the following page(s).

检测报告
Test Report报告编号 A2250387173101002E
Report No. A2250387173101002E第 3 页 共 12 页
Page 3 of 12

检测方法:

Test Method:

测试项目 Test Item(s)	测试方法 Test Method	测试仪器 Test Instrument	方法检出限 Method Detection Limit
苯 Benzene	客户要求 Customer's requirement	ATD,GCMS,烘箱 Oven	0.095μg/样品 (μg/specimen)
甲苯 Toluene			0.095μg/样品 (μg/specimen)
乙苯 Ethylbenzene			0.095μg/样品 (μg/specimen)
二甲苯 Xylene			0.095μg/样品 (μg/specimen)
苯乙烯 Styrene			0.095μg/样品 (μg/specimen)
TVOC			/
甲醛 Formaldehyde		HPLC	0.119μg/样品 (μg/specimen)
乙醛 Acetaldehyde			0.119μg/样品 (μg/specimen)
丙烯醛 Acrolein			0.119μg/样品 (μg/specimen)
丙酮 Acetone			0.119μg/样品 (μg/specimen)
丁酮 Butanone			0.119μg/样品 (μg/specimen)
丁醛 Butyraldehyde			0.119μg/样品 (μg/specimen)
环己酮 Cyclohexanone			0.119μg/样品 (μg/specimen)

样品描述

Sample Description

胶带

Tape

样品存储条件

Condition of the Sample Storage

23°C ± 2°C, 相对湿度 50% ± 5%

23°C±2°C, 50%±5%RH

检测报告
Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 4 页 共 12 页
Page 4 of 12

实验设备：
Equipment:

名称/项目 Name/Item	型号/参数 Model/Parameter	设备编号 Equipment No.	校准有效期 Calibration Valid Date
VOC 试验箱 Oven	V-BIR-56	TTE20164427	2025.11.07 Nov.07,2025
气相色谱质谱联用仪 GC-MS	Agilent 7890B-5977B / Ultra 2 50m*320μm *0.52μm	TTE20180157	2025.11.24 Nov.24,2025
气相色谱质谱联用仪 GC-MS	Agilent 7890B-5977B / Ultra 2 50m*320μm *0.52μm	TTE20165583	2025.07.02 Jul.02,2025
高效液相色谱仪 HPLC	SHIMADZU LC-20A / CNW Athena C18-WP 100A,4.6mm*150mm,5μm	TTE20150549	2025.06.30 Jun.30,2025

检测报告
Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 5 页 共 12 页
Page 5 of 12

测试条件：
Test Condition:

样品尺寸 Test specimen dimensions	28.5cm*18.5cm	样品重量 Test specimen weight	10.4g
样品平衡条件/时间 Sample condition/Time	23℃ ± 2℃,相对湿度 50% ± 5%/24h 23℃ ± 2℃,50% ± 5%RH/24h	使用采样袋容量 Bag capacity	50L
采样袋有无前处理 Bag pretreatment	有 Yes	捕集速度(TENAX) Collection rate(TENAX)	200 mL/min
封入氮气容量 N ₂ Amount	25L	捕集时间(TENAX) Collection time(TENAX)	15min
充氮气时温度 Temperature of N ₂ injection	23.0℃	捕集容量(TENAX) Collection amount(TENAX)	3L
加热温度 Heating time	65℃	捕集速度(DNPH) Collection rate(DNPH)	800 mL/min
加热时间 Heating time	2h	捕集时间(DNPH) Collection time (DNPH)	15min
采样日期 Date of sampling	2025.06.16 Jun.16,2025	捕集容量(DNPH) Collection amount(DNPH)	12L
分析日期 Date of analysis	2025.06.16-2025.06.17 Jun.16,2025-Jun.17,2025	/	/

检测报告
Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 6 页 共 12 页
Page 6 of 12

检测结果：
Test Results:

检测项目 Test Items	零件挥发量(μg/样品) Sample Volatilization (μg/specimen)
苯 Benzene	N.D.
甲苯 Toluene	N.D.
乙苯 Ethylbenzene	N.D.
二甲苯 Xylene	N.D.
苯乙烯 Styrene	N.D.
TVOC*	4.068
甲醛 Formaldehyde	0.154
乙醛 Acetaldehyde	0.165
丙烯醛 Acrolein	N.D.
丙酮 Acetone	0.165
丁酮 Butanone	N.D.
丁醛 Butyraldehyde	N.D.
环己酮 Cyclohexanone	N.D.

检测报告 Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 7 页 共 12 页
Page 7 of 12

备注:

Note:

1. “*”表明利用甲苯作为校准物质进行半定量分析;
“*” Quantification through response of toluene (toluene equivalent), Semiquantitative.
2. N.D. 表示未检出(小于检出限),
N.D. means not detected(<detection limit).

检测报告
Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 8 页 共 12 页
Page 8 of 12

TOP 50 物质分析：
TOP 50 Substance Analysis:

物质名称 Substance	保留时间 Retention time (minutes)	CAS No.	相似度 Similarity	面积百分比 Percentage of peak area	甲苯半定量 值 Amount (µg/样品) (µg/specimen)
2-Ethyl hexanol	14.404	104-76-7	97.8%	59.4%	2.417
1-Methoxy-2-propyl acetate	11.279	108-65-6	96.4%	13.8%	0.560
Propanenitrile, 2,2'-azobis[2-methyl-	14.447	78-67-1	86.0%	9.0%	0.367
n-Nonylaldehyde	15.480	124-19-6	97.4%	6.8%	0.275
2-(2-Methoxypropoxy)-1 -propanol	14.176	13588-28-8	84.7%	4.3%	0.173
Benzene+ 1-Butanol	6.039	71-43-2+ 71-36-3	82.1%+ 83.7%	3.5%	0.143
2-Ethylhexyl acetate	15.997	103-09-3	93.4%	3.3%	0.134

检测报告

Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 9 页 共 12 页
Page 9 of 12

注释举例 Designation example	说明 Explanation
Toluene, methylbenzene	MS 谱库检索及相应标准物质的保留时间完全一致(准确识别)。 Mass spectrum and retention of reference substance coincide (regarded as identified with high level of certainly).
? 1,1-bis(p-toloyl)ethane 210 195 179 104	“问号”前缀, 表明该物质通过 MS 谱库检索及保留时间无法准确识别, 但通过分析应该是较正确的一个, 并给出明显的质谱峰的质量数。 Prefixed question mark: based on mass spectra/retention no unique assignment is possible. This substance is, however, considered possible (very similar). Significant mass fragments are also indicated.
? Alcohol, 31 57 85	“问号”前缀+该物质可能的物质归类, 表明能通过典型的质谱峰判断该物质类型。 Question mark + class of substances: Typical fragment patterns provide indications of a class of substances.
? 54 76 99 109	“问号”前缀+特征离子, 表明根据 MS 谱图及保留时间无法判断是哪种物质。 No conclusions can be drawn with regard to compound, distinctive masses are indicated.
Isomeric paraffinic fraction, boiling range “n-C16 to n-C26”	若出现油峰, 应注明该油峰的物质分类及大致的沸点范围(以正构烷烃作为参考)。在“保留时间”一栏填写油峰的时间范围。 In the case of accumulated isomeric compounds, the class of substances and the approximate boiling range, referenced to n-Alkanes, should be indicated as substance designation. In the “retention time” column, the time of the accumulated compound maximum should be entered.
Cyclohexanone + ?	一个确认的物质, 但被其他未知物的色谱峰所覆盖 An identified peak is superimposed by one or several known substances.
Artifact	不是来自样品, 是系统中存在的 Peak which cannot originate from the sample or has been created in the system.


检测报告
Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E


第 10 页 共 12 页
Page 10 of 12

谱图：
Chromatogram:

(1) VOC-1VOC-1



(2) 醛酮-1Aldehyde&Ketone-1




检测报告 Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 11 页 共 12 页
Page 11 of 12

样品图片

Photo(s) of the Sample(s)



检测报告

Test Report

报告编号 A2250387173101002E
Report No. A2250387173101002E

第 12 页 共 12 页
Page 12 of 12

声明 Note:

1. 检测报告无批准人签字、“专用章”及报告骑缝章无效;
The test report is valid only with signature of the approver, the "specialized stamp" and the check mark of the report,
2. 样品及样品信息由申请者提供, 申请者应对其真实性负责, CTI 未核实其真实性;
Samples and the sample information shall be provided by the applicant, and the applicant shall be responsible for their authenticity, CTI has not verified their authenticity,
3. 本报告检测结果仅对受测样品负责;
The result(s) on this report refer only to the sample(s) tested,
4. 未经 CTI 书面同意, 不得部分复制本报告;
This report can not be copied without written approval of CTI,
5. 检测项目不在 CMA 资质认定范围内, 出具的数据结果供科研、教学、企业内部质量控制、企业产品研发等目的用;
The test item(s) is(are) not in CMA accreditation scope, the testing data and result is just for scientific research, education, internal quality control and product development etc,
6. 无 ‘CENTRE TESTING INTERNATIONAL’ 数字证书签章的电子版报告视为无效。
An electronic report without the signature of the ' CENTRE TESTING INTERNATIONAL ' digital certificate is considered invalid.

*** 报告结束 ***

*** End of Report ***