

Bulk α -Fe₂O₃: Raman-active Γ modes