



Professional Coating Systems

SPACHTEL / PUTTY

		Farbton colour	Produkt product	MV MR	Spachtel : Härter putty : hardener	Topfzeit pot life	Schleifbar sandable	Haftung / adhesion						Art.-Nr. item-no.	Geb. unit	styrolreduziert erhältlich styrene reduced available
								Eisen/Stahl iron/steel	Alu alu	Verzinkte Bleche zinc	GFK fibre glass	Kunststoff plastic	Holz wood			
Mipa PX 9		beige beige	2K-PE-Universalspachtel 2K-PE-Universal body filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 3-4 min.	 20° C - 20 min. 60° C - 7 min.							28892 0000	1 l	
Mipa P 99 Multi Star		beige beige	2K-PE-Profispachtel 2K-PE-High build body filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 3-4 min.	 20° C - 20 min. 60° C - 5 min.							28825 0000 28821 0000 28822 0000	250 g 1 kg 2 kg	
Mipa P 97		beige grün green	2K-PE-Multi-Softspachtel 2K-PE-Multi-soft putty		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 3-4 min.	 20° C - 20 min. 60° C - 5 min.							29262 0000 29262 0006	2 kg 1,6 kg	styrolfrei erhältlich styrene free available
Mipa P 16		beige beige	2K-PE-Universal-Leichtspachtel 2K-PE light weight universal putty		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20-25 min. 60° C - 5-10 min.							29391 0000	1 l	
Mipa P 111		gelb yellow	2K-PE-Leichtspachtel 2K-PE light weight putty		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20 min. 60° C - 5-10 min.							29621 0000	1 l	
Mipa P 118 Ultra		grün green	2K-PE-Universal-Leichtspachtel 2K-PE light weight universal putty		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 3-4 min.	 20° C - 15-20 min. 60° C - 5-10 min.							29601 0000 29603 0000	1 l 3 l	
Mipa P 90 Easy		hellgrau light grey	2K-PE-Füllspachtel 2K-PE-High build body filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20 min. 60° C - 5-10 min.							28815 0000 28811 0000 28812 0000 28816 0000S	250 g 1 kg 2 kg 4 kg	
Mipa P 96 Anti-Rust		rotbraun redbrown	2K-PE-Füllspachtel 2K-PE-High build body filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 3-4 min.	 20° C - 20 min. 60° C - 5 min.							29332 0000	2 kg	
Mipa P 70		silbergrau- metallic silver-grey metallic	2K-PE-Füllspachtel metallic 2K-PE-High build body filler metallic		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20 min. 60° C - 10 min.							28851 0000 28852 0000	1 kg 2 kg	
Mipa P 80 Kaltmetall		silbergrau- metallic silver-grey metallic	2K-PE-Hartspachtel 2K-PE-Hard putty		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-6 min.	 20° C - 20 min. 60° C - 10 min.							28881 0000	1 kg	
Mipa P 85		hochweiß bright white	2K-PE-Feinspachtel 2K-PE-Finisher		100 : 2 Nach Gewicht/ by weight Mipa Härter P weiß	 4-5 min.	 20° C - 15 min. 60° C - 10 min.							28835 0000 28831 0000 28832 0000	250 g 1 kg 2 kg	
Mipa P 12		hellgrau light grey	2K-PE-Leichtspachtel mit 40 % reduziertem Gewicht 2K-PE-Light weight putty with 40 % reduced specifical weight		100 : 2-3 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20-30 min. 60° C - 5-10 min.							29131 0000 29133 0000S	1 l 3 l	
Mipa P 182		hellgrün light green	2K-PE-Leichtgewicht Glasurspachtel 2K-PE-light weight glazing putty		100 : 2 Nach Gewicht/ by weight Mipa Härter E 65 S Komponente B	 3-4 min.	 20° C - 15-20 min. 60° C - 5-10min.							29611 0000	850 ml	
Mipa P 88 hellgrün		hellgrün light green	2K-PE-Feinspachtel 2K-PE-Finisher		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 3 min.	 20° C - 15-20 min. 60° C - 5-10 min.							28961 0000	500 ml	
Mipa P 35 Elastic		dunkelgrau darkgrey ca. RAL 7024	2K-PE-Kunststoffspachtel 2K-PE-Bodyfiller for plastic parts		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20-30 min. 60° C - 10-15 min.							29031 0000	1 kg	
Mipa P 50		hellgelb milchig milky yellow	2K-PE-Faserspachtel 2K-PE-Glass fibre filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20 min. 60° C - 10 min.							28900 0000 28901 0000 28902 0000	200 g 875 g 1,8 kg	
Mipa P 51 grün		grün green	2K-PE-Faserspachtel 2K-PE-Glass fibre filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20 min. 60° C - 10 min.							29201 0000 29202 0000	1 kg 1,8 kg	
Mipa P 53		gelb yellow	2K-PE-Faserleichtspachtel 2K-PE-light weight glass fibre filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 25 min. 60° C - 10 min.							29301 0000	1 l	
Mipa P 55		grau grey	2K-PE-Zinkfaserspachtel 2K-PE-Zinc fibre filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 20 min. 60° C - 10 min.							28911 0000	875 g	
Mipa P 57		schwarz black	2K-PE-Carbonfaser- spachtel 2K-PE-Carbon fibre filler		100 : 2 Nach Gewicht/ by weight Mipa Härter P	 4-5 min.	 20° C - 25 min. 60° C - 10 min.							29372 0000	1,8 kg	
Mipa P 27 Crystal		transparent transparent	2K-PE-Transparentsapachtel speziell für Carbonuntergründe 2K-PE-Transparent putty esp. for carbon surfaces		100 : 2-3 Nach Gewicht/ by weight Mipa MEKP Härter	 15-20 min.	 2 h 20° C - 2 h							29221 0000	1 kg	
Mipa E 80 Kaltzinn		silbergrau- metallic silver-grey metallic	2K-EP-Füllspachtel Kaltzinn 2K-EP-High build bodyfiller Cold tin		2 : 1 Nach Gewicht/ by weight Mipa Härter EPN	 15-30 min.	 4-5 h 20° C - 4-5 h 60° C - 20-30 min.							29251 0000	1 kg	
Mipa E 90		hellgrau light grey	2K-EP-Spachtel seewasserfest 2K-EP-Putty impermeable to seawater		2 : 1 Nach Gewicht/ by weight Mipa Härter EPN	 25-35 min.	 3-5 h 20° C - 3-5 h 60° C - 20-30 min.							29211 0000	1 kg	
Mipa N 30		grau grey	1K-Feinspachtel auf Nitrocellulose-Basis 1K-Fine putty on nitrocellulose base		-	-	 1-2 h 20° C - 1-2 h							28935 0000S 28931 0000	250 g (Tube) 900 g	
Mipa P 20		transparent transparent	PE-Reparatur-Harz PE-Refinishing-resin		100 : 1-3 Nach Gewicht/ by weight Mipa Härter P	 10-15 min.	 1 h 20° C - 60 min.							28941 0000 28947 0000 28955 0000 (Set) 28951 0000 (Set)	1 kg 5 kg 250 g 1 kg	
Mipa P 60 S		grau grey	PE-Dickschicht-Spritzfüller PE-High build polyester spray filler		30 : 1 Nach Gewicht/by weight 100 : 5 Nach Volumen/by volume Mipa Härter PS	 30 min.	 2-3 h 20° C - 2-3 h 60° C - 30 min.							28701 0000	1 l	
Mipa P 67 S		transparent transparent	2K-PE-Spritzfüller, transparent speziell für Carbonuntergründe 2K-PE-Spray filler, transparent esp. for carbon surfaces		100 : 2-3 Nach Gewicht/ by weight Mipa MEKP Härter	 20 min.	 12 h 20° C - 12 h 60° C - 30 min.							28771 0000	1 kg	
Mipa E 65 S		grau grey	2K-EP-Streich- und Spritzfüller 2K-EP-Spray and brush filler		5 : 1 Nach Gewicht/ by weight Mipa Härter E 65 S Komponente B	 30-40 min.	 24 h 20° C - 24 h 60° C - 1 h							28752 0000	1,5 kg	
Mipa 1K- UV-Spachtel		grau-grünlich grey-greenish	1K-UV-Feinspachtel 1K-UV fine putty		-	-	-					ABS, PVC, PC		29690 0000	500 g	

