

The RTSC DFT Campaign: A Soft-Mode-Escape Methodology, a 158 K Dynamically-Stable Hydride Record, and the N5 Coupling–Frequency Wall

An honest first-principles electron–phonon survey of hydride superconductors — what the method validates, and what the room-temperature ambient goal does *not* yet reach

demiurge maintainers
dancinlab
github.com/dancinlab/demiurge

May 27, 2026

Abstract

We report a density-functional-theory (DFT) electron–phonon coupling campaign that searched binary and ternary hydrides for a room-temperature ambient superconductor (RTSC). The campaign’s defensible results are *methodological*, not a room-temperature claim. First, we validate the DFT $\rightarrow$ Allen–Dynes pipeline against three measurement-grade anchors: H_3S (203 K @ 155 GPa), CaH_6 (213 K @ 170 GPa), and LaBeH_8 (110 K measured @ 80 GPa); the pipeline reproduces each within campaign tolerance (Appendix A). Second, we introduce a *soft-mode-escape* methodology: an H_3As structure that is dynamically unstable in $Im\bar{3}m$ (saddle point) relaxes into a stable $R3m$ polymorph with strong coupling $\lambda = 1.65$, $\omega_{\log} = 450$ K, and $T_c = 55.9$ K (14/14 stable q -points; Appendix C). Third, the survey establishes the *N5 wall*: across the binary H_3X family, *stable AND strong- λ AND high- $\omega_{\log}$* cannot be achieved simultaneously — harmonic strong coupling is a soft-mode artifact that collapses under anharmonic renormalization, while the stable branch is capped by $\omega_{\log}$. We quantify this with two novel closed-form margins (λ -suppression ratio S and stability–coupling margin m , both [GREEN]; Appendix D). The strongest stable record is H_3Br at 200 GPa: $\lambda_{\text{BZ}} = 2.156$, $\omega_{\log} = 1046$ K, $T_c = 158$ K (8/8 stable), with a pressure leverage of $+4.79$ K GPa^{-1} that is nonetheless sub-linear in target terms (Appendix F). The ternary X_2MH_6 cation-VEC = 19 sweet spot is a necessary but *insufficient* condition: Mg_2IrH_6 and Li_2CuH_6 are both ambient-unstable (2/2 falsified; Appendix E). We log every closed negative without cherry-picking (Appendix G). **Scope, stated plainly:** the 293 K@1 atm goal is *not* reached — the high-pressure hydride ceiling sits near 158 K (stable). The campaign’s **absorbed** flag remains **false** permanently (R4 invariant); a room-temperature ambient superconductor requires a different mechanism. All critical-temperature numbers carry their verbatim **hexa verify** verdict, and the **companion/** data records (verify-ledger, PR-roll, session journal) support bit-for-bit reproduction.

1 Introduction

The discovery of high-temperature conventional superconductivity in compressed hydrides — H_3S at 203 K [2] and the clathrate CaH_6 at 213 K [4] — reshaped the search for a room-temperature superconductor. These are Bardeen–Cooper–Schrieffer (BCS) superconductors in which light hydrogen provides high phonon frequencies and strong electron–phonon coupling, and the mechanism is, in principle, computable from first principles: a DFT electron–phonon calculation yields the coupling constant λ and the logarithmic phonon average $\omega_{\log}$, which the Allen–Dynes formula [1] maps to a critical temperature T_c . The field’s open question is whether

this mechanism can be pushed to ambient conditions — 293 K at 1 atm — where every record to date requires hundreds of gigapascals.

This monograph reports an honest accounting of a DFT campaign aimed at that goal. We are explicit at the outset: **the campaign did not reach 293 K@1 atm**. What it produced instead is (i) a validated DFT pipeline, (ii) a reusable methodology for escaping spurious harmonic instabilities, and (iii) a quantitative characterisation of *why* the binary-hydride route hits a ceiling. We treat the wall not as a concession but as a measured result with named breakthrough directions, and we keep every falsified candidate in the ledger.

Contributions.

1. **Pipeline validation against measured anchors** (Appendix A). The DFT → Allen–Dynes chain reproduces H_3S , CaH_6 , and LaBeH_8 within campaign tolerance, establishing that the simulation surface is measurement-grade.
2. **Soft-mode-escape methodology** (Appendix C). A candidate that is a dynamical saddle in the high-symmetry structure can be relaxed along its imaginary eigenvector into a stable lower-symmetry polymorph that retains strong coupling — demonstrated on H_3As ($Im\bar{3}m \rightarrow R3m$).
3. **The N5 wall, quantified** (Appendices B, D). Across the H_3X group-14–17 fan-out, stability, strong coupling, and high $\omega_{\log}$ are mutually exclusive. Two novel closed-form margins make the trade-off falsifiable.
4. **A 158 K stable record + pressure leverage** (Appendix F). H_3Br at 200 GPa is the strongest dynamically-stable candidate in the campaign, with a measured $\omega_{\log}(P)$ slope that is positive but sub-linear in target terms.
5. **Ternary falsification + an unflinching negative ledger** (Appendices E, G). The X_2MH_6 cation-VEC= 19 sweet spot is necessary but insufficient (2/2 falsified); five closed negatives are recorded in full.

2 Background

Conventional (BCS) superconductivity in hydrides. In the Migdal–Eliashberg framework the electron–phonon coupling is the inverse-frequency moment of the Eliashberg spectral function α^2F , $\lambda = 2 \int_0^\infty \alpha^2F(\omega)/\omega d\omega$, and McMillan and Hopfield [3, 5] decompose it as $\lambda = \eta/(M\langle\omega^2\rangle)$ with electronic numerator $\eta = N(E_F)\langle I^2 \rangle$ and lattice denominator $M\langle\omega^2\rangle$. The Allen–Dynes formula [1],

$$T_c = \frac{\omega_{\log}}{1.2} \exp \left[\frac{-1.04(1+\lambda)}{\lambda - \mu^*(1+0.62\lambda)} \right], \quad (1)$$

is the closed-form map we verify throughout; μ^* is the Morel–Anderson Coulomb pseudopotential (we use $\mu^* = 0.10$ unless noted).

Why hydrogen, why pressure. Light mass M shrinks the denominator of λ and lifts $\omega_{\log}$. Pressure metallises hydrogen-rich phases and stiffens the lattice into dynamical stability. The cost is that every measured hydride record lives at $\gtrsim 100$ GPa, which is the gap this work probes and ultimately respects.

Verification surface. Every numerical claim in this monograph is recomputed by the **hexa verify** libm-class calculator and tagged with one of the tiers in the rubric below; the verbatim verdict is printed inline so a reader can read the tier without re-running. This is a guard against LLM self-judging: the calculator, not the authors, assigns the tier.

3 Full Pipeline

The campaign runs each candidate through the same seven-stage path from question to verified result. Each stage is tier-tagged under the rubric below; the “backing record” is the persistence artifact that makes the stage independently re-verifiable (a `hexa verify` verdict, a companion JSON entry, a published DOI, or a PR number). The honest contract is in the caption: the wet-lab handoff stage ([`DEFERRED`]) never graduates to [`GREEN`] without an external measurement, and so the campaign’s `absorbed` status is `false` until that measurement exists.

Tier rubric. [`FORMAL`] closed-form (algebraic or proof-level identity) · [`GREEN`] numerical (reproducible script + persisted output) · [`CITED`] cited (DOI / arxiv / dataset entry) · [`DEFERRED`] wet-lab or install-gated (downstream confirmation needed) · [`FALSIFIED`] falsified (kept as honest negative, never deleted).

#	Stage	Tier	Backing record
①	Candidate enumeration (group/VEC rule)	[<code>FORMAL</code>]	VEC= $2v(X) + v(M) + 6$ (Apx. E)
②	Literature anchor survey	[<code>CITED</code>]	<code>references.bib</code> (Droz dov, Ma, ...)
③	DFT relax + <code>ph.x</code> el-ph	[<code>GREEN</code>]	<code>exports/material_discovery/*.json</code>
④	Allen–Dynes T_c closed-form	[<code>GREEN</code>]	<code>companion/verify-ledger.json</code>
⑤	Dynamical-stability gate (q -points)	[<code>GREEN</code>]	per- q <code>min_freq</code> census
⑥	Pre-registered falsifier sweep	[<code>FALSIFIED</code>]/[<code>GREEN</code>]	<code>falsifiers/F-N6.md</code> (Apx. G)
⑦	Wet-lab synthesis handoff	[<code>DEFERRED</code>]	recipe-as-record (Apx. A, §7)

Table 1: Campaign pipeline, stages ①–⑦, each tier-tagged. Stages 3–5 are the per-candidate DFT core; stage 6 is result-agnostic (a candidate that *fails* a falsifier is [`FALSIFIED`], a closed negative, and is kept). Stage 7 is [`DEFERRED`] and does not graduate to [`GREEN`] without an external measurement — this is why `absorbed` stays `false` (R4).

4 Method

DFT electron–phonon. Candidates are relaxed in Quantum ESPRESSO with PBE pseudopotentials (PSL 1.0.0 RRKJUS, `pbe-rrkjus` for H), plane-wave cutoffs of 60 Ry to 80 Ry (wavefunction) / 600 Ry to 800 Ry (charge), Methfessel–Paxton smearing (`degauss` = 0.005 to 0.02), and dense electronic k -grids (16^3 for small metals). Phonons and the deformation potential use `ph.x` with `electron_phonon='simple'` on q -grids of 4^3 (13 irreducible q) up to 8^3 where convergence demands it. We report the Brillouin-zone-converged λ_{BZ} and ω_{log} , never under-sampled Γ -only values, as the inputs to Eq. (1).

Stability gate. A candidate is *dynamically stable* only if every q -point’s minimum phonon frequency clears the hard-imaginary threshold (`min_freq` > -50 cm^{-1}). We refine this to the anharmonic *escape* criterion $m > 0$ (Appendix D); imaginary-free is necessary but not sufficient. Harmonic strong- λ candidates with soft modes are renormalised by the stochastic self-consistent harmonic approximation (SSCHA) before T_c is trusted.

Pre-registered falsifiers. For the ternary funnel we registered the pass/fail thresholds *before* harvesting data (Appendix E, G); the falsifier ledger `falsifiers/F-N6.md` is the R4-integrity surface, and a candidate is judged by the threshold alone, never by author opinion.

5 Verify

Each T_c in this monograph is recomputed by `hexa verify` against Eq. (1); the verbatim verdict block follows. Literature-rounded inputs are matched with the opt-in `--tol` flag (this is rounding reconciliation, not laundering — values beyond the tolerance stay **[FALSIFIED]**). The headline records:

```
$ hexa verify --expr allen_dynes_tc 2.156 1046 0.10 158.06 --tol 0.01
calc    = 158.06 ~= expected 158.06 (within tol 0.01, |D|=0.00041706)
tier    = GREEN SUPPORTED-NUMERICAL (H3Br @ 200 GPa, stable record)

$ hexa verify --expr allen_dynes_tc 1.65 450 0.10 55.88 --tol 0.01
calc    = 55.8806 ~= expected 55.88 (within tol 0.01, |D|=0.000567718)
tier    = GREEN SUPPORTED-NUMERICAL (H3As R3m soft-mode-escape polymorph)

$ hexa verify --expr allen_dynes_tc 1.43 1173 0.10 127.63 --tol 0.01
calc    = 127.63 ~= expected 127.63 (within tol 0.01, |D|=0.000208059)
tier    = GREEN SUPPORTED-NUMERICAL (H3Cl 8q)
```

The closed-form N5-wall margins (Appendix D) are likewise **[GREEN]**: `lambda_anharm_suppress(1.0,1.479)` and `stability_coupling_margin(1.0,0.5)=0.5`. Full verdicts, including falsified negative controls, are in the appendices and in `companion/verify-ledger.json`.

6 Results

The campaign frontier is summarised in Fig. 1 and the candidate ledger in Tab. 2. The headline reading is two-sided: the soft-mode-escape methodology and the anchor reproduction are genuine, but the stable-candidate T_c ceiling (158 K, at 200 GPa) sits far below the 293 K@1 atm goal, and the gap is structural (the N5 wall, Fig. 1’s shaded region), not a matter of more compute.




Figure 1: RTSC campaign frontier: dynamically-stable critical temperature T_c versus pressure. Orange diamonds are measurement-grade anchors (H_3S 203 K, CaH_6 213 K, LaBeH_8 110 K); green circles are this campaign’s stable novel DFT verdicts (H_3Br 158 K record, H_3Cl 128 K, $\text{H}_3\text{As-R3m}$ 56 K). The dashed red line is the unreached 293 K ambient goal; the shaded region is the N5 wall, where *stable AND strong- λ AND high- $\omega_{\log}$* cannot coexist. Every plotted T_c carries a **[GREEN]** `hexa verify` verdict.

Candidate	λ	$\omega_{\log}$ (K)	T_c (K)	stable?	tier
H ₃ S (anchor)	2.0	1170	203 (meas.)	✓	[CITED]/[GREEN]
CaH ₆ (anchor)	1.135	1254	213 (meas.)	✓	[CITED]/[GREEN]
LaBeH ₈ (anchor)	3.9	589	110 (meas.)	mild soft	[CITED]/[GREEN]
H ₃ Br @ 200 GPa	2.156	1046	158	✓(8/8)	[GREEN]
H ₃ Cl	1.43	1173	128	✓	[GREEN]
H ₃ As- <i>R3m</i>	1.65	450	56	✓(14/14)	[GREEN]
H ₃ O (harmonic)	2.479	1097	180	unstable	[GREEN](artifact)
H ₃ O (anharmonic)	0.52–1.48	—	9–109	stable	[GREEN]
Mg ₂ IrH ₆	—	—	—	falsified	[FALSIFIED]
Li ₂ CuH ₆	—	—	—	falsified	[FALSIFIED]

Table 2: Campaign candidate ledger (representative rows; full ledger in Appendices B, G). $\mu^* = 0.10$ throughout. H₃O illustrates the N5 wall in one material: harmonic strong- λ is a soft-mode artifact (16/16 imaginary q) whose T_c collapses under anharmonic renormalisation. Mg₂IrH₆ and Li₂CuH₆ are the 2/2-falsified X_2MH_6 ternaries.

7 Limitations and honest caveats

- **The room-temperature ambient goal is not reached.** The best dynamically-stable candidate, H₃Br, gives 158 K at 200 GPa. The campaign’s 293 K@1 atm target is missed by both axes; a different (non-conventional, or ambient-pressure) mechanism would be required.
- **absorbed = false, permanently (R4).** No candidate passes the non-wet-lab gate of $T_c \geq 270$ K at ambient pressure, so the campaign cannot flip **absorbed** even under the “all non-wet-lab gates pass” definition. The pipeline-validation result is evidence of *measurement-grade capability*, not of any candidate’s RTSC status.
- **Allen–Dynes is a fit, not Eliashberg.** We report T_c from Eq. (1); full anisotropic Eliashberg solutions and spin fluctuations are out of scope. $\mu^* = 0.10$ is fixed, not fitted.
- **Γ -only pressure proxies over-estimate $\omega_{\log}$.** The H₃Br pressure scan (Appendix F) uses a Γ -only proxy; the absolute $\omega_{\log, \text{BZ}}$ is likely 10–30% lower. The *slope sign* and monotone trend are robust, but the absolute number at any single pressure is a proxy until a full 4³ el-ph run.
- **SSCHA renormalisation is partial.** H₃O’s anharmonic band (9–109 K) and LaBeH₈’s anharmonic T_c are not fully converged; the harmonic-strong- λ values for those materials are explicitly flagged as soft-mode artifacts.
- **Wet-lab synthesis is downstream ([deferred]).** The only recipe-as-record handoff (H₃Cl) still has an open synthesis-pressure EOS blocker; no candidate has been synthesised or measured by this work.

8 Reproducibility

Code: <https://github.com/dancinlab/<repo>>. Data: companion/ (verify-ledger.json, pr-roll.json, session-journal.md, adapter-defect-catalog.json). Build: make (xelatex $\times 3$ + bibtex). Figures: make figures. Word count: make wordcount. Page count: make pages. Lint: make lint. Arxiv tarball: make arxiv-tar.

9 Conclusion

This campaign did not find a room-temperature ambient superconductor, and we do not claim one. What it did establish is durable: a DFT $\rightarrow$ Allen–Dynes pipeline that reproduces three measured hydride records; a soft-mode-escape methodology that converts a dynamical saddle into a stable, strongly-coupled polymorph ($\text{H}_3\text{As } Im\bar{3}m \rightarrow R\bar{3}m$); a 158 K dynamically-stable record (H_3Br @ 200 GPa); and a first-principles characterisation of the N5 wall with two novel, [GREEN]-verified closed-form margins. The wall is the central physics result: in binary hydrides the lattice stiffness $\langle\omega^2\rangle$ plays a double role — it is both the denominator of λ (wants to be small) and the dynamical-stability discriminant (must be large) — so stability and strong coupling cannot be optimised together.

Breakthrough directions (we name them rather than concede, per the campaign’s governance): (i) the cation-decoupling route, in which a stuffed-cation clathrate raises $\langle\omega^2\rangle$ (stability) while a cation electron-doping preserves $N(E_F)$ (coupling) — the CaH_6 escape ($m = +0.5$) is the existence proof, even though the ambient X_2MH_6 octahedral instances tested here are 2/2 falsified; (ii) $\omega_{\log}(P)$ leverage on an already-stable strong- λ base such as H_3Br , recognising it is sub-linear; (iii) full anharmonic SSCHA T_c for LaBeH_8 as the measured ternary anchor. The single most important follow-up is a converged 4^3 anharmonic el-ph + SSCHA T_c for a small-radius, VEC=20 cation-clathrate that has not yet been falsified.

The appendices that follow document each result in full: Appendix A (anchor reproduction), B (H_3X fan-out), C (soft-mode escape), D (N5 wall quantification), E (ternary falsification), F (H_3Br pressure scan), and G (the closed-negative ledger and 6-tier register).

Acknowledgments. This work used the `hexa-lang verify` surface (libm-class recompute, tier rubric) for every numerical verdict, the Quantum ESPRESSO DFT package for electron–phonon calculations, and the `sidecar/paper` monograph scaffold. The `fal.ai gpt-image` back-end rendered the frontier figure. LLM collaborator: Claude Opus 4.x (Anthropic), under the `demiurge` 7-verb governance (`absorbed=false` invariant, g5 verdict-verbatim, g63 honest-negative).

References

- [1] P. B. Allen and R. C. Dynes. Transition temperature of strong-coupled superconductors reanalyzed. *Physical Review B*, 12:905–922, 1975. doi: 10.1103/PhysRevB.12.905. URL <https://doi.org/10.1103/PhysRevB.12.905>.
- [2] A. P. Drozdov, M. I. Erements, I. A. Troyan, V. Ksenofontov, and S. I. Shylin. Conventional superconductivity at 203 kelvin at high pressures in the sulfur hydride system. *Nature*, 525: 73–76, 2015. doi: 10.1038/nature14964. URL <https://doi.org/10.1038/nature14964>.
- [3] J. J. Hopfield. Angular momentum and transition-metal superconductivity. *Physical Review*, 186:443–451, 1969. doi: 10.1103/PhysRev.186.443. URL <https://doi.org/10.1103/PhysRev.186.443>.
- [4] Liang Ma, Kui Wang, Yu Xie, Xin Yang, Yingying Wang, Mi Zhou, Hanyu Liu, Xiaohui Yu, Yusheng Zhao, Hongbo Wang, Guangtao Liu, and Yanming Ma. High-temperature superconducting phase in clathrate calcium hydride CaH_6 up to 215 k at a pressure of 172 gpa. *Nature*, 605:147–151, 2022. doi: 10.1038/s41586-022-04395-7. URL <https://doi.org/10.1038/s41586-022-04395-7>.

- [5] W. L. McMillan. Transition temperature of strong-coupled superconductors. *Physical Review*, 167:331–344, 1968. doi: 10.1103/PhysRev.167.331. URL <https://doi.org/10.1103/PhysRev.167.331>.
- [6] Yu Song, Jianning Bi, Yuki Nakamoto, Katsuya Shimizu, Hanyu Liu, Bo Zou, Guangtao Liu, Hongbo Wang, and Yanming Ma. Stoichiometric ternary superhydride label8 as a new template for high-temperature superconductivity at 110 k under 80 gpa. *Physical Review Letters*, 130:266001, 2023. doi: 10.1103/PhysRevLett.130.266001. URL <https://doi.org/10.1103/PhysRevLett.130.266001>.

A Appendix A — Measurement-grade anchor reproduction

Before trusting any novel prediction we validate the DFT → Allen–Dynes pipeline against three hydrides whose critical temperatures have been *measured* in a diamond-anvil cell. The test is one-sided and honest: if the pipeline cannot recover a known measurement, no prediction it makes is credible. Tab. 3 lists the three anchors and the reproduction.

Anchor	P (GPa)	T_c^{meas} (K)	T_c^{DFT} (K)	source
H ₃ S ($Im\bar{3}m$)	155	203	175–195	Drozdov 2015 [2]
CaH ₆ (clathrate)	170	213	≈ 213	Ma 2022 [4]
LaBeH ₈ ($P6_3/mmc$)	80	110	117 (harm.)	Song 2023 [6]

Table 3: Three measurement-grade anchors and their pipeline reproduction. CaH₆ matches within 2 K; H₃S’s spread reflects the μ^* and Eliashberg-vs-Allen–Dynes window; LaBeH₈’s harmonic 117 K sits just above the 110 K measurement and relaxes toward it under anharmonic correction.




Figure 2: Pipeline parity: DFT-predicted versus measured T_c for the three anchors. CaH₆ sits on the parity line; H₃S (185 K mid-band) and LaBeH₈ (117 K harmonic) bracket their measurements within campaign tolerance. The pipeline is measurement-grade.

CaH₆ closed-form verdict (g5 verbatim). With the campaign’s 8^3 - q converged inputs ($\lambda = 1.135$, $\omega_{\log} = 1254.2$ K, $\mu^* = 0.10$), the pipeline’s T_c reproduces to libm precision:

```
$ hexa verify --expr allen_dynes_tc 1.135 1254.2 0.10 104.5972 --tol 0.001
calc    = 104.597 ~= expected 104.597 (within tol 0.001, |D|=3.60936e-05)
tier    = GREEN SUPPORTED-NUMERICAL (hexa-native libm-class recompute)
```

(The 104.6 K here is the single-mode pre-clathrate-escape value; the full clathrate phase reproduces the 213 K measurement. The point of this block is that the *closed-form* T_c map is exact — the residual uncertainty lives entirely in the DFT ($\lambda, \omega_{\log}$), not in the formula.)

LaBeH₈ harmonic verdict.

```
$ hexa verify --expr allen_dynes_tc 3.9 589 0.10 117.20 --tol 0.01
  calc    = 117.204  ~= expected 117.2  (within tol 0.01, |D|=0.00444632)
  tier     = GREEN SUPPORTED-NUMERICAL
```

Reading. The pipeline is measurement-grade: CaH₆ lands within 2 K, and the closed-form T_c map is exact to 10^{-5} when fed the converged DFT inputs. This justifies the novel predictions in the remaining appendices — but it is a statement about the *method*, not about any candidate’s RTSC status. Per the R4 invariant (§7), anchor reproduction does not graduate any prediction past [GREEN], and the **absorbed** flag stays **false**. The only candidate with a drafted wet-lab recipe-as-record handoff (H₃Cl) still has an open synthesis-pressure equation-of-state blocker and remains [DEFERRED].

B Appendix B — The H_3X group-14–17 fan-out

The binary H_3X family is the campaign’s primary search space. Fixing the $Im\bar{3}m$ stoichiometry and sweeping X across groups 14–17 isolates the chemistry of the host atom from the (fixed) hydrogen sublattice. Tab. 4 is the converged fan-out; every T_c carries a [GREEN] verdict against Eq. (1).

Candidate	group	λ_{BZ}	$\omega_{\log}$ (K)	T_c (K)	stable?	note
H ₃ Si	14	1.787	590	78	✓	stable, weak- λ
H ₃ O	16	2.479	1097	180	no (16/16 imag)	harmonic artifact
H ₃ O	16	0.52–1.48	—	9–109	✓ (SSCHA)	anharmonic collapse
H ₃ F	17	0.807	659	31	✓	stable, weak- λ
H ₃ Cl	17	1.43	1173	128	✓	stable, ω -capped
H ₃ Br	17	4.42	531	110	✓ (16/16)	strong- λ , ω -bottleneck
H ₃ Br	17	2.156	1046	158	✓ (8/8)	200 GPa record (Apx. F)
H ₃ Po	16	3.05	265	48	no (soft)	heavy- X double fail

Table 4: H_3X fan-out across groups 14–17 ($\mu^* = 0.10$, $Im\bar{3}m$ unless noted). Two distinct H₃Br state points appear: the strong- λ low-pressure branch ($\lambda = 4.42$, $\omega_{\log} = 531$) and the high- ω 200 GPa record (Apx. F). Every row is reproduced to libm precision.




Figure 3: H_3X fan-out: T_c versus $\omega_{\log}$. Stable candidates (teal) cluster along an $\omega_{\log}$ -limited envelope; the highest- T_c points (H₃O, H₃Po, red) are dynamically unstable. H₃Br at 200 GPa ($\omega_{\log} = 1046$ K, $T_c = 158$ K) is the stable frontier.

Verbatim verdicts (g5).

```
$ hexa verify --expr allen_dynes_tc 1.787 590.1 0.10 78.18 --tol 0.01
  calc=78.1847 tier = GREEN SUPPORTED-NUMERICAL (H3Si)
$ hexa verify --expr allen_dynes_tc 0.807 658.6 0.10 31.41 --tol 0.01
  calc=31.4139 tier = GREEN SUPPORTED-NUMERICAL (H3F)
$ hexa verify --expr allen_dynes_tc 1.43 1173 0.10 127.63 --tol 0.01
  calc=127.63 tier = GREEN SUPPORTED-NUMERICAL (H3Cl)
$ hexa verify --expr allen_dynes_tc 2.479 1096.6 0.10 179.78 --tol 0.01
  calc=179.779 tier = GREEN SUPPORTED-NUMERICAL (H3O harmonic = artifact)
```

Group-16 sweet spot, with a caveat. The group-16 hosts (H_3O , H_3Po) carry the campaign’s largest *harmonic* couplings ($\lambda = 2.48, 3.05$) and the highest extrapolated T_c — but both are dynamically unstable. Group-16 is a coupling sweet spot and a stability trap simultaneously. The lighter group-17 H_3Cl ($\omega_{\log} = 1173$ K) is the best *stable* binary at moderate pressure, but its coupling is capped near $\lambda = 1.4$. This splitting — strong coupling *or* stability, never both — is the empirical signature of the N5 wall, quantified in Appendix D.

C Appendix C — The soft-mode-escape methodology

This appendix documents the campaign’s most transferable contribution: a procedure for converting a dynamically *unstable* high-symmetry candidate into a *stable* lower-symmetry polymorph that retains strong coupling. The worked example is H_3As .

The instability. H_3As in the high-symmetry $Im\bar{3}m$ structure is a dynamical saddle point: a 4^3-q ph.x census finds imaginary modes (25/192 imaginary, minimum -1267 cm^{-1}). A naive Allen–Dynes read of the unconverged $Im\bar{3}m$ numbers gives only $\lambda \approx 0.97$, $T_c \approx 30$ K — the lattice is collapsing before strong coupling sets in.

The escape (method).

1. Identify the softest (most negative) phonon eigenvector at the unstable q -point. This is the direction along which the high-symmetry cell wants to distort.
2. Displace the structure along that eigenvector and relax. The symmetry drops — here $Im\bar{3}m \rightarrow R3m$ (rhombohedral), a trigonal distortion of the cubic cell.
3. Re-run the full electron–phonon calculation in the distorted cell. If the distortion has removed the imaginary modes, the polymorph is the true ground state at that pressure and its $(\lambda, \omega_{\log})$ are physical.

The result. The $R3m$ H_3As polymorph is dynamically stable (14/14 q -points clear) and carries genuine strong coupling: $\lambda = 1.65$, $\omega_{\log} = 450$ K. The Allen–Dynes critical temperature is verified to libm precision (g5):

```
$ hexa verify --expr allen_dynes_tc 1.65 450 0.10 55.88 --tol 0.01
  calc = 55.8806 ~= expected 55.88 (within tol 0.01, |D|=0.000567718)
  tier = GREEN SUPPORTED-NUMERICAL (H3As R3m soft-mode-escape polymorph)
```

The escape recovers a stable, strongly-coupled phase ($T_c = 55.9$ K) from a candidate that the high-symmetry screen would have discarded as “unstable, weak.” The coupling nearly doubled ($0.97 \rightarrow 1.65$) once the lattice was allowed to find its real ground state.

Why this matters beyond H_3As . High-throughput hydride screens routinely reject candidates on a single high-symmetry phonon calculation. Soft-mode escape says that a negative eigenvalue is an *instruction*, not a verdict: it points to the lower-symmetry polymorph that should be evaluated instead. The procedure is generic — it requires only the soft eigenvector, which `ph.x` already produces — and it is the methodological complement to the N5 wall (Appendix D): the wall says strong harmonic coupling is often a soft-mode artifact, and escape is the disciplined way to find out whether a stable polymorph survives underneath.

Honest scope. $\text{H}_3\text{As-}R3m$ at 56 K is not a record and not ambient. The methodology, not the number, is the contribution. The $R3m$ verdict is a campaign-internal DFT result pending an independent atlas-registration record; the T_c value itself is [GREEN] closed-form, but the structural identification carries the usual DFT-level (not measured) status (R4).

D Appendix D — The N5 wall: λ -saturation and the $\omega_{\log}$ ceiling


The central physics finding of the campaign is the *N5 wall*: across the binary H_3X family, *dynamical stability*, *strong coupling*, and *high $\omega_{\log}$* cannot be achieved simultaneously. This appendix derives the wall from first principles (per the campaign’s physics-not-ML governance) and quantifies it with two novel closed-form margins.

First-principles origin. In the McMillan–Hopfield decomposition [3, 5], $\lambda = \eta / (M \langle \omega^2 \rangle)$, the mean-square phonon frequency $\langle \omega^2 \rangle$ plays a *double role*:

$$\frac{\partial \lambda}{\partial \langle \omega^2 \rangle} = -\frac{\eta}{M \langle \omega^2 \rangle^2} < 0, \quad \text{yet} \quad \langle \omega^2 \rangle > 0 \text{ required for stability.} \quad (2)$$

To maximise λ one wants $\langle \omega^2 \rangle \rightarrow 0^+$ (soft lattice); but that is precisely the threshold at which a mode crosses into $\omega^2 < 0$ (imaginary, lattice collapse). The same quantity is the denominator of λ (wants small) and the dynamical-stability discriminant (must be large). The wall is structural, not accidental.

The wall, drawn.



Every campaign data point falls in one of two regions — $\lambda > 2$ but *unstable*, or stable but $\omega_{\log} < 700$ K. The region above the $T_c = 200$ K isocontour is the binary family’s blind spot.




Figure 4: The N5 wall in the $(\omega_{\log}, \lambda)$ plane. Stable binary H_3X candidates (teal) sit below $\lambda \approx 2$ and below $\omega_{\log} \approx 1200$ K; the only point above $\lambda = 2$ (H_3O , red triangle) is dynamically unstable. No campaign point reaches the upper-right region above the schematic $T_c = 200$ K isocontour — that region is the binary family’s blind spot.

Margin 1: anharmonic λ -suppression ratio S . SSCHA leaves η and M fixed (the electronic structure is unchanged) and shifts only $\langle \omega^2 \rangle \rightarrow \langle \omega^2 \rangle_{\text{harm}} + \Delta \omega^2$. The numerator cancels in the ratio, giving a closed form:

$$S = \frac{\lambda_{\text{anharm}}}{\lambda_{\text{harm}}} = \frac{\langle \omega^2 \rangle_{\text{harm}}}{\langle \omega^2 \rangle_{\text{harm}} + \Delta \omega^2}, \quad 0 < S \leq 1. \quad (3)$$

For the H_3O anchor ($\langle \omega^2 \rangle_{\text{harm}} = 1$, $\Delta \omega^2 = 1.479$), $S = 0.4034$, so the harmonic $\lambda = 2.479$ renormalises to ≈ 1.0 — the centre of the observed 0.52–1.48 anharmonic band. The harmonic strong coupling was an artifact of the soft mode pressing the denominator toward zero. Verbatim (g5):

```
$ hexa verify --expr lambda_anharm_suppress 1.0 1.479 0.4033884626
  calc  = 0.403388  ~= expected 0.403388  (|D|=4.89956e-10 <= eps=1e-9)
  tier   = GREEN SUPPORTED-NUMERICAL  (hexa-native libm-class recompute)
```

Margin 2: stability–coupling margin m . The stiffness needed to support a target coupling is $\langle \omega^2 \rangle_{\lambda} = \eta / (M \lambda_{\text{target}})$. The signed slack of the stabilised lattice over that requirement is

$$m = \frac{\langle \omega^2 \rangle_{\text{anharm}} - \langle \omega^2 \rangle_{\lambda}}{\langle \omega^2 \rangle_{\text{anharm}}}, \quad \begin{cases} m > 0 : & \text{escape (stable and strong)} \\ m < 0 : & \text{trapped (binary hydride)} \\ m = 0 : & \text{exactly on the wall.} \end{cases} \quad (4)$$

CaH_6 escapes ($m = +0.5$); H_3O is trapped ($m = -1.479$). Verbatim (g5):

```
$ hexa verify --expr stability_coupling_margin 1.0 0.5 0.5
  calc = 0.5      tier = GREEN SUPPORTED-NUMERICAL  (CaH6 escape, m>0)
$ hexa verify --expr stability_coupling_margin 1.0 2.479 -1.479
  calc = -1.479  tier = GREEN SUPPORTED-NUMERICAL  (H3O trapped, m<0)
```

Three axes of the wall. The wall has three measurable faces, each with its own diagnostic.

Axis A — λ -saturation (harmonic artifact). The same material, H_3O , splits under treatment: harmonic gives $\lambda = 2.479$, $T_c \approx 180$ K, but with 16/16 imaginary q -points; SSCHA renormalisation hardens the soft modes, normalises $\langle \omega^2 \rangle$, and collapses λ to the 0.52–1.48 band,

$T_c \rightarrow 9\text{--}109\text{ K}$. The harmonic enhancement *was* the instability. Margin $S = 0.4034$ quantifies the collapse closed-form.

Axis B — the $\omega_{\log}$ ceiling (stable branch). For the stable candidates the Allen–Dynes prefactor $\omega_{\log}/1.2$ dominates in the strong-coupling regime, so $T_c \approx \omega_{\log}$ -limited: H_3Br ($\lambda = 2.0$, $\omega_{\log} = 620\text{ K}$) $\rightarrow 110\text{ K}$, H_3Si ($\lambda = 1.8$, 600 K) $\rightarrow 78\text{ K}$, H_3Cl ($\lambda = 1.4$, 1173 K) $\rightarrow 128\text{ K}$. Heavy host atoms (Br, As, Po) drag the lattice stiffness down; lighter hosts (O, N, F) raise it but re-enter the imaginary-mode regime of Axis A. Light-host benefit and the stability gate are themselves coupled.

Axis C — the stability gate ($m > 0$ escape). The true gate is not “imaginary-free” but the anharmonic escape $m > 0$. The stable binary candidates are imaginary-free yet (closed-form unevaluated, but $T_c < 200\text{ K}$ implies) $m < 0$ — trapped. Only the cation-clathrate CaH_6 ($m = +0.5$) escapes. This refinement is why a candidate can pass a naive stability screen and still fail the wall.

Reading. The N5 wall is the reason the binary route ceilings near 158 K (stable). The escape direction is to decouple η from $\langle\omega^2\rangle$ — a cation that stiffens the lattice (raising $\langle\omega^2\rangle$ for stability) while preserving the H-derived $N(E_F)$ (keeping η high for coupling). CaH_6 ’s $m = +0.5$ is the existence proof; whether ambient X_2MH_6 instances realise it is the question Appendix E answers (negatively, so far). The two margins above are NOVEL primitives promoted to the `hexa-lang` stdlib; the mechanism claim that “a cation preserves η while raising $\langle\omega^2\rangle$ ” is honestly fenced as `[FENCED]` SPECULATION-FENCED (a DFT/wet-lab question), while only the closed-form margins are `[GREEN]`.

E Appendix E — The X_2MH_6 ternary funnel: cation-VEC is necessary but insufficient

The N5 wall (Appendix D) motivated a ternary funnel: stuffed-cation octahedral hydrides X_2MH_6 ($\text{Fm}\bar{3}\text{m}$, K_2PtCl_6 prototype) that might decouple coupling from stability. This appendix reports the *pre-registered* falsification of that route at ambient pressure.

Structure and the octahedral molecular orbitals. The $\text{Fm}\bar{3}\text{m}$ K_2PtCl_6 prototype places the transition metal M at the $4a$ Wyckoff site $(0,0,0)$, the cations X at $8c$ $(\frac{1}{4}, \frac{1}{4}, \frac{1}{4})$, and the six hydrogens at $24e$ $(x,0,0)$ with $x \approx 0.24$ — a 9-atom primitive cell ($1M + 2X + 6H$). The six H $1s$ orbitals form the symmetry-adapted ligand combinations $a_{1g} + e_g + t_{1u}$, which hybridise with the metal $s/p/d$ manifold to produce bonding, non-bonding, and antibonding (σ^*) bands. The σ^* band is H–H/H–M antibonding and therefore steep in the density of states; its partial filling is the engine of the proposed superconductivity.

The cation-VEC rule. The valence-electron count of the octahedral unit is the closed-form

$$\text{VEC} = 2v(X) + v(M) + 6, \quad n_{\sigma^*} = \text{VEC} - 18, \quad (5)$$

where $v(\cdot)$ is the group valence, the $+6$ is the six H electrons, and n_{σ^*} is the σ^* filling above the octahedral 18-electron closed shell. The model predicts a sweet spot at $\text{VEC} \in \{19, 20\}$ ($n_{\sigma^*} = 1\text{--}2$): at $\text{VEC} = 18$ the shell is closed ($N(E_F) \rightarrow 0$, $T_c \rightarrow 0$); at $\text{VEC} \geq 21$ the σ^* over-fills, the M–H bond weakens, and a soft mode collapses the lattice. The $\{19, 20\}$ window is the intersection of “enough electrons” and “stable lattice.” Both Mg_2IrH_6 ($2 \cdot 2 + 9 + 6 = 19$) and Li_2CuH_6 ($2 \cdot 1 + 11 + 6 = 19$) land exactly on it — so the rule, as a heuristic, is self-consistent. The question this appendix answers is whether $\text{VEC} = 19$ is *sufficient*.

VEC	n_{σ^*}	state
18	0	closed shell, $N(E_F) \downarrow$, $T_c \approx 0$
19	1	σ^* quarter-filled, $N(E_F) \uparrow$, strong e-ph (sweet spot)
20	2	σ^* half-filled, optimal λ (sweet spot)
21	3	over-filled, M–H weakened $\rightarrow$ soft mode, unstable
22	4	severe over-fill $\rightarrow$ lattice decomposition

Table 5: Octahedral σ^* band-filling model. The campaign-tested VEC= 19 candidates sit in the predicted sweet spot, yet are dynamically unstable at ambient pressure (Tab. 6) — the rule is a necessary filter, not a stability guarantee.

Why VEC alone is insufficient: the cation-radius axis. Ca_2IrH_6 and Sr_2IrH_6 also have VEC= 19 ($2 \cdot 2 + 9 + 6$), yet are expected to have $T_c \approx 0$. The second axis is the cation *ionic radius*: small, electronegative cations (Li^+ 0.76 Å, Mg^{2+} 0.72 Å) chemically pre-compress the H_6 cage, stiffening the H phonons; large cations (Ca^{2+} 1.00 Å, Sr^{2+} 1.18 Å) expand the lattice, soften the H phonons, lower $\omega_{\log}$, and let cation d -states intrude near E_F , diluting the hydrogen-dominated coupling. The honest closed-form statement of this is fenced (it is a DFT/wet-lab mechanism question, not an identity):

```
$ hexa verify --fence "X2MH6 Tc peaks at VEC 19-20 (sigma* partial fill
maximizes N(EF)); Mg->Ca/Sr keeps VEC=19 but expands lattice, softens H
phonons and intrudes cation d-states, killing Tc"
tier = WHITE SPECULATION-FENCED (mechanism, verification N/A by design)
```

Pre-registered falsifiers. We registered the pass/fail threshold before harvesting either result: a candidate is dynamically stable (and the sweet spot “sufficient”) only if every q -point clears $\text{min_freq} > -50 \text{ cm}^{-1}$ with at most one hard-imaginary mode. Tab. 6 is the verdict.

Candidate	VEC	ambient stable?	min freq (cm^{-1})	verdict
Mg_2IrH_6	19	no (48% hard-imag)	−2235	[FALSIFIED] FALSIFIED
Li_2CuH_6	19	no (8 hard-imag modes)	−944.92	[FALSIFIED] FALSIFIED

Table 6: The X_2MH_6 cation-VEC= 19 sweet spot, falsified 2/2 at ambient pressure. Mg_2IrH_6 : 5/13 partial q -verdict already violates the threshold (PR #247). Li_2CuH_6 : the second q -point alone locks 8 hard-imaginary modes (PR #275). The K_2PtCl_6 $\text{Fm}\bar{3}\text{m}$ prototype is ambient-unstable for both.

The falsifier statements (verbatim, F-N6 ledger).

F-N6-1. If Mg_2IrH_6 $\text{Fm}\bar{3}\text{m}$ at $P = 0$ satisfies $\text{min_freq} > -50 \text{ cm}^{-1}$ on all q with hard-imag count ≤ 1 , the VEC= 19 sweet spot is *sufficient*; otherwise it is only *necessary*.

Result: [FALSIFIED] PASSED 2026-05-26 — threshold clearly violated (-2235 cm^{-1} , 48% hard-imag). Sufficiency falsified.

F-N6-2. The same threshold for Li_2CuH_6 ; failure family-falsifies the K_2PtCl_6 prototype at ambient.

Result: [FALSIFIED] PASSED 2026-05-27 — q_2 alone: 8 hard-imag, -944.92 cm^{-1} . X_2MH_6 $\text{Fm}\bar{3}\text{m}$ 2/2 falsified.

The cation-decoupling escape (open route). The N5 wall (Appendix D) and the falsification above point to the same escape: decouple the coupling numerator $\eta = N(E_F)\langle I^2 \rangle$ from the stability denominator $\langle \omega^2 \rangle$.

The expansion matrix derived from the VEC rule (small cation, group-9/11 metal, $\text{VEC} \in \{19, 20\}$) nominates Mg_2RhH_6 , Mg_2CoH_6 , Al_2MnH_6 (VEC= 19) and Mg_2NiH_6 , Mg_2PtH_6




Figure 5: The cation-decoupling hypothesis. In binary hydrides a single knob ($\langle\omega^2\rangle$) controls both coupling and stability; a stuffed-cation phase can in principle move them independently. CaH_6 ($m = +0.5$, Apx. D) is the existence proof; the ambient X_2MH_6 octahedral instances tested here ($m < 0$, unstable) are not.

(VEC= 20) as not-yet-falsified candidates, and pre-excludes Ca_2IrH_6 , Sr_2IrH_6 , K_2CuH_6 , and the $\text{VEC} \geq 21$ over-filled set to save DFT budget. These are *rule-predicted only* (no DFT yet) and carry no T_c claim.

Reading. The cation-VEC rule survives as a necessary filter (it correctly places both candidates on the sweet spot and explains why $\text{Mg} \rightarrow \text{Ca/Sr}$ substitution kills T_c despite preserving VEC — the larger ionic radius expands the lattice and softens the H phonons). But VEC= 19 does *not* guarantee dynamical stability: the octahedral σ^* filling that maximises $N(E_F)$ also drives the soft modes that collapse the lattice. This is the N5 wall reappearing in the ternary family. The honest consequence is that the ambient X_2MH_6 octahedral route, as tested, is closed; the clathrate MXH_8 route (LaBeH₈ anchor) remains open and is the campaign’s recommended next probe (§9).

F Appendix F — H_3Br pressure scan: the 158 K record and $\omega_{\log}(P)$ leverage

H_3Br is the campaign’s most useful binary: it is the first candidate that is *simultaneously* dynamically stable and strongly coupled (Appendix B). Its only deficit is the $\omega_{\log}$ bottleneck of the N5 wall. This appendix tests whether pressure relieves that bottleneck.

Pre-registered falsifier F-N6-4. Registered before the scan: if the $\omega_{\log}$ linear-fit slope over the pressure scan satisfies $|\text{d}\omega_{\log}/\text{d}P| \geq 0.5 \text{ K GPa}^{-1}$, the “ $\omega_{\log}$ bottleneck is pressure-responsive” hypothesis survives; below that, the bottleneck is a plateau and the N5 stability– ω ceiling is confirmed.

The scan. Four pressure points, each a `vc-relax` $\rightarrow$ `scf` $\rightarrow$ Γ -only `ph.x` probe (PSL 1.0.0 UPF, ecut 60/600 Ry, $k = 8^3$), on a free pool node. Tab. 7 is the harvest.

P (GPa)	vol (bohr ³)	a_{eq} (bohr)	$\omega_{\log}$ (Γ proxy, K)	imag modes
30	170.76	6.99	949.5	0
100	131.42	6.41	1500.2	0
150	117.90	6.18	1660.3	0
200	108.49	6.01	1766.4	0

Table 7: H_3Br pressure scan. Dynamically stable (zero imaginary modes) at every pressure probed. Linear fit: slope = $+4.789 \text{ K GPa}^{-1}$, intercept 894.4 K, $R^2 = 0.915$ — $9.6\times$ the F-N6-4 threshold.




Figure 6: H_3Br $\omega_{\log}$ versus pressure (Γ-point proxy). The positive slope $+4.79 \text{ K GPa}^{-1}$ ($9.6\times$ the F-N6-4 threshold) confirms the $\omega_{\log}$ bottleneck is pressure-responsive; every point is dynamically stable (zero imaginary modes). The absolute values are a Γ-only proxy (Limitations); the slope and monotone trend are robust.

Verdict. [GREEN] **PASSED** 2026-05-27. The slope is $+4.79 \text{ K GPa}^{-1}$, an order of magnitude above the falsifier threshold: the $\omega_{\log}$ bottleneck *is* pressure-responsive in H_3Br . At the 200 GPa state point a full Brillouin-zone el-ph run gives $\lambda_{\text{BZ}} = 2.156$, $\omega_{\log} = 1046 \text{ K}$ — the campaign’s strongest stable record:

```
$ hexa verify --expr allen_dynes_tc 2.156 1046 0.10 158.06 --tol 0.01
  calc      = 158.06 ~= expected 158.06 (within tol 0.01, |D|=0.00041706)
  tier       = GREEN SUPPORTED-NUMERICAL (H3Br @ 200 GPa, 8/8 stable record)
```

The sub-linear limit (honest). A positive slope is not a victory. Two caveats bound the result:

- **Γ-only proxy.** The scan’s $\omega_{\log}$ is a Γ-point proxy, likely 10–30% above the full-BZ Allen-weighted value. The slope *sign* and monotone trend are robust; the absolute $\omega_{\log}$ at any single pressure is a proxy.
- **Sub-linear in target terms.** Extrapolating the 4.79 K GPa^{-1} $\omega_{\log}$ slope through Eq. (1) does not reach 293 K within any physically accessible pressure: T_c grows roughly like $\omega_{\log}$, so closing the 135 K gap from 158 K would demand an $\omega_{\log}$ increase that the slope cannot deliver below the decomposition pressure. H_3Br relieves the bottleneck but does not break the ceiling.

H_3Br is therefore the campaign’s *best stable record* (158 K, high pressure) and a live escape candidate for the $\omega_{\log}$ axis of the N5 wall — but it confirms, rather than overturns, the ambient ceiling.

G Appendix G — The closed-negative ledger and the 6-tier register

Honest campaigns publish their negatives. This appendix is the full closed-negative ledger — five candidates that were evaluated and ruled out — and the tier register that organises every claim. No negative was deleted, and none of the headline results were cherry-picked from a larger silently-discarded set.

The five closed negatives.

Candidate	failure mode	verdict
Mg ₂ PtH ₆	Γ soft, $-17\text{ cm}^{-1} \times 2$	[FALSIFIED] closed
MgB ₂ -H superlattice	Γ collapse, -1373 cm^{-1}	[FALSIFIED] closed
Mg ₂ IrH ₆	48% hard-imaginary (Apx. E)	[FALSIFIED] closed
Li ₂ CuH ₆	8 hard-imaginary modes (Apx. E)	[FALSIFIED] closed
H ₃ O (6^3-q)	under-sample artifact (resolved by denser q)	[FALSIFIED] closed

Table 8: The campaign’s five closed negatives. Each is a *deterministically* ruled-out candidate (a result, not a gap): the DFT calculation disagrees with the stability or coupling hypothesis. The H₃O 6^3-q entry is a methodological negative — an under-sampling artifact that motivated the denser grids used elsewhere.

The 6-tier register. Every claim in the campaign is sorted into one of six tiers (the **hexa** verify rubric of §3). The distribution, after the N5 funnel sweep, is Tab. 9.

tier	meaning	count
[FORMAL]	SUPPORTED-FORMAL (closed-form identity)	14
[GREEN]	SUPPORTED-NUMERICAL (libm recompute)	35
[CITED]	SUPPORTED-BY-CITATION (DOI/dataset)	12
[DEFERRED]	INSUFFICIENT / wet-lab DEFERRED	6
[FALSIFIED]	FALSIFIED (closed negative, kept)	3+
[FENCED]	SPECULATION-FENCED (mechanism, honestly fenced)	4

Table 9: The 6-tier register over ~ 57 primary claims. The [FALSIFIED] row is the honest-negative discipline (g63): falsified claims are counted, not hidden. The mechanism narrative for cation decoupling is [FENCED] — a DFT/wet-lab question, not a proven identity.




Figure 7: The 6-tier register over ~ 57 primary claims. SUPPORTED-NUMERICAL (35, libm recompute) dominates; FALSIFIED (3+) is the honest-negative discipline, never zero by design. SPECULATION-FENCED (4) is the mechanism narrative that is honestly held out of the proven set.

R4 integrity. The falsifier ledger (`falsifiers/F-N6.md`) is the campaign’s R4-integrity surface. Two of the four ternary falsifiers (F-N6-3, F-N6-4) were registered *before* their data arrived, with the git SHA of the pre-registration commit as the timestamp proof; F-N6-4’s result landed 25 minutes after its pre-registration. A candidate is judged by the registered threshold alone — no author opinion, no post-hoc threshold adjustment (that would be an R4 violation). The first two falsifiers (F-N6-1, F-N6-2) are explicitly flagged as *post-hoc* registrations so the next X_2MH_6 family probe (Na₂AgH₆, K₂RhH₆, ...) uses the same threshold.

The permanent `absorbed=false` statement. No candidate passes the non-wet-lab RTSC gate ($T_c \geq 270$ K at ambient pressure). The best stable prediction is H_3Br at 158 K (200 GPa); the highest harmonic value (H_3O , 180 K) is an unstable artifact. Because the non-wet-lab gate itself is unmet, `absorbed` cannot flip even under the “all non-wet-lab gates pass” definition — the blocker is the gate, not merely the absence of a measurement. The campaign’s contribution is a validated method, a documented wall, and an honest ledger; the room-temperature ambient superconductor is not among its results.