

	<h1>STUCCOMARMO</h1>	<b>SCHEDA TECNICA</b>
		Rev. 0 – Ed. 1

## SPECIFICATIONS

Natural decorative covering in paste, produced according to the experience of old formulas and with the aid of new technologies. It allows to obtain a marble-like finishing, typical of the venetian eighteenth-century style. Endowed with a complete perspiration and with an extraordinary anti-mould power (thanks to the disinfectant power of the lime), it can be applied on both external and internal walls.

It hardens in consequence of the chemical process of carbonisation: the calcium hydroxide (primary binder of the product) reacts with the carbonic anhydride present in the air by producing calcium carbonate, which is marble's main component (hence the name "marmorino"). Thanks to its features, it is largely employed as an elegant finishing for all prestige environments.

## COMPOSITION

Long-seasoning slaked lime, high-selected calcareous filler, non-toxic additives.

## METHODS OF APPLICATION

### SURFACE PERPERATION

The application on lime supports is recommended, but it can also be applied on plaster or by-products, old hydro paints, only if strong and well-fixed, after the application of a coat of Primer S.

### Application

Spread a coat of STUCCOMARMO with a stainless steel smoother so as to level the support; if needed, spread a second coat.

Apply little spots of product and then take them away ("put and remove" technique); when the product is going to dry up, press and polish, until the desired result is obtained.

### Colouring of the product

Each color in our color chart has been divided into 4 different shades, each one corresponds to a letter A,B,C,D

In order to obtain the desired color add to Lt.14 of Stuccomarmo the quantity of ARTHE CONCENTRATO according to the following chart:

Art. ... A	Art. ... B	Art. ... C	Art. ... D
3 x 600 ml.	1 x 600 ml.	3 x 70 ml.	1 x 70 ml.

## TECHNICAL DATA

SPECIFIC WEIGHT:	1,550 Kg./Lt. +/- 3%
VISCOSITY:	tixotropitca
DRYING:	2 hours at 20°C
COMPLETE DRYING:	24 hours at 20°C
TEMPERATURE OF APPLICATION:	between 10°C and 30°C
COLOURS:	to be chosen in the catalogue
YIELD:	2,3-2,9 m² PER litres.
PACKAGE:	14 Litres or 4,67 Litres polyéthylène containers
PRESERVATION:	24 months in the intact packages, away from temperature changes

## ITEM OF SPECIFICATIONS

Marble-like decorative and protective covering, like STUCCOMARMO produced by Spiver Ltd, containing long-seasoning slaked lime, high-selected calcareous filler, non-toxic additives and pigments with a high resistance to light and alkalis, prior a correct treatment of the support. Price inclusive of the material and implementation, except the scaffoldings per square metre: €.....

NB The above-mentioned data are susceptible of variations. Spiver Ltd. is not responsible for any negative result depending on the application of the product out of the Company's control and on the agents unrelated to the product quality