

Stress and strain in ferroelectrics

Zhigang Suo

Ferroelectrics are being integrated into many structures, both large and small. Various innovations have once again brought the fundamentals of ferroelectricity into focus. Advances have been made in understanding stress and strain effects, especially on phenomena at small size scales. These phenomena include depoling and cracking in actuators, and properties of small free particles, fine grain ceramics and thin films.

Addresses

Mechanical and Aerospace Engineering Department, and Princeton Materials Institute, Princeton University, Princeton, NJ 08544, USA; e-mail: suo@princeton.edu

Current Opinion in Solid State & Materials Science 1998, 3:486–489

Electronic identifier: 1359-0286-003-00486

© Current Chemistry Ltd ISSN 1359-0286

Abbreviations

BST $\text{Ba}_x\text{Sr}_{1-x}\text{TiO}_3$
PZT $\text{PbZr}_{1-y}\text{Ti}_y\text{O}_3$

Introduction

Barium titanate (BaTiO_3) undergoes a phase transition at $\sim 120^\circ\text{C}$. Above the transition temperature, the crystal has a cubic lattice. At room temperature, the crystal has a tetragonal lattice structure and a spontaneous polarization; that is, an applied electric field can switch the polarization from one direction to another. The high temperature phase is paraelectric and the room temperature phase is ferroelectric. Commercial uses of BaTiO_3 and related materials have largely been in the form of bulk ceramics [1]. Paraelectric $\text{Ba}_x\text{Sr}_{1-x}\text{TiO}_3$ (BST) capacitors can store a large amount of electric charge per unit weight. Ferroelectric $\text{PbZr}_{1-y}\text{Ti}_y\text{O}_3$ (PZT) ceramics are ubiquitous as sensors and actuators. Some single crystals of ferroelectric materials can have large actuation strains and small hysteresis, and are being investigated for ultrasonic transducers [2•]. The past decade has seen intense research into thin films, motivated by the potential of integrating ferroelectrics onto silicon chips [3]. Applications of such materials include high-permittivity capacitors in dynamic random access memories, bistable media in nonvolatile memories and active parts in micromachines.

Drawing mainly upon work published since 1997, this article reviews stress and strain effects in ferroelectrics, and their relations to theoretical models at several length scales. Phenomenological constitutive laws, together with the field equations in mechanics and electrostatics, determine various fields in bulk structures. Domain dynamics underlie bulk behavior and are even more important to understanding thin films. Atomistic descriptions are needed for ultrathin films where interfaces dominate material behavior.

Paraelectric behavior

Due to their high permittivities, paraelectric BST ceramic films are being developed for dynamic random access memories. The capacitance of BST films, however, is lower than that anticipated from the bulk permittivity. Causes for this difference include interfacial capacitance, residual stress, and a fine grain structure. Experimental data have been fitted to an empirical relation [4•]:

$$\frac{1}{C} = \frac{1}{C_i} + \frac{t}{\epsilon_f} \quad (1)$$

Here C is the capacitance per unit film area and t the film thickness; C_i and ϵ_f are fitting parameters. The data are interpreted as follows [5•]: in a BST film, near a film-electrode interface, thin layers (thickness of approximately a few lattice constants) are 'dead', equivalent to a capacitor of a low-permittivity material. An applied voltage drops across the interfacial layers and the film in series. Consequently, C_i and ϵ_f are interpreted as the interfacial capacitance and the film permittivity, respectively. For a film thinner than 50 nm, C_i significantly limits the overall capacitance. The use of oxide, rather than metallic electrodes can increase the capacitance [6,7].

If a film was to be free-standing, a voltage applied across the thickness would cause it to contract in its plane by an electrostrictive strain $Q_{12}D^2$, where Q_{12} is the electrostrictive coefficient and D the electric displacement [8•]. A BST film on a silicon substrate, however, is often under a tensile residual stress, σ , as a result of the deposition process and a thermal expansion misfit. The Devonshire theory predicts a change in permittivity [9]:

$$\frac{1}{\epsilon_f} = \frac{1}{\epsilon_u} - 4Q_{12}\sigma \quad (2)$$

where ϵ_f is the permittivity of the stressed film and ϵ_u the permittivity of the unstressed film. Because $Q_{12} < 0$, a residual tension in the film reduces the permittivity. This above formula is valid for all dielectrics. For BST films, the change in permittivity can be pronounced because ϵ_u and σ are large. In an experiment (TM Shaw, Z Suo, M Huang, unpublished data), the residual stress was determined by a wafer curvature method, and Q_{12} by the capacitance change as the wafer was bent by a known mechanical load. The value of Q_{12} was found to be comparable with that of bulk BST.

Another cause for the permittivity reduction is the small grain size in the films. For $\text{Ba}_x\text{Sr}_{1-x}\text{TiO}_3$ the composition x is often chosen such that the bulk crystal undergoes the cubic–tetragonal transition near room temperature, where permittivity peaks. For thin films of the same composition,

x, the permittivity-temperature curve has no peak and the material remains paraelectric down to very low temperatures. This grain size effect will be discussed later in this review.

The residual stress in BST films can be in the gigaPascal range; this raises the question as to whether a ceramic film can sustain such a large tensile stress without cracking. The answer depends on the film thickness. The formation of a crack reduces elastic energy, but increases surface energy. As the film becomes thinner, the volume-to-surface ratio decreases, and the elastic energy reduction cannot compensate for the increase in surface energy, such that the crack cannot form. This energetic condition is expressed by

$$\beta\sigma^2/\gamma < \gamma \quad (3)$$

where t is the film thickness, σ the residual stress in the film, Y is Young's modulus, γ the surface energy, and β a dimensionless number of order unity. Consequently, a very thin film can sustain a large stress without cracking. This well established energetic approach has recently been applied to integrated microstructures [9].

Large stresses can also be generated by an electric field. In a multilayer actuator, around an internal electrode edge, the electric field is nonuniform and intense. Consequently, a stress field arises, which may cause the ceramic to crack. The problem causes a dilemma in developing new materials. On the one hand, materials capable of large strains are desired for actuators; on the other hand, the large strains make the devices prone to cracking near field concentration sites. There have been anecdotal observations that, as the device feature size miniaturizes, cracking may be averted. The trend can be understood in terms of the energetic consideration outlined above [10–12]. So far, no systematic experimental demonstration has been made. Note that the electric field is very high around an electrode edge. A constitutive law that captures the high field effects in electrostrictive materials has been implemented into finite element codes to analyze realistic device structures [11,12,13*].

Ferroelectric behavior

A ceramic must be poled by a strong electric field to exhibit overall piezoelectricity. Used as an actuator, the ceramic deforms under an electric field against a mechanical force. The compressive stress so generated may depole the material, leaving it nonpiezoelectric. An order of magnitude estimate of the depoling stress is given by,

$$E\Delta P \approx \sigma\Delta\gamma \quad (4)$$

Here E is the electric field needed to pole a sample under no stress, σ is the stress needed to depole the sample under no electric field; and ΔP and $\Delta\gamma$, respectively, are the changes in polarization and strain associated with the poling. Several types of measurements can quantify depoling [14,15].

Ferroelectricity has several effects on the fracture in bulk ceramics. Stress-induced switching is a toughening mechanism that leads to the fracture resistance curve behavior [16]. Tests using Vickers indenters have shown that poling of a ferroelectric ceramic increases toughness in the poling direction, and decreases it in the direction perpendicular to the poling direction. Toughness also depends on whether or not an electric field is applied and in what direction it is applied. A cyclic electric field causes a crack to grow stably by a certain amount per cycle. All such effects have been analyzed using micromechanics models ([17–20]; T Zhu, W Yang, personal communication). There are no generally accepted constitutive laws for ferroelectrics, although earlier attempts to formulate such laws have been revived ([21,22]; M Kamlah, C Tsakmakis, personal communication; RM McMeeking, ACF Cocks, personal communication), their usefulness in modeling field concentration and fracture remains to be established.

At room temperature, bulk BaTiO₃ is in the tetragonal phase. With submicron free particles, as the particle size decreases, the degree of tetragonality decreases and below a critical size, the particles are all in the cubic phase. A common explanation for this particle size effect is as follows [23,24*,25]. For a ferroelectric particle, spontaneous polarization gives rise to electric charges on the surfaces of the two poles. The charges may be compensated for by drawing free charges from the environment, an external circuit, or the particle itself. If not compensated, however, spontaneous polarization causes electric energy. In a large particle, domains form a pattern to reduce this electric energy. As the particle size decreases, however, the surface-to-volume ratio increases, and the reduction in the electric energy cannot compensate for the increase in wall energy, such that the domain size scales down disproportionately. In a small particle, the electric energy can be large enough to destabilize the tetragonal phase in favor of the cubic phase. In an experiment by Liu *et al.* [26*], particles were coated with a copper layer, allowing an electric charge to flow from one pole to the other to compensate the spontaneous polarization and thereby stabilizing the tetragonal phase.

In a dense ceramic, elastic energy, as well as electric energy, plays a similar role in destabilizing the ferroelectric phase. Domains in each grain select their polar directions among a set of crystalline directions. Consequently, neighboring grains suffer misfits in both spontaneous polarization and spontaneous strain; these misfits may be partially compensated by charges and dislocations, respectively. In large grain ceramics, the formation of a domain pattern reduces the misfit energy. In fine grain ceramics, just as in small free particles, domains cannot be refined proportionally, such that the misfit energy can be large enough to destabilize the ferroelectric phase. As stated before, thin BST films are paraelectric even at very low temperatures, and their permittivities are lower than those of bulk BST [4**]. In some large grain PZT ceramics, over half of the

piezoelectric response comes from domain wall motion. This contribution is eliminated from fine grain ceramics [27,28**]. If, however, neighboring grains have similar crystalline orientations, the texture should have two effects: a reduction in the misfit energy and more cooperative domain switching among neighboring grains, both of which tend to reduce the size effects.

In addition to being fine grained, a thin film is constrained by the substrate. In the limit where a film is much thinner than the substrate, when a voltage is applied across the film thickness no net strain can occur in the plane of the film. That is, any strain caused by non-180° switching must be compensated for by an elastic strain. The latter corresponds to a stress that resists the switching. It should be pointed out that the substrate constraint persists even for large grains and thick films, so long as the film is much thinner than the substrate. Ideally one should distinguish the grain size effect from the substrate constraint effect. This is difficult in practice because the grain size in a film is often comparable to the film thickness. Even for thick PZT films (12 μm), dielectric and piezoelectric properties are still lower than bulk values [29]. This seems to suggest that the substrate constraint should have some effect on non-180° domain wall motion. In thin PZT films, non-180° domain wall motion is limited and makes little contribution to dielectric and piezoelectric responses [30**]. Furthermore, such responses do not change significantly under an applied stress of the order of 100 MPa, tension or compression, in the plane of the film.

A single crystal ferroelectric film may grow epitaxially on a substrate of a similar crystal structure. If the lattice constants of the film and the substrate are different, the film may be stressed to match the lattice constant of the substrate. Alternatively, the film may form a domain pattern to reduce the elastic energy (see [31,32] for recent work; N Sridhar, JM Rickman, DJ Srolovitz, personal communication). The effect of substrate constraint on the paraelectric-ferroelectric transition has also been considered [33**]. Furthermore, calculations have shown that, when a polydomain film is subject to a small electric field, non-180° domain walls can move, contributing to dielectric and piezoelectric responses [34,35**].

Two approaches have been developed to simulate ferroelectric domain dynamics. One approach is an extension of the classical grain growth model [36,37**]; it treats a domain wall as a sharp surface. Each domain is piezoelectric, straining and polarizing in the vicinity of a spontaneous state. The free energy includes both field energy and domain wall energy. A kinetic law relates the domain wall velocity to the free energy reduction associated with the domain wall motion, for which intrinsic length and time scales have been identified [36]. The second approach is an extension of the Landau-Ginsburg model [38,39**]. The domain wall is modeled as a diffuse interface by adding polarization gradient terms to the free energy. A kinetic law

relates the rate of polarization change to the reduction in the free energy. This model has been implemented with electric and elastic effects, together with a domain nucleation condition. Further progress may benefit from concepts developed in the strain gradient theory [40].

Conclusions

Multiple energetics underlie diverse ferroelectric effects, particularly in small or constrained objects. Many such effects are understood individually in principle. Further quantitative experiments and computations are needed to weigh their relative significance. Substantial work is needed to elucidate ferroelectricity at interfaces, as they begin to dominate the response of thin films as most materials in use are traditional ones optimized for bulk applications. Insight into small object behaviors should lead to novel materials for thin film applications.

Acknowledgements

The author is grateful to the financial support of the Office of National Research (contract N00014-97-1-0260), National Science Foundation (grant MSS-9258115), and the Institute for Materials Research and Engineering, Singapore.

References and recommended reading

Papers of particular interest, published within the annual period of review, have been highlighted as:

- of special interest
- of outstanding interest

1. Uchino K: *Piezoelectric Actuators and Ultrasonic Motors*. Boston: Kluwer Academic Publications; 1997.
2. Park SE, Shrout TR: **Ultra-high strain and piezoelectric behavior in relaxor based ferroelectric single crystals**. *J Appl Phys* 1997, **82**:1804-1811.
- Under no stress, an electric field of the order of 1 MV/m generates more than 1% strains in these crystals. For a rhombohedral ferroelectric crystal, high strains are induced in the <001> direction, possibly by rotating polar axes from the <111> directions. Because no domain wall motion is necessary, the large strains are achieved with little hysteresis. For actuator applications, the resistance to cracking and depoling must be investigated.
3. Ramesh R: *Thin Film Ferroelectric Materials and Devices*. Boston: Kluwer Academic Publications; 1997.
4. Basceri C, Streifer SK, Kingon AI, Waser R: **The dielectric response as a function of temperature and film thickness of fiber-textured (Ba,Sr)TiO₃ thin films grown by chemical vapor deposition**. *J Appl Phys* 1997, **82**:2497-2504.
- For a film in the thickness range 24–160 nm, the interfacial capacitance is approximately 0.1 F/m² and the film dielectric constant is ~300. The film is in a paraelectric phase and can be described by the Devonshire theory.
5. Zhou C, Newns DM: **Intrinsic dead layer effect and the performance of ferroelectric thin film capacitors**. *J Appl Phys* 1997, **82**:3081-3088.
- A phenomenological lattice vibration model shows the low permittivity of surface layers.
6. Izuha M, Abe K, Fukushima N: **Electrical properties of all-perovskite oxide (SrRuO₃/Ba,Sr_{1-x}TiO₃/SrRuO₃) capacitors**. *Jpn J Appl Phys* 1997, **36**:5866-5869.
7. Liu KS, Tesng TF, Lin IN: **Improvement of (Pb_{1-x}La_x)(Zr_yTi_{1-y})_{1-x/4}O₃ ferroelectric thin films by use of SrRuO₃/Ru/Pt/Ti bottom electrodes**. *Appl Phys Lett* 1998, **72**:1182-1185.
8. Newnham RE, Sundar V, Yimnirun R, Su J, Zhang QM: **Electrostriction: nonlinear electromechanical coupling in solid dielectrics**. *J Phys Chem B* 1997, **101**:10141-10150.
- An overview of electrostrictive behaviors.
9. Liu XH, Suo Z, Ma Q, Fujimoto H: **Cracking and debonding in integrated microstructures**. *MRS Symp Proc* 1998, **516**:in press.

10. Hao TH, Gong X, Suo Z: **Fracture mechanics for the design of ceramic multilayer actuators.** *J Mech Phys Solids* 1996, **44**:23-48.
 11. Gong X, Suo Z: **Reliability of ceramic multilayer actuators: a nonlinear finite element simulation.** *J Mech Phys Solids* 1996, **44**:751-769.
 12. Hom CL, Shankar N: **A finite element method for electrostrictive ceramic devices.** *Int J Solids Struct* 1996, **33**:1757-1779.
 13. Hom CL, Shankar N: **A dynamics model for nonlinear electrostrictive actuators.** *IEEE T Ultrason Ferroelectr* 1998, **45**:409-420.
- A three-dimensional, nonlinear constitutional law for electrostrictive materials is used to analyze an actuator.
14. Lynch CS: **The effect of uniaxial stress on the electro-mechanical response of 8/65/35 PLZT.** *Acta Mater* 1996, **44**:4137-4148.
 15. Schaufele A, Hardtl KH: **Ferroelastic properties of lead zirconate titanate ceramics.** *J Am Ceram Soc* 1996, **79**:2637-2640.
 16. Meschke F, Kolleck, Schneider GA: **R-curve behavior of BaTiO₃ due to stress-induced ferroelectric domain switching.** *J Euro Ceram Soc* 1997, **17**:1143-1149.
 17. Zhu T, Yang W: **Toughness variation of ferroelectrics by polarization switch under non-uniform electric field.** *Acta Mater* 1997, **45**:4695-4702. [Correction: 1998, **46**:2251-2251].
 18. Yang W, Zhu T: **Switch-toughening of ferroelectrics subjected to electric fields.** *J Mech Phys Solids* 1998, **46**:291-311.
 19. Fulton CC, Gao H: **Electrical nonlinearity in fracture of piezoelectric ceramics.** *Appl Mech Rev* 1997, **50**:S56-S63.
 20. Gao HJ, Zhang TY, Tong P: **Local and global energy release rates for an electrically yielded crack in a piezoelectric ceramic.** *J Mech Phys Solids* 1997, **45**:491-510.
 21. Jiang Q, Huo Y: **Modeling of domain switching in ferroelectric ceramics: an example.** *Int J Solids Struct* 1998, **35**:1339-1353.
 22. Chen X, Fang DN, Hwang KC: **Micromechanics simulation of ferroelectric polarization switching.** *Acta Mater* 1997, **45**:3181-3189.
 23. Frey MH, Payne DA: **Grain-size effect on structure and phase transformations for barium titanate.** *Phys Rev B* 1996, **54**:3158-3168.
 24. McNeal MP, Jang SJ, Newnham RE: **The effect of grain and particle size on the microwave properties of barium titanate (BaTiO₃).** *J Appl Phys* 1998, **83**:3288-3297.
- The paper contains a review of earlier work on size effects.
25. McCauley D, Newnham RE, Randall CA: **Intrinsic size effects in a barium titanate glass-ceramic.** *J Am Ceram Soc* 1998, **81**:979-987.
 26. Liu X, Shih WY, Shih WH: **Effects of copper coating on crystalline structure of fine barium titanate particles.** *J Am Ceram Soc* 1997, **80**:2781-2788.
- An experimental demonstration of the depolarization effect on phase transition. The boundary condition is better prescribed than by many other studies.
27. Cao WW, Randall CA: **Grain size and domain size relations in bulk ceramic ferroelectric materials.** *J Phys Chem Solids* 1996, **57**:1499-1505.
 28. Randall CA, Kim N, Kucera JP, Cao WW, Shrout TR: **Intrinsic and extrinsic size effects in fine-grained morphotropic-phase boundary lead zirconate titanate ceramics.** *J Am Ceram Soc* 1998, **81**:677-688.
- Properties are measured for ceramics over the grain size range of 0.1–10 μm . Dielectric and piezoelectric properties start to reduce around a grain size of 1 μm . The paper also contains a review of previous models and experiments.
29. Chen HD, Udayakumar KR, Gaskey CJ, Cross LE, Bernstein JJ, Niles LC: **Fabrication and electrical properties of lead zirconate titanate thick films.** *J Am Ceram Soc* 1996, **79**:2189-2192.
 30. Trolor-McKinstry S, Aungkavattana P, Chu F, Lacey J, Maria JP, ●● Shepard JF, Su T, Xu F: **The impact of domains on the dielectric and electromechanical properties of ferroelectric thin films.** *Mater Res Soc Symp Proc* 1998, **493**:59-68.
- For thin PZT films, non-180° domain wall motion is limited, properties are lower than the bulk values. External stress has a modest effect on film properties.
31. Streiffer SK, Parker CB, Romanov AE, Lefevre MJ, Zhao L, Speck JS, Pompe W, Foster CM, Bai GR: **Domain patterns in epitaxial rhombohedral ferroelectric films. I. Geometry and experiments.** *J Appl Phys* 1998, **83**:2742-2753.
 32. Romanov AE, Lefevre MJ, Speck JS, Pompe W, Streiffer SK, Foster CM: **Domain patterns in epitaxial rhombohedral ferroelectric films. II. Interfacial defects and energetics.** *J Appl Phys* 1998, **83**:2742-2753.
 33. Pertsev NA, Zembilgotov AG, Tagantsev AK: **Effect of mechanical boundary conditions on phase diagrams of epitaxial ferroelectric thin films.** *Phys Rev Lett* 1998, **80**:1988-1991.
- It is shown that the free energy includes the effect of substrate constraint. A phase diagram was constructed for BST and PZT on the temperature-misfit strain plane. Only single domain films are allowed in the model; the constraint effect may be overestimated for polydomain films.
34. Pertsev NA, Arlt G, Zembilgotov AG: **Prediction of a giant dielectric anomaly in ultrathin polydomain ferroelectric epitaxial films.** *Phys Rev Lett* 1996, **76**:1364-1367.
 35. Pertsev NA, Emelyanov AY: **Domain-wall contribution to the piezoelectric response of epitaxial ferroelectric thin films.** *Appl Phys Lett* 1997, **71**:3646-3648.
- The elasticity problem is solved to analyze the motion of 90° domain walls in response to a small electric field. The domain wall motion contributes significantly to piezoelectric response.
36. Loge RE, Suo Z: **Nonequilibrium thermodynamics of ferroelectric domain evolution.** *Acta Mater* 1996, **44**:3429-3438.
 37. Suo Z: **Motions of microscopic surfaces in materials.** *Adv Appl Mechanics* 1997, **33**:193-294.
- Describes a method to simulate domain dynamics. The domain walls are treated as a sharp surface. The domain wall energy, electric energy and elastic energy are included.
38. Hu HL, Chen LQ: **Computer simulation of 90° ferroelectric domain formation and evolution.** *Mater Sci Eng A* 1997, **238**:182-189.
 39. Hu HL, Chen LQ: **Three-dimensional computer simulation of ferroelectric domain formation.** *J Am Ceram Soc* 1998, **81**:492-500.
- A time dependent Landau-Ginsburg model was used to simulate domain dynamics. The domain walls were treated by a gradient of polarization. Elastic and electric energy are included.
40. Fleck NA, Hutchinson JW: **Strain gradient plasticity.** *Adv Appl Mech* 1997, **33**:296-369.