

Laboratory Test Report

TechBond Industries - R&D Laboratory

Report Information

Field	Value
Report Number	LAB-2025-1547
Product	BondMax 500
Batch Number	TB-2025-1547
Production Date	October 5, 2025
Test Date	October 6-7, 2025
Laboratory	Dusseldorf R&D Center
Analyst	Dr. Maria Fischer

Batch Information

Parameter	Value
Batch Size	5,000 kg
Raw Material Lot	RM-2025-892
Production Line	Line 2
Operator	K. Schmidt

Test Results

Physical Properties

Test	Specification	Result	Status
Viscosity (25°C)	2,500-3,500 cP	2,980 cP	PASS

Density	1.05-1.10 g/cm ³	1.07 g/cm ³	PASS
Color	Light amber	Light amber	PASS
Clarity	Clear to slight haze	Clear	PASS
pH (water extract)	6.5-7.5	7.0	PASS

Mechanical Properties (Cured)

Test	Specification	Result	Status
Tensile Strength	> 15 MPa	18.2 MPa	PASS
Lap Shear (steel)	> 12 MPa	14.5 MPa	PASS
Elongation at Break	> 5%	6.8%	PASS
Shore D Hardness	75-85	79	PASS

Cure Properties

Test	Specification	Result	Status
Pot Life (100g, 25°C)	40-50 min	45 min	PASS
Handling Strength	< 6 hours	4.5 hours	PASS
Full Cure Time	< 24 hours	18 hours	PASS

Environmental Testing

Test	Specification	Result	Status
Heat Resistance (120°C, 500h)	> 90% strength	94%	PASS
Cold Resistance (-40°C)	No cracking	No cracking	PASS
Humidity (85°C/85% RH, 1000h)	> 85% strength	89%	PASS

Quality Assessment

Overall Status: APPROVED FOR RELEASE

All tested parameters meet or exceed product specifications. Batch is cleared for customer shipment.

Retention Samples

Sample ID	Location	Retention Period
TB-2025-1547-A	Lab Storage B, Shelf 12	24 months
TB-2025-1547-B	Lab Storage B, Shelf 12	24 months
TB-2025-1547-C	Lab Storage B, Shelf 12	24 months

Approvals

Role	Name	Signature	Date
Analyst	Dr. Maria Fischer	[Signed]	Oct 7, 2025
QA Manager	Stefan Braun	[Signed]	Oct 7, 2025
Lab Manager	Dr. Anna Schmidt	[Signed]	Oct 7, 2025

Certificate of Analysis available upon request Contact: lab@techbond.com