

Product Specification

Polymer Li-Ion Cell

3.8V 14000mAh 10C

(Model No.: SLPB9270175HV)



Shenzhen Melasta Battery Co.,Ltd

Hesheng Industrial Zone, Dalang, Longhua District, Shenzhen, 518109, China

Tel: +86-755-83693563

Fax: +86-755-28120114

E-mail: sales@melasta.com

Http://www.melasta.com

MELASTA

锂聚合物电池 LIPO BATTERIES

Sept 23rd, 2023

This information is generally descriptive only and is not intended to make or imply any representation, guarantee or warranty with respect to any cells and batteries. Cell and battery designs/specifications are subject to modification without notice. Contact MELASTA for the latest information.

Content

目录

1. 序言	3
Preface	
2. 型号: SLPB9270175HV	3
Model: SLPB9270175HV	
3. 产品规格	3
Specification	
4. 电芯性能检查及测试	4
Battery Cell Performance Criteria	
5. 贮存及其它事项	5
Storage and Others	
6. 聚合物锂离子充电电芯操作指示及注意事项	5- 8
Handling Precautions and Guideline	
6.1. 充电	5- 6
Charging	
6.2. 放电	6- 7
Discharging	
6.3. 贮存	7
Storage	
6.4. 电芯操作注意事项	7
Handling of Cells	
6.5. 电池外壳设计注意事项	7
Notice for Designing Battery Pack	
6.6. 电池与外壳组装注意事项	7-8
Notice for Assembling Battery Pack	
7. 其它事项	8-9
Others	

1. 序言 PREFACE

此规格书适用于深圳市风云电池有限公司的锂聚合物可充电电池产品


The specification is suitable for the performance of Lithium-Polymer (LIP) rechargeable battery produced by the SHENZHEN MELASTA BATTERY CO., LTD.

2. 型号 MODEL

SLPB9270175HV 14000mAh 10C 3.8V

3. 产品规格 SPECIFICATION

单颗电池规格 Specifications of single cell



◆电芯正极材料 Cell Cathode Material		LiCoO2
◆标称容量 Typical Capacity①		14000mAh
◆标称电压 Nominal Voltage		3.8V
◆ 充电条件 Charge Condition	最大电流 Max. Continuous charge Current	14A
	峰值充电 Peak charge current	21A(≤3sec)
	电压 Voltage	4.35V±0.03V
◆ 放电条件 Discharge Condition	Max Continuous Discharge Current	108A
	Peak Discharge Current	162A(≤4sec)
	Cut-off Voltage	3.0V
◆交流内阻 AC Impedance(mΩ)		≤1.5
◆循环寿命【充电:0.5C,放电:5C】 Cycle Life【CHA:0.5C,DCH:5C】		≥300cycles
◆使用温度 Operating Temp.	充电 Charge	0℃~45℃
	放电 Discharge	-20℃~60℃
◆ 电芯尺寸 Cell Dimensions	厚度 Thickness(T)	8.9±0.3mm
	宽度 Width(W)	69.0±1.0mm
	长度 Length(L)	173.0±1.0mm
	极耳间距 Distance between 2 tabs	32.0±1.5mm
◆ 极耳尺寸 Dimensions of Cell tabs	极耳材料 Tab Material	Nickel-plated Copper
	极耳宽度 Tab Width	18mm
	极耳厚度 Tab Thickness	0.2mm
	极耳长度 Tab Length	37.0±1.5mm
◆重量 Weight(g)		234±5g
①标称容量: 0.2C,4.35V~3.0V@23℃±2℃ Typical Capacity:0.2C,4.35V~3.0V@23℃±2℃		

4. 电芯性能检查及测试 BATTERY CELL PERFORMANCE CRITERIA

在进行下列各项测试前每颗电池应用 0.5C 放至 3.0V。如果没有特别规定，测试应在电池交付 1 个月内按以下各项条件进行：

Before proceed the following tests, the cells should be discharged at 0.5C to 3.0V cut off. Unless otherwise stated, tests should be done within one month of delivery under the following conditions:

环境温度 Ambient temperature: $20^{\circ}\text{C} \pm 5^{\circ}\text{C}$

相对湿度 Relative Humidity: $65 \pm 20\% \text{RH}$

注意标准充放电为 Note Standard Charge/Discharge Conditions:

充电 Charge: 以 0.5C 电流恒流充电至限制电压 4.35V 时,改为恒压充电,直到截止电流为 0.05C 时停止充电;The battery will be charged to 4.35V with 0.5C from constant current to constant voltage, when the current is 0.05C, stop to charge.;

放电 Discharge: 0.5C to 3.0V/cell

测试项目 Test	单位 Unit	规格 Specification	条件 Condition	备注 Remarks
容量 Capacity	mAh	≥ 14000	标准充放电 Standard Charge / Discharge	允许循环 3 次 Up to 3 cycles are allowed
开路电压 Open Circuit Voltage (OCV)	V	≥ 4.20	标准充电后 1 个小时内 Within 1 hr after standard charge	单位颗 Unit cell
内阻 Internal Impedance (IR)	m Ω	≤ 1.5	充满电后用 1kHz 测试 Upon fully charge at 1kHz	*
高倍率放电 High Rate Discharge (108A)	min	≥ 7.0	标准充电/休息 5 分钟 用 108A 放电至 3.0V Standard Charge/rest 5min discharge at 108A to 3.0V	允许循环 3 次 Up to 3 cycles are allowed
低温放电 Low Temperature Discharge	min	≥ 210	标准充电后贮藏在 $-20 \pm 2^{\circ}\text{C}$ 环境中 2 小时 然后用 0.2C 放电 Standard Charge, Storage: 2hrs at $-20 \pm 2^{\circ}\text{C}$ 0.2C discharge at $0 \pm 2^{\circ}\text{C}$	3.0V/cell Cut-off
自放电 Charge Reserve	min	$\geq 85\%$ (初始容量 First Capacity)	标准充满电后 20 度贮藏 30 天, 标准 0.5C 放电 Standard charge Storage at 20 degree: 30days Standard discharge (0.5C)	3.0V/cell Cut-off
寿命测试 Cycle Life Test	Cycle times	≥ 300	充电: 0.5C 充电至 4.35V, 放电, 5C 放电至 3.0V, 当放电容量降至初始容量的 80% 时, 所完成的 循环次数定义为该电芯的循环寿命 Charge: 0.5C to 4.35V, Discharge: 5C to 3.0V, 80% or more of 1 st cycle capacity at 5C discharge of Operation	Retention capacity 容量保持 $\geq 80\%$ of initial capacity

短路测试 External Short Circuit	N/A	不着火不爆炸 No Fire and No Explosion	标准充电后, 在 20℃±5 环境中用超过 0.75mm ² 金属丝将单颗电池短路至电池恢复到常温。 After standard charge, short-circuit the cell at 20℃±5℃ until the cell temperature returns to ambient temperature.(cross section of the wire or connector should be more than 0.75mm ²)	*
自由跌落测试 Free Falling(drop)	N/A	不着火不爆炸 No Fire and No Explosion	跌标准充电后, 搁置 2 小时。从 1.2M 高任意方向自由跌落 30MM 厚木板 3 次 Standard Charge,and then leave for 2hrs,check battery before / after drop Height: 1.2m Thickness of wooden board: 30mm Direction is not specified Test for 3 times	*

5. 贮存及其它事项 STORAGE AND OTHERS

5.1 环境温度 Ambient temperature: 20℃±5℃

相对湿度 Relative Humidity: 65±20%RH

5.2 请每隔 3 个月按下面方法激活电池一次:

Please activate the battery once every 3 months according to the following method:

0.2C 充电至 4.35V, 休息 5 分钟, 然后用 0.2C 放电至每颗电池 3.0V, 休息 5 分钟, 0.2C 充电 3.9V。

Charge at 0.2C to 4.35V, rest 5 min, then discharge with 0.2C to 3.0V/cell, rest 5 min, then charge at 0.2C to 3.9V.

6. 聚合物锂离子充电电芯操作指示及注意事项 HANDLING PRECAUTIONS AND GUIDLINE

声明一:

客户若需要将电芯用于超出文件规定以外的设备, 或在文件规定以外的使用条件下使用电芯, 应事先联系风云公司, 因为需要进行特定的实验测试以核实电芯在该使用条件下的性能及安全性。

Note(1):

The customer is requested to contact MELASTA in advance, if and when the customer needs other applications or operating conditions than those described in this document. Additional experimentation may be required to verify performance and safety under such conditions.

声明二:

对于在超出文件规定以外的条件下使用电芯而造成的任何意外事故, 风云公司概不负责

Note (2):

MELASTA will take no responsibility for any accident when the cell is used under other conditions than those described in this Document.

声明三:

如有必要, 风云公司会以书面形式告之客户有关正确操作使用电芯的改进措施。

MELASTA will inform, in a written form, the customer of improvement(s) regarding proper use and handing of the cell, if it is deemed necessary.

6.1. 充电 Charging

6.1.1 充电电流 Charging current:

充电电流不得超过本标准书中规定的最大充电电流。使用高于推荐值电流充电将可能引起电芯的充放电性能、机械性能和安全性能的问题, 并可能会导致发热或泄漏。

Charging current should be less than maximum charge current specified in the Product Specification.

Charging with higher current than recommended value may cause damage to cell electrical, mechanical and safety performance and could lead to heat generation or leakage.

6.1.2. 充电电压 Charging voltage:

充电电压不得超过本标准书中规定的额定电压 (4.35V/电芯)。4.38V 为充电电压最高极限, 充电器的设计应满足此条件; 电芯电压高于额定电压值时, 将可能引起电芯的充放电性能、机械性能和安全性能的问题, 可能会导致发热或泄漏。

Charging shall be done by voltage less than that specified in the Product Specification (4.35V/cell).

Charging beyond 4.38V, which is the absolute maximum voltage, must be strictly prohibited. The charger shall be designed to comply with this condition. It is very dangerous that charging with higher voltage than maximum voltage may cause damage to the cell electrical, mechanical safety performance and could lead to heat generation or leakage.

6.1.3. 充电温度 Charging temperature:

电芯必须在 0℃~45℃的环境温度范围内进行充电

The cell shall be charged within 0℃~45℃ range in the Product Specification.

6.1.4. 禁止反向充电 Prohibition of reverse charging:

正确连接电池的正负极, 严禁反向充电。若电池正负极接反, 将无法对电芯进行充电。同时, 反向充电会降低电芯的充放电性能、安全性, 并会导致发热、泄漏。

Reverse charging is prohibited. The cell shall be connected correctly. The polarity has to be confirmed before wiring. In case of the cell is connected improperly, the cell cannot be charged. Simultaneously, the reverse charging may cause damaging to the cell which may lead to degradation of cell performance and damage the cell safety, and could cause heat generation or leakage.

6.2. 放电 Discharging

6.2.1. 放电电流 Discharging current

放电电流不得超过本标准书规定的最大放电电流, 大电流放电会导致电芯容量剧减并导致过热。

The cell shall be discharged at less than the maximum discharge current specified in the Product Specification. High discharging current may reduce the discharging capacity significantly or cause over-heat.

6.2.2. 放电温度 Discharging temperature

电芯必须在-20℃~60℃的环境温度范围内进行放电。

The cell shall be discharged within -20℃~60℃ range specified in the Product Specification.

6.2.3. 过放电 Over-discharging:

需要注意的是, 在电芯长期未使用期间, 它可能会用其它自放电特性而处于某种过放电状态。为防止放电的发生, 电芯应定期充电, 将其电压维持在 3.6V 至 3.9V 之间。

过放电会导致电芯性能、电池功能的丧失。

充电器应有装置来防止电池放电至低于本标准书规定的截止电压。此外, 充电器还应有装置以防止重复充电, 步骤如下:

电池在快速充电之前, 应先以一小电流 (0.01C) 预充电 15~30 分钟, 以使 (每个) 电芯的电压达到 3V 以上, 再进行快速充电。可用一计时器来实现该预充电步骤。如果在预充电规定时间内, (个别) 电芯的电压仍未升到 3.0V 以上, 充电器应能够停止下一步快速充电, 并显示该电芯/电池正处于非正常状态。

It should be noted that the cell would be at over-discharged state by its self-discharge characteristics in case the cell is not used for long time. In order to prevent over-discharging, the cell shall be charged periodically to maintain between 3.6V and 3.9V.

Over-discharging may causes loss of cell performance, characteristics, or battery functions.

The charger shall be equipped with a device to prevent further discharging exceeding a cut-off voltage specified in the Product Specification. Also the charger shall be equipped with a device to control the recharging procedures as follows:

The cell battery pack shall start with a low current (0.01C) for 15-30 minutes, i.e.-charging, before rapid charging starts. The rapid charging shall be started after the (individual) cell voltage has been reached above 3V within 15-30 minutes that can be determined with the use of an appropriate timer for pre-charging. In case the (individual) cell voltage does not rise to 3V within the pre-charging time, then the charger shall have functions to stop further charging and display the cell/pack is at abnormal state.

6.3. 贮存 Storage:

电芯储存温度必须在 -10°C ~ 45°C 的范围内,长期存储电池(超过3个月)须置于温度为 $23\pm 5^{\circ}\text{C}$ 、湿度为 $65\pm 20\%\text{RH}$ 的环境中,贮存电压为3.6V~3.9V

The cell shall be stored within -10°C ~ 45°C range environmental condition, If the cell has to be stored for a long time (Over 3 months), the environmental condition should be; Temperature: $23\pm 5^{\circ}\text{C}$

Humidity: $65\pm 20\%\text{RH}$, The voltage for a long time storage shall be 3.6V~3.9V range.

6.4. 电芯操作注意事项 Handling of Cells:

由于电芯属于软包装,为保证电芯的性能不受损害,必须小心对电芯进行操作。

Since the battery is packed in soft package, to ensure its better performance, it's very important to carefully handle the battery;

6.4.1. 铝箔包装材料易被尖锐部件损伤, 诸如镍片, 尖针。

The soft aluminum packing foil is very easily damaged by sharp edge parts such as Ni-tabs, pins and needles.

- 禁止用尖锐部件碰撞电池;

Don't strike battery with any sharp edge parts;

- 取放电芯时, 请修剪指甲或戴上手套;

Trim your nail or wear glove before taking battery;

- 应清洁工作环境, 避免有尖锐物体存在;

Clean work table to make sure no any sharp particle;

6.4.2. 禁止弯折顶封边;

Don't bend or fold sealing edge;

6.4.3. 禁止打开或破坏折边;

Don't open or deform folding edge;

6.4.4. 禁止弯折极片;

Don't bend tab ;

6.4.5. 禁止坠落、冲击、弯折电芯;

Don't Fall, hit, bend battery body;

6.4.6. 任何时候禁止短路电芯, 它会导致电芯严重损坏;

Short circuit terminals of battery is strictly prohibited, it may damage battery;

6.5. 电池外壳设计 Notice Designing Battery Pack;

- 电池外壳应有足够的机械强度以保证其内部电芯免受机械撞击;

Battery pack should have sufficient strength and battery should be protected from mechanical shock;

·外壳内安装电芯的部位不应有锋利的边角;

No Sharp edge components should be inside the pack containing the battery;

6.6. 电芯与外壳组装注意事项 Notice for Assembling Battery Pack

6.6.1. 电芯的连接 Tab connection

建议使用超声波焊接或点焊技术来连接电芯与保护电路模块或其它部分。如使用手工锡焊, 须注意以下事项, 以保证电芯的功能:

Ultrasonic welding or spot welding is recommended to connect battery with PCM or other parts. If apply manual solder method to connect tab with PCM, below notice is very important to ensure battery performance.

a) 烙铁的温度可控能防静电;

The solder iron should be temperature controlled and ESD safe

b) 烙铁温度不能超过 350℃

Soldering temperature should not exceed 350℃

c) 锡焊时间不能超过 3 秒;

Soldering time should not be longer than 3s

d) 锡焊次数不能超过 5 次;

Soldering time should not exceed 5 times Keep battery tab cold down before next time soldering

e) 必须在极片冷却后再进行二次焊接; 禁止直接加热电芯, 高于 100℃会导致电芯损坏。

Directly heat cell body is strictly prohibited, Battery may be damaged by heat above approx. 100℃

6.6.2. 电芯的安装 Cell fixing

·应将电芯的宽面安装在外壳内;

The battery should be fixed to the battery pack by its large surface area

·电芯不得在壳内活动。

No cell movement in the battery pack should be allowed

7. 其它事项 OTHERS

7.1. 防止电池内短路 Prevention of short circuit within a battery pack

使用足够的绝缘材料对线路进行保护

Enough insulation layers between wiring and the cells shall be used to maintain extra safety protection.

7.2. 严禁拆卸电芯 Prohibition of disassembly

7.2.1. 拆卸电芯可能会导致内部短路, 进而引起鼓气、着火及其它问题

The disassembling may generate internal short circuit in the cell, which may cause gassing, firing, or other problems.

7.2.2. 聚合物锂电池理论上不存在流动的电解液, 但万一有电解液泄漏而接触到皮肤、眼睛或身体其它部位, 应立即用清水冲洗电解液并就医

LIP battery should not have liquid from electrolyte flowing, but in case the electrolyte come into contact with the skin, or eyes, physicians shall flush the electrolyte immediately with fresh water and medical advice is to be sought.

7.3. 在任何情况下, 不得燃烧电芯或将电芯投入火中, 否则会引起电芯燃烧, 这是非常危险的, 应绝对禁止

Never incinerate nor dispose the cells in fire. These may cause firing of the cells, which is very dangerous and is prohibited.

7.4 不得将电芯浸泡液体，如淡水、海水、饮料(果汁、咖啡)等

The cells shall never be soaked with liquids such as water, seawater drinks such as soft drinks, juices coffee or others.

7.5 更换电芯应由电芯供应商或设备供应商完成，用户不得自行更换

The battery replacement shall be done only by either cells supplier or device supplier and never be done by the user.

7.6 禁止使用已损坏的电芯 Prohibition of use of damaged cells

电芯在运输过程中可能因撞击等原因而损坏，若发现电芯有任何异常特征，如电芯塑料封边损坏，外壳破损，闻到电解液气体，电解液泄漏等，该电芯不得使用。

有电解液泄漏或散发电解液气味的电池应远离火源以避免着火。

The cells might be damaged during shipping by shock. If any abnormal features of the cells are found such as damages in a plastic envelop of the cell, deformation of the cell package, smelling of electrolyte, electrolyte leakage and others, the cells shall never be used any more.

The cells with a smell of the electrolyte or a leakage shall be placed away from fire to avoid firing.

Edition (版 本)	Description (记 述)	Prepared by (编 制)	Checked (审核)	Date (日 期)
A0	First Publish (首次编写)	沈阳	吴新伟	2023-09-23