

Best-achievable optical--tactile discrepancy by process and parameter

Surface-generation process

GLA: glass bead blasting	4.5	4.3	100	3.5	0.8	5.2	0.8
WEDM_R: rough wire EDM	1.2	1.8	100	2.6	1.6	0.3	1.8
HON: honing	4.3	2.2	100	4.2	3.8	1.2	2.5
WEDM_F: finish wire EDM	5.7	5.0	100	9.2	6.6	3.4	6.5
MF: finish milling	9.0	7.6	100	2.1	14.4	9.1	1.7
GRI: grinding	13.6	11.2	100	8.2	1.2	7.6	8.9
MR: rough milling	27.7	25.9	100	17.5	3.8	9.8	19.0
TF: finish face turning	13.0	11.8	100	25.4	4.1	16.3	24.2
TR: rough face turning	52.4	47.0	100	8.0	21.1	31.2	7.8
B: burnishing after MF	18.1	8.0	100	14.0	15.7	21.3	16.6
	Ra	Rq	Rsm	Rt	Rv	Rz	Rz1max

Roughness parameter

