Method Name: ME213_Tensile_Test_Slow Output Name: ME213_Tensile_Test_Slow

Width	Thickness	Area	Modulus	Ultimate Force	Ultimate Stress	Offset @ 0.2%	Offset @ 0.2%	TE (Auto)	
mm	mm	mm²	MPa	N	MPa	N	MPa	%	
6.33	1.29	8.17	823	3710	455	169	20.6	238	

