

Properties	Test Method	Property or attribute	Unit	Result
SURFACE QUALITY				
Surface Quality	EN 438-2.4	Spots, dirt and similar surface defects	mm2/m2	≤ 1
		Fibers, hair and scratches	mm/m2	≤ 10
DIMENSIONAL TOLERANCES				
Dimensional Tolerances	EN 438-2.5	Thickness tolerance	mm	± 0.10
	EN 438-2.6	Length and width	mm	+ 10 / 0
	EN 438-2.7	Straightness of edge	mm/m	≤ 1.5
	EN 438-2.8	Squareness	mm/m	≤ 1.5
	EN 438-2.9	Flatness	mm/m	≤ 60
GENERAL PROPERTIES				
Resistance to surface wear*	EN 438-2.10	Initial Point	Revolutions	≥ 100
Resistance to immersion in boiling water	EN 438-2.12	Appearance	Rating	≥ 4
Resistance to water vapor	EN 438-2.14	Appearance	Rating	≥ 4
Resistance to dry heat (180C)	EN 438-2.16	Appearance	Rating	≥ 4
Resistance to wet heat (100C)	EN 12721:1997	Appearance	Rating	≥ 4
Dimenionsional stability at high temperatures	EN 438-2.17	Cumulative dimensional change	Longitudinal %	≤ 0.55
		Cumulative dimensional change	Transversal %	≤ 1.05
Resistance to impact with small diameter ball	EN 438-2.20	Spring force	N	≥ 20
Resistance to impact with large diameter ball	EN 438-2.21	Drop height	mm	≥ 800
		Indentation diameter	mm	≤ 10
Resistance to cracking	EN 438-2.23	Appearance	Rating	≥ 4
Resistance to scratching	EN 438-2.25	Appearance	Rating	≥ 3
Resistance to staining	EN 438-2.26	Appearance - Group 1 and 2	Rating	≥ 5
		Appearance - Group 3	Rating	≥ 4
Light fastness (xenon-arc)	EN 438-2.27	Contrast	Grey scale rating	≥ 4
Electrostatic property	EN 61340-4-1	Surface electrical resistance: Point to point resistance Vertical resistance	ohms ohms	10 ⁹ ÷ 10 ¹¹ 10 ⁹ ÷ 10 ¹¹
Density	EN ISO 1183	Density	g/cm3	≥ 1.35
*with textured finishes, the surface wear resitance values may be 10 or more revolutions lower than the normal values in proportion to how the shape is accentuated				
REACTION TO FIRE				
Reaction to fire	EN 133501-1	Flame spread and smoke developed	Classification	Must be tested on substrate.

				Compact passes B-s1,d0
OTHER PROPERTIES				
Thermal resistance/ conductivity	EN 12664	Thermal resistance / conductivity	W/mK	0.2 to 0.5
Formaldehyde Emissions	EN 13986	Formaldehyde emission rating	rating	E1
Hygiene (Suitability for Food Service)	NSF	NSF/ANSI 35	pass/not pass	pass
VOC emissions	AFNOR NF EN ISO 16000-9	Individual VOCs	TLV	≤ 0.1
		Formaldehyde	ppm	≤ 0.025
		Total Aldehydes	ppm	≤ 0.05
		4-Phenylcyclohexene	mg/m3	≤ 0.0033
		Total respirable particles	mg/m3	≤ 0.025
		TVOC	mg/m ³	≤ 0,25
Contact with food - overall migration	EN 1186-3	3% acetic acid 24h @ 40C	mg/dm2	< 10
	EN 1186-3	50% ethanol 24h @ 40C		< 10
	EN 1186-14	95% ethanol 24h @ 40C		< 10
	EN 1186-14	isooctane 24h @ 40C		< 10
Contact with food - formaldehyde specific migration	EN 13130-23	3% acetic acid 24h @ 40C	mg/kg	< 15
Evaluation of micro-organisms action	EN ISO 846	Microbial growth - Textured finish	Rating	1 - slight and slow microbial growth