

TECHNICAL DATA SHEET

KODEX BTM 800

Latex Modified bituminous elastomeric waterproofing coating membrane

DESCRIPTION

Kodex BTM 800 is a liquid applied, latex modified bituminous elastomeric waterproofing membrane which, when fully cured, forms a permanently flexible waterproof lining to most building surfaces including reinforced concrete, block work, brick work and cement render.

Principal Characteristics:

- Single component, user friendly.
- Simple application – brush, roller or spray
- Excellent elasticity.
- Seamless
- Environmentally friendly
- Nontoxic water based
- Fast curing

Use Areas:

- Retaining Walls
- Planter Boxes



Packing:

- 2 Litre
- 15 Litre

Technical Information:

PROPERTIES	SPECIFICATION	RANGE
Nature and Type		Liquid & Viscous
Appearance		Brown when wet & Black after drying
Solid Content %	ASTM D 1644	55-60%
Water Resistant	ASTM D 870	No Blistering & Re emulsification
Drying Time (hrs)		3 – 4 hrs
Specific Gravity	ASTM D1475 – 13	0.99 – 1.05
Viscosity (cP)	ASTM D5125 – 10	30000 – 50000
pH of the Mix	ASTM D5125 – 10	8.0 – 10.0
Hardness (shore A)	ASTM D 2240 : 91	>50
Application Temperature		Between 05 – 30°C
Elongation at break%	ASTM D412 : 2002	>700%
Tensile Strength (N/mm ²)	ASTM D412 : 2002	1.1 N/mm ²
Brushability		No sag, Slip & Run off
Peel Adhesion to concrete N/mm ²		1.6

Substrate Preparation:

Concrete must be cured for a minimum of 28 days and render 7 days. Remove dirt, dust, loose particles, oil and unsound concrete etc. Water blast if necessary. Surface must be dry. Fill holes and open joints in block work or concrete prior to application of membrane.

Priming:

Kodex BTM 800 is self-priming when used on most surfaces e.g. Sound concrete, block work. Surfaces may be primed with Kodex BTM 800 thinned with 50% water or with DUROTECH AR SEALER. Areas subject to rising damp should be first sealed with an epoxy coating, such as Kodex Moisture Seal.

Bond Breaker:

Apply a bead of Kodex Neutral-cure silicone to the following areas:-Wall / footing junction where movement is expected and expansion joints, generally to all areas where movement is likely to occur.

Reinforcement:

A reinforcing fabric such as 140-200mm wide polyester bandage should be used over the following areas:- expansion joints, cracks, footing / floor to wall junctions, around floor/wall penetrations, and any other area movement will occur. Reinforcement is also required over construction joints in walls.

Application:

Reinforced: To the prepared surface apply a heavy coat of Koex BTM 800 by brush or roller at approximately 2m²/litre. Immediately lay the reinforcing fabric into the wet surface, then apply another coat and work in carefully by brush or roller to saturate the fabric. When dry apply one or more coats to give a fully waterproof lining. Ensure a minimum coverage of 1.6 litres/m². When dry, check for pinholes or misses and recoat if necessary.

Un-Reinforced: To areas where a reinforcing fabric is not utilised apply 3 coats of Kodex BTM 800 at a total rate of 1.8 litres/m² ensuring full coverage, by brush, roller or spray (use 21 thou Min tip size + airless spray).

Porous Surfaces (Masonry): May require 3 coats to obtain a satisfactory dry film thickness.

Precautions:

Do not apply above 30°C or below 10°C ambient temperature. Be sure coating will cure before contact with water. Wash equipment with water before dry. Protect Kodex BTM 800 from extended sunlight exposure. Planter box membrane must be fully cured before being subject to moisture or soil. Protect membrane against damage before and during backfilling or covering. Kodex protection board may be used where suitable. Use an approved drainage system and protection board in planter boxes and retaining walls before filling to protect membrane from any damage. Do not expose to solvents.

Clean Up:

Clean up with water before dry.

***Disclaimer:** The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contract the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Kodex term and conditions of sale apply.*