

TECHNICAL DATA SHEET

KODEX UTM 400

WATERBORNE ACRYLIC RESIN BASED WATERPROOFING MEMBRANE FOR UNDER-TILE, AND PROTECTED APPLICATION

DESCRIPTION

Kodex UTM 400 is a tough, ready to use waterproofing membrane specifically designed for use under the tiles. Kodex UTM 400 has been uniquely formulated with acrylic emulsion, additives as well as high quality filler and pigment to increase its waterproofing performance. Kodex UTM 400 is based on the most advanced thermosetting acrylic emulsion technology, and is totally resistant to re-emulsification once cured. It fully complies with the test requirements of ASTM as well as AS:4858-2004 and AS:3740:2004 "Waterproofing of Wet Areas within residential building.

PRINCIPAL CHARACTERISTICS

- Single component
- Water based
- Excellent water resistance
- High Solids Ease of application – brush / roller
- Tenacious bond Suitable for most substrates
- High tensile film strength & elongation
- Does not bleed or leach Extremely low VOC

Use Areas:

- Internal Wet Areas and Shower Recesses
- External Balconies and Decks Tanking
- Roofs - topcoat with Kodex KODCOAT EXP resistance coating.

Packing:

- 15 Litres
- 2 Litres

Technical Information:

PROPERTIES	SPECIFICATION	RANGE
Appearance		Viscous Liquid
Colour		White, Gray, terracotta & Green
Solid Content%	ASTM D1353-13	68-70
pH	ASTM D1293 - 18	08 to 10
Viscosity	ASTM D5125- 10	Above 50K cP
Specific Gravity	ASTM D789	1.34-1.36
Drying Time	ASTM D1640	3-4 hrs
Hardness (Shore A)	ASTM D2240: 2002	65-70
Tensile Strength, (N/mm ²)	ASTM D412 : 2002	1.8-2.0
Elongation at Break, (%)	ASTM D412 : 2002	350-400
Adhesion Strength, (N/mm ²)	ASTM D4541 : 2002	0.7-0.8
Algae & Fungus Resistant	D-2574 & D3273	No algae & fungus Growth
Crack Bridging	ASTM C836: 1995	a) No cracks up to 2 mm width b) No cracks up to 1 mm (10 cycles)

METHOD OF APPLICATION

1. Surface Preparation

Ensure wall and floor lining sheets are firmly fixed to manufacturer's directions. Surfaces must be free of dirt, dust, loose particles, oil, contaminants and curing compounds etc. Concrete must be a minimum strength of 20MPa and have cured a minimum of 28 days. Surfaces must be dry. Fill all screw holes, cracks and voids with neutral-cure silicone sealant. Install leak control flanges to all pipe penetrations.

2. Application

Dilute Kodex Kodseal with 1:2 ratio with water. this dilution will cover 7 to 8 sq.mt. allow it to dry for 6 to 8 hrs. Apply the first coat of UTM-400 without any dilution at the rate of 1 m² per liter and Keep it to dry before applying the second coat, the rate of application being the same. Do not apply above 40°C or below 5°C.

3. Flood Test & Tiling

A flood test may be carried out after 72 hours of drying at 25°C and 50% R.H.. Apply water to a depth of 25mm for approximately 2 hours. Kodex UTM-400 may be tiled over after 3-4 days, using a quality cement based tile adhesive installed as per AS 3958.1.

Coverage – 1m² per liter per coat with 1mm wet thickness.

SHELF LIFE & STORAGE

shelf life is 12 months from the date of manufacturing in unopened condition. Store in a cool & dry place. Keep away from direct Sunlight.

HEALTH & SAFETY PRECAUTIONS

Skin Contact: Wash skin with soap & water.

Remove contaminated clothes.

On eye contact: immediately splash eyes with plenty of water.

Consult Physician if irritation persists.

Ingestion: Do not induce vomiting.

Never give anything by mouth to an unconscious person.

***Disclaimer:** The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contract the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Kodex term and conditions of sale apply.*