PRODUCT DATA SHEET

DUROTITE RAPID SBR BLUE

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Durotite Rapid SBR Blue is a Class 3 fast curing water-based and micro- fibre reinforced SBR based waterproofing membrane which provides excellent flexibility and crack bridging capability. It is a 2-coat system, to be applied over primed "porous and non-porous" substrates for internal and external under tile applications.

FEATURES AND BENEFITS

- Fast drying. Recoat in 2 hours @ 22° C & 50% RH
- Flood test after 24 hours @ 22°C & 50% RH
- Can be tiled over after 4-6 hours @ 22°C & 50% RH in non-critical areas
- Class III, high elasticity as per AS/NZS 4858 Wet Area Membranes
- Water-based, pre-mixed -ready and easy to use and easy clean up
- Environmentally friendly – LOW VOC and free of respirable silica
- For commercial and residential internal/external wet areas, balconies, decks and other areas that will be tiled over

USES

- As a waterproofing membrane under tile to internal wet area shower, bathroom, kitchen, laundry and toilet areas when installed according to AS/NZ 3740
- As a waterproofing membrane under tile to external balconies, rooftops & podium levels when installed to AS/NZ 4654.2
- Suitable for concrete; cement rendered masonry; FC sheeting; water resistant plasterboard; and structural plywood (Type A Stamped "PAA JAS-ANZ" to AS/NZS 2269- 2004) substrates

TYPICAL PHYSICAL PROPERTIES

Appearance	Heavy thick and high viscous liquid membrane
Odour	mild
Solid content (weight)	69%
Solid content (volume)	60%
Density	1.30 kg/li
Dry to handle per coat (@22°C / 50% RH)	60 min
Recoat time per coat (@22°C / 50% RH)	2 -3 hours
VOC (calculated)	3.44 g/l
Shore "A" hardness	Approx. 60
Elongation	300%
Tensile Strength	≥ 1.0 MPa
Membrane Rating	Class 3
Flammability	Non-flammable

LIMITATIONS

- Not to be used directly to impervious or non-porous substrates.
- Not suitable for permanent immersed conditions such as pools, spas, and ponds.
- Cannot be used as exposed trafficable exterior membrane.
- Cannot be applied over damp or wet substrates.
- Not suitable for negative head of water pressure

SINCE 1977

PACKAGING

Available in a 4L, 15L pail

COLOURS

Blue

PRODUCT INFORMATION

Coverage

Coverage rate will depend on the porosity of the substrate. Two coats are recommended to get the optimum performance

For floors:
A minimum dry film thickness of 1 mm after 2 coats is required. 15 litres will cover 9 sq. meter (based on two coats)

For walls:
A minimum dry film thickness of 0.6 mm after 2 coats is required. 15 Litres pail will cover approximately 15 sq. m (based on two coats).

Shelf Life

Approximately 12 months in unopened containers stored in a cool, dry place

SURFACE PREPARATION

- Surfaces must be clean, dry and free from voids, laitance, grease, oil, wax, curing compounds, coatings, adhesive residues or any loose contaminating material.
- New Concrete substrates and render must have a wood float finish and be allowed to cure for a minimum of 28 days. Concrete substrates must not contain moisture greater than 4.5%. Use Tramex CME 4 Moisture Meter. Additional concrete testing maybe be required depending on concrete construction and jobsite location. 2 coats of 2K Moisture barrier primer must be used to seal concrete slabs subject to a hydrostatic head of pressure from the negative side. Moisture Barrier primer must be clean, dry and smooth immediately prior to membrane application
- Sand & cement screeds and polymer modified renders must have cured for a minimum 7 days.
- A High alkaline resistant primer/sealer is recommended to prime over screed prior to membrane application.
- A reactive mineral primer/sealer must be applied as a primer coat on all applications to porous or semi porous cementitious substrates.
- Glazed ceramic tiles, Dry rigid plastic & metallic non-porous substrates shall be lightly abraded and then cleaned. Non-Porous Substrates primer must be applied as primer coat/

Membranes should not be applied until substrates suitability has been assessed and all preparation steps have been completed.

MIX PREPARATION

It is a premix product and ready to use.
However, if products have been stored longer, condensation may occur. Stir contents thoroughly before and during use.

APPLICATION

Apply membrane according to the recommended coverage rate with paintbrush or roller. Allow the first coat to dry for a minimum of 2 hours and a maximum of 6 hours, at temperatures of 22°C and above but below 35°C before recoating. Longer drying times will be required at lower temperatures. Drying times will vary depending on humidity, surface temperature and porosity of substrates.

CLEAN-UP & RETURN TO SERVICE

Water can be used to clean up excess product, spills and tools while product is wet. When fully cured, tools and spills can be only removed mechanically.

HEALTH & SAFETY PRECAUTIONS

- Durotite Rapid SBR Blue is a non-hazardous and non-dangerous product.
- The Safety Data Sheet (SDS) must be read and understood prior to use.

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©
ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet