PRODUCT DATA SHEET

# DUROMASTIC ACS

COMPLIES TO AS/NZS4858: 2004 - CLASS III MEMBRANE

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

## DESCRIPTION

**DURO MASTIC ACS** is a liquid applied acrylic membrane which, when fully cured, forms a flexible waterproof lining for showers and other wet areas described in Australian Standard AS3740:2004 "Waterproofing of wet areas within residential buildings" and AS4858:2004 "Wet Area Membranes"

**DURO MASTIC™ ACS** forms a waterproof lining to most building materials including reinforced concrete, cement render, water resistant plasterboard and fibre cement sheet flooring etc. The surface must be firmly fixed to manufacturers directions, free of protrusions, dirt, oil and other contaminants and surface must be dry.

## FEATURES

- Simple application - single pack, water based
- Good flexibility
- Seamless, no joins.
- Environmentally friendly
- Non toxic

## USE AREA

- Shower tray and wet areas
- Decks and balconies

## PACKAGING

- 15 Litre White & Grey
- 10 Litre White & Grey
- 4 Litre White only

## TECHNICAL INFORMATION

| | |
|---|---|
| **Colour** | Grey or Green |
| **Weather Resistance** | Good |
| **Dry Time** | 2-4 hours @ 25°C |
| **Recoat Time** | 4-6 hours @ 25°C |
| **Coverage** | Min 2 Coats, each @1 litre/m² |
| **Elongation** | Over 300% |
| **Moisture Vapour Transfer** | 1.55g / m² / 24hr |
| **Shelf Life** | 12 months in unopened containers @ 20°C |

## CLEAN UP

- Clean up with fresh water before dry.



SINCE 1977



## APPLICATION

**NOTE:** Floor wastes in concrete should be cut to floor level with no up-stands. For sheet flooring, leak control flanges should be fitted and be recessed, flush with the substrate. All PVC fittings, shall be etch primed.

**STEP 1 :**STEP Remove all dirt, dust, plaster droppings, protrusions, oil and contaminants. Fill screw holes with Neutral Cure Silicone. All sheet joints should be filled with Neutral Cure Silicone.

**STEP 2 :** All wall/floor junctions, wall/wall junctions and all hob junctions, apply 12mm neutral-cure silicone* sealant as a bond breaker/slip joint. Vertical joints should extend 75-100mm from floor and to 1.8m high in showers. Apply sealant around floor penetrations, tap flanges and other protrusions. For all floor joints up to 5mm wide install bond breaker tape greater than 12mm or Neutral Cure Silicone.

**STEP 3:** Concrete Render, CFC, timber and Plaster board.
Prime internal substrates with DUROTECH ARW Sealer.
Prime external substrates with DUROTECH AR Sealer, DUROMIX™ WBE, for damp surfaces at the rate of 3 - 4 m²/Ltr.

**STEP 4:** To the prepared surface apply a heavy coat of DURO MASTIC™ ACS by brush or roller at approx 0.5-1 litre/m². Immediately lay the matting into the wet surface, then apply another coat and work in carefully by brush or roller to saturate the matting. Completely saturate the matting ensuring no misses. Excessive application of DURO MASTIC™ ACS will greatly reduce drying time. Apply sufficient coats for overall DFT of 1mm.

**Reinforcement:**
Use 225gsm fiberglass and/or equivalent synthetic reinforcement as follows. Use reinforcement to total floor area and bandage floor joints, wall/floor junction, wall/wall junctions and shower hobs. Ensure the membrane is dressed down into the floor waste or well sealed around the leak control flange and also ensure membrane is turned up around penetrations.

**STEP 5** : When dry apply one or more coats to give a fully waterproof lining. Apply one heavy coat to the walls above shower tray to finish 50mm above the shower rose.

When dry check for pin holes or misses and rectify if necessary.

## APPLICATION RATES

| Use Area | Dry Film Thickness |
|---|---|
| **Wet Area Walls** | 0.6mm |
| **Wet Area Floors** | 1.0mm |
| **External Areas** | 1.2mm |

## FLOOD TEST & TILING

A flood test may be carried out after 72 hours of drying, @25°C, 50% R.H. Water shall cover to a depth of 25mm for approximately 2 hours.

DURO MASTIC™ ACS may be tiled over after 3-4 days @25°C, 50% R.H., using a quality cement based tile adhesive installed as per AS 3958.1.

## PRECAUTIONS

Do not apply above 30°C or below 10°C. Wash equipment with water before dry. Do not fix tiles until fully cured. Areas subject to rising damp should be first sealed with an epoxy coating, i.e. DUROMIX™ WBE. Protect membrane against damage before and during tiling. Tile over external compressed cement sheeting within 4 weeks. When tiling over external membrane surfaces ensure full allowance is made for expansion and contraction which may damage the membrane.

Do not expose to solvents.



*"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."*

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet