PRODUCT DATA SHEET

DUROTECH BITUMEN PRIMER

Solvent based bituminous primer

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Durotech Bitumen Primer is a primer for bituminous waterproofing materials such as prefabricated and liquid membranes and hot bitumen. The product consists of bitumen in solution, with solvents regenerated by distillation, fast drying and adheres to any surface. Durotech Bitumen Primer may also be used to protect ferrous materials such as scaffolding, tanks, pipes, structures etc.

COLOURS AVAILABLE

Black

PACKAGING

5 Litre, 10 Litre & 20 Litre

STORAGE TEMPERATURE

MIN –5° C – MAX 40° C

STABILITY IN THE ORIGINAL PACKAGE

24 months

TECHNICAL INFORMATION

CHARACTERISTICS	VALUE	TOLERANCE	U.M.
Specific weight	0.9	± 0,1	Kg/dm^3
Dry mass residue at 130° C	41	± 2	%
Viscosity (with Ford cup, hole n. 4)	15	± 2	Sec
Viscosity DIN/4 at 20° C	15	± 2	Sec
Closed cup flashpoint	<21		° C
Auto-flammability	>200		° C
pH at 20° C	Neutral		
Water volume %	<0,5		
Viscosity at 25° C	25 Sec		
Penetration	10-20	dmm	

Durotech Bitumen Primer is conforming to ASTM D41-05 “Type 1”: Asphalt primer with a generally higher solvent-toasphalt ratio.

APPLICATION INSTRUCTIONS

TOOLS	THINNING	TYPE OF THINNER	TOOL CLEANING
Brush	Ready to use		DIL S1
Roller	Ready to use		DIL S1
Spray	Ready to use	DIL S1	DIL S1

SINCE 1977

LAYING SURFACE

Ensure that the deck is clean and dry removing all traces of dirt, grease and loose parts, if necessary, repair excessive roughness and ensure sufficient slope to ensure rainwater runoff.

CONSUMPTION

Coverage depends on the absorbing properties of the deck. Generally about 200 ml/sqm for cement surfaces.

APPLICATION INSTRUCTIONS

Temperature limit during application: MIN 5°C - MAX 40°C. When applying the product indoors use appropriate breathing equipment.

DRYING AT 23° C AND 50% U.R.

On surface: 30 – 60'
At touch: 100' – 140'
Intrval beetween coatings: 3 h

The times shown are for standard laboratory conditions. The drying times are strongly fluenced by the weather; high temperatures and direct sunlight accelerate drying; shadows, low temperatures and high humidity levels delay drying. In winter the product should be laid in the warmer hours in the middle of the day. Always ensure that the previous layer has cured properly before applying a new coating.

CHARACTERISTICS OF THE DRY PRODUCT

CHARACTERISTICS	VALUE	UM
Frass brittle point of oxidized bitumen	- 10	° C
Dow penetration at 25 °C of bitumen	10 – 20	Dmm
PA Softening Point of bitumen	90 – 100	° C

Durotech Industries Pty Ltd

Address 14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone +61 2 9603 1177
Fax +61 2 9475 5059
Email sales@durotechindustries.com.au
Web www.durotechindustries.com.au



"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 1400 FC Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet