DUROTECH

DUROMASTIC POLYTC

Tintable Exterior Membrane coating for facades, walls, fascias & balconies

DuroMastic PolyTC is a siloxane modified acrylic waterproof and UV resistant liquid membrane. The acrylic system is based on materials with years of proven use. The product is used either for long-term facade waterproofing or as an architectural decorative coating. It can also be used as a protective coating over mineral chip bitumen membranes and PPM. It is highly resistant to weathering, fungi and algae. Although the membrane is waterproof it allows the substrate to breathe, reducing the risk of blistering.



PRINCIPLE CHARACTERISTICS

- UV stable, weather resistant
- Water-based, non hazardous
- Protects against damage by UV, CO_2, water and chlorides
- Tintable to 100's of colours in flat & low sheen
- Permanently flexible, with low dirt pickup
- Application by brush, roller and airless spray
- Good crack bridging capability
- Mould, fungi, bacteria and algae resistant
- Environmentally friendly, low odour and VOC compliant.
- Easily maintained and repaired
- Suitable for light to moderate traffic area.
- Excellent adhesion to concrete, fibrous cement, timber, water based paints, aged gal. PVC, timber, colorbond, aged alkyd, bitumen

USE AREA

- Concrete, brick, blockwork and render walls, parapets, balconies and facades
- Bitumen roof top coating
- As topcoat of PPM
- As a colour topcoat for Duroroof, Duromastic AC

PACKAGING

- 15 Litre
- 4 Litre

TECHNICAL INFORMATION

Colour	Can be easily tinted to 100's of colours in low sheen & flat finishes.
Dry Time	Touch dry 1-2 hours @ 25ºC
Recoat	4-6 hours @ 25ºC
Coverage	Façade membrane – min. 2 coats, total 1.0 sq. m../ litre at 0.5mm DFT Coating – 1- 2 coats, total 2 - 4 sq. m. / litre at 0.13 - 0.25 mm DFT.
Elongation at Break:	>300% at 25°C
Tensile Strength:	> 1.7MPa, white

Solids Content	58-61%, white
Water vapour permeability, SD	Class II (medium 0.14-1.4 m), ISO 7783-2
Water absorption, W24	<0.1 kg/m2 h 0.5 Class III (low), ISO 1062-3
VOC	40 grams/litre, SCAQMD Method 304-91
Shelf Life	min. 12 months, unopened and stored @ 20°C

PREPARATION

All surfaces shall be sound, clean, dry and free of release curing agents, laitance, efflorescence, oils, bird droppings, mould, algae and other contaminants. Check adhesion by applying to a test area. Concrete, blockwork and cement render should be at least 28 days old, dry and free of voids and other surface defects. Make sure painted surfaces are sound and remove any chalking by pressure spray and/or a 'sugar soap' detergent wash. For mould, fungi and algae affected areas pressure spray and then treat with Duroprep Antifungal Concentrate to destroy fungal spores and algae remains.

PRIMING

Prime absorbent surfaces with Durotech ARW. For weakly bound chalky surfaces that require strengthening, prime with Durotech AR. Treat rusted metal with Durotech ZR (refer to TDS) . Treat the top of cement rendered parapet and balcony walls with Durotech AR or Duromix™ Hibuild WBE .

For surfaces that are extensively cracked but still adhering well, Duroroof may be applied as a basecoat. Alternatively, incorporate Durotech polyester reinforcing fabric. For substrates suspected of damp, apply Duromix™ Hibuild WBE, but seek technical advice first.

PRIMING

Do not dilute with water. For spray application the recommended system is an airless spray system using a piston pump. The recommended spray tip is a 19 to 21 thou (thousands of an inch) fan type. The pump can be electric or driven by compressed air, and needs to produce a pressure of about 3000 psi.

For joints subject to movement, seal with Durotech PU sealant. Contact Durotech beforehand for technical details. To reinforce joints, apply a first coat of DUROARMOR by brush or roller to about a metre length of the prepared and sealed joint. Immediately lay 150mm to 200mm wide reinforcing fabric into the wet surface. Then apply another coat and work in carefully in one direction by brush or roller to saturate the fabric, before moving onto the next section of the joint.

To apply as a decorative colour coat over waterproofing roof membranes such as Duroroof, apply 1 coat at 3-4m²/litre. To seal and protect slate chip bitumen roof membranes, apply at 2m²/litre. As a topcoat of PPM, must apply DuroMastic PolyTC within 24-36 hours of PPM drying at room temperature.

PRECAUTIONS

Do not apply Duromastic PolyTC below 10°C ambient or above 30°C or in hot windy conditions, or if rain is likely within 6 hours. In summer apply in the cooler part of the day. Be sure coating is cured before contact with water. Wash equipment with water before dry. Do not expose to solvents. Clean periodically to maintain surface and re-coat when necessary.

CLEANUP Use fresh water before material has set. Soften cured material with mineral turps.

SAFETY Avoid breathing vapours and contact with skin and eyes. FIRST AID: In case of contact rinse immediately with plenty of water . SPILLS: Contain spill and prevent entry into to waterways. Refer to Durotech Safety Datasheet before use.

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.