PRODUCT DATA SHEET

DURO CETSEAL

SEALANT / ADHESIVE

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Duro CETSEAL is a multi-purpose, single component polyether moisture cure sealant/adhesive. Duro CETSEAL is a low VOC, 100% solids, nonshrinking product with excellent UV resistance.

APPLICATIONS

- Grade termination sealant
- Membrane lap sealant
- Waterstop adhesive

INSTALLATION

Grade Termination Sealant: At grade termination of waterprooing membrane, apply continuous tooled bead of Duro CETSEAL along the top edge of the termination bar that covers and seals the top edge of the waterprooing membrane to the substrate.

Membrane Lap Sealant: Apply a bead of Duro CETSEAL in accordance with waterprooing membrane installation guidelines.

Waterstop Adhesive: Apply a continuous bead of Duro CETSEAL to substrate and/ or waterstop then install waterstop before Duro CETSEAL skins over. Yield will vary with use, substrate and application. Typical yield at 6 mm (1/4") diameter bead: 300 ml (10 oz) cartridge - 6 m (20 linear feet) 600 ml (20 oz) foil pack - 12 m (40 linear feet)

INSTALLATION

Remove all dirt and debris, surface coatings and sealers before application. Prepare metal by removing rust, scale and oil residue. Allow treated lumber to cure for six months prior to application. Do not apply in standing water conditions or at temperature below -4°C (25°F)

PACKAGING

300 ml (10 oz) cartridges - 12 cartridges per case. Typical weight per case: 5.4 kg (12 lbs) 600 ml (20 oz) foil packs - 12 foil packs per case. Typical weight per case: 9 kg (20 lbs)

TYPICAL UNCURED PROPERTIES

Gun Grade	Zero Slump ASTM C 697
Viscosity	750,000+ cps Brookield RVF, TF spindle, 4 RPM, 23° C (73° F)
Initial Skin Formation	10-15 minutes
Odor	Almost odorless

TYPICAL CURED PROPERTIES

Elongation at Break	ASTM D412	600%
Hardness Shore A	ASTM C661	20 +/- 3
Low Temperature Flex	ASTM D816	-10°C (-23°F)
Shrinkage		No measurable shrinkage after 14 days
Service Temperature		-40°C to 90°C (-40°F to 194°F)
Shelf Life		1 year

DUROTECH INDUSTRIES

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System
ISO 14001 Environment Certified System
ISO 45001 Health and Safety Certified System