PRODUCT DATA SHEET

DURO GLAZE EPOXY

100% Solids, VOE Free, Clear Resin

DUROTECH
Epoxy Flooring Systems

DESCRIPTION

DURO Glaze Epoxy is an 100% solids, two-part system. It is a clear gloss system. Gloss level is above 80.It can be used as a coating or self-levelling system Formulated for use in a wide range of environments, from heavy industrial to residential applications, DURO Glaze can provide a lasting solution with exceptional resistance to chemicals.It can also give non slip performance when used with Non slip additives.

FEATURES

- High Gloss
- Excellent Adhesion
- Self-Levelling
- No VOC's (Volatile Organic Compounds)
- Low Viscosity.
- Excellent Abrasion Resistance
- Excellent Chemical Resistance
- High Durability
- Water Clear
- Solvent Free
- Waterproof

USE AREAS

- Automobile Workshops
- Factories and Manufacturing Facilities
- Warehouses
- Loading Bays and Ramps
- Car Parks
- Food Processing Plants
- Chemical and Pharmaceutical Industries
- Laboratories
- Washrooms and Cloakrooms
- Wet and Dry Processing Areas
- Government and Education Facilities
- Residential Properties

Product Information

Pot Life	1 hour at 25°C
Shelf Life	2 years. Store in a cool, dry area and out of direct sunlight
Mixing Ratio	(2:1) 2 (Part A) : 1 (Part B)
Coverage	6m²/L depending on the method of application and porosity of the surface.
Heat Resistance	Continuous service 6°C
Clean Up	Clean tools with Xylene while still wet and discard rollers and brushes
Return to Service	**Light Foot Traffic**: 24 hours after completion of the job. **Full Chemical Cure:** 7 days after the completion of the job

Physical Properties

Solids content	100 %
Finish	Clear, Gloss
Impact Strength	High
Compressive Strength	Above 60 Mpai
Tensile Strength	Above 10 Mpa
Elongation at Break	7.00%

AUSTRALIAN MADE SINCE 1977

SINCE 1977 Trialled • Tested • Approved

SURFACE PREPARATION

Diamond Grind or Polyvac the substrate. Surfaces must be clean, dry and free from all traces of loose material, old coatings, curing compounds, release agents, laitance, oil and greases etc. Substrate compressive strength should be at least 25MPa, cohesive bond strength at least 1.5MPa and moisture content below 4%.

Structurally unsound layers and surface contaminants must be mechanically removed by grinding or other methods. Substrates heavily impregnated with oil must be cleaned by grinding or suitable solvent cleaning methods. To check that all traces of oil have been completely removed, sprinkle a few drops of water over the surface. If all water is quickly absorbed, the surface is sufficiently oil and grease free. Cleaning methods are to be repeated if the water is pooling on the surface.

Repair and fill cracks with DURO Crack Filler epoxy.

PRODUCT APPLICATION

Mix 2 Parts A with 1 Part B (2:1) by volume. Mix with a drill mixer at a slow speed for 2 minutes. Ensure the sides and bottom of the container/bucket are mixed. Tilt the drill to the side to ensure the product on top of the container/bucket is mixing in with the product on the bottom. In normal curing conditions, the DURO Glaze Coating Kit does not require an induction time and coating can begin immediately after mixing. For colder climates, see product cautions for further information on mixing and induction times.

For system specific instructions, consult the All Purpose Coatings Installation Instruction documentation, located on the website.

It is recommended that the first coat of DURO Glazebe applied with up to 10% Epoxy Thinners to ensure high penetration and adhesion to the coating substrate. Subsequent coats can be thinned but, a sufficient curing time will be required to allow the solvent content to evaporate from the product before re-coating or top coating when used as part of an All Purpose Coatings system. The re-coat time is typically, 12-24 hours at 25°C. Apply using a brush or lint free roller.

If recoating after 72 hours a light sand will be required to ensure adhesion of any following coats.

Without exceeding 4mm, apply thicker coats using a squeegee or notched trowel and let the product self-level.

CAUTION

- When used as a self-levelling floor coating, DURO Glaze will not profile irregular substrates. For the profiling of defects on horizontal surfaces a suitable patching or repair mortar will be required. The patching or repair mortar can be of either epoxy or cementitious base depending on the scope & particular condition of the project.
- Thoroughly mix Part A and Part B using a powered drill with a paint mixing attachment for 2 minutes. Ensure that all materials on the sides and on the mixer are combined thoroughly to avoid hot spots in the coating that may never cure on application.
- The mix ratio is calculated by product volume. NOT BY PRODUCT WEIGHT. Mixing product by weight may result in an unsatisfactory cure time or failure of the mix to cure entirely.
- To achieve optimum results in colder climates, you may need to warm the resin or introduce an induction time before application. This will jump start the curing process. For further information, consult All Purpose Coatings technical advisers.
- Exposure to sunlight and UV radiation can result in discoloration and chalking of the cured surface.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet