DUROTECH

DURO TORCH GREEN ROOF

APP COMPOUND HIGH STRENGTH POLYESTER

Duro Torch Green Roof is a bituminous plastomeric torch on waterproofing sheet membrane. It is manufactured from a compound based on a selected distilled bitumen modified with a tactic polypropylene (APP), anti-root additives and reinforced with a high strength non-woven polyester fabric. The combination of a high performance polymer bitumen and high strength polyester reinforcement provides a durable solution ensuring

GUARANTEED QUALITY

The Duro Torch range is manufactured under ISO 9001 Total Quality guidelines.

USES

Duro Torch Green Roof exhibits both excellent dimensional and mechanical stability, making it particularly suitable for waterproofing civil, industrial and residential building projects. Limited land resources and expensive energy costs have contributed to creating the need for green roofs. Green roofs provide excellent insulation, reduce noise transmission and improve air quality .

APPLICATION

The underside of Duro Torch Green Roof is finished with a thermofusible film. This melts upon torching ensuring a clean application. Surfaces to be waterproofed should be dry, clean and free from protrusions. All surfaces should be primed with Duroproof™ Bitumen Primer. The product is torched on with minimal use of a propane gas flame, making it easy and quick to apply. Apply the heat to the underside of the membrane and melt down part of the bituminous undercoating. Form overlaps along the side of 8-10cm and 12-15cm laps at end .

ADDITIONAL INFORMATION

Keep the product away from solvents and organic liquids as they may damage the product. When laying the membrane, the surface must be free from any items which may puncture the membrane. Do not apply in rain or below 5°C.Store in an upright position.
When unloading avoid impact damage.



TECHNICAL SPECIFICATION

Test Method	Features	UOM	Nominal Values
EN 1848 - 1	Length	m	10
EN 1848 - 1	Width	m	1
EN 1849 - 1	Thickness	mm	4.0mm
EN 1107 - 1	Dimensional stability	%	Conforms to UNI8629
EN 12311 - 1	Tensile Strength long Tensile Strength trans	N/50mm N/50mm	>850 >550
EN 12311 - 1	Elongation at break longitudinal Elongation at break transversal	% %	40 40
EN 12310 - 1	Tear Resistance L & T	N	150
EN 1109	Cold Flexibility	°C	- 10
EN 1110	Heat Resistance	°C	120
EN 1928	Water Tightness	Kpa	>60
EN 1928	Water Resistance	%	±2

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.