PRODUCT DATA SHEET

DUROPVC 1000 FR

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

DuroPVC 1000 FR is a roofing membrane on the basis of PVC-P reinforced with a polyester grid. It is resistant to UV-radiation and can be exposed to the direct weathering influences. The membrane is not compatible with bitumen. DuroPVC 1000 FR by a multi-extrusion processing.

USE

- mechanically fastened roofs (membrane)
  - with spot, linear and induction fastening
  - using fastened fixing discs adhered to membrane
- ballasted flat roofs, when ballast is placed later in time
- pitched ballasted roofs
- other ballasted roofs, where due to small size, logistics or other

reasons the use of DuroPVC 1000 FR is more advantegous than that of DuroPVC 1000 FR-UV

APPLICATION

The laying of DuroPVC 1000 FR can be made by specialized and for this purpose trained firms at the constructions.
DuroPVC 1000 FR is applied conformable with fundamentals being set and described in a Construction and Technologic Instruction of the producer, being valid in the time of waterproofing providing. The membrane must be fixed to a stable part of a roofing coating by suitable way and it is by means of special anchoring elements. The kind of anchoring must be proposed for the particular applications so for being the membrane secured from the dimensional changes and wind suction.

The membrane can be mutual jointed by welding of hot air or heat key (one-trace weld). The laying and jointing can be made under the temperature till up to -5 °C.

COLOUR

DuroPVC 1000 FR is produced in a basic colour of the top layer of RAL 7035, RAL 7040 a RAL 7012. It can be produced in other coloures after agreement between producer and customer.

PERFORMANCE

DuroPVC 1000 FR is packed into the rolls, which are laid on the wood pallets and fixed by a packing film. DuroPVC 1000 FR must be transported in covered transporting means and stored in original closed packing. The recommended storage temperature is from -5 °C to +30 °C. There is necessary to protect the product from pollution at the building site. There is recommended to protect it from weathering influences till the processing time.

SINCE 1977

DIMENSIONS

Thickness [mm] (EN 1849-2)	Width [mm] (EN 1848-2)	Length [m]*) (EN 1848-2)	Quantity [m^2]	Weight of the roll [kg]**)
1.20 (-0.06; +0.12)	2000 (-10; +20) 2000 (-10; +20) 1000 (-5; +10) 2050 (-10; +20) 1025 (-5; +10) 1600 (-10; +20) 1600 (-10; +20)	25 (-0; +1) 20 (-0; +1) 25 (-0; +1) 25 (-0; +1) 25 (-0; +1) 25 (-0; +1) 20 (-0; +1)	50 40 25 51.25 25.625 40 32	78 61 39 75 37 61 49
1.50 (-0.07; +0.15)	2000 (-10; +20) 1000 (-5; +10) 2050 (-10; +20) 1025 (-5; +10) 1600 (-10; +20) 1600 (-10; +20) 1300 (-10; +20) 750 (-10; +20)	20 (-0; +1) 20 (-0; +1) 20 (-0; +1) 20 (-0; +1) 20 (-0; +1) 15 (-0; +0.7) 20 (-0; +1) 20 (-0; +1)	40 20 41 20.5 32 24 26 15	78 39 75 38 61 46 47 27
1.80 (-0.09; +0.18)	2000 (-10; +20) 1000 (-5; +10) 2050 (-10; +20) 1025 (-5; +10) 1600 (-10; +20)	16.5 (-0; +0.8) 16.5 (-0; +0.8) 16.5 (-0; +0.8) 16.5 (-0; +0.8) 16.5 (-0; +0.8)	33 16.5 33.825 16.9 26.4	77 39 78 37 61
2.00 (-0.10; +0.20)	2000 (-10; +20) 1000 (-5; +10) 2050 (-10; +20) 1025 (-5; +10) 1600 (-10; +20)	15 (-0; +0.7) 15 (-0; +0.7) 15 (-0; +0.7) 15 (-0; +0.7) 15 (-0; +0.7)	30 15 15 15 24	78 39 74 37 61
2.40 (-0.12. +0.24)	2000 (-10; +20) 1600 (-10; +20)	13 (-0; +0.65) 13 (-0; +0.65)	26 20.8	81 64

*) The membrane can be provided also in another winding lengths (deviation from the nominal length is of - 0 %; + 5 %) after agreement between producer and customer.

**) Informative value

TECHNICAL PARAMETERS:

Characteristic		Test standard	Values of individual product Thicknesses				
			1.20 mm	1.50 mm	1.80 mm	2.00 mm	2.40 mm
Visible defects		EN 1850-2	meets				
Straightness		EN 1848-2	≤ 50 mm				
Flatness		EN 1848-2	≤ 10 mm				
Dimensional stability		EN 1107-2	max. ± 0,3 %				
Maximum tensile force	MD	EN 12311-2 method A	≥ 1000 N/50 mm				≥ 1100 N/50 mm
	CD		≥ 1000 N/50 mm				≥ 1100 N/50 mm

Elongation at maximum tensile force MD CD		≥ 15 % ≥ 20 %		
Tear resistance MD CD	EN 12310-2	≥ 200 N ≥ 220 N		≥ 250 N ≥ 270 N
Foldability at low temperature	EN 495-5	≤ -25 °C		
Joint peel resistance MD CD	EN 12316-2	≥ 260 N/50 mm ≥ 260 N/50 mm		
Joint shear resistance MD CD	EN 12317-2	≥ 1000 N/50 mm ≥ 1000 N/50 mm		≥ 1100 N/50 mm ≥ 1100 N/50 mm
Water tightness, 400 kPa	EN 1928 method B	meets		
Resistance to static load	EN 12730 method B	meets 20 kg		
Reaction to fire	EN 13501-1	Class E		
Resistance to impact	EN 12691 method A	meets 1000 mm	meets 1250 mm	meets 1750 mm
	EN 12691 method B	meets 2000 mm		
Exposure to UV radiation, elevated temperature and water (5000 h)	EN 1297	meets, grade 0		
Water vapour properties - factor μ	EN 1931	15000 ± 30 %		
Resistance to root penetration	EN 13948 FLL test	meets		

MD - Machine Direction, CD - Cross Direction

SAFETY INSTRUCTION

There is necessary to keep all safety, hygienic and fire regulations valid in the time of laying and membrane joining.

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet