PRODUCT DATA SHEET

DUROPVC 900 FLEECE

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

DUROPVC 900 FLEECE is the roofing membrane on the basis of PVC-P with underlay sheet of a non-woven PES-textile. The membrane is produced by multiple extrusion.
It is resistant to UV-radiation and can be exposed to the direct weathering influences.
One edge of the membrane is without non-woven textilie due to enable a longitudinal band joining.

USE

DUROPVC 900 FLEECE is intened for adhered roofs. The membrane can be adhered to thermal insulation boards or directly on flat, load bearing substrate free of dust and free of particals, or to the concrete plate, wood-based boards and similar. Appropriatte polyurethane adhesives must be used.
The membrane DUROPVC 900 FLEECE is not suitable for mechanical fastening. Adhering to the top of bitumen membranes is generally not recommended. If DUROPVC 900 FLEECE is intended to be laid directly on bitumen membrane´s surface, it is necessary to consult with producer.
It is necessary to apply a homogeneous sheet DUROPVC 900 FLEECE due to detail working.

APPLICATION

The laying of DUROPVC 900 FLEECE can be made by specialized and for this purpose trained firms at the constructions. The waterproofing membrane is applied under conformity with valid mounting instructions.
Adhesives being used for the membrane adhesion must ensure enough cohesion to the certain underlay.
There is possible to join the membrane together by heat air weldings. A laying setting of the waterproofing membrane is necessary to provide under recommended temperatures of the adhesive producer; band jointing between each other can be made under the temperature till up to -5 °C.

COLOUR

DUROPVC 900 FLEECE is produced in a colour of the upper layer of light grey RAL 7040 and dark grey RAL 7012.

PACKING, TRANSPORT, STORAGE

DUROPVC 900 FLEECE is packed into the rolls, which are laid on the wood pallets and fixed by a packing film. DUROPVC 900 FLEECE must be transported in covered transporting means and stored in original closed packing. The recommended storage temperature is from -5 °C to +30 °C. There is necessary to protect the product from pollution at the building site. There is recommended to protect it from weathering influences till the processing time.

SINCE 1977

DIMENSIONS

Product data

DUROPVC 900 FLEECE meets the requirements of the Standard EN 13956.

Dimensions

Effective thickness (PVC layer)[mm] (EN 1849-2)	**Width [mm]** (EN 1848-2)	**Length [m]** (EN 1848-2)	**Quantity [m²]**
1.20 (- 0.06; + 0.12) *)	total: 2050 (- 10; + 20) free edge: 70 (± 10)	19 (- 0; + 0.95)	38.95
	total: 1650 (- 10; + 20) free edge: 70 (± 10)	19 (- 0; + 0.95)	31.35
		15 (- 0; + 0.75)	24.75
1.50 (- 0.07; + 0.15) **)	total: 2050 (- 10; + 20) free edge: 70 (± 10)	16 (- 0; + 0.8)	32.8
	total: 1650 (- 10; + 20) free edge: 70 (± 10)	16 (- 0; + 0.8)	26.43
		12 (- 0; + 0.6)	19.8

*) overall thickness 1.80 mm (informative value)

**) overall thickness 2.10 mm (informative value)

TECHNICAL PARAMETERS:

Characteristic	Test standard	Value	
		1.20 mm	1.50 mm
Visible defects	EN 1850-2	meets	meets
Straightness	EN 1848-2	≤ 50 mm	≤ 50 mm
Flatness	EN 1848-2	≤ 10 mm	≤ 10 mm
Dimensional stability	EN 1107-2	max. ± 1.0 %	max. ± 1.0 %
Maximum tensile force MD CD	EN 12311-2 method A	≥ 650 N/50 mm ≥ 650 N/50 mm	≥ 700 N/50 mm ≥ 700 N/50 mm
Elongation at maximu MD tensile force CD		≥ 80 % ≥ 80 %	≥ 80 % ≥ 80 %
Tear resistance	EN 12310-2	≥ 160 N	≥ 180 N
Foldability at low temperature	EN 495-5	≤ -25 °C	≤ -25 °C
Joint peel resistance	EN 12316-2	≥ 200 N/50 mm	≥ 250 N/50 mm
Joint shear resistance	EN 12317-2	≥ 600 N/50 mm	≥ 700 N/50 mm
Water tightness, 400 kPa	EN 1928 method B	meets	meets
Resistance to static load	EN 12730 method B	meets 20 kg	meets 20 kg

Reaction to fire	EN 13501-1	Class E	Class E
Resistance to impact	EN 12691 method A	meets 1000 mm	meets 1250 mm
	EN 12691 method B	meets 1500 mm	meets 2000 mm
Exposure to UV radiation, elevated temperature and water	EN 1297	meets, grade 0	meets, grade 0
Water vapour properties - factor μ	EN 1931	10000 ± 3000	10000 ± 3000
Mass per unit area	EN 1849-2	1.73 (-0.09; +0.18) kg/m^2	2.12 (-0.11; +0.22) kg/m^2
Resistance to root penetration	EN 13948 FLL test	meets	meets

MD - Machine Direction, CD - Cross Direction

SAFETY INSTRUCTION

There is necessary to keep all safety, hygienic and fire regulations valid in the time of laying and membrane joining.

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet