DUROTECH

DUROCOAT 90A

CHEMICAL RESISTANCE CHART

Open Spot Test after 24 hours Curing

Product or chemical Tested	Clear (1 hour)	Gray (1 hour)	Clear (8 hour)	Gray (8 hour)	Clear (24 hour)	Gray (24 hour)
10% Acetic Acid	SO – R	SO – R	SO – R	SO – R	SO – R	SO – R
DOT3 Brake Fluid	SO - R	SO - R	SO - DR	SO - DR	SO - DR	SO - DR
Acetone	SO - R	SO - R	E	E	E	E
10% Sodium Hydroxide	na	na	na	na	na	na
Motor Oil TC-WS	na	na	na	na	na	na
Paint Thinner	na	na	na	na	na	na
10% Muriatic Acid	SO – R	SO – R/LG	SO – R	SO – R	SO – R	SO – R
Transmission Fluid	na	na	na	na	na	na
40% Ethyl Alcohal	SO – R	SO – R	E	E	E	E
Pennzoil 10W-30 Motor Oil	na	na	na	na	na	na
Prestone Anti-freeze/ Coolant	na	na	na	na	na	na
Glass Cleaner	SO - R	SO - R	SO - R	SO - R	E	E
10% Sulfuric Acid	SO - R/LG	SO - R	SO - R/LG	SO - R/LG	SO - R/LG	SO - R/LG
Red Wine	SO - R	SO - R	SO - R/SLG	SO - R/SLG	E-ST	E-ST
Gasoline	SO - R	SO - R	SO - R	SO - R	SO - R	SO - R
Diesel	na	na	na	na	na	na
50% Sodium Hydroxide	na	na	na	na	na	na
kleen Flo Gas Line Anti- freeze	ST	ST	ST	ST	ST	ST
Distilled Water	na	na	SO - R	SO - R	E	E
Tap Water	na	na	SO - R	SO - R	E	E
Coffee	na	na	SO - R	SO - R	E	E

LEGEND

SO- softened
ST - stained
e- evaporated
na - not affected
R - recovered
DR - did not recover after
SLG - slight loss of gloss
LG - loss of gloss

Open Spot Test after 72 Hours curing

Product or chemical Tested	Clear (1 hour)	Gray (1 hour)	Clear (8 hour)	Gray (8 hour)	Clear (24 hour)	Gray (24 hour)
10% Acetic Acid	SO – R	SO – R	SO – R	SO – R	SO – R	SO – R
DOT3 Brake Fluid	SO - R	SO - R	SO - DR	SO - DR	SO - DR	SO - DR
Acetone	SO - R	SO - R	E	E	E	E
10% Muriatic Acid	na	na	na	na	na	na
40% Ethyl Alcohal	SO – R	SO – R	SO – R	SO – R	E	E
Prestone Anti-freeze/ Coolant	na	na	na	na	SO-R	SO-R
Glass Cleaner	na	na	na	na	na	na
10% Sulfuric Acid	na	na	na	na	LG	LG
Red Wine	SO - R	SO - R	SO - R	SO - R	E-SLG	E-SLG
Gasoline	na	na	na	na	na	na
50% Sodium Hydroxide	na	na	na	na	na	na
Kleen Flo Gas Line Anti- freeze	ST	ST	ST	ST	ST	ST
Distilled Water	na	na	na	na	na	na
Tap Water	na	na	na	na	na	na
Coffee	na	na	na	na	ST	ST

Close Spot Test after 72 hours curing

	Durocoat 90A Clear 24 Hours Close Spot test	Durocoat 90A Gray 24 Hours Close Spot test
Acetone	Destroyed	Destroyed
Motor Oil	na	na
10% Acetic Acid	Softened -R	Softened -R
Transmission Fluid	na	na
40% Ethyl Alcohal	Softened -R	Softened -R
Glass Cleaner	Softened -R	Softened -R
Distilled Water	na	na
Coofee	Softened -R	Softened -R
Root Beer	Softened -R	Softened -R
Red Wine	Softened -R	Softened -R
Gasoline	Softened -R	Softened -R
Diesel	na	na

na - not affected R - recovered

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | 1300 791 177 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.