DUROTECH
Waterproofing • Sealants • Adhesives

DUROELASTO TAPE

Description :

The DUROELASTO Tape joint band is an innovative detailing system designed for waterproofing and sealing all types of joints, junctions and general areas subject to movement. Featuring the central "Flexible Zone" the tape joint band can accommodate movement in longitudinal, lateral and transverse directions enabling high elongation, rupture resistance, and up to 100% elastic recovery. The DUROELASTO tape joint band is easy to install and provides for considerable time saving efficiencies and durable properties over conventional bond breaking sealant and tapes.

Features :

- Approved bondbreakers system conforming to AS3740
- Time saving simplified installation
- Eliminates need to sealant bondbreakers and tapes
- Long term protection at critical joint intersections and movement zones.
- Accommodates movement in longitudinal and lateral directions with up to 100% elastic recovery.
- Constructed of a unique high strength rubber compound that is rupture, chemical and water resistant.
- Can be used in areas subject to full immersion.
- Compatible with Gripset class A, B and C membranes.

Application :

Suitable for commercial, industrial and residential application.

Uses:

For use as bond breaker at the following critical areas:

- Wall/floor junctions
- Substrate abutments
- Control joints
- Movement and expansion joints

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.

Installing DUROELASTO Tape Band:

Measure and cut Duroproof joint band for all wall/floor junction areas. Apply first coat of membrane to approximately 150mm extending up walls and on to floors, and embed DUROELASTO Tape joint band into wet bed of liquid membrane, ensuring fabric edges are fully wet out and no air bubbles exist behind the fabric. Rear rubber section of DUROELASTO Tape is not bonded to substrates. At sections where tape is to be joined, a minimum 50mm overlap is required. DUROELASTO Tape prefabricated Corners are available for both internal (90^0C) and external (270^0C) junctions, enabling DUROELASTO Tape to overlap and avoid joint at critical areas. If Prefabricated corners are not used, DUROELASTO Tape is to have bottom leg cut and folded; ensuring fabric is completely bonded with the Durotech membrane.

PACKAGING:

- 120mm x 50m roll
- 120mm x 10m roll

PRECAUTIONS IN USE :

- Not compatible with solvent based material, e.g. adhesives, sealants or coatings.
- Not to be used as UV exposed joint seal in external applications.
- Do not apply when surface temperature is below 5^0C or above 30^0C
- For further information about this product contact technical department of Durotech Industries.

TECHNICAL DATA :

Rubber	NBR (Acrylonitrile butadiene rubber)
Carrier Edging	Ployester fleece with lateral flexibility
Total Width:	120mm
Thickness	0.6 – 0.8mm
Rubber Width	70mm span, 20mm central stretch zone
Material Weight	50g/m

PHYSICAL PROPERTIES:

Shore a hardness	65
Temperature resistance	-20^0C to 90^0C
Tensile strength (DIN 53504)	>1.0N/mm^2 lateral direction >7.0N/mm^2 longitudinal direction
Rupture strain (DIN 53504)	>208% lateral direction >48% longitudinal direction
Moisture vapour transmission Resistance coefficient µ	8.4
Equivalent air thickness sd	5.0
Water pressure resistance	3 bar
Fire class (DIN, EN)	B3, F

CHEMICAL RESISTANCE:

Lactic acid	5%
Acetic acid	5%
Hydrochloric acid	3%

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.

Chloric acid	3%
Sulphuric acid	35%
Citric acid	10%
Potassium hydroxide	20%
Sodium hypochlorite	(0.3g/L)
Sea water	Sea salt (20g/L)
Sodium hydroxide solution	pH 12.5
Sodium hydroxide solution	pH 14
Diesel oil, grease, oil, paraffin	0 to 14pH

MOVEMENT PARAMETERS:

Starting Joint Width	20mm (maximum)
Movement capacity	No more than 50% of starting joint width

NOTES

It is recommended before commencing the application; that adhesion of products to be used (e.g. primers, membranes, coatings adhesives etc) is tested over a typical area of the prepared surface to ensure satisfactory adhesion. It is the responsibility of the applicator to carry this out and accept the substrate suitability before any application starts. Durotech Industries offers a service for pre testing adhesion to surfaces for large commercial areas or unusual substrates. For further details contact Durotech Industries.

Details contained in product data sheet are general. For any situation or items not cover in this data sheet, it is the responsibility of the applicator to check with Durotech Technical Services before commencing the application. A written confirmation will then be issued by Durotech Technical Services.

DUROTECH

14 Essex Street, P.O Box 5092, Minto, NSW 2566

+61 2 9603 1177 | +61 2 9475 5059 | sales@durotechindustries.com.au

www.durotechindustries.com.au

The information provided in this data sheet is correct at the time of printing (albeit is subject to change at any time) and is intended to give a simple description of the product and its capabilities. In practice, the substrate, intended surface to be treated and environmental conditions vary widely, making it essential for the user to determine the products suitability for a particular application and to ensure that the product is not used beyond its physical limitations. If in doubt contact the manufacturer. The product will perform as described herein provided it is applied in accordance with the manufacturer's instructions as stated in this data sheet and provided that the building and installation is structurally sound and the application is carried out competently. Durotech terms and conditions of sale apply.