PRODUCT DATA SHEET

DUROFLEX BASEMENT

POLYMER CEMENTITIOUS SLURRY

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Duroflex basement is a 1 component polymer enhanced, rigid setting cementitious slurry coat designed for a range of positive and negative waterproofing applications over concrete and masonry surfaces. Suitable for underground structures including retaining walls, basements walls, lift shafts, car parks, building foundations and footings to prevent water migration through both positive and negative faces of structures.

Once cured Duroflex basement can be finished over with paint, render and other decorative finishes.

FEATURES

- Non toxic Excellent adhesion properties
- Fast drying
- Dries without cracking, low shrinkage
- 1 component, mixed on site with water, ready to use
- Able to withstand positive and negative water pressure (up to 5m head of pressure on negative side)
- Protects against chlorides, sulphates, sea water, subterranean water, freeze thaw and varying pH water
- Suitable on damp concrete or green freshly laid concrete
- Can be finished over with paints, renders and other decorative finishes

USE AREAS

- Retaining walls
- Basements, cellars, subterranean walls
- Lift shafts
- Car parks

GENERAL PREPRATION DETAILS

- Surfaces must be free of oil, paints, grease, laitance and foreign residues ensuring the area is clean and free of contaminants. Repair surface cracks, voids or unstable areas with a repair mortar.
- All active leaks must be first repaired using Durotech Duroflex Water Plug.
- Surfaces should be damp or pre dampened prior to application

GENERAL APPLICATION DETAILS

- Slurry is formed by mixing approximately 1litre of water per 4.5kg of powder
- Into a clean mixing container, add 2/3 of the required water. Slowly add powder and mix using an electric stirrer with paddle attachment, ensuring the mixing of components is continuous while the powder is added. Continue mixing to form a lump free consistency. Then slowly add the 1/3 balance of water to the mixture until it is evenly dispersed and a homogenous consistency is formed.
- Mix for approx. 2-3 minutes and allow to settle for 5 minutes before a light re-stir and ready to use. Pot life is approx. 40 minutes. If using in hot conditions, chilled water should be used for mixing. Once product has dried or settled, do not re-mix. Remove the residue and commence a fresh batch.

SINCE 1977

APPLICATION, COVERAGE AND CURING

- Ensure all surfaces are pre-dampened prior to applying the slurry. This can be done by water mist or watering area down. Surfaces should be damp but free of surface water.
- Using a stiff bristle brush, apply the product in a liberal coat ensuring all surface pores are covered.
- Optimum results are achieved in 2 coats with the first coat being applied at approx. 1.5kg/m^2 followed by a second coat at a coverage of 1kg/m^2 . Total coverage should be approx. 2.5kg/m^2 with a dried film thickness of around 2- 2.5mm.
- Recoat time is 2 hours.
- Allow minimum 4 days curing before backfilling or applying finishes

IMPORTANT NOTES

- Ensure surface is prepared correctly with surface pre-dampened prior to applying product.
- Surface temperature is to be between 5°C & 30°C
- Wear rubber gloves, protective eye wear and cover face when mixing and applying product.
- Do not mix with any other materials
- Do not apply if early rain is imminent after the application to prevent wash out.

PACKAGING

- 20Kg bag

GENERAL TECHNICAL DATA

Wet Form

Specific gravity of mixed product:	1.5kg/litre
Appearance:	When mixed – grey viscous slurry When dried – grey film

CURED MEMBRANE

Elongation:	20%
Tensile Strength:	>1.1MPa
Adhesion to concrete:	>1.1MPa
Water pressure resistance:	0.45g/24h/m^2
Shore A hardness:	68

WATER PRESSURE

0.5 Bar negative pressure
6 bar positive pressure

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ ©

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet