PRODUCT DATA SHEET

DUROGRIT

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Durogrit also referred as quartz sand is the most versatile used mineral in the epoxy flooring industry that is generally combined with epoxy, polyaspartic or polyurea coatings. Durogrit is a notoriously hard mineral which makes it ideal use for floors in commercial, industrial and residential environments. It has many great qualities such as anti-slip aggregate, filler for selflevelling systems, filler for grouting & coving & crack repair, as decorative component, or as bonding agent for inter-coat adhesion.

FEATURES

- Superior colourfastness/UV stability
- Extreme abrasion resistance
- Excellent chemical resistance
- Optimal shape and size uniformity
- Outstanding slip-resistance qualities
- Customizable to compliment any environment
- Perfect for heavy-duty environments
- Extraordinary resilience
- Easy to apply

USE AREAS

- Bars, Pubs & Taverns
- Butcher Shops and Commercial Kitchens
- Food Processing Plants & Grocery Stores
- Schools, Stadiums & Hallways
- Showrooms, Garages and Workshops
- Lobbies, Lounges, Nightclubs & Foyers
- Salons, Retail Stores and Wineries
- Shopping Centres and Retail Flooring
- Museums, Office Buildings & Galleries
- Restaurants & Lunch Rooms
- Veterinary Clinics, Zoos & more...

TECHNICAL DATA

APPEARANCE	Granular Solid
COLOUR	Natural
VOLUME SOLIDS	N/A
FINISH	N/A
COVERAGE	12 – 18m² when used as anti-slip additive
MIX RATIO	20kg
PACK SIZES	20kg
SPECIFIC GRAVITY	20kg
POT LIFE	20kg
DRYING TIME	20kg
RECOAT TIME	20kg
FULL CURE	20kg
SHELF LIFE	60 months, if properly stored in original unopened containers at temperatures between 10° C and 30°C, away from sunlight.

* The pot life time depends on climatic conditions and temperatures.

** Drying times generally depend on air circulation, temperature, film thickness, and application methods. The figures given above are typical with good ventilation, typical film thickness and single coat application.

SINCE 1977

SURFACE PREPARATION

All surface preparations must be carried out to Australian Standard or International Standard. New concrete must be cured for a minimum of 28 days before a coating.

Concrete moisture test should be carried out prior to coating application as per Standard ASTM4263 and/ or International Standard. The moisture content should be less than 4%.

Surface to be treated must be structurally sound and the substrate compressive strength should be at least 25MPa. The substrate tensile strength should be at least 1.5N/mm^2. All non-structural cracks, holes and surface deformities should be repaired.

In general, the surface to be treated MUST be clean and free of all traces of loose material, dirt, debris, mildew, oil, grease, old coatings, curing compounds, release agents, laitance, dust and other contaminants.

All new or old concrete surfaces should be prepared by mechanical grinding, abrasive blasting, blast tracking, or any other suitable preparation/cleaning methods. Surface profile should exceed CSP 3 after preparation. Check if all traces of oil and other contaminations has been completely removed prior coating application.

For more detailed information, see following standard codes of practice, guides and techniques:
ASTM D4258 Standard practice for surface cleaning concrete for coating
ASTM D4259 Practice for abrading concrete
ASTM D4260 Practice for liquid and gelled acid etching of concrete
ASTM D4262 Test method for pH of chemically cleaned or etched concrete surfaces
ASTM D4263 Test method indicating moisture in concrete by the plastic sheet method
ASTM D4285 Test method for indicating oil or water compresses air

MIXING

No mixing required.

APPLICATION WHEN USED AS ANTI-SLIP ADDITIVE

Always prime surface before the first coat to prevent pin holing and to minimise sink-back of material/basecoat. Prime coat with approximately 7-12m^2/L, check for pinholes and do a 2nd prime coat if necessary.

Wearing spike shoes for this application type is strongly recommended. Apply basecoat and work from the end of the room backwards to the exit.

Note the Durogrit must be applied during the process of the basecoat application while the basecoat is still wet to ensure the Durogrit will stick properly to the basecoat. Be cautious if the basecoat becomes too dry, the Durogrit will not stick to it and you might end up with areas looking patchy and not evenly covered.

With big flooring projects we recommend using more applicators to carry out the task in a timelymanner. While the basecoat is still wet, start throwing or scattering the Durogrit over the wet epoxy base coat to the amount and coverage desired. After 24 hours when the basecoat has been cured, sweep the floor and keep left over material aside. Then use a vacuum cleaner to thoroughly remove any remaining loose Durogrit. Apply top coat on the Durogrit. If there is some patchiness within the floor, sprinkle some Durogrit from the left over material onto the patchy areas into the first top coat to rectify the look, while the coat is still wet and backroll the area. Use a lint free epoxy roller to apply the product. Discard all left over Durogrit material.

CURING TIMES

Depend on the epoxy and coatings system used. In general allow coating to cure for at least 24 hours before subjecting to light pedestrian traffic and at least 7 days for full cure and vehicular traffic. The pot life time depends on climatic conditions and temperatures. All drying times depend on film thickness, ventilation, temperature, humidity and application methods. All curing times mentioned in this TDS are based on temperatures of 25°C. Lower temperatures will extend curing times. If the temperature in your region is 12.5°C, all curing times will double e.g. full cure will be approximately 14 days. DCC does not recommend epoxy application when temperatures are below 10°C as the epoxy goes into B-staging (the epoxy stops curing).

CLEANING

Clean all equipment immediately after use with water or solvents, depending on the epoxy system used.

COATING MAINTENANCE

In general dirt, dust, contaminants, and excessive wear and tear will shorten the life of coating. Keep these areas clean and free from such pollutants and avoid excessive wear and tear. Clean coating regularly with warm mild detergent water up to 60°C and rinse with clean water. Do not use abrasive brushes, scouring pads or solvent to clean the coated surface. It is advisable if abnormal wear and tear will occur through moving furniture such as office chairs, keep these areas protected with a protective mat. Further to the above cleaning recommendations please ensure immediate cleaning of any spills. Refer to DCC Maintenance & Cleaning Guide for detailed information.

COMPATIBILITY & SUITABILITY

Do NOT mix this product or use this product in combination with any other products or brands. Due to the differences in substrates, material and site conditions, and environmental surrounds, the applicator holds whole responsibility for checking the products suitability for its intended purpose prior application. Only products of the same brand/system should be used in combination as a system.

PRECAUTIONS

Safety Data Sheet and Technical Data Sheet must be read before using and opening this product. Keep out of reach of children. Always wear personal protective equipment (PPE) when handling this product. Keep away from heat and flame. No smoking. Provide adequate ventilation. For more details refer to safety data sheet (SDS).

Do not apply if the air or surface temperature is below 10°C, or if the temperatures is subject to drop below 10°C during applying, or after application within the curing time.

Do not apply if substrate is subject to hydrostatic pressure or rising dampness.

Do not apply if surface is subjected to unusual high temperatures above ambient temperature.

Do not apply if the surface temperature is over 30°C, or if the surface temperature is subject to raise above 30°C during applying, or after application within the curing time, or if relative humidity is suspected to become above 85%.

Do not apply if substrate is subject to rain or moisture, and protect surface at least 24 hours against any water impact, or moisture after application within the curing time. Do not use any product past its pot life. Store locked up, in a cool, dry, well ventilated place, away from sunlight, between 10°C and 30°C. Keep container tightly closed.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet