PRODUCT DATA SHEET

DUROGUARD 80A BC

MUTITHANE ALIPHATIC TOP COAT - PROVIDES GREATER UV PROTECTION & COLOUR FASTNESS FOR MULTITHANE MEMBRANES

DUROTECH
Engineered Contruction Chemicals
Made In Australia For Over 42 Years

DESCRIPTION

Duroguard 80A BC is Cross Linked Moisture curing Polyurethane single pack liquid applied top coat.

Duroguard 80A BC is single pack, Trafficable aliphatic polyurethane waterproofing top coat which has been formulated as a complimentary and compatible top coat for Multithane 2P-A80. UV Aliphatic technology provides greater UV protection, colour fastness and anti-chalking properties and is designed to extend the life of exposed aromatic polyurethanes. Duroguard 80A BC forms a tough, flexible, seamless, highly UV stable waterproof coating.

Duroguard 80A BC meets the 'Green Star' environmental criteria.

FEATURES

- Provides excellent UV protection.
  Trafficable (Foot & Vehicular) It is also ideal as a stand-alone trafficable coating or clear top coat over flake flooring systems
- Extends the life of the waterproofing membrane system.
- Single pack - no mixing.
- Fast curing (usually within 24 hours.
- Semi flexible
- Suitable for immersion in water.
- Good chemical resistance.
- High strength and puncture resistant.
- Provides seamless membrane (no joints or laps)
- Easily repaired and or maintained.
- Odourless (subjective) when cured.
- Formulated to provide long term protection.
- Easy to apply.
- Has good hydrostatic resistance.

USE AREAS

Duroguard 80A BC is formulated as a highly UV stable top coat over Duroguard range to give greater long term UV protection and colour fastness thereby extending the life and performance of the waterproofing membrane.

TESTS AND TECHNICAL DATA

Duroguard 80A BC represents the highest standards in Cross Linked Moisture curing Polyurethane waterproofing technology

1. AS4654.2 Exterior area installation of membranes (non UV exposed applications)
2. 'Green Star' environmental criteria (Less than 1%. i.e. Less than 150gr per 15 lt pail)

Tensile Bond	2N/mm after 14 days
Application temperature range	10 to 35*C
Elongation	> N/A
Moisture Vapour Transmission	0.26 g/m²/24 hours

SINCE 1977

SPECIFICATION

The information contained in this product data sheet is typical but does not constitute a full specification as conditions and specific requirements may vary from project to project. The instructions should be considered as a minimum requirement but the applicator or contractor must use their skill, knowledge and experience to carry out additional works as may be necessary to meet the requirements of the project. Specification for specific projects should be sought from the Company in writing.

LIMITATIONS

- Duroguard 80A BC is not suitable for direct contact with high concentrations of chlorine above 10ppm.
- Duroguard 80A BC cannot be applied directly to damp surfaces as this will cause gassing and bubbling of the membrane.
- Duroguard 80A BC cannot be applied to slightly damp surfaces the product will not adhere. The surface must dry before the membrane can be applied, freedom from surface water and continual dampness is essential

PRECAUTIONS IN USE

Risk is considered low when properly used. Precautions on can, label and / or data sheets should be observed. Use in well ventilated areas. Uncured product is combustible so keep all sources of ignition away from product and its vapours.

SURFACE PREPARATION

Good preparation is essential. Surfaces must be sound, stable, dry, clean and free of dust, loose, flaking, friable material and substances that may diminish adhesion.

New membranes.
Providing the existing membranes are clean, dry and that the Duroguard 80A BC is being applied within 24 hours of applying the Duroguard membranes - no other preparation is required. If the existing membranes have been contaminated refer to 'TO EXISTING MEMBRANES' below.

Existing membranes.
Duroguard 80A BC may be applied to 'aged' Duroguard membranes. These surfaces should be dry, clean and free of dirt, dust and contaminants and should be suitably cleaned depending upon the type of contaminant, e.g. if oil, then clean with detergent, flushed and allowed to dry. The surface should be wiped down with Durotech Solvent to 'rejuvenate' the top layer, allowed to flash off before applying the Duroguard 80A BC.

Applicator must carry out test sample areas for performance and adhesion if not primed

Surfaces should ideally be suitably primed with Durotech Sealant applied at no less than 1 Lt per 4m² or Durotech Sealant Papplied at 1Lt per 7m² and allowed to dry, primers need to be applied at no less than the relevant Durotech Primer TDS

Blow Holes.
Blow-holes and surface imperfections must be made sound and filled with sealant or alternatively a non-shrink mortar, finished flush with the surface. Allow to cure and dry.

PRIMING

As its main purpose is to be applied over cured Duroguard UVR and Duram 195, it can be applied as follows:

New membranes.
Providing the existing membranes are clean, dry and that the Duroguard 80A BC is being applied within 24 hours of applying the Duroguard membranes - no other preparation is required. If the existing membranes have been contaminated refer to 'TO EXISTING MEMBRANES' below.

Existing membranes.
Duroguard 80A BC may be applied to 'aged' Duroguard membranes. These surfaces should be dry, clean and free of dirt, dust and contaminants and should be suitably cleaned depending upon the type of contaminant, e.g. if oil, then clean with detergent, flushed and allowed to dry. The surface should be wiped down with Durotech Solvent to 'rejuvenate' the top layer, allowed to flash off before applying the Duroguard 80A BC.

Applicator must carry out test sample areas for performance and adhesion if not primed

Surfaces should ideally be suitably primed with Durotech Sealant applied at no less than 1 Lt per 4m² or Durotech Primeseal SP applied at 1Lt per 7m² and allowed to dry, primers need to be applied at no less than the relevant Durotech Primer TDS

DETAILING PREPARATION

As per relevant TDS of chosen membrane selection

APPLICATION

Apply Duroguard 80A BC by brush, roller, and broom or squeegee so that the dry film thickness is 300 microns.

The second coat is best applied within 24 hours to achieve inter-coat adhesion bonding and avoid the need to reprime.

Duroguard 80A BC is an aliphatic based polyurethane top coat which extends the life of the exposed membrane.

When top coating Duroguard STD, with Duroguard 80A BC, allow Multithane STD to cure and then apply Duroguard 80A BC at the approximate rate of 3 to 4 m² per Lt

COVERAGE

Coverage rate varies depending upon type, condition, porosity, texture of the surface and application technique.
Duroguard 80A BC: Generally, 3 m² per litre per coat application.

DRYING AND CURING

Drying and curing of the product is affected by type, dryness and porosity of the surface, temperature, humidity, ventilation, climate conditions and application technique and therefore drying and curing can only be given as a guide.

Generally, Duroguard 80A BC is touch- dry within 4 to 6 hours with full cure within 24 hours. Recoat between 6-24 hours

TILING, TOPPING OR TOP COATING

Duroguard 80A BC is usually not tiled or covered:

COLOURS

Grey. Colour may lighten after application in direct sunlight. Note: Slight colour variation may occur between batches

STORAGE AND PACKAGING

Keep in cool, dry place away from heat, flame or combustible material. Product contains flammable solvents. Available in 15 Lt Pails. 15 litres equates to 19kg.
Shelf life: 6 months in unopened container, best used within that period.

As this is a moisture curing polyurethane some skinning of the product may occur. This should be cut out and removed. Balance of the product will be suitable for use

SAFETY AND PRECAUTIONS

Duroguard 80A BC is solvent based. Keep container in safe, ventilated area. Wear appropriate PPE during use. The use of solvent resistant gloves and goggles (against splashes) are recommended. If spraying, which is very rare, the use of self-contained breathing apparatus is recommended. If swallowed do not induce vomiting, give plenty of water to drink. Seek urgent medical advice. If in eyes, flush thoroughly with clean water, holding lid open to ensure any trapped product may be flushed away. Seek medical assistance. If on skin, remove contaminated clothing and wash skin with soap and water. This may not remove the product but will encourage it to cure and can later be peeled off. If inhaled, unlikely due to viscosity of the product, remove person to fresh air and apply artificial respiration if required and seek urgent medical attention. Ensure adequate ventilation. Vapours may collect in low lying areas.
For full safety data refer to the SDS. Observe precautions as per label

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au



"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet