PRODUCT DATA SHEET

DUROPOXY U200 LP

(LONG POT LIFE)

100% solids Epoxy Universal primer for concrete, steel and wood surfaces

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

DUROPOXY U200 LP (universal) is formulated as a 100% solids universal epoxy primer for substrates such as concrete, steel and wood surfaces. U200is supplied as a two-component system and Part A is clear. U200 LP can also be used as a sealer over dense concrete and cementitious surfaces.

FEATURES

- High adhesive strength – creates an extremely good bond to concrete substrates and aggregates
- Lower viscosity and clear
- Excellent cure rate
- Wide window of application
- Excellent adhesion concrete
- Multipurpose epoxy Clear Sealer
- Non-flammable
- Very low VOC content

USE AREAS

- Dense concrete sealer
- Primer for base coat for polyurethane spray systems and hand applied 1k and 2k polyurethane membranes
- Primer for trafficable epoxy systems

PACKAGING and COLOUR AVAILABILITY

DUROPOXY U200 LP is supplied in 10 kg pre-weighed kit

- DUROPOXY U200 Part A 6 kg
- DUROPOXY U200 Part B 3 kg

COMPONENT PROERTIES

PROPERTY	RESIN	HARDENER
Appearance	Straw coloured liquid	Straw to amber colour liquid
Specific gravity g/cm3	1.1 ± 0.1	1.1 ± 0.1
Viscosity @ 25°C / cps	500-1000	500-1000
Gardener Colour Index	-	< 2

MIXING AND CURING CONDITIONS

PROPERTY	RESIN / HARDENER
Mix ratio by Vol (A/B)	2:1
Mix ratio by weight (resin/ hardener)	100/50
Solids Content	100%
Mixed specific gravity	1.08 g/cm^3
Work Time (150 grams)	1 hour @ 25°C minimum
Overcoat time	6-8hours @ 25°C
Dry film thickness	250 microns

SINCE 1977

APPLICATION

Surface Preparation: will vary depending on surface conditions. The surface must be clean and dry from dust and particles, including grease, coatings and curing compounds. The substrate must be prepared by any way of degreasing or grinding or captive shot blasting to expose aggregate and provide a profile. Allow floor to dry if degreasing has been carried out.

Surfaces must be dry and failure to comply with the above results may result in failures. All substrates must be at least 3°C above the current dew point temperature. The minimum temperature for curing must be at least 3 °C above the current dew temperature.

All substrate repairs must be fully cured and compatible with polyurethane spray and polyurethane membrane. The substrate must be of a load bearing quality.

MIXING

DUROPOXY U200 LP is supplied in pre-weighed kits. It is essential the Part B hardener is added to all of the Part A and mixed thoroughly in a separate 20 litre vessel using an electric drill and paddle at (300 – 600 rpm) for a minimum of 2 minutes, mixing along the bottom and around the sides on the container. The mixing will involve working the paddle around the sides and bottom of the vessel ensuring that no unmixed material remains.

Once fully mixed, U200 LP should be applied by flat rubber or foam squeegee, twin-armed brush, airless spray or by roller, immediately to fill voids and pores in the substrate. Extremely porous substrate can be susceptible to rising damp/ moisture and may require two-coat primer application to seal the surface. To provide an additional mechanical key, the primer can be fully aggregated with Silica 50N sand immediately after the primer has been back rolled. Once the primer has been cured to a tack free state – the excess sand must be removed using a stiff bristled broom followed by vacuuming or compressed air blowing prior to over-coating. If the surface is very rough, porous or textured, the DUROPOXY U200 LP should be applied by roller. Be careful to remove excess pools of primer before broadcasting aggregate.

Take care to ensure all substrates are kept dry and ambient temperature. The DUROPOXY U200 LP to be used at ambient temperatures 8-35°C. Part A and Part B temperature should be at 15-30°C at time of processing – these are the ideal temperature range.

Limitations: Under no circumstances should applications be carried out in damp weather conditions or if rain is forecast. If the temperature falls below 8°C, the DUROPOXY U200 LP should not be used.

STORAGE

DUROPOXY U200 LP should be stored in its original sealed containers for up to 12 months in controlled environment. Place out of direct sunlight at temperatures between 15-30°C.

COVERAGE

6 – 8m2 /L (coverage will vary depending on the porosity of the surface).

160 - 125 um, DFT.

CLEANING

Clean the tools and equipment with rags, then wipe off using a solvent such as xylene before the resin system hardens.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use the product, please make sure that you obtain a copy MSDS.

Durotech Industries Pty Ltd

Address	14 Essex Street, P.O Box 5092, Minto, NSW 2566
Phone	+61 2 9603 1177
Fax	+61 2 9475 5059
Email	sales@durotechindustries.com.au
Web	www.durotechindustries.com.au

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet

ISO 14001 Environment Certified System IQNet

ISO 45001 Health and Safety Certified System IQNet