PRODUCT DATA SHEET

DUROPOXY 2K CLEAR COAT

High gloss, clear, 2 part concrete sealer

DUROTECH
Engineered Construction Chemicals
Made In Australia For Over 45 Years

DESCRIPTION

Duropoxy 2K Clear Coat is a clear straw coloured two pack sealer with good wear and chemical resistance.

FEATURES

- UV resistant & non yellowing
- Very good solvent and chemical resistance
- Long pot life

Use Area

As a high gloss clear sealer over stamped and stencil concrete, resurfacing systems, coloured and plain concrete and exposed aggregate, flake flooring and can be applied to most concrete surfaces including polished or ground concrete/ polished concrete bench tops.

TECHNICAL INFORMATION

Coverage rate	Approx. 3 - 10m² per coat dependent on porosity of surface.
Solids	39+- 2% w/w
Specific Gravity	0.99 (mixed A + B)
Tack free time @ 25°C	30 min - 2 hours (depending on conditions)
Pot Life @ 25°C	Approx 6 hours
Film properties after mixing A + B and cured 7 days	Appearance clear Flexibility semi rigid
Weathering Resistance	Excellent- non yellowing

PACKAGING:

PART A 8.75L (10L drum)

PART B 1.25L (2L can)

Application Instructions

Preparation for external application

Ensure concrete is sufficiently cured (recommended minimum 14 days).

- Concrete is to be clean and free of grease, oil, stiff broom and general purpose cleaner recommended.
- Paint, curing agents and acrylic sealers must be removed by either stripping or grinding.
- Pressure clean surface at minimum 2000 psi and allow to dry.
- Acid etch with hydrochloric acid. Dilute approximately 20parts water to 1 part acid (depending on porosity) to remove any loosely bound cement and laitence. NOTE: smooth concrete will require a higher acid content. Maximum strength - 10 parts water to 1 part acid.
- Pressure clean immediately to clean and remove all remnants of acid (do not allow acid to dry on surface). Pressure clean at minimum 2000 psi.
- Allow surface to dry and ensure is dust and dirt free before sealing (sealing over damp concrete will cause whitening). Refer to Dry Test.
- NOTE: When surface needs to be resealed, a physical abrasion will be required.

Dry Test

- Place a piece of plastic over a small area, tape the edges and leave for 1 hour.
- Remove plastic, if there is no moisture on either surface, concrete is sufficiently dry for sealing.

SINCE 1977

Preparation for internal application

Ensure concrete is sufficiently cured (recommended minimum 14 days).

- Concrete is to be clean and free of grease, oil, stiff broom and general purpose cleaner recommended.
- Paint, curing agents and acrylic sealers must be removed by either stripping or grinding.
- The surface should be dry, containing no solvent or moisture as once Duropoxy 2K Clear Coat is dry it can trap moisture or solvent underneath which could cause the sealer to lift.
- For epoxy coatings, surface must be abraded and solvent wiped before sealing.

Preparation for Flake Flooring

- Ensure all loose/excess flake has been scraped, broomed, vacuumed and completely removed before sealing.

Mixing Instructions

- Mix 8.75L Part A and 1.25L Part B to make 10L kit.
- Mix product with a paint stirrer for minimum 3 minutes.

Application 1st Coat

- For non porous surfaces the first coat must be diluted to penetrate into the substrate and provide better wetting. Dilution can be up to 20% with Durotech Solvent.
- Diluted sealer must be used immediately. Do not store or return to original sealer.
- If there are some doubts about application and appearance, test a small area first.
- Apply Duropoxy 2K Clear Coat by either a suitable paint brush, 100% mohair 4mm pile nap roller or airless spray. For spray application, 10% Durotech Solvent should be added.

Application 2nd Coat

- Second coat should be applied within 6 -18 hours dependent on conditions prevailing. If too much time is allowed for cure, adhesion can be difficult to obtain on subsequent coats.
- If too much time has elapsed then the first coat will have to be abraded and solvent wiped to provide extra key before the second or third coats are applied.
- Durotech Slip Reducing Additive may be added to the final coat, particularly if the area gets wet. Refer to Slip Resistant Additive TDS.

Curing Time

After sealing it is recommended that the sealed surface be protected from:

- Rain/water/sprinkler systems for minimum 6 hours
- Foot traffic for a minimum of 48 hours
- Vehicle traffic for a minimum of 72 hours

The time depends on weather conditions and coating thickness, therefore, check suitability before allowing traffic.

Limitations

- Cannot be applied over solvent based acrylic sealers.
- Surface must be abraded for second coat if over 18 hours between coats.
- NOT tintable with any colour tints
- When surface requires resealing, the surface will be need to be abraded before sealing.

Coverage

1 x 10 litre kit covers approximately 30 to 100m2 per coat depending on the porosity of the surface.

Storage

Parchem recommends storage in a cool, well ventilated space away from heat sources. Keep tightly lidded. Keep away from reducing agents and strong oxidising agents. Take precautions against static electricity discharges.

Shelf Life

3 years in unopened container stored as recommended. After this time product should be checked to ensure suitability for use.

Cleaning

Clean up with Durotech Solvent.

Safety

- Organic vapour respirator mask
- Solvent resistant gloves
- Safety eye wear
- Appropriate foot wear

"This document, including any attached files, is strictly confidential and intended solely for the use of the individual or entity to which it is addressed. Durotech Industries prohibits the right to publish, copy, distribute or disclose any information contained in this document, or its attachments, by any party other than the intended recipient. If you have received this document in error please notify the sender and delete it from your system immediately. no employee or agent is authorised to conclude any binding agreement or make any representation on behalf of Durotech Industries. The views or opinions presented in this document are solely those of the author and do not necessarily represent those of Durotech Industries, except where the sender expressly, and with clear authority, states them to be the views of Durotech Industries. Durotech Industries accepts no liability for any loss or damage (direct or indirect or consequential) arising from the use of or in connection with this document and any attacchments and suggests that the recipient check this document and any attached files for the presence of viruses."

JAS-ANZ

ISO 9001 Quality Certified System IQNet
ISO 14001 Environment Certified System IQNet
ISO 45001 Health and Safety Certified System IQNet